

Microencapsulation in the Food Industry
A Practical Implementation Guide

Edited by
Gaonkar
Vasisht
Khare
Sobel

Microencapsulation in the Food Industry

A Practical Implementation Guide

TP
371
.M53
2014

Edited by
Anilkumar Gaonkar, Niraj Vasisht,
Atul Khare, and Robert Sobel





Microencapsulation in the Food Industry

A Practical Implementation Guide

Edited by

Anilkumar Gaonkar, Mondelēz International, Glenview, IL, USA

Niraj Vasisht, Biodelivery Sciences International, Inc., Raleigh, NC, USA

Atul Khare, KhareConsulting, Palatine, IL, USA


Robert Sobel, FONA International, Inc., Geneva, IL, USA

Microencapsulation in the Food Industry is written for those who see the potential benefit of using microencapsulation but need practical insight into using the technology. With coverage of the process technologies, materials, testing, regulatory and even economic insights, this book presents the key considerations for putting microencapsulation to work.

An **Introduction** to the field of microencapsulation as applicable to the food industry is the first of 7 sections presented. **Concept of Microencapsulation** describes how the concepts of mass transfer, heat transfer, kinetics, diffusion coefficient, partition coefficient, solubility, permeability, release etc. can be used in solving formulation development challenges. **Process Technologies in Microencapsulation** presents the different microencapsulation technologies along with relevant equipment design aspects, their critical process attributes and factors that impact the phase transition to create microcapsules and microspheres. The state-of-the-art for different processes are highlighted along with commercial examples and with relevant patent literature assisting the reader from an industrial scientist's perspective. **Materials Used in Microencapsulation** explains the matching of shell materials to the appropriate encapsulation technique, in addition to considering "best use" of selected carriers and techniques as they translate into final product form. **Testing And Quality Control** provides information on physical and chemical characterization methods for encapsulated actives and food products containing them. **Regulatory, Quality, Process Scale-Up, Packaging, and Economics** explores the influence of ingredient regulations and how they are disclosed to the consumer (e.g., product labeling). **Microencapsulation Applications** bridges the fundamental research in microencapsulation to the applied research aspect of this art.

Key Features:

- Focuses on applying understanding to real-world products including functional foods, flavor and oxidation stabilization, and color and taste masking
- Includes the latest in processes and methodologies
- Maximizes microencapsulation efforts by providing starting points for frequent use scenarios
- Encompasses over 50 years of combined industry and professional teaching experience



ACADEMIC PRESS

An imprint of Elsevier
store.elsevier.com

ISBN 978-0-12-404568-2



9 780124 045682

Microencapsulation in the Food Industry

A Practical Implementation Guide

Edited by

Anilkumar G. Gaonkar

Niraj Vasisht

Atul Ramesh Khare

Robert Sobel



AMSTERDAM • BOSTON • HEIDELBERG • LONDON • NEW YORK • OXFORD • PARIS
SAN DIEGO • SAN FRANCISCO • SINGAPORE • SYDNEY • TOKYO

Academic Press is an imprint of Elsevier



Academic Press is an imprint of Elsevier
525 B Street, Suite 1800, San Diego, CA 92101-4495, USA
32 Jamestown Road, London NW1 7BY, UK
225 Wyman Street, Waltham, MA 02451, USA

Copyright © 2014 Elsevier Inc. All rights reserved except:
Chapter 10 Copyright © 2014 Thorsten Brandau.
Chapter 19 Copyright © 2014 Commonwealth Scientific and Industrial Research Organisation (CSIRO).

No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopying, recording, or any information storage and retrieval system, without permission in writing from the publisher. Details on how to seek permission, further information about the Publisher's permissions policies and our arrangements with organizations such as the Copyright Clearance Center and the Copyright Licensing Agency, can be found at our website: www.elsevier.com/permissions.

This book and the individual contributions contained in it are protected under copyright by the Publisher (other than as may be noted herein).

Notice

Knowledge and best practice in this field are constantly changing. As new research and experience broaden our understanding, changes in research methods, professional practices, or medical treatment may become necessary.

Practitioners and researchers must always rely on their own experience and knowledge in evaluating and using any information, methods, compounds, or experiments described herein. In using such information or methods they should be mindful of their own safety and the safety of others, including parties for whom they have a professional responsibility.

To the fullest extent of the law, neither the Publisher nor the authors, contributors, or editors, assume any liability for any injury and/or damage to persons or property as a matter of products liability, negligence or otherwise, or from any use or operation of any methods, products, instructions, or ideas contained in the material herein.

Trademarks/Registered Trademarks

Brand names mentioned in this book are protected by their respective trademarks and are acknowledged.

British Library Cataloguing-in-Publication Data

A catalogue record for this book is available from the British Library

Library of Congress Cataloging-in-Publication Data

A catalog record for this book is available from the Library of Congress

ISBN: 978-0-12-404568-2

For information on all Academic Press publications
visit our website at <http://store.elsevier.com/>

		Working together to grow libraries in developing countries
www.elsevier.com • www.bookaid.org		

Contents

Foreword	xiii	2.4 Microcapsule size, shape, and payload	16
Preface	xv	2.5 Physicochemical factors	18
About the Editors	xvii	2.6 Mechanism of diffusion	20
List of Contributors	xix	2.7 Conclusion	24
		References	24
Part I		3. Applications of Mass and Heat Transfer in Microencapsulation Processes	
Introduction		<i>Niraj Vasisht</i>	
1. Introduction to Microencapsulation and Controlled Delivery in Foods		3.1 Introduction	25
<i>Robert Sobel, Ronald Versic, and Anilkumar G. Gaonkar</i>		3.2 Mechanism of diffusion	25
1.1 Introduction	3	3.3 Zero order or pseudo-zero order diffusion model	26
1.2 Microencapsulation defined	3	3.4 Fickian diffusion model	27
1.3 Reasons for microencapsulation	4	3.5 First order diffusion model	32
1.4 Types of microcapsules	5	3.6 Conclusion	32
1.5 Historical account of microencapsulation	5	References	32
1.6 Materials used for microencapsulation purposes	8		
1.7 Microencapsulation techniques used within the food industry	9	Part III	
1.8 Trends in microencapsulation	9	Process Technologies in Microencapsulation	
1.9 Challenges in microencapsulation of food ingredients	10	4. Overview of Microencapsulation Process Technologies	
1.10 The future of microencapsulation of food ingredients	11	<i>James Oxley</i>	
References	11	4.1 Introduction	35
		4.2 Process components	35
Part II		4.3 Processes	37
Concept of Microencapsulation		4.4 Comparisons	39
2. Factors and Mechanisms in Microencapsulation		4.5 Emerging processes and trends	44
<i>Niraj Vasisht</i>		4.6 Process selection	44
2.1 Introduction	15	References	45
2.2 Structural design of the microcapsule	15	5. Atomization and Spray-Drying Processes	
2.3 Microcapsule or microsphere type	16	<i>Irwin C. Jacobs</i>	
		5.1 Introduction	47

5.2	Atomization	48	9.3	Batch fluidized beds for drying, agglomeration, and coating	88
5.3	Drying configurations	50	9.4	Continuous fluidized beds for drying, agglomeration, spray granulation, and coating	89
5.4	Operational practice	54	9.5	ProCell type of continuous spouted beds for drying, agglomeration, spray granulation, and coating	90
5.5	Feed preparation	55	9.6	Technical options for pelletization	92
5.6	Recent advances in atomization and spray-drying processes	55	9.7	Technical options for high-shear granulation	93
5.7	Conclusion	55	9.8	Technical options for extrusion	93
References		56	9.9	Application case studies	94
6.	New Advances in Spray-Drying Processes		9.10	Formulation of enzymes	94
	<i>Karin Nordström Dyvelkov and Jakob Sloth</i>		9.11	Formulation of vitamins	96
6.1	Introduction	57	9.12	Encapsulation of volatile ingredients	96
6.2	Technologies	57	9.13	Conclusion	97
6.3	Computational optimization	57	References		98
6.4	Analyzing the drying process of a droplet	58	10.	Annular Jet-Based Processes	
6.5	Drying kinetics as input for computational fluid dynamics	60		<i>Thorsten Brandau</i>	
6.6	Conclusion	63	10.1	Introduction	99
References		63	10.2	Process technologies	99
7.	Fluid Bed Coating-Based Microencapsulation		10.3	Equipment	102
	<i>Charles Frey</i>		10.4	Materials	107
7.1	Introduction	65	10.5	Conclusion	110
7.2	Wurster (bottom spray) fluid bed coating	68	References		110
7.3	Top-spray granulation	69	11.	Monodispersed Microencapsulation Technology	
7.4	Rotary tangential spray granulation	69		<i>Nathan H. Dormer, Cory J. Berkland and Milind Singh</i>	
7.5	Static tangential spray granulation	69	11.1	Introduction	111
7.6	Discussion	69	11.2	Monodisperse particle fabrication technologies	111
7.7	Formulation considerations	76	11.3	Conclusion	121
7.8	Conclusion	77	References		121
References		78	12.	Coacervation Processes	
8.	Extrusion-Based Microencapsulation for the Food Industry			<i>Cuie Yan and Wei Zhang</i>	
	<i>Jenni Harrington and Martin Schaefer</i>		12.1	Introduction	125
8.1	Introduction	81	12.2	Selection of wall materials	126
8.2	Evolution of extrusion technology	83	12.3	Coacervation encapsulation processes	128
8.3	Conclusion	84	12.4	Parameters influencing the formation of coacervates	130
References		84	12.5	Evaluation of coacervates	132
9.	Spheronization, Granulation, Pelletization, and Agglomeration Processes				
	<i>Michael Jacob</i>				
9.1	Introduction	85			
9.2	Basic equipment	87			

12.6	Stability, controlled release, and bioavailability	134
12.7	Conclusion	135
	References	135
13.	Application of Liposomes in the Food Industry	
	<i>Zahra Mirafzali, Courtney S. Thompson, and Karim Tallua</i>	
13.1	Introduction	139
13.2	What are liposomes?	139
13.3	Liposome stability	141
13.4	Conclusion	149
	References	150
14.	Nanoencapsulation in the Food Industry: Technology of the Future	
	<i>Atul Ramesh Khare and Niraj Vasisht</i>	
14.1	Introduction	151
14.2	Technology advantages	151
14.3	Classification of nanoencapsulated systems	151
14.4	Liquid–liquid systems	152
14.5	Microemulsions	152
14.6	Nanoemulsions	154
14.7	Liposomes	154
14.8	Solid–lipid nanoparticles	154
14.9	Solid–solid systems	154
14.10	Nanofibers	155
14.11	Conclusion	155
	References	155
15.	Aqueous Two-Phase Systems for Microencapsulation in Food Applications	
	<i>Anna Millqvist-Fureby</i>	
15.1	Introduction	157
15.2	Encapsulation in films, gels, and dispersed gel particles	158
15.3	Encapsulation in particulate systems	159
15.4	Conclusion	168
	References	168
	Part IV	
	Materials Used in Microencapsulation	
16.	Selection of Materials for Microencapsulation	
	<i>Niraj Vasisht</i>	
16.1	Introduction	173
16.2	Morphological design	173
16.3	Material selection	173
16.4	Hydrophilic materials	177
16.5	Hydrophobic materials	180
16.6	Conclusion	180
	References	180
17.	Cellulose Polymers in Microencapsulation of Food Additives	
	<i>Dave Wallick</i>	
17.1	Introduction	181
17.2	Properties of cellulosic polymers	181
17.3	Applications of cellulosic polymers in microencapsulation	186
17.4	Process considerations using cellulosic polymers	190
	References	191
18.	The Use of Starch-Based Materials for Microencapsulation	
	<i>Jason Z. Li</i>	
18.1	Introduction	195
18.2	Starch and starch modifications	195
18.3	Characteristics of OSA starches	200
18.4	Using modified starches for microencapsulation	200
18.5	Conclusion	209
	Acknowledgments	209
	References	209
19.	Use of Milk Proteins for Encapsulation of Food Ingredients	
	<i>Mary Ann Augustin and Christine Maree Oliver</i>	
19.1	Introduction	211
19.2	Milk proteins and their function in encapsulation	212

19.3	Encapsulation systems using caseins and whey proteins	214	23.4	Parameters that affect yeast encapsulation performance	268
19.4	Milk proteins in combination with other materials as the encapsulating matrix	216	23.5	Properties of yeast microcapsules	276
19.5	Patent-based strategies	220	23.6	Applications of yeast microcapsules in the food industry	278
19.6	Conclusion	222	23.7	Conclusion	280
References		222	References		280
20.	Gelatin and Other Proteins for Microencapsulation		24.	Pollen and Spore Shells—Nature's Microcapsules	
	<i>Yang Meng and Sylvie Cloutier</i>			<i>Grahame Mackenzie, Stephen Beckett, Stephen Atkin, and Alberto Diego-Taboada</i>	
20.1	Introduction	227	24.1	Introduction	283
20.2	Gelatin	227	24.2	Concept behind using pollen shells for microencapsulation	283
20.3	Soy protein	232	24.3	Structural and chemical features of pollen shells useful for microcapsule formation	284
20.4	Zein protein	234	24.4	Extraction of pollen shells	286
20.5	Pea protein	235	24.5	Modifications to pollen shells	288
20.6	Conclusion	236	24.6	Loading of actives	288
References		236	24.7	Quality control of loaded shells	290
21.	Hydrocolloids and Gums as Encapsulating Agents		24.8	Release of actives	290
	<i>Erin Burnside</i>		24.9	Applications of pollen shells for microencapsulation relevant to the food industry	292
21.1	Introduction	241	24.10	Perceived advantages of pollen shells for microencapsulation	293
21.2	Materials	241	Appendix: Chemical Structure of Sporopollenin		294
21.3	Applications	245	References		295
21.4	Conclusion	250			
References		250			
22.	Fats and Waxes in Microencapsulation of Food Ingredients		25.	Mesoporous Solid Carrier Particles in Controlled Delivery and Release	
	<i>Farah Jean-Jacques Touban</i>			<i>Anna Millqvist-Fureby, Anders Larsson, Mikael Järn, Emiel Speets, Anwar Ahniyaz, Lubica Macakova, and Ulla Hlofsson</i>	
22.1	Introduction	253	25.1	Introduction	299
22.2	Structural diversity in lipids	253	25.2	Carrier particles	301
22.3	Physicochemical properties of lipids	257	25.3	Loading methods	303
22.4	Lipids in microencapsulation applications	261	25.4	Characterization of unloaded and loaded particles	307
22.5	Conclusion	265	25.5	Release measurements	308
References		265	25.6	The effects of characteristics of the active on loading and release	310
23.	Yeast Cells and Yeast-Based Materials for Microencapsulation		25.7	Effects of loading medium	315
	<i>Efstathia I. Paramera, Vaios T. Karathanos, and Spyros J. Konteles</i>		25.8	How can loading and release be controlled?	316
23.1	Introduction	267	References		317
23.2	Description of the yeast cell as encapsulation material	267			
23.3	The yeast cell encapsulation process	268			

Part V Testing and Quality Control

26. Testing Tools and Physical, Chemical, and Microbiological Characterization of Microencapsulated Systems

Linda L. Moran, Yun Yin, Keith R. Cadwallader, and Graciela W. Padua

26.1 Introduction	323
26.2 Physical characterization	323
26.3 Chemical characterization	337
26.4 Conclusion	346
References	348

27. Real-Time Analysis of Oxidative Barrier Properties of Encapsulation Systems

Rohan V. Tikekar and Nitin Nitin

27.1 Introduction	353
27.2 Rapid methods to measure interaction of encapsulation systems with oxidizing agents	354
27.3 Applications of rapid measurement techniques	359
27.4 Conclusion	363
References	364

28. Stability Characterization and Sensory Testing in Food Products Containing Microencapsulants

Young Soo Lee, Soo-Yeun Lee, and Joseph D. Donovan

28.1 Introduction	367
28.2 Measuring stability	367
28.3 Factors affecting wall stability	367
28.4 Factors affecting core stability	370
28.5 Sensory impacts of microencapsulated ingredients in foods	373
28.6 Conclusion	377
References	377

Part VI Regulatory, Quality, Process Scale-Up, Packaging, and Economics

29. Regulatory Considerations of Encapsulation Used in the Food Industry

Jennifer Hoffmann

29.1 Introduction	385
29.2 Animal derivatives	385
29.3 Allergens	386
29.4 Genetic modification and organic	386
29.5 "Natural" claims	387
29.6 Nutritional content	387
29.7 Safe consumption	388
29.8 Safe handling	389
29.9 Conclusion	390
References	390

30. Process Scale-up Considerations for Microencapsulation Processes

Irwin C. Jacobs

30.1 Definition of scale-up within the context of microencapsulation process technology	391
30.2 Physical phenomena in controlled-release process technology	391
30.3 Basic quality by design principles	393
30.4 Tools for improved scaling of microencapsulation process technologies	394
30.5 Troublesome assumptions	396
30.6 Why there are often problems in scale-up	396
30.7 Time and cost constraints	396
30.8 Case study: spray drying and spray congealing	396
30.9 Conclusion	398
References	398

31. Microencapsulation and Packaging—Value-Added Solutions to Product Development

Jose Maria Lagaron, Amparo Lopez-Rubio, Maria José Fabra, and Rocio Pérez-Masiá

31.1 Smart packaging: sensors and heat management materials	399
31.2 Bioactive packaging	402
31.3 Innovative packaging technologies: printing, printed electronics, and scratch and sniff	405
31.4 Conclusion and outlook	406
References	406

32. The Economics of Microencapsulation in the Food Industry

Ronald J. Veršič

32.1 Introduction	409
32.2 The process	409
32.3 Criteria	410
32.4 Processing costs	411
32.5 Conclusion	417
References	417

Part VII Microencapsulation Applications

33. Novel Concepts and Challenges of Flavor Microencapsulation and Taste Modification

Robert Sobel, Michael Gundlach, and Chin-Ping Su

33.1 Introduction	421
33.2 Challenges of flavor encapsulation	423
33.3 Summary of common flavor microencapsulation techniques	429
33.4 Summary of flavor microencapsulation materials	433
33.5 Applications of microencapsulated flavor	435
33.6 Conclusion	439
Acknowledgments	439
References	439

34. Flavor Release and Application in Chewing Gum and Confections

Marc A. Meyers

34.1 Introduction	443
34.2 Why microencapsulate flavors?	443
34.3 Microencapsulation forms	444
34.4 Microencapsulation forms—other types	445
34.5 Chewing gum applications—designing for customized performance	445
34.6 Microencapsulated flavors—when to use them?	448
34.7 To be effective, microencapsulated flavors also require sustained and long-lasting sweetness and sourness	449
34.8 Where is microencapsulated flavor applied in chewing gum applications?	449
34.9 Challenges in microencapsulating flavors	450
34.10 Other confectionery applications	450
34.11 Chewing gum patent review—main companies: Wrigley, Warner—Lambert, Cadbury—Adams/Kraft Foods Global, Nabisco/Hershey confectionery companies (1990–2013)	450
34.12 Conclusion	450
Appendix: Chewing gum patent review	450
References	453

35. Novel Microencapsulation System to Improve Controlled Delivery of Cup Aroma during Preparation of Hot Instant Coffee Beverages

Bary Zeller, Anilkumar Gaonkar, Stefano Ceriali, and Anthony Wragg

35.1 Introduction	455
35.2 Novel microencapsulation system development	456
35.3 Guide to related publications by the authors	457
35.4 Volatile carrier liquids	457
35.5 Model coffee aroma systems	458
35.6 Coffee microcapsule properties	460
35.7 Coffee-aromatized carriers	461
35.8 Carrier-free coffee essences	463
35.9 Discussion	463
Acknowledgments	467
References	467

36. Protection and Delivery of Probiotics for Use in Foods*Moti Harel and Qiong Tang*

36.1	Introduction	469
36.2	Microencapsulation and delivery concepts for probiotics	470
36.3	Drying methods	474
36.4	Delivery forms	478
36.5	Methods for estimating process loss and product shelf-life	479
36.6	Conclusion	481
	References	482

37. Protection and Masking of Omega-3 and -6 Oils via Microencapsulation*Michael Nickerson, Cuie Yan, Sylvie Cloutier, and Wei Zhang*

37.1	Introduction	485
37.2	Encapsulation technologies used for omega-3 and -6 polyunsaturated fatty acids	487
37.3	Characterization methods	492
37.4	Applications	495
	References	496

38. Microencapsulation of Vitamins, Minerals, and Nutraceuticals for Food Applications*Yao Olive Li, Verónica Paula Dueik González, and Levente L. Diosady*

38.1	Microencapsulation as a tool for effective delivery of micronutrients and nutraceuticals	501
38.2	Criteria for developing microencapsulated delivery systems for micronutrients and nutraceuticals	505
38.3	Development of fortified and functional foods	507
38.4	Case study: technical approaches to the fortification of staple foods	511
38.5	Conclusion and perspectives	518
	References	519

39. Taste-Masking and Controlled Delivery of Functional Food Ingredients*Ahmad Akashe and Anilkumar G. Gaonkar*

39.1	Introduction	523
39.2	Why controlled delivery?	523

39.3	Product application	524
39.4	Matrix to core compatibility	524
39.5	Process of microencapsulation	525
39.6	Characterization of microparticles	528
39.7	Summary	532
	Acknowledgments	532
	References	532

40. Microencapsulated Enzymes in Food Applications*Douglas Dale*

40.1	Introduction	533
40.2	Food enzyme market	533
40.3	Enzyme properties and challenges	535
40.4	Encapsulation	535
40.5	Food applications	538
40.6	Conclusion	541
	References	541

41. Commercial Applications of Microencapsulation and Controlled Delivery in Food and Beverage Products*Rufino Perez and Anilkumar G. Gaonkar*

41.1	Introduction	543
41.2	Flavor and taste	545
41.3	Health and wellness	545
41.4	Experiential and interactive effects	546
41.5	Interactive packaging	546
41.6	Trends and outlook	547
	References	548

42. Inventing and Using Controlled-Release Technologies*Ronald J. Veršič*

42.1	Introduction	551
42.2	A needs-based process	551
42.3	Developmental principles	551
42.4	Release profile	552
42.5	Other issues	552
42.6	Releasing the core	553
42.7	Developing a new technology	553
42.8	Public knowledge	554
42.9	Conclusion	554
	References	555

Index	557
-------	-----

Chapter 20

Gelatin and Other Proteins for Microencapsulation

Yang Meng and Sylvie Cloutier

DSM Nutritional Products, Dartmouth, Nova Scotia, Canada

20.1 INTRODUCTION

As nutritious food ingredients, proteins, such as gelatin, soy protein, zein, pea protein, and so on, have many superior properties making them good and widely used microencapsulation shell materials in the food industry.

Emulsifying property is important for microencapsulation shell materials, especially for microencapsulation of oil-soluble ingredients, such as flavor oil, oil-soluble vitamins, and fish oil, and so on. Due to its amphiphilic nature, protein can orient at the oil–water interface with the hydrophilic groups oriented toward the water phase and the hydrophobic groups oriented toward the oil phase to lower the interfacial tension and form the emulsion. Protein can also build the protective barrier around the oil droplet to prevent the emulsion coalescence and maintain the stability of the formed emulsion (Zayas, 1997).

Through microencapsulation, the volatility, flavor, odor, and reactivity of food ingredients are suppressed. The protection of the microencapsulated contents from degradation or loss is provided by the barrier properties of the shell materials. Oxygen is involved in many degradation reactions in foods, such as fat and oil rancidity and vitamin loss. As a group, proteins appear to have lower oxygen permeability (Avena-Bustillos et al., 2011). Table 20.1 lists the oxygen permeabilities of different protein films.

Crosslinking can enhance the barrier properties of protein films, which can be achieved by either chemical or enzymatic treatment. Aldehydes, such as glutaraldehyde and formaldehyde, are generally used to chemically crosslink proteins. However, the toxicity of aldehydes enormously limits the exploitation of their use in food applications. To overcome the restriction in using toxic crosslinkers, microbial transglutaminase (MTGase) has been proposed as a crosslinking reagent for proteins. MTGase catalyzes an acyl-transfer reaction between the γ -carboxyamide group of peptide-bound glutamine residues (acyl donors) and a variety of primary amines (acyl acceptors), including the ϵ -amino group of lysine residues, to form an ϵ -(γ -glutamyl)lysine isopeptide bond (Motoki and Seguro, 1998). Crosslinking protein via Maillard reaction is also widely used in microencapsulation (Graham, 1996). The “Maillard crosslinks” can be formed by heating a protein in the presence of a reducing sugar. The Maillard reaction could also generate antioxidative compounds that can be useful for retarding the oxidation of core material (Anarowicz, 2009).

In addition to the emulsifying and barrier properties, most proteins have high water solubility, good drying property, and are widely available and generally regarded as safe (GRAS), making them ideal shell materials for microencapsulation in the food industry.

20.2 GELATIN

20.2.1 Gelatin Manufacture: From Collagen to Gelatin

As a substantially pure protein food ingredient, gelatin is obtained by partial hydrolysis of collagen derived from the skin, white connective tissue, and bones of animals (Haug and Draget, 2011).

TABLE 20.1 Oxygen Permeability of Protein Films

Protein Type	Test Conditions	Oxygen Permeability, $\text{cm}^3 \text{ mm}^{-2} \text{ d}^{-1} \text{ kPa}^{-1}$
Pork skin ^a	23°C, 55% RH	0.0055
Cattle hide ^a	23°C, 55% RH	0.0048
Warm water fish skin (catfish) ^a	23°C, 55% RH	0.0035
Cold water fish skin (Alaska pollock) ^a	23°C, 55% RH	0.0023
Soy protein isolate ^b	25°C, 50% RH	0.0518
Corn zein ^{c,d}	25°C, 0% RH	0.0120

^aAvena-Bustillos *et al.* (2011).^bCho *et al.* (2010).^cKrochta (2002).^dGlycerol used as plasticizer.

The primary structure of collagen consists of approximately 1050 amino acids called alpha chain. Collagen consists of three alpha chains and each alpha chain is coiled into a left-handed helix to form the secondary structure of collagen. The three chains are twisted around each other to form a right-handed triple helix, which is a rigid rod-like structure that makes the tertiary structure of collagen. These rods assemble together in a quarter-stagger arrangement to form the quaternary structure of the collagen (Schrieber and Gareis, 2007).

The triple-helical structure of collagen arises from its unique amino acid composition and sequence. Table 20.2 shows the amino acid composition of gelatin compared with globular protein (soy protein isolate). Glycine constitutes around 33% of the amino acid component, proline and hydroxyproline together about 22%. The amount varies among different species although the high content of proline and hydroxyproline seems to be characteristic of collagen (Boran and Regenstein, 2010). The predominant sequence of amino acids in alpha chain is Gly-X-Y, where X and Y could be any amino acids but are often proline and hydroxyproline, respectively. This unique sequence allows for the feasible helix formation. Proline and hydroxyproline display a lateral group that loops back to reattach the main chain and results in a ring, which limits the rotation of the polypeptide backbone and thus explains the stabilization of the collagen triple helix and gives collagen rigid structure to serve as the main stress-bearing component of tissues. The entire structure of the collagen is stabilized and reinforced by crosslinks in the form of covalent bonds (Schrieber and Gareis, 2007).

In the manufacture of gelatin, collagen containing raw material is first pretreated with acid or alkali to partially cleave the crosslinks, resulting in two types of gelatin. Type A gelatin is produced by the acid process, which is mainly used with pig skin and fish skin and are not heavily crosslinked (Schrieber and Gareis, 2007). In the acid process, the raw material is soaked in dilute mineral acid for up to 24 h. Type B gelatin is pretreated by the alkali process, in which the raw material is subject to alkali treatment. The alkali process is used for heavily cross-linked collagen, such as bovine hide, and takes longer time (Haug and Draget, 2011). During the pretreatment, the regular triple-helix structure of collagen is hydrolyzed to form random gelatin coils, which can then be extracted with hot water. After extraction, the gelatin solution is usually filtered, deionized, concentrated by evaporation, and then sterilized. The gelatin solution is then cooled to gel. The gels are extruded into "noodles" that are fed onto conveyor belts for drying. The dried gelatin noodles are then ground into particles of 0.1 to 10 mm in diameter, which is usually translucent, brittle, colorless or slightly yellow, nearly tasteless, and odorless (Haug and Draget, 2011).

Type A gelatin has an isoionic point of 7 to 9 based on the severity and duration of the acid treatment, which is hardly different from collagen. For type B gelatin, the alkali hydrolyzes the asparagine and glutamine side chains and almost completely converts them to aspartic and glutamic acid, respectively. As a result, type B gelatin has an isoionic point of 4.8 to 5.2 (Schrieber and Gareis, 2007).

Gelatin is generally regarded as safe (GRAS). Bovine spongiform encephalopathy (BSE) is virtually impossible to survive the gelatin production process (Haug and Draget, 2011).

TABLE 20.2 Amino Acid Composition (% mole) of Gelatin and Globular Proteins

Amino Acid	Pork Skin ^a	Cattle Hide ^b	Warm Water Fish Skin (Catfish) ^b	Cold Water Fish Skin (Alaska Pollock) ^c	Soy Protein Isolate ^d
Aspartic acid	4.6	4.83	4.59	5.21	11.81
Hydroxyproline	9.1	10.39	7.72	5.3	N/A
Threonine	1.8	2.01	2.6	2.68	4.1
Serine	3.5	3.52	3.61	5.85	5.48
Glutamic acid	7.2	7.78	7.22	7.17	21.29
Proline	13.2	13.78	11.14	10.1	5.29
Glycine	33	28.74	34.01	35.7	3.86
Alanine	11.2	11.91	12.4	10.9	3.83
Valine	2.6	2.16	2.19	1.67	4.41
Cystine	0	0.04	0.1	0.14	0.06
Methionine	0.4	0.33	0.49	1.13	0.93
Isoleucine	1	1.28	1.17	1.07	4.48
Leucine	2.4	2.59	2.09	2.1	7
Tyrosine	0.3	0.22	0	0.24	3.71
Phenylalanine	1.4	1.33	1.3	1.2	5.3
Hydroxylysine	0.6	0.86	0.58	0.61	N/A
Lysine	2.7	2.77	3.1	2.78	5.39
Histidine	0.4	0.47	0.6	0.8	2.9
Arginine	4.9	4.98	5	5.18	7.57
Tryptophan	0	N/A	N/A	N/A	N/A
Homocystine	N/A	0.02	0.09	0.16	N/A

^aZhou et al. (2006).^bAvena-Bustillos et al. (2006).^cChou et al. (2006).^dTang et al. (2006).

20.2.2 Gelation of Gelatin

Gelatin is insoluble in cold water and swells or hydrates when stirred into cold water. The swollen gelatin particles can hold water 5 to 10 times their weight. When the temperature is raised above 40°C, the swollen gelatin particles dissolve and form a colloid solution or sol, in which the gelatin molecules behave as random coils in water. When the sol temperature is lowered the sol-gel transition happens, during which the gelatin molecules partly revert to the triple-helix structure of collagen as some crosslinks are formed. This sol-gel transition is thermoreversible because the bonding energy in gelatin is relatively weak (Schrieber and Gareis, 2007).

Forming thermally reversible gels is the most remarkable characteristic of gelatin. Gelatin solution will start gelling when the temperature drops below a certain point, which is called gelling temperature. The formed gel will start melting when the temperature increases above a certain point, which is called the gel melting point, and is usually lower than human body temperature. This melt-in-the-mouth property makes gelatin superior as the shell material to encapsulate

TABLE 20.3 Gelling and Melting Temperature of Gelatins

Gelatin Type	Gelling Temperature °C	Melting Temperature °C
Pork skin ^a	27	29
Cattle hide ^b	24.7	32.3
Warm water fish skin (catfish) ^a	22	25
Cold water fish skin (Alaska pollock) ^c	11.9	21.2

^aLi et al. (2008).^bCadmundson (2002).^cZhou et al. (2006).

flavors and nutrients in the food industry (Baziwane and He, 2003). Table 20.3 shows the gelling and melting temperatures of different gelatins. In general, mammalian gelatin has the highest gelling temperature, followed by warm water fish gelatin; the cold water fish gelatin has the lowest gelling temperature.

Gel strength is the most important attribute of gelatin. It depends on the gelatin type, molecular size, concentration, temperature, and setting time. Gelation of gelatin is a slow setting process and the full gel strength is attained after 15 h. When determined by the standard method (GMIA, 1986), gel strength is graded by the Bloom value. Gelatin gel is made by cooling 6.67% gelatin solution at 10 °C for 17 h. The gel strength, or Bloom value, is measured as the force, in grams, required to impress a 0.500 in diameter plunger to a depth of 4 mm into the surface of the gel. Commercial gelatins have Bloom values from 50 to 300 Bloom grams, varying from low Bloom (<150), medium Bloom (150–220), to high Bloom (>220) types. Gelatin is usually priced according to the gelling ability; consequently, the higher the Bloom, the higher the price.

Gelatin is a mixture of polymers with different chain lengths. The molecular weight distribution of gelatin is important for its gelation properties. For example, gelatin with high molecular weight normally has high gel strength and high gelling temperature. In the gelatin manufacturing process, with the control of pretreatment and extraction conditions, the desired molecular weight distribution of gelatin is obtained (Haug and Draget, 2011). For example, lower temperature extraction produces high molecular weight gelatin because less hydrolysis of the polypeptide backbone occurs.

Gelatin type is another important factor for gelation properties. Normally, fish gelatin from warmer waters has a similar gel strength to mammalian gelatins and they share similar hydroxyproline content. Fish gelatin from cold water species has low or no gel strength, which is due to its low hydroxyproline content (Table 20.2) (Karim and Bhat, 2009). But there are advantages to using low Bloom gelatin as a stabilizer of emulsions. The emulsion can be produced at or below room temperature, which allows the loading materials (e.g., fish oil) to avoid harsh conditions (e.g., high process temperatures), which can be detrimental to the stability of the loading substance.

As shown in Table 20.1, gelatin has better oxygen barrier properties than globular proteins because of its more linear structure, leading to higher cohesive energy density and lower free volume (Miller and Krochta, 1997).

20.2.3 Gelatin as Shell Material in Microencapsulation

Gelatin has been used as shell material to encapsulate different food ingredients through different technologies due to its superior physical and chemical properties.

20.2.3.1 Spray Drying

In the food industry, spray drying is the most commonly used microencapsulation method. Gelatin microcapsules prepared by spray drying are good carriers for many food ingredients due to the emulsifying and film-forming properties of gelatin.

Lipophilic food ingredients are normally emulsified before being encapsulated by spray drying. Compared with globular proteins, such as casein and whey protein, gelatin is a relatively weaker emulsifier (Dickinson and Lopez, 2001). But gelatin has very good film-forming properties during spray drying. Matsuno and Adachi (1993) interpreted the drying curve of different microencapsulation wall materials in terms of the ability to form a dense network. They suggested that the gelatin drying curve showed that the drying speed decreased rapidly at the early stage of drying,

which implied the rapid formation of a dense film and a good protection of core ingredient. Gelatin is thus considered as the most suitable for microencapsulation using a spray-drying process (Gharsallaoui et al., 2007). Liu et al. (2001) used gum arabic and maltodextrin to encapsulate ethyl butyrate by spray drying. The retention of ethyl butyrate was quite low. By adding 1% gelatin they found that the formation of crust on the surface of the droplets was improved and the retention of ethyl butyrate was appreciably increased.

Gelatin is normally used together with hydrocarbon compounds as shell materials in microencapsulation by spray drying. Shu et al. (2006) prepared lycopene microcapsules using spray drying with gelatin and sucrose as shell materials. Sucrose was used as a plasticizer, which was also believed to promote the formation of spherical and smooth-surfaced microcapsules (Ozgun and Mustafa, 2005). Bruschi et al. (2003) developed propolis ethanolic extraction powder encapsulated in gelatin by spray drying. When mannitol was added in the formulation, the dried powder had a very smooth and uniform surface, and spherical shape. Mannitol retains some water molecules linked to its own structure and could fill the empty space of the microparticles, preserving the hydration, avoiding depressions on the surface, and assuring a more uniform wall of the obtained microparticles (Bruschi et al., 2003).

20.2.3.2 Gelation

Gelatin has been used for microencapsulation based on its gelation property. Different approaches can be used to encapsulate food ingredients in gelatin gels. Gelatin gels show high permeability and dissolve under warm conditions, so the crosslinking of gelatin matrix is normally essential.

A simple way to use gelatin gel for encapsulation is to directly incorporate the core materials in the gelatin solution and then induce the gelation and crosslink the gel.

In patent US 5153177 (Bower et al., 1992), a crosslinked gelatin hydrogel was prepared to encapsulate fat-soluble vitamins. The gelatin was dissolved in 60°C water together with a reducing sugar, like fructose, and a salt, like calcium acetate. The oil containing fat-soluble vitamin was mixed into the solution and the mixture was allowed to gel. The gelled slab was dried at ambient condition and then kept at 70°C for 6 h for Maillard reaction crosslinking. The crosslinked slab was kept insoluble in boiling water. US Patent 4670247 (Scialpi, 1987) revealed a process called powder catch to make water-insoluble beadlets to encapsulate fat-soluble vitamins. The first step was the emulsification of the fat-soluble vitamins in gelatin and reducing sugar solution. The emulsion was then sprayed into collecting powder, which converted droplets to particles. The gelatin gelled during this process. The collecting powder can be starch or modified starch, such as starch esters. The particles were then separated and dried with air stream. The dried beadlets were heated to high temperature (90–180°C) to induce a Maillard reaction to make insoluble beadlets. US Patent 6444227 (Leuenberger et al., 2002) reported a similar process to prepare beadlets but crosslinked the gelatin matrix by radiation or enzyme treatment. Patent WO 2005/089569 (Diguett et al., 2005) applied these beadlets containing polyunsaturated fatty acid in the extruded foods with excellent sensory properties.

Another way to encapsulate food ingredients in gelatin gel constitutes two steps. Gelatin microspheres are first prepared, which are then loaded with the food ingredients.

Gelation-induced phase separation is normally used to prepare the gelatin microspheres. Iwanaga et al. (2003) used the water-in-oil emulsion technique to prepare gelatin microspheres. Gelatin aqueous solution (10%) was preheated to 40°C and added drop-wise into olive oil under stirring to form the water-in-oil emulsion. The emulsion was cooled to induce the gelation of the gelatin droplets under stirring. The collected gelatin microspheres were crosslinked using glutaraldehyde and then freeze dried. Kong et al. (2011) prepared gelatin microspheres by the water-in-water emulsion technique. Gelatin was dissolved in water under stirring at 60°C to form a homogeneous solution, which was used as the dispersed phase. This gelatin solution was added drop-wise into polyethylene glycol (PEG) aqueous solution under agitation at 60°C. The PEG solution formed the continuous phase in this water-in-water emulsion system. Then the gelatine microspheres were solidified by rapidly cooling to 5°C. The gelatin microspheres were purified by multiple washing with chilled water. These microspheres were then crosslinked with glutaraldehyde and dried. Morita et al. (2001) prepared gelatin microspheres by freeze drying aqueous solutions containing gelatin and PEG. Phase separation between gelatin and PEG during freezing was assumed to be the mechanism of the formation of gelatin microspheres.

The prepared gelatin microspheres can be loaded with ingredients by diffusion. Dinarvand et al. (2005) loaded gelatin microspheres with lactic acid by immersing them in an aqueous solution of lactic acid. Yamamoto et al. (2001) prepared an aqueous solution of the protein to be loaded and dropped it onto the prepared dry gelatin microspheres. Iwanaga et al. (2003) discussed the *in vitro* release rate of insulin from gelatin microspheres prepared with various crosslinking densities and concluded that the release rate could be controlled by the density of the crosslinking.

20.2.3.3 Coacervation

Microencapsulation by proteins can be obtained by the formation of an insoluble layer of protein around fine droplets of core material. Usually, the formation of the insoluble layer is achieved by simple or complex coacervation. The first approach is based on the addition of compounds with high affinity for water, such as alcohols. The second approach is based on the formation of a protein-rich layer around the core material, by interaction with oppositely charged polymers (Magdassi and Vinetsky, 1995). The gelatin crosslinking process is often used to fix the shell structure and the coacervates can be dried by different ways, such as spray drying and freeze drying.

Patent US 5035896 (Apfel et al., 1991) described a simple coacervation process using low melting point fish gelatin being soluble at 5 to 10°C. The coacervation of fish gelatin can be brought by lower alkyl alcohols such as ethanol and inorganic salts such as sodium sulfate. In the gelatin-based microencapsulation process, normally gelatin must be heated to approximately 40°C or above to dissolve the gelatin. This temperature may adversely affect heat labile core materials. The process of this invention is particularly useful for heat-sensitive core materials to be encapsulated in gelatin shell.

In a complex coacervation process, gelatin has been widely used as positively charged polymer. Patent US 7727629B2 (Yan, 2010) revealed a complex coacervation process to make multicore microcapsules. Type A gelatin with 275 of Bloom and isoelectric point of 9 was dissolved in 50°C deionized water. Fish oil was dispersed into the gelatin solution followed by homogenization to form oil-in-water emulsion. The emulsion was diluted with deionized water at 50°C. The sodium polyphosphate solution was then added into the emulsion with agitation. The pH was then adjusted to 4.5 with a 10% aqueous acetic acid solution. During pH adjustment and the cooling step that followed, coacervates formed from gelatin and polyphosphate coated onto the oil droplets to form primary microcapsules. After cooling, the primary microcapsules started to agglomerate to form lumps under agitation. After further cooling, polymers remaining in the solution further coated the lumps of primary microcapsules to form microcapsules with an outer shell and average size of 50 µm. Once the mixture was cooled to 5°C, glutaraldehyde was added to crosslink the shell. The mixture was then warmed to room temperature and stirred for 12 h. Finally, the microcapsule suspension was washed with water. The washed suspension was then spray dried to obtain a free-flowing powder. The powder particle size would be a little bigger than the size of microcapsules in the slurry and vary according to the drying conditions.

Gelatin has been used in complex coacervation with different polyanions. With acacia as polyanion, Junyaprasert et al. (2001) prepared gelatin acacia complex coacervates with vitamin A palmitate in corn oil as the core material. Silva et al. (2012) used bovine gelatin and pectin as wall material to encapsulate lycopene by a complex coacervation process.

The gelatin coacervation process can be controlled by pH, polymer concentration, and agitation (Yan, 2010). Nakagawa and Nagao (2012) used a freezing process to control the gelatin complex coacervation. An oil-in-water emulsion stabilized by gelatin–acacia solution was prepared, and the pH of the emulsion was adjusted with acetic acid. When emulsion pH was adjusted to 3 and 4, clear phase separations were confirmed. When emulsion pH was adjusted to 4.7, the emulsion was visibly stable at ambient temperature. By freezing the pH 4.7 emulsion, complex coacervation was confirmed. The membrane properties were found to be dependent on the cooling rate during freezing. However, freezing the emulsions with pH levels of 3.0 and 4.0 caused damage to the membrane due to ice crystal formation.

Surfactants play an important role in the gelatin complex coacervation process. Bhattacharyya and Argillier (2005) and Li et al. (2009) enhanced the shell structure of the gelatin–acacia complex coacervation microcapsules using cationic surfactants. Li et al. (2009) enhanced the shell structure of the gelatin–sodium carboxymethylcellulose complex coacervate by using sodium dodecyl sulfate (SDS). Magdassi and Vinetsky (1995) prepared gelatin microcapsules using type A gelatin and anionic surfactant SDS with soybean oil as the core material.

20.3 SOY PROTEIN

Soybean is a species of legume that contains 35 to 40% of proteins. Ten percent of soy proteins are water-soluble albumins and around 90% of soy proteins are globulins (Fukushima, 2004). Globulins are soluble in diluted salt solutions. β -Conglycinin and glycinin are the two major globulins in soy protein. β -Conglycinin is a trimeric protein with the sedimentation coefficient (SC) of 7S and the molecular weight (MW) of 70 kDa, whereas glycinin is a hexameric protein and has the SC of 11S and the MW of 350 kDa (Fukushima, 2004). The ratio between β -conglycinin and glycinin, which varies with the species and production process, has a significant effect on protein functionality (Swanson, 1990). For example, the higher hydrophobicity and more easily unfolded structure in β -conglycinin make its emulsifying ability much stronger than that of glycinin (Fukushima, 2004).

In the food industry, soybean attracts people's attention partly due to the nutritional value of soy proteins and other components in soybean, such as genistin, and partly due to the functional properties of soy proteins in food systems. Soy protein has superior functional properties, such as fat absorption, gelation, emulsification, film forming, and good barrier property, which make soy protein a good microencapsulation shell material. However, off-flavors (grassy, beany, bitter, astringent, and chalky) and allergen issue limit the application of soy proteins (Okubo et al., 1992). Soy protein isolate (SPI) is the most widely used soy protein product used for microencapsulation in the food industry. Aqueous alkaline extraction followed by isoelectric precipitation and salt extraction are commonly used for producing SPIs.

20.3.1 Spray Drying

Soy protein has been used in microencapsulation through different techniques. Spray drying is the commonly used one. Solubility is important for a microencapsulation shell material used in the spray-drying method. Protein solubility results from the hydrophilic groups on the surface of the protein interacting with water. The pH of the system is a major factor in determining solubility of a legume protein, as solubility decreases around the isoelectric point of the protein. In general, most legume proteins have very low solubility between pH 4 and 6, but outside this range, solubility increases dramatically (Boye et al., 2010). Soy protein possesses good solubility in water at pH higher than 9 (Fukushima, 2004). Soy protein has good drying and film-forming properties (Nesterenko et al., 2012) and good fat-absorbing property, which make it widely explored in microencapsulation of fat-soluble ingredients by spray drying.

With flavor compounds as core materials, Charve and Reineccius (2009) evaluated the microencapsulation performance of SPI, whey protein isolate (WPI), sodium caseinate, modified starch, and gum arabic by spray drying. The proteins effectively reduced the oxidation of the core material, which was pronounced in modified starch and gum arabic shells. WPI and SPI were good materials for the production of dried flavors based on volatile retention during spray drying. However, they performed poorly during storage as nonenzymatic browning occurred. Sodium caseinate performed poorly due to the low infed solids limited by viscosity and its susceptibility to browning.

Casein hydrolysate has high biological activity for nutraceutical food formulation, but its application is limited by its intense bitter taste and high hygroscopicity. Ortiz et al. (2009) encapsulated casein hydrolysate by spray drying with SPI as wall material, which significantly attenuated the bitter taste of the casein hydrolysate. The bitter taste of casein hydrolysate is directly related to the existence of hydrophobic groups, which were probably less exposed due to hydrophobic interactions with the SPI in the encapsulating process. But the microcapsules had much higher hygroscopicity. Favaro-Trindade et al. (2010) used SPI and gelatin mixture as the shell and made the spray-dried casein hydrolysate microcapsules with lower hygroscopicity.

Rascón et al. (2011) evaluated the performance of SPI and gum arabic on encapsulating carotenoid by spray drying. When gum arabic was used as shell material, the microcapsules were stable at low water activities during storage. But if water activity (a_w) is above 0.318, the degradation rate of carotenoid increased substantially, and if a_w is above 0.743, microcapsules became unable to keep their structural integrity and led to the gradual dissolution of the walls. The microcapsules with SPI as wall material were very stable at high water activities from 0.721 to 0.851.

Emulsification is critical for microencapsulation by spray drying. Soy proteins exhibit high emulsifying properties compared to other plant proteins (Zayas, 1997). Like other proteins, SPI is an ineffective emulsifier near the isoelectric point, where charges and solubility are minimal.

Kim et al. (1996) investigated the abilities of gum arabic, sodium caseinate, WPI, and SPI to form orange oil emulsion. Although SPI generated the largest orange oil emulsion droplets, SPI-emulsified orange oil droplets were found the most stable against creaming during 10 days of storage at room temperature, which could be due to SPI-emulsified orange oil droplets being surrounded by the thickest membrane structures. The spray-drying study (Kim and Morr, 1996) showed that SPI was the most effective wall material for retaining orange oil during spray drying.

Soy protein has been investigated through different modification processes to improve the emulsifying property. Protein hydrolysis results in peptides with smaller molecular size and less secondary structure than the original proteins, which give increased solubility and decreased viscosity. A strictly controlled hydrolysis usually improves the emulsifying property of the protein. Wu et al. (1998) prepared soy protein peptides by papain hydrolysis and obtained high emulsifying properties and protein solubility. Nesterenko et al. (2012) modified SPI by enzymatic hydrolysis and N-acylation. The oil-in-water emulsions prepared with native or modified SPI and hydrophobic α -tocopherol were spray dried to produce α -tocopherol microparticles. The results demonstrated that emulsions prepared with modified SPI had smaller droplet size and lower viscosity compared to those prepared with native proteins. The efficiency of oil retention decreased after protein hydrolysis from 79.7 to 38.9%, but the grafting of hydrophobic chain by acylation improved efficiency of α -tocopherol retention up to 94.8%. Molina et al. (2001) reported that the emulsifying ability index (EAI)

reached the highest level after treatment under 400 to 600 MPa. Wang et al. (2008) suggested that unfolding of proteins and subsequent exposure of hydrophobic groups during the high pressure treatment improved the emulsifying property of SPI. But high pressure treatment resulted in a gradual and significant decrease in emulsion stability index (ESI).

20.3.2 Coacervation

SPI is amphoteric and has an isoelectric point of pH 4.5, similar to that of gelatin. Its potential to be used as a polycation in complex coacervation has been explored. Mendanha et al. (2009) encapsulated casein hydrolysate by SPI–pectin complex coacervation. The bitterness was significantly masked. Compared with the spray-dried casein hydrolysate microcapsules (Ortiz et al., 2009), the complex coacervates had much lower hygroscopicity. Nori et al. (2011) encapsulated propolis extract with SPI and pectin by the complex coacervation process to obtain it in powder form. The microencapsulation also preserved the phenolic and flavonoid compounds present in free propolis from oxidation. Gan et al. (2008) used SPI as shell material and prepared fish oil microcapsules by simple coacervation. Microbial transglutaminase (MTGase) and ribose were tried to crosslink the microcapsules. It was found that compared to the use of ribose, the use of MTGase to crosslink SPI did not satisfactorily yield sufficient protection to the fish oil.

20.3.3 Gelation

Similar to gelatine, soy protein has been used as microencapsulation shell materials based on its gelation property.

Heat denaturation is normally regarded as a prerequisite for gel formation of globular proteins (Chen and Subirade, 2009). In a stable soy protein solution, the surface of the soy protein micelles is predominantly occupied by the hydrophilic group. Heating protein dispersion causes protein molecular unfolding, in which functional groups (such as sulfhydryl groups or hydrophobic groups) become exposed and interact with each other through disulfide interchange reaction or hydrophobic bonding leading to protein aggregation (Zhang et al., 2012). When the protein concentration is high enough, aggregation leads to formation of a gel. At lower concentrations, aggregation leads to precipitation of the protein. For SPI, the minimal protein concentration for gelation is around 6.6% (Bikbov et al., 1979). Disulfide bond formation on heating makes the gelation process irreversible. In contrast, gelatin gels are stabilized mainly by hydrogen bonds and the gelation process is thermoreversible. The gelation and characteristics of soy protein gel depend on the protein species and concentration, pH, and ionic strength. Minerals, especially calcium, can serve as a salt bridge to enable polypeptide chains to approach one another, facilitate the protein aggregation, and therefore enhance the strength of the gel. In the case of β -conglycinin and glycinin, the larger numbers of sulfhydryl groups and their topology in glycinin make glycinin gel much harder and more turbid in comparison with β -conglycinin gel (Fukushima, 2004). Chen and Subirade (2009) prepared SPI microspheres using the gelation method and loaded the prepared microspheres with riboflavin.

Excluding heat-induced gelation, enzyme-induced soy protein gelation was also explored for microencapsulation purposes. Cho et al. (2003) encapsulated fish oil using the double emulsification and subsequent enzymatic gelation method. SPI was used as shell material and it showed higher reactivity with MTGase.

20.4 ZEIN PROTEIN

Commercial zein is essentially a by-product of the corn wet-milling industry. The protein content of corn varies from 6 to 12% on a dry basis. According to the solubility in selected solvents, corn proteins primarily include albumin (soluble in water), globulin (soluble in salt), glutelin (soluble in alkali), and zein (soluble in alcohol). Depending on the protocol used for protein fractionation, zein content ranges from 35 to 60% of the total protein of corn (Shukla and Cheryan, 2001). Zein contains a rich amount of glutamic acid (21–26%), leucine (20%), proline (10%), and alanine (10%), but lacks basic and acidic amino acids. The high amount of nonpolar amino acid residues and lack of basic and acid amino acids are responsible for the insolubility of zein (Shukla and Cheryan, 2001). Biologically, zein is a mixture of proteins with various molecular size, solubility, and charge. Esen (1986) separated zein into three fractions labeled α -zein, β -zein, and γ -zein, based on the solubility in isopropyl alcohol (IPA) solutions. α -Zein can be extracted using only aqueous alcohol, whereas the other zeins need a reducing agent in the solvent to be extracted. α -Zein accounts for 75 to 85% of the total zein. Commercial zein is mainly α -zein (Anderson and Lamsa, 2011) extracted by 86% aqueous IPA, which selectively dissolves α -zein and minimizes the other fractions of zein.

Zein has been employed as an edible coating for foods and pharmaceuticals because of its low moisture absorption, high thermal resistance, and good mechanical, oxygen, and aroma barrier properties (Shukla and Cheryan, 2001).

From a nutritional point of view, zein is deficient in essential amino acids, such as lysine and tryptophan. At the same time, its insolubility in water limits its use in food products. However, zein has good potential as a shell material in microencapsulation due to its unique hydrophobic properties. For example, it is interesting to use zein as a food grade biopolymer carrier of antimicrobials because zein is insoluble in conventional food beverages (Zhong and Jin, 2009).

20.4.1 Spray Drying

Zein can form tough, glossy, hydrophobic, greaseproof films that are resistant to microbial attack, with excellent flexibility and compressibility. Therefore, zein has been explored for microencapsulation through spray drying. Zhong and Jin (2009) prepared spray-dried zein microcapsules to encapsulate lysozyme, an antimicrobial. Sustained release of lysozyme was obtained, which is important for an antimicrobial to enhance its efficacy. Quispe-Condori et al. (2011) prepared flax oil microcapsules using zein as a coating material by spray and freeze drying. It was demonstrated that spray drying had much higher microencapsulation efficiency than freeze drying.

20.4.2 Zein Microspheres by Solvent Evaporation

Zein is soluble only in aqueous ethanol, so aqueous ethanol may be used as a solvent to dissolve both lipophilic bioactive compounds and the carrier zein. Ethanol is easily removed through evaporation, which makes it possible to prepare zein microspheres by phase separation in a nonsolvent followed by solvent removal by evaporation.

Parris et al. (2005) reported a process to make zein microspheres to encapsulate essential oils. In the process, the oil and corn zein were dissolved in aqueous alcohol, and then rapidly sheared in water containing a small amount of dispersant. The decrease of overall ethanol concentration resulted in the precipitation of oil-loaded zein particles. The suspension of particles was freeze dried. Zhong and Jin (2009) used a similar method and prepared fish oil-loaded zein microspheres. Su (2012) encapsulated citral flavor in zein by the solvent evaporation method. Patent WO 91/06286 prepared zein microspheres containing insulin. Zein was dissolved in 90% ethanol to form the encapsulating phase. Insulin was added to the zein solution. The mixture was dispersed into an immiscible phase (corn oil) with agitation. The first solvent (ethanol) is then removed by heating the mixture to 45°C, then cooled down to room temperature. Zein is insoluble in corn oil, and precipitates after evaporation of ethanol, forming a suspension of microspheres. The resulting microspheres were repeatedly washed with petroleum ether to remove the oil and filtered. The washed microspheres were then dried. Low temperature is one of the advantages of this process. Zein was also found promising in microencapsulation by other techniques, such as electrospinning (Torres-Giner et al., 2010).

20.5 PEA PROTEIN

Pea is a leguminous plant. Like other legume seeds, pea seeds contain high amounts of protein (20–30%). Pea proteins mainly exist as globulins (65–80%), which are also the main components in pea protein isolate (PPI) products. Globulins are composed of legumin 11S and vicilin 7S. Legumin is a hexameric oligomer consisting of 6 subunits with a molar mass of 60 kDa. Each subunit has one basic and one acidic subunit associated via a disulfide bond. Vicilin is a trimer and each subunit has a molar mass of about 50 kDa. The ratio of legumin to vicilin ranges from 0.2 to 1.5 depending on the genetics as well as the processing involved (Casey et al., 1982). The use of pea protein in the food industry for the formulation of new food products is very interesting because of its nonallergenic characteristic, despite the high nutritive value and good functional properties (Gharsallaoui et al., 2009).

20.5.1 Spray Drying

Pea protein has good film-forming properties (Viroben et al., 2000) and has been used as shell material in microencapsulation by the spray-drying method.

Gharsallaoui et al. (2012a) encapsulated medium chain triglyceride oil using PPI and maltodextrin by spray drying. They found that microcapsules with lower dextrose equivalent (DE) maltodextrin were shallow and presented rough surfaces, and microcapsules with higher DE maltodextrin were circular and uniform showing minimum cracks and dents on the surface. Qi (2004) encapsulated β -carotene in a PPI and corn syrup solid (DE40) system using emulsification and spray drying. They found that corn syrup solid had significant effect on the β -carotene retention during storage. Pea protein-stabilized emulsions can be very sensitive to environmental factors such as pH and ionic strength. For this reason, they are usually combined with another emulsifier/stabilizer such as high methoxyl pectin (Gharsallaoui et al., 2010).

Gharsallaoui et al. (2012b) prepared multilayered emulsions using PPI and pectin to encapsulate flavor compounds (ethyl esters) and spray dried the emulsions to obtain dry powders. The results were compared with spray-dried powders from monolayered emulsion stabilized only by PPI. They suggested that the addition of pectin markedly improved the retention of the flavor compounds, which was possibly due to pectin being able to improve physical integrity of emulsion oil droplets during spray drying by preserving the β -sheet secondary structure of pea protein when pea globulins/pectin complexes are heated. Pea proteins were also successfully used for microencapsulation of hydrophilic ingredients by spray drying (Pereira et al., 2009).

To be used as a shell material in spray-dried emulsion, emulsifying property is important. Ducl et al. (2004a) reported that pea globulins were highly surface active at the oil–water interface, even more than gelatin at the same concentration. Karaca et al. (2011) compared emulsifying properties of PPI with SPL. PPI had lower emulsion capacity and stability, which was attributed to its higher surface hydrophobicity, lower surface charge, and lower solubility. They suggested that isolates produced by isoelectric precipitation had higher surface charge and solubility compared to those produced by salt extraction. Gharsallaoui et al. (2009, 2012a) evaluated the pH dependence of the stability of PPI emulsifying capacity. They reported the lowest emulsifying capacity at pH around the isoelectric point ($pI \approx 4.3$), and both acidic and alkaline pH improved the emulsion capacity indicating the positive correlation between solubility and emulsifying capacity of PPI. The high emulsifying capacity of PPI at pH values below 4 and above 5 is due to intermolecular repulsion of charged amino and carboxyl groups, respectively; this aided dispersion of the protein molecules and increased repulsions between protein-stabilized oil droplets. At pH 4 to 5, the lack of electrostatic repulsions among emulsion particles promoted rapid coalescence and this decreased the volume of the emulsified fraction. They also stated that emulsions were more stable to creaming at acidic pH than at alkaline pH ranges, which was interpreted in terms of pea protein solubility, globulin dissociation, and oil-droplet surface electrostatic charge. Koyoro and Powers (1987) reported similar results. They found that at pH 4, pea protein globulins had minimum solubility and emulsifying capacity, which was improved when pH went higher or lower. They reported higher emulsifying capacity of pea protein globulins at pH 3 than pH 7, which followed their solubility profiles. As pea protein contains a large amount of reactive amino groups (lysine residue), chemical modification reactions onto the amino group, such as acetylation or succinylation, could effectively be carried out. These reactions were powerful to improve, for instance, emulsifying properties (De Graaf et al., 2001).

20.5.2 Coacervation and Gelation

Ducl et al. (2004b) demonstrated the potential of using PPI as polycation in complex coacervation to encapsulate medium chain triglyceride. Gum arabic was used as polyanion in the process and the optimum coacervation condition was obtained at pH 2.75 with a protein:polysaccharide ratio of 3:7.

PPI shows good potential as a matrix material for the microencapsulation of β -carotene, by means of supercritical CO_2 technology (De Graaf et al., 2001). In this process, microspheres based on PPI were first prepared by a water-in-oil emulsion technique. Stable PPI microspheres were obtained by gelation of the pea protein by heat treatment. The PPI microspheres were isolated and dried to give a free-flowing powder. β -Carotene was then loaded in the microspheres via supercritical CO_2 treatment.

20.6 CONCLUSION

Gelatin and other plant source proteins, such as soy protein, corn zein, and pea protein, have good emulsifying and oxygen barrier properties. Proteins, especially gelatin, have excellent drying property, film-forming property, and unique gelation property. Based on those physical and chemical properties, different techniques, including spray drying, coacervation, gelation, and so on, have been used to microencapsulate food ingredients with proteins as shell materials.

REFERENCES

- Amarowicz, R., 2009. Antioxidant activity of Maillard reaction products. *Eur. J. Lipid Sci. Technol.* 111, 109–111.
- Anderson, T.J., Lamsa, B.P., 2011. Zein extraction from corn, corn products, and coproducts and modifications for various applications: a review. *Cereal Chem.* 88, 159–173.
- Apfel, M.A., Ghebrey-Sellassie, I., Nesbitt, R.U., 1991. Water insoluble drugs coated by coacervated fish gelatin. US Patent 5,035,896.
- Avena-Bustillos, R.J., Olsen, C.W., Olson, D.A., Chiou, B., Yee, E., Bechtel, P.J., et al., 2006. Water vapor permeability of mammalian and fish gelatin films. *J. Food Sci.* 71, E202–E207.

- Avena-Bustillos, R.J., Chiou, B., Olsen, C.W., Bechtel, P.J., Olson, D.A., McHugh, T.H., 2011. Gelation, oxygen permeability, and mechanical properties of mammalian and fish gelatin films. *J. Food Sci.* 76, 519–524.
- Baziwane, D., He, Q., 2003. Gelatin: the paramount food additives. *Food Rev. Int.* 19, 423–435.
- Bhattacharyya, A., Argillier, J.-F., 2005. Microencapsulation by complex coacervation: effect of cationic surfactants. *J. Surf. Sci. Technol.* 21, 161–168.
- Bikbov, T.M., Grinberg, V.Y., Antonov, Y.A., Tolstoguzov, V.B., Schmandke, H., 1979. On the concentration dependence of the elasticity modulus of soybean globulin gels. *Polym. Bull.* 1, 865–869.
- Boran, G., Regenstein, J.M., 2010. Fish gelatin. In: Taylor, S.L. (Ed.), *Advances in Food and Nutrition Research*, vol. 60. Academic Press, London, pp. 119–144.
- Bower, D.K., Chaundy, F.K., Kilbride, T.K. Jr., 1992. Process for incorporating a material in a crosslinked gelatin, and product therefrom. US Patent 5,153,177.
- Boye, J., Aksay, S., Roufik, S., Ribereau, S., Mondor, M., Famworth, E., et al., 2010. Comparison of the functional properties of pea, chickpea and lentil protein concentrates processed using ultrafiltration and isoelectric precipitation techniques. *Food Res. Int.* 43, 537–546.
- Bruschi, M.L., Cardoso, M.L.C., Lucchesi, M.B., Gremiao, M.P.D., 2003. Gelatin microparticles containing propolis obtained by spray-drying technique: preparation and characterization. *Int. J. Pharm.* 264, 45–55.
- Casey, R., Charman, J.E., Wright, D.J., Bacon, L.R., Guldager, P., 1982. Quantitative variability in *Pisum* seed globulins: its assessment and significance. *Plant Foods Human Nutr.* 31, 333–346.
- Charve, J., Reineccius, G.A., 2009. Encapsulation performance of proteins and traditional materials for spray dried flavors. *J. Agric. Food Chem.* 57, 2486–2492.
- Chen, L., Subirade, M., 2009. Elaboration and characterization of soy/zein protein microspheres for controlled nutraceutical delivery. *Biomacromolecules.* 10, 3327–3334.
- Chiou, B., Avena-Bustillos, R.J., Shey, J., Yee, E., Bechtel, P.J., Imam, S.H., et al., 2006. Rheological and mechanical properties of cross-linked fish gelatins. *Polymer.* 47, 6379–6386.
- Cho, S.Y., Lee, S.Y., Rhee, C., 2010. Edible oxygen barrier bilayer film pouches from corn zein and soy protein isolate for olive oil packaging. *LWT—Food Sci. Technol.* 43, 1234–1239.
- Cho, Y.H., Shim, H.K., Park, J., 2003. Encapsulation of fish oil by an enzymatic gelation process using transglutaminase cross-linked proteins. *J. Food Sci.* 68, 2717–2723.
- De Graaf, L.A., Harmsen, P.F.H., Vereijken, J.M., Mönikes, M., 2001. Requirements for non-food applications of pea proteins: a review. *Nahrung/Food.* 45, 408–411.
- Dickinson, E., Lopez, G., 2001. Comparison of the emulsifying properties of fish gelatin and commercial milk proteins. *J. Food Sci.* 66, 118–123.
- Diguet, S., Feltes, K., Kleemann, N., Leuenberger, B., Ulm, J., 2005. Extrusion-stable poly-unsaturated fatty-acid compositions for food products. WO2005/089569.
- Dinarvand, R., Mahmoodi, S., Salehi, M., Atyabi, F., 2005. Preparation of gelatin microspheres containing lactic acid—effect of cross-linking on drug release. *Acta Pharm.* 55, 57–67.
- Ducel, V., Richard, J., Popineau, Y., Boury, F., 2004a. Adsorption kinetics and rheological interfacial properties of plant proteins at the oil-water interface. *Biomacromolecules.* 5, 2088–2093.
- Ducel, V., Richard, J., Saulnier, P., Popineau, Y., Boury, F., 2004b. Evidence and characterization of complex coacervates containing plant proteins: application to the microencapsulation of oil droplets. *Colloids Surf. A.* 232, 239–247.
- Esen, A., 1986. Separation of alcohol-soluble proteins (zeins) from maize into three fractions by differential solubility. *Plant Physiol.* 80, 623–627.
- Favaro-Trindade, C.S., Santana, A.S., Monterrey-Quintero, E.S., Trindade, M.A., Netto, F.M., 2010. The use of spray drying technology to reduce bitter taste of casein hydrolysate. *Food Hydrocoll.* 24, 336–340.
- Fukushima, D., 2004. Soy proteins. In: Phillips, G.O., Williams, P.A. (Eds.), *Handbook of Food Proteins*. Woodhead Publishing Limited, Cambridge, UK, pp. 210–232.
- Gan, C., Cheng, L., Easa, A.M., 2008. Evaluation of microbial transglutaminase and ribose cross-linked soy protein isolate-based microcapsules containing fish oil. *Innov. Food Sci. Emerg. Technol.* 9, 563–569.
- Gharsallaoui, A., Roudaut, G., Chambin, O., Voilley, A., Saurel, R., 2007. Applications of spray-drying in microencapsulation of food ingredients: an overview. *Food Res. Int.* 40, 1107–1121.
- Gharsallaoui, A., Cases, E., Chambin, O., Saurel, R., 2009. Interfacial and emulsifying characteristics of acid-treated pea protein. *Food Biophys.* 4, 273–280.
- Gharsallaoui, A., Saurel, R., Chambin, O., Cases, E., Voilley, A., Cayot, P., 2010. Utilisation of pectin coating to enhance spray-dry stability of pea protein-stabilised oil-in-water emulsions. *Food Chem.* 122, 447–454.
- Gharsallaoui, A., Saurel, R., Chambin, O., Voilley, A., 2012a. Pea (*Pisum sativum*, L.) protein isolate stabilized emulsions: a novel system for microencapsulation of lipophilic ingredients by spray drying. *Food Bioprocess. Technol.* 5, 2211–2221.
- Gharsallaoui, A., Roudaut, G., Beney, L., Chambin, O., Voilley, A., Saurel, R., 2012b. Properties of spray-dried food flavours microencapsulated with two-layered membranes: roles of interfacial interactions and water. *Food Chem.* 132, 1713–1720.
- GMLA, 1986. *Gelatin Handbook*. Gelatin Manufacturers of America, New York.
- Graham, L., 1996. A comprehensive survey of the acid-stable fluorescent cross-links formed by ribose with basic amino acids, and partial characterization of a novel Maillard cross-link. *Biochim. Biophys. Acta.* 1297, 9–16.

- Gudmundsson, M., 2002. Rheological properties of fish gelatins. *J. Food Sci.* 67, 2172–2176.
- Haug, I.J., Draget, K.I., 2011. Gelatin. In: Phillips, G.O., Williams, P.A. (Eds.), *Handbook of Food Proteins*. Woodhead Publishing, Cambridge, UK, pp. 92–115.
- Iwanaga, K., Yabuta, T., Kakemi, M., Morimoto, K., Tabata, Y., Ikada, Y., 2003. Usefulness of microspheres composed of gelatin with various cross-linking density. *J. Microencapsul.* 20, 767–776.
- Junyaprasert, V.B., Mitrevej, A., Sinchaipanid, N., Boonme, P., Wurster, D.E., 2001. Effect of process variables on the microencapsulation of vitamin A palmitate by gelatin-acacia coacervation. *Drug Dev. Ind. Pharm.* 27, 561–566.
- Karaca, A.C., Low, N., Nickerson, M., 2011. Emulsifying properties of chickpea, faba bean, lentil and pea proteins produced by isoelectric precipitation and salt extraction. *Food Res. Int.* 44, 2742–2750.
- Karim, A.A., Bhat, R., 2009. Fish gelatin: properties, challenges, and prospects as an alternative to mammalian gelatins. *Food Hydrocoll.* 23, 563–576.
- Kim, Y.D., Morr, C.V., 1996. Microencapsulation properties of gum arabic and several food proteins: spray-dried orange oil emulsion particles. *J. Agric. Food Chem.* 44, 1314–1320.
- Kim, Y.D., Morr, C.V., Schenz, T.W., 1996. Microencapsulation properties of gum arabic and several food proteins: liquid orange oil emulsion particles. *J. Agric. Food Chem.* 44, 1308–1313.
- Kong, Y., Li, D., Wang, L., Adhikari, B., 2011. Preparation of gelatin microparticles using water-in-water (w/w) emulsification technique. *J. Food Eng.* 103, 9–13.
- Koyoro, H., Powers, J.R., 1987. Functional properties of pea globulin fractions. *Cereal Chem.* 64, 97–101.
- Krochta, J.M., 2002. Proteins as raw materials for films and coatings: definitions, current status, and opportunities. In: Gennadios, A. (Ed.), *Protein-Based Films and Coatings*. CRC Press, Boca Raton, Florida, pp. 1–41.
- Leuenberger, B., Tritsch, J., Ulm, J., 2002. Process for preparing fat soluble beadlets. US Patent 6,444,227.
- Li, W., Wu, G., Chen, H., Wang, M., 2009. Preparation and characterization of gelatin/SDS/NaCMC microcapsules with compact wall structure by complex coacervation. *Colloids Surf. A* 333, 133–137.
- Liu, H., Li, D., Guo, S., 2008. Extraction and properties of gelatin from channel catfish (*Ictalurus punctatus*) skin. *LWT—Food Sci. Technol.* 41, 414–419.
- Liu, X., Atarashi, T., Furuta, T., Yoshii, H., Aishima, S., Ohkawara, M., et al., 2001. Microencapsulation of emulsified hydrophobic flavors by spray drying. *Drying Technol.* 19, 1361–1374.
- Magdassi, S., Vinetsky, Y., 1995. Microencapsulation of O/W emulsions by formation of a protein-surfactant insoluble complex. *J. Microencapsul.* 12, 537–545.
- Matsuno, R., Adachi, S., 1993. Lipid encapsulation technology—techniques and applications to food. *Trends Food Sci. Technol.* 4, 256–261.
- Mendandia, D.V., Ortiz, S.E.M., Favaro-Trindade, C.S., Mauri, A., Monterrey-Quintero, E.S., Thomazini, M., 2009. Microencapsulation of casein hydrolysate by complex coacervation with SPI/pectin. *Food Res. Int.* 42, 1099–1104.
- Miller, K.S., Krochta, J.M., 1997. Oxygen and aroma barrier properties of edible films: a review. *Trends Food Sci. Technol.* 81, 228–237.
- Molina, E., Papadopoulos, A., Ledward, D.A., 2001. Emulsifying properties of high pressure treated soy protein isolate and 7S and 11S globulins. *Food Hydrocoll.* 15, 263–269.
- Morita, T., Horikiri, Y., Suzuki, T., Yoshino, H., 2001. Preparation of gelatin microparticles by co-lyophilization with poly(ethylene glycol): characterization and application to entrapment into biodegradable microspheres. *Int. J. Pharm.* 219, 127–137.
- Motoki, M., Seguro, K., 1998. Transglutaminase and its use for food processing. *Trends Food Sci. Technol.* 9, 204–210.
- Nakagawa, K., Nagao, H., 2012. Microencapsulation of oil droplets using freezing-induced gelatin–acacia complex coacervation. *Colloids Surf. A* 411, 129–139.
- Nesterenko, A., Alric, I., Silvestre, F., Durrieu, V., 2012. Influence of soy protein's structural modifications on their microencapsulation properties: α -tocopherol microparticle preparation. *Food Res. Int.* 48, 387–396.
- Nori, M.P., Favaro-Trindade, C.S., de Alencar, S.M., Thomazini, M., de Camargo Balieiro, J.C., Castillo, C.J.C., 2011. Microencapsulation of propolis extract by complex coacervation. *LWT—Food Sci. Technol.* 44, 429–435.
- Okubo, K., Iijima, M., Kobayashi, Y., Yoshikoshi, M., Uchida, T., Kudou, S., 1992. Components responsible for the undesirable taste of soybean seeds. *Biosci. Biotech. Biochem.* 56, 99–103.
- Ortiz, S.E.M., Mauri, A., Monterrey-Quintero, E.S., Trindade, M.A., Santana, A.S., Favaro-Trindade, C.S., 2009. Production and properties of casein hydrolysate microencapsulated by spray drying with soybean protein isolate. *LWT—Food Sci. Technol.* 42, 919–923.
- Ozgun, A.B., Mustafa, B.A.T., 2005. Spray drying of sumac flavor using sodium chloride, sucrose, glucose and starch as carriers. *J. Food Eng.* 69, 253–260.
- Parris, N., Cooke, P.H., Hicks, K.B., 2005. Encapsulation of essential oils in zein nanospherical particles as a delivery system for antimicrobials. *J. Agric. Food Chem.* 53, 4788–4792.
- Pereira, H.V.R., Saraiva, K.P., Carvalho, L.M.J., Andrade, L.R., Pedrosa, C., Pierucci, A.P.T.R., 2009. Legumes seeds protein isolates in the production of ascorbic acid microparticles. *Food Res. Int.* 42, 115–121.
- Qi, J., 2004. Microencapsulation of Beta-Carotene in Pea Protein Wall System. Master's Thesis. University of Manitoba.
- Quispe-Condoni, S., Saldafia, M.D.A., Temelli, F., 2011. Microencapsulation of flax oil with zein using spray and freeze drying. *LWT—Food Sci. Technol.* 44, 1880–1887.
- Rascón, M.P., Berstain, C.I., García, H.S., Saigado, M.A., 2011. Carotenoid retention and storage stability of spray-dried encapsulated paprika oleoresin using gum arabic and soy protein isolate as wall materials. *LWT—Food Sci. Technol.* 44, 549–557.

- Schrieber, R., Gareis, H., 2007. Gelatin Handbook Theory and Industry Practice. Wiley-VCH Verlag GmbH & Co. KGaA, Weinheim.
- Scialpi, L.J., 1987. Process for preparing fat-soluble vitamin active beadlets. US Patent 4,670,247.
- Shu, B., Yu, W., Zhao, Y., Liu, X., 2006. Study on microencapsulation of lycopene by spray-drying. J. Food Eng. 76, 664–669.
- Shukla, R., Cheryan, M., 2001. Zein: the industrial protein from corn. Ind. Crop. Prod. 13, 171–192.
- Silva, D.F., Favaro-Trindade, C.S., Rochai, G.A., Thomazine, M., 2012. Microencapsulation of lycopene by gelatin-pectin complex coacervation. J. Food Process. Preserv. 36, 185–190.
- Su, C., 2012. Zein Encapsulation of Amphiphilic Compounds. Master's Thesis. University of Illinois at Urbana-Champaign.
- Swanson, B.G., 1990. Pea and lentil protein extraction and functionality. J. Am. Oil Chem. Soc. 67, 276–280.
- Tang, C., Ten, Z., Wang, X., Yang, X., 2006. Physicochemical and functional properties of hemp (*Cannabis sativa* L.) protein isolate. J. Agric. Food Chem. 54, 8945–8950.
- Torres-Gimer, S., Martinez-Abad, A., Ocio, M.J., Lagaron, J.M., 2010. Stabilization of a nutraceutical omega-3 fatty acid by encapsulation in ultrathin electrosprayed zein prolamine. J. Food Sci. 75, N69–N79.
- Viroben, G., Barbot, J., Mouloungui, Z., Gueguen, J., 2000. Preparation and characterization of films from pea protein. J. Agric. Food Chem. 48, 1064–1069.
- Wang, X., Tang, C., Lia, B., Yang, X., Lia, L., Ma, C., 2008. Effects of high-pressure treatment on some physicochemical and functional properties of soy protein isolates. Food Hydrocoll. 22, 560–567.
- Wu, W.U., Hettiarachchy, N.S., Qi, M., 1998. Hydrophobicity, solubility, and emulsifying properties of soy protein peptides prepared by papain modification and ultrafiltration. J. Am. Oil Chem. Soc. 75, 845–850.
- Yamamoto, M., Ikada, Y., Tabata, Y., 2001. Controlled release of growth factors based on biodegradation of gelatin hydrogel. J. Biomater. Sci. Polym. 12, 77–88.
- Yan, N., 2010. Encapsulated agglomeration of microcapsules and method for the preparation thereof. US Patent 7,727,629 B2.
- Zayas, J.F., 1997. Functionality of Proteins in Food. Springer-Verlag, Berlin, Heidelberg.
- Zhang, J., Liang, L., Tian, Z., Chen, L., Subirade, M., 2012. Preparation and in vitro evaluation of calcium-induced soy protein isolate nanoparticles and their formation mechanism study. Food Chem. 133, 390–399.
- Zhong, Q., Jin, M., 2009. Nanoscale structures of spray-dried zein microcapsules and in vitro release kinetics of the encapsulated lysozyme as affected by formulations. J. Agric. Food Chem. 57, 3886–3894.
- Zhou, P., Mulvaney, S.J., Regesteijn, J.M., 2006. Properties of Alaska pollock skin gelatin: a comparison with tilapia and pork skin gelatins. J. Food Sci. 71, C313–C321.