

DuPont CB028

SILVER CONDUCTOR

Technical Data Sheet

Product Description

DuPont CB028 silver conductor is used to provide electromagnetic interference/radio frequency interference (EMI/RFI) shielding on-board or to fabricate low-voltage circuitry, on rigid or flexible substrates. It can be used with manual or automatic screen printing equipment.

Product Benefits

- Superior conductivity
- Fine line printing capability
- Excellent flexibility

Processing

Screen Printing Equipment

Reel-to-reel, semi-automatic, manual

Ink Residence Time on Screen

> 1 hr

Screen Types

Stainless steel, polyester

Typical Cure Conditions

Box Oven: 160°C (320°F) for 60 min

Typical Circuit Line Thickness Printed with 200-mesh stainless steel screen

8-10 microns

Clean up Solvent

Ethylene diacetate or methyl propasol acetate

Substrate

Epoxy glass, Mylar and DuPont™ Kapton® polyimide film

Maximum temperature exposure

Lamination temperature > 175° C may cause delamination of the CB028

Table 1
Typical Physical Properties

Test	Properties
Sheet Resistivity (mΩ/sq/mil)	7 - 10
Resistivity after Flex (mΩ/sq/mil) 15 sec after test crease (180°, 1 cycle)	100
Abrasion Resistance, Pencil Hardness (H) [ASTM D3363-74]	≥ 2
Solderability	Not Recommended
% TML (Total Mass Loss) ASTM 595 (NASA Out gassing, Specification < 1.0%)	0.18
%CVCVM (Collectible Volatile Con- densable Material) ASTM 595 (NASA Out gassing, Specification < 0.1%)	0.01
Change in Physical Properties after Environmental tests	Insignificant
Change in Electrical properties after Environmental test*, (%)	< 10
Environmental Test A. Thermal Shock (+ 85°C to - 40°C, 30 min each, cycles) B. Dry Heat (+ 85°C, 10 days) C. Humidity (+ 40°C, 95% RH, 10 days) [MIL Std 202E, method 103, cond. A] D. Salt Spray (+ 35°C, 5% salt, 10 days) [ASTM B117] E. Silver Migration (1 V DC/mil gap, + 40°C, 90 % RH, 500 hr., tested on 40-and 7-mil gaps) F. Sulfur Dioxide (+ 45°C, 90% RH, 400 hr, in a 9-liter chamber containing 500 mg of flowers of sulfur)	

These tables shows anticipated typical physical properties for DuPont CB028 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Table 2
Composition Properties

Test	Properties
Viscosity (Pa.S) [Brookfield HBT, 10 rpm #14 spindle & UC, 25°C]	15 - 30
Coverage ¹ , cm ² /g	120 - 230
Thinner	DuPont 3610
¹ Dependent on print thickness	

Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates ("DuPont"). NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 ("Medical Applications Policy") and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user's consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data's accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user's responsibility to satisfy itself that the product is suitable for the user's intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



The miracles of science™

For more information on CB028 or other DuPont Microcircuit Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709
Tel.: 800-284-3382

Europe

Du Pont (U.K.) Limited
Coldharbour Lane
Bristol BS16 1QD
U.K.
Tel.: 44-117-931-3191

Asia

DuPont Kabushiki Kaisha
Sanno Park Tower, 11-1
Nagata-cho 2-chome
Chiyoda-ku, Tokyo 100-611
Japan
Tel.: 81-3-5521-8650

DuPont Taiwan Ltd
45, Hsing-Pont Road,
Taoyuan, Taiwan 330
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,
Pudong New District, Shanghai 201203, China
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.
3~5th Floor, Asia tower #726,
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens,
Sector-25A, DLF City, Phase-III,
Gurgaon 122 002 Haryana, India
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One,
Singapore 098633
Tel.: 65-6586-3022

<http://www.mcm.dupont.com>

MCMCB028 (03/2013)