US007921678B2

(12) **United States Patent**
Norris et al.

(10) **Patent No.: US 7,921,678 B2**
(45) **Date of Patent: Apr. 12, 2011**

(54) **COMPRESSIBLE RESILIENT FABRIC, DEVICES, AND METHODS**

(75) Inventors: **Stephanie Booz Norris**, Rocky Point, NC (US); **Martin Monestere, Jr.**, Hollywood, SC (US); **Brian L. McMurray**, Pinehurst, NC (US)

(73) Assignee: **Atex Technologies, Inc.**, Pinebluff, NC (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 46 days.

(21) Appl. No.: **12/143,442**

(22) Filed: **Jun. 20, 2008**

(65) **Prior Publication Data**

US 2008/0319521 A1 Dec. 25, 2008

Related U.S. Application Data

(60) Provisional application No. 60/936,405, filed on Jun. 20, 2007.

(51) **Int. Cl.**
D04B 1/22 (2006.01)

(52) **U.S. Cl.** **66/195**

(58) **Field of Classification Search** 66/202, 66/191, 194; 623/1.49–1.54
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,655,474 A * 4/1972 Constantine 156/178
3,878,565 A * 4/1975 Sauvage 623/1.5
4,047,252 A * 9/1977 Liebig et al. 623/1.52
4,193,137 A * 3/1980 Heck 623/1.52
4,567,075 A * 1/1986 Krawczyk 428/91
4,892,539 A * 1/1990 Koch 623/1.52
5,292,328 A * 3/1994 Hain et al. 606/151
5,611,127 A 3/1997 Ceriani et al.

(Continued)

FOREIGN PATENT DOCUMENTS

EP 08768655.6 2/2010

(Continued)

OTHER PUBLICATIONS

International Search Report, PCT/US02/007684, mailed Jan. 28, 2009.

(Continued)

Primary Examiner — Danny Worrell
(74) *Attorney, Agent, or Firm* — Boggs IP Law, LLC

(57) **ABSTRACT**

A compressible resilient fabric can include a ground layer of knitted yarn, and a loop layer comprising a plurality of loops of yarn, each loop having a point knit into the ground layer. The fabric can be compressible from an non-compressed configuration, in which each loop has an apex extending substantially perpendicularly outward from the ground layer, into a compressed configuration, in which each loop is collapsed onto the ground layer. The fabric can further be resilient so as to substantially resume the non-compressed configuration when compression is relieved. The loop layer yarn can include a multifilament yarn having a high denier per filament ratio. The ground layer yarn can include a yarn shrinkable substantially more than the loop layer yarn. The loops can be densely knit so as to support the extension of the loops outward from the ground layer.

11 Claims, 2 Drawing Sheets





Edwards v. Aortic Innovations
U.S. Patent 11,497,634
Edwards Ex. 1074

U.S. PATENT DOCUMENTS

5,732,572	A *	3/1998	Litton	66/195
6,015,431	A	1/2000	Thornton et al.	
6,221,099	B1 *	4/2001	Andersen et al.	623/1.15
6,547,820	B1 *	4/2003	Staudenmeier	623/1.49
6,663,667	B2 *	12/2003	Dehdashtian et al.	623/1.51
6,783,554	B2 *	8/2004	Amara et al.	623/23.76
6,994,722	B2	2/2006	DiCarlo	
2001/0056303	A1 *	12/2001	Caneiro et al.	623/23.74
2002/0116070	A1 *	8/2002	Amara et al.	623/23.74
2003/0028239	A1	2/2003	Dong	
2004/0054376	A1 *	3/2004	Ory et al.	606/151
2004/0243221	A1	12/2004	Fawzi et al.	

FOREIGN PATENT DOCUMENTS

EP	08768655.6	3/2010
WO	WO 02/28314	4/2002

OTHER PUBLICATIONS

Written Opinion of the International Searching Authority, PCT/US02/007684, mailed Jan. 28, 2009.

* cited by examiner



Fig. 1



Fig. 2



Fig. 3



Fig. 4

Stitch Notation:

Bar 1: 1-0 / 0-0 / 0-0 / 1-1 //
Bar 2: 1-1 / 0-0 / 0-1 / 1-1 //
Bar 3: 1-0 / 1-1 / 1-2 / 1-1 //
Bar 4: 2-3 / 2-2 / 1-0 / 2-2 //



Fig. 5

COMPRESSIBLE RESILIENT FABRIC, DEVICES, AND METHODS

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims benefit of U.S. Provisional Patent App. No. 60/936,405, filed Jun. 20, 2007, which is incorporated by reference herein in its entirety.

FIELD OF THE INVENTION

The present invention relates to compressible resilient fabric, devices including a compressible resilient fabric, and methods for making and/or using a compressible resilient fabric and/or device having a compressible resilient fabric.

BACKGROUND

Medical devices such as vascular and endovascular grafts and stent-grafts can include fabric components that function to promote sealing of the device to the lumen or structure in which it is implanted. Insertion of such devices and fabric components into target sites can require that the fabric be compressed and collapsed so as to be placed inside a delivery catheter or cannula. When such a device having a fabric component is inserted to a target site and the delivery catheter is removed, at least the fabric component is often expected to rebound to approximately its original shape, structure, and dimensions. Regaining its original shape, structure, and dimensions is important to achieve an adequate seal between the exterior of the device and the lumen or structure in which it is implanted. This is critical because any gaps or voids between the device and the implant site can prevent a reliable seal, which can lead to complications and/or device failure. The ability of such a fabric component to regain its original shape, structure, and dimensions after being compressed and implanted can often depend on the fabric having sufficient resiliency.

In some applications, medical devices comprising fabric and designed for insertion into vessels or ducts may be stored in a compressed, or collapsed, configuration for extended periods, for example, a number of months, before use. When stored in sterile packaging, such devices are secluded from exposure to ambient air. In such devices stored for prolonged periods in a compressed state and without exposure to ambient air, recovery of fabric to its original shape and dimensions can be adversely affected. In addition, some implantable medical devices can be stored in fluid media over various periods of time. Fabric components of such medical devices can absorb fluid media in which they are packaged and stored. When medical device fabric absorbs fluid media, the fabric may be lose some resiliency for regaining its original shape and dimensions when deployed.

Thus, there is a need for a fabric that can be compressed for ease of delivery to an implant site and that has sufficient resiliency to regain its original shape, structure, and dimensions when implanted. There is a need for such a fabric that can avoid the loss of performance characteristics during storage prior to use.

SUMMARY

The present invention can include embodiments of a compressible resilient fabric, devices including a compressible resilient fabric, and methods for making and/or using a fabric and/or device having a compressible resilient fabric.

In an illustrative embodiment, a compressible resilient fabric can include a ground layer of knitted yarn, and a loop layer comprising a plurality of loops of yarn, each loop having a point knit into the ground layer. The fabric can be compressible from a non-compressed configuration, in which each loop has an apex extending substantially perpendicularly outward from the ground layer, into a compressed configuration, in which each loop is collapsed onto the ground layer. The fabric can be resilient so as to substantially resume the non-compressed configuration when compression is relieved.

In some embodiments, the loop layer yarn can comprise a multifilament yarn having a high denier per filament ratio. For example, the loop layer yarn can comprise a multifilament yarn having 5-20 denier per filament. In some embodiments, the loop layer yarn can comprise a total denier of 60-70. In some embodiments, the ground layer yarn can comprise a yarn shrinkable substantially more than the loop layer yarn. For example, the ground layer yarn may comprise a yarn shrinkable about 40-60%, and the loop layer yarn can comprise a yarn shrinkable about 7-8%. In some embodiments, the loops can be densely knit so as to support the extension of the loops outward from the ground layer.

Some embodiments of the present invention can include a device comprising a substantially tubular inner member, and an intraluminal sealing member attachable to an exterior of the inner member. The sealing member can include a ground layer of knitted yarn and a loop layer comprising a plurality of loops of yarn, each loop having a point knit into the ground layer. The sealing member can be compressible from an non-compressed configuration, in which each loop has an apex extending substantially perpendicularly and radially outward from the ground layer, into a compressed configuration, in which each loop is collapsed onto the ground layer. The sealing member can further be resilient so as to substantially resume the non-compressed configuration when compression is relieved, for example, after the device is implanted into a lumen in a human or animal body. The intraluminal sealing member can be adapted to promote sealing between the inner member and a lumen wall. In some embodiments, the inner member can comprise a stent.

Some embodiments of the present invention can include a system and/or kit. Such a system and/or kit can include a compressible resilient fabric and/or devices including a compressible resilient fabric as described herein.

Some embodiments of the present invention can include a method of making a compressible resilient fabric and/or devices including a compressible resilient fabric. Such a method can include knitting a ground layer of yarn and a loop layer comprising a plurality of loops of yarn, each loop having a point knit into the ground layer. The method can further include washing the fabric in about 90 degree C. water. The method can further include drying the fabric at about 60-65 degrees C., which further shrinks the fabric. In the fabric and/or device made by such a method, the fabric can be compressible from a non-compressed configuration, in which each loop has an apex extending substantially perpendicularly outward from the ground layer, into a compressed configuration, in which each loop is collapsed onto the ground layer. The fabric can further be resilient so as to substantially resume the non-compressed configuration when compression is relieved.

Features of a fabric, device, system, kit, and/or method of the present invention may be accomplished singularly, or in combination, in one or more of the embodiments of the present invention. As will be realized by those of skill in the art, many different embodiments of a fabric, device, system, kit, and/or method according to the present invention are

possible. Additional uses, advantages, and features of the invention are set forth in the illustrative embodiments discussed in the detailed description herein and will become more apparent to those skilled in the art upon examination of the following.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. **1** is a diagrammatic side view of a compressible resilient fabric in a non-compressed configuration in an embodiment of the present invention.

FIG. **2** is a diagrammatic side view of the compressible resilient fabric shown in FIG. **1**, showing the loops compressed into the ground layer in a compressed configuration.

FIG. **3** is a diagrammatic cross-sectional view of a tubular-shaped compressible resilient fabric in a non-compressed configuration in an embodiment of the present invention.

FIG. **4** is a diagrammatic perspective view of a partially cut-away intraluminal sealing member on the exterior of a stent in an embodiment of a device of the present invention.

FIG. **5** is a view of a knitting stitch diagram of one four-course repeat for a compressible resilient fabric showing two loops in four courses in an embodiment of the present invention.

DETAILED DESCRIPTION

For the purposes of this specification, unless otherwise indicated, all numbers expressing quantities, conditions, and so forth used in the specification are to be understood as being modified in all instances by the term "about." Accordingly, unless indicated to the contrary, the numerical parameters set forth in the following specification are approximations that can vary depending upon the desired properties sought to be obtained by the embodiments described herein. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to the scope of the claims, each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques.

Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the described embodiments are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any numerical value, however, inherently contains certain errors necessarily resulting from the standard deviation found in their respective testing measurements. Moreover, all ranges disclosed herein are to be understood to encompass any and all subranges subsumed therein. For example, a stated range of "1 to 10" should be considered to include any and all subranges between (and inclusive of) the minimum value of 1 and the maximum value of 10; that is, all subranges beginning with a minimum value of 1 or more, e.g. 1 to 6.1, and ending with a maximum value of 10 or less, for example, 5.5 to 10. Additionally, any reference referred to as being "incorporated herein" is to be understood as being incorporated in its entirety.

For the purposes of this specification, terms such as "forward," "rearward," "front," "back," "right," "left," "upwardly," "downwardly," and the like are words of convenience and are not to be construed as limiting terms. As used in this specification and the appended claims, the singular forms "a," "an," and "the" include plural referents unless the context clearly dictates otherwise. Thus, for example, the term "a loop" is intended to mean a single loop or more than one loop.

The present invention can include embodiments of a compressible resilient fabric, devices including a compressible resilient fabric, and methods for making and/or using a fabric and/or device comprising a compressible resilient fabric. Some embodiments of compressible resilient fabrics, devices, and methods according to the present invention may be useful for medical applications, for example, a stent comprising an intraluminal sealing member.

For purposes herein, "compressible" is defined as the ability of the fabric or intraluminal sealing member to be compressed from a relatively larger, expanded configuration to a relatively smaller, compressed configuration. For example, the fabric and/or intraluminal sealing member can be compressed from its original non-compressed configuration to the compressed configuration. In some embodiments, the entire dimension of the fabric along its length and width can be compressed. For purposes herein, "resilient" is defined as the ability of the fabric or intraluminal sealing member to recover from the compressed configuration to substantially its original shape, structure, and dimensions as in the non-compressed configuration.

In an illustrative embodiment, as shown in FIGS. **1-3**, a compressible resilient fabric **10** can include a ground layer **20** of knitted yarn, and a loop layer **30** comprising a plurality of loops **32** of yarn **31**, each loop **32** having a point **33** knit into the ground layer **20**. The fabric **10** can be compressible from a non-compressed configuration **40**, in which each loop **32** has an apex **34** extending substantially perpendicularly outward **42** from the ground layer **20**, into a compressed configuration **41**, in which each loop **32** is collapsed onto the ground layer **20**. The fabric **10** can be sufficiently resilient so as to substantially resume the non-compressed configuration **40** when compression is relieved.

In some embodiments, the loop layer yarn **31** can comprise a multifilament yarn **31** having a high denier per filament ratio. For example, the loop layer yarn **31** can comprise a multifilament yarn **31** having 5-20 denier per filament. In some embodiments, the loop layer yarn can comprise a total denier of 60-70.

In some embodiments, the ground layer yarn can comprise a yarn substantially more shrinkable than the loop layer yarn **31**. For example, the ground layer yarn may comprise a yarn shrinkable about 40-60%, and the loop layer yarn **31** can comprise a yarn **31** shrinkable about 7-8%.

In some embodiments, the loops **32** can be densely knit so as to support the extension of the loops **32** outward from the ground layer **20**. For example, in certain embodiments, the loop layer **30** can include two loops **32** in every four courses of the ground layer **20**. In particular embodiments, the loop layer **30** can include between about 600 and about 750 loops **32** per square inch of the fabric **10**. In some embodiments, each loop **32** can have a substantially uniform height **43** in the non-compressed configuration **40**.

In the non-compressed configuration **40**, some embodiments of the fabric **10** can have a thickness **43** of about 1-5 mm. In the compressed configuration **41**, some embodiments of the fabric **10** can have a thickness **44** of about 0.004-0.008 inches. Thus, some embodiments of the fabric **10** can be compressed into a very thin profile for insertion to a target site in a location in a body, and recover to substantially its original non-compressed configuration **40** when positioned in the location and compression is relieved.

In some embodiments, the loops **32** can be constructed as "unitary" with the ground layer **20**. A "unitary" construction means that loops **32** are knit in a set repeat pattern so as to provide a uniform density. With a uniform density, gaps and voids in the knit pattern can be avoided. In some embodi-

ments, the loops **32** can be constructed as "integral" with the ground layer **20**. An "integral" construction means that the loops **32** are knit simultaneously with and into the ground layer **20**. In some embodiments, the apex **34** of the loops **32** can be substantially erect, or perpendicular **42** to the face side, or technical face, of the ground layer **20** of the fabric **10**.

The fabric **10** may be compressed from its original non-compressed configuration **40** into the smaller, compressed configuration **41** by employing, for example, a mechanical crimping apparatus (not shown) designed for reducing the overall size of an intraluminal medical device **50**. Once crimped to the smaller size, the fabric **10** (and device) can be loaded into a delivery catheter. When a compressive pressure, such as the wall of a delivery catheter, is removed from the compressible resilient fabric **10** and/or medical device **50** comprising the fabric **10**, the fabric **10** can recover from the compressed configuration **41** to substantially its original non-compressed, or expanded, configuration **40**. Such recovery to substantially the original non-compressed configuration **40** can include return of the loops **32** to approximately the original, non-compressed loop, or pile, height **43** and other dimensions and shape.

Such self-recovery can be facilitated by various aspects of the present invention, as described herein. For example, in some embodiments, resilient recovery of the loops **32** to the non-compressed configuration **40**, including their non-compressed loop height **43**, can be provided at least in part by loop yarns **31** having higher denier per filament and relatively fewer filaments of yarn **31**. In some embodiments, resilient recovery of the loops **32** to the non-compressed configuration **40** can be provided at least in part by the ground layer yarns having substantially higher shrinkage capacity than the loop layer yarns **31**, which can cause the loops **32** to be tightly held in the ground layer **20** when the fabric **10** is heated. In some embodiments, resilient recovery of the loops **32** to the non-compressed configuration **40** can be provided at least in part by each loop **32** being integrally knit into the ground layer **20**, thereby providing tightly held loops **32** that tend to extend in an upright manner **42** away from the ground layer **20**. In some embodiments, resilient recovery of the loops **32** to the non-compressed configuration **40** can be provided at least in part by the loops **32** being densely knit into the ground layer **20** so as to enhance the stability of the loops **32** in their outwardly extended position **42**. In some embodiments, resilient recovery of the loops **32** to the non-compressed configuration **40** can be provided at least in part by thermoset memory of the fabric **10**, as described herein.

The "point" **33** of the loop **32** is the portion of the loop **32** that is integrally knit into the ground layer **20**. The "apex" **34** of the loop **32** is the portion opposite the point **33** of the loop **32** that extends outwardly away from the ground layer **20**.

Due to the resilient recovery property of embodiments of the fabric **10** of the present invention, each loop **32** can stand up by itself from its point **33** knitted to the ground layer **20**. Accordingly, in the non-compressed configuration **40**, the dense, extended loops **32** in the loop layer **30** of the fabric **10** can provide a consistent height **43** and contour. In this manner, the loop layer **30** can have a consistent contact with the interior wall of a vessel, duct, or other anatomical structure along the length and width of the fabric **10**. Such consistent contact with an adjacent vessel, duct, or other anatomical structure can enhance clotting and prevention of fluid flow between the exterior of an implanted device **50** such as the stent **53** and the vessel, duct, or other anatomical structure.

In some embodiments, the loop layer yarn **31** can comprise a multifilament yarn **31** having a high denier per filament ratio. "Multifilament" is defined as a manufactured fiber yarn composed of many fine filaments. Multifilament yarn **31** is desirable in some embodiments of the present invention due to the greater surface area exposed to a target location provided by multiple filaments in the yarn **31**. In applications in which the fabric **10** is utilized in vascular implantation, for example, the multifilament loop yarn **31** can promote enhanced cellular ingrowth and encapsulation to promote clotting and fixation of the fabric **10** to a vessel wall. Lower denier filament yarns, such as those used in conventional medical textiles, provide increased surface area but generally fail to exhibit sufficient recovery or resiliency from compression (due to limited memory retention) to provide optimal sealing between an implantable device and an adjacent anatomical structure, such as a vessel wall.

The stability and resilience of the fabric **10**, and in particular the loops **32**, can be related to the denier per filament ratio (dpf) in the multifilament loop yarn **31**. "Denier" is defined as the weight per unit length of yarn. Denier is numerically equal to the weight, in grams, of 9,000 meters length of yarn. The lower the denier, the lighter and finer the yarn. The higher the denier, the heavier and more coarse the yarn. "Denier per filament" (dpf) is defined as the size of each filament in a multifilament yarn equal to the total yarn denier divided by the number of filaments. The lower the dpf ratio, the harder it is for the loops **32** to spring back to their original configuration **40**. Conversely, the higher the dpf ratio, the easier it is for the loops **32** to recover to the non-compressed configuration **40**. Conventional medical device fabrics may comprise yarn having a total denier of about 150 and about 96 filaments, for a relatively low denier per filament (dpf) ratio of about 1.56.

In some embodiments of the compressible resilient fabric **10** of the present invention, the loop layer yarn **31** can have a total denier of about 60-70 denier and a relatively high denier per filament (dpf) ratio of about 5-20. That is, the denier per filament ratio in loop layer yarn **31** in the compressible resilient fabric **10** can be about 5-20 dpf, or about three to ten times greater, and the number of filaments can be about 40-50% less, than in conventional medical device fabric. In certain embodiments, the total denier for the loop yarn **31** in the compressible resilient fabric **10** can be less than about 60, for example, as low as about 10-15 denier, depending on the particular application for the fabric **10**.

In addition to providing more stable loops **32** having greater resiliency, the higher denier per filament yarn **31** in the fabric **10** can provide loops **32** that are more compressible than conventional fabric having lower denier per filament yarn. It was discovered in experimentation that two layers of multifilament loop yarn **31** having a total denier of about 60-70 allows a compressed fabric thickness **45** of about 0.008 inches. This degree of compressibility was found to be sufficient for utilization in medical device applications. In addition, multifilament loop yarn **31** having a total denier of about 60-70 was found to provide sufficient resilience for the loops **32** to recover substantially their non-compressed configuration **40** having a thickness between about 1 mm and about 2 mm of when compression was relieved.

Fluid media may have an impact on resiliency and/or uniformity of resiliency of the fabric **10**. Yarns having a relatively lower denier per filament ratio tend to absorb more fluid from fluid media in which they are packaged than yarns having a relatively high denier per filament ratio. Absorption of fluid from packaging media can cause the yarns to increase in volume, resulting in less resiliency when a compressive force is released from the fabric **10**. Therefore, some embodiments of the compressible resilient fabric **10** of the present invention comprising high denier per filament yarn **31** may absorb less fluid from packaging media, and the resiliency of such fabric

10 may thus be less adversely affected by fluid media, than conventional medical device fabrics.

In some embodiments, yarn in the ground layer **20** can have heat shrinkage rates, or shrinkability, up to 40% to 60% of the length and width of the unprocessed ground layer **20**. Such high rates of shrinkage in the yarn in the ground layer **20** can cause the courses and wales in the ground layer **20** to move closer together. In some embodiments, the yarns in the ground layer **20** can be under a higher tension than the yarns **31** in the loop layer **30**. A tighter ground layer **20** can provide more densely positioned loops **32**, thereby helping the loops **32** stand up and extend outwardly from the ground layer **20**. As a result, the dense positioning of the loops **32** can help stabilize the loops **32**. In this manner, the loops **32** can be securely positioned for consistent functionality after the compressible resilient fabric **10** is implanted within a patient and the fabric **10** is expanded to the non-compressed configuration **40**. That is, when the compressive force is removed from the fabric **10**, the loops **32** can recover, or resiliently reposition, to approximately their original, non-compressed height **43**, which can be a substantially uniform height **43**. Such a recoverable, substantially uniform loop layer height **43** can be particularly useful in medical applications in which a device may not completely conform to the contours of an anatomical structure in which it is implanted.

As described herein, the fabric **10** can be washed, dried, and heated during fabrication in order to shrink the high shrinkage ground layer yarn so as to cause the loop layer yarns **31** to stand up more effectively. A higher tension ground layer **20** can cause the loop points **33** to be tightly packed and the loop apices **34** to be at the greatest possible distance from the surface of the ground layer **20**, thereby providing maximum loop height **43**.

In particular embodiments, the loop yarn **31** can be a synthetic yarn, for example, a polyester yarn, with a heat shrinkage rate of between about 5% and about 8%. Maintaining the heat shrinkage rate of the loop yarn **31** in such a narrow range can provide shrinkage control of the loops **32** so that the compressibility, resilience, and other properties of the finished fabric **10** can be more consistent and predictable. Alternatively, a polyester yarn having a heat shrinkage rate in a broader range, such as between about 2% and about 10%, may be utilized for the loop yarn **31**. When using such a yarn having a broader range of heat shrinkage rate, finish processing can be varied to control the compressibility, resilience, and other properties of the finished fabric.

Embodiments of the compressible resilient fabric **10** and/or device **50** can comprise various materials. Many synthetic materials can be utilized to promote thrombogenesis when implanted as an intraluminal sealing device **50**. For example, nylon and/or polyolefins can serve as thrombogenic material(s) useful in the intraluminal sealing device **50**. In certain embodiments, polyester may be utilized for the ground layer **20** and/or the loop layer **30** yarn(s) **31**. In particular embodiments, different polyester yarns may be used in the ground layer **20** and loop layer **30**. Polyester is known to be well-adapted for promoting tissue in-growth in and around the yarn.

In alternative embodiments, the compressible resilient fabric **10** can be fabricated with dissolvable materials. Such dissolvable materials can include, for example, polyglycolic acid (PGA) and/or ploylactide acid (PLA). Depending on the particular application, the compressible resilient fabric **10** can be fabricated with dissolvable materials alone or in combination with non-dissolvable materials, such as polyester.

In the compressed configuration **41**, the fabric **10** can have a thickness **44** in the range of about 0.004-0.008 inches. Such a thin compressed configuration **41** can allow the fabric **10** to be easily inserted into a delivery catheter along with an intraluminal medical device, such as the device **50**. The compressed thickness **44** of the fabric **10** can be affected by various factors, including, for example, the type of yarn, the porosity of the ground layer **20**, and the density and height **43** of the loop layer **30**.

For example, in the non-compressed, or expanded, configuration **40**, the ground layer **20** can be very thin, for example, in the range of about 0.05-0.1 mm in height. The loops **32** can have a height **43** from the ground layer **20** of about 1-3 mm. In certain embodiments, the loop height **43** can be greater than 3 mm, depending on the size of the implantable device (for example the device **50**) to which it is attached relative to the size and configuration of the vessel into which the device **50** is implanted. For example, if the design of the implantable device **50**, such as the stent **53**, is inserted into a particularly tortuous vessel and leaves a 4-5 mm gap between the exterior surface of the device **50** and the wall of the vessel into which it is implanted, the height **43** of the loops **32** can be 4-5 mm.

The compressibility and/or resiliency in the compressible resilient fabric **10** needed for particular applications can vary. For example, in some clinical situations, compressibility may be of greater concern in order to compress the fabric **10** or device **50** comprising such fabric **10** into a small enough delivery catheter to reach a target implant site. In other situations, resiliency may be a more important consideration for fuller recovery of the loops **32** to their non-compressed height **43** so as to provide a tighter seal between the device **50** and the vessel wall. That is, in some embodiments of the present invention, the fabric **10** can be constructed to provide an optimized balance between a sufficiently low number of loops **32** and/or height/density for adequate compressibility and a sufficiently high number of loops **32** and/or height/density for resilient recovery. Such balanced loop density and height **43** can be optimized for particular applications, for example, a heart valve or for a stent-graft for an aneurysm.

The compressibility and recovery of embodiments of the fabric **10** from the compressed configuration **41** to its substantially original non-compressed configuration **40** can be affected by a variety of factors. Such factors can include the type of yarn, the denier per filament of yarn, the fabric construction, and the method of fabrication, among others. For example, in some embodiments, the ground layer **20** can have a porosity that can provide some space into which the loops **32** can be compressed. In some embodiments, the loops **32** can be held tightly and/or densely packed on the ground layer **20**. In some embodiments, the loops **32** can be sufficiently thin to allow packing in a compressed state and/or sufficiently thick to allow sealing with clots. In particular embodiments, the yarn in the ground layer **20** can comprise about two-thirds of the fabric volume, and the yarn **31** in the loops **32** can comprise about one-third of the fabric volume.

Some embodiments of the present invention can include a device **50**, as shown in FIG. **4**, comprising a substantially tubular inner member **51**, and an intraluminal sealing member **52** attachable to the exterior of the inner member **51**. In some embodiments, the inner member **51** can comprise an implantable medical device, for example, a stent **53**. FIG. **3** illustrates a cross-section of the fabric **10** (or sealing member **52**) in a tubular configuration, as may be applied to the inner member **51**. The sealing member **52**, or fabric **10**, may be attached to the tubular inner member **51** using various techniques. For example, the sealing member **52**, or fabric **10**, may be attached to the tubular inner member **51** with an adhesive

material, by stitching the sealing member **52**, or fabric **10**, to the inner member **51**, or by other methods.

The sealing member **52** can include the ground layer **20** of knitted yarn and a loop layer **30** comprising a plurality of loops **32** of yarn **31**, each loop **32** having a point **33** knit into the ground layer **20**. The sealing member **52** can be compressible from a non-compressed configuration **40**, in which each loop **32** has an apex **34** extending substantially perpendicularly and radially outward **42** from the ground layer **20**, into a compressed configuration **41**, in which each loop **32** is collapsed onto and/or into the ground layer **20**. The sealing member **52** can be resilient so as to substantially resume the non-compressed configuration **40** when compression is relieved, for example, after the device **50** is implanted into a lumen in a human or animal body. The intraluminal sealing member **52** can be adapted to promote sealing between the inner member **52** and a lumen wall.

As shown in FIGS. **3** and **4**, the implantable device **50** and the inner member **51** can be tubular in shape. Such tubular embodiments can be utilized in cardiovascular applications, such as with a heart valve or stent-graft. In such applications, the intraluminal sealing member **52** can be formed, wrapped, or attached about the radially expanding inner member **51**. In this manner, when the device **50** is implanted in a target location, flow of blood between the exterior of the device **50** and the wall of the vessel can be restricted and/or prevented. When the device **50** is radially expanded, there can be gaps and/or voids between the implanted device **50** and the vessel wall because the flexibility of the device **50** may not completely conform to the contours of the vessel. The intraluminal sealing member **52** can fill those gaps and/or voids. Accordingly, the sealing member **51**, and/or fabric **10**, can function as an in vivo sealant or gasket for the expandable medical device **50**. In certain embodiments, the loops **32** can comprise a thrombogenic material, such as polyester, that can further enhance clotting by the sealing member **52**, or fabric **10**. In addition, the intraluminal sealing member **52** can serve as a frictional retention mechanism to help secure the implanted device **50** to the target location in the body.

In some embodiments of such a device **50**, the loop layer yarn **31** can comprise a high denier per filament multifilament yarn **31**. For example, the multifilament yarn **31** in the device **50** can have 5-20 denier per filament. In some embodiments, the loop layer yarn can comprise a total denier of 60-70. The high denier per filament yarn **31** can enhance the ability of the loops **32** to stand upright so as to extend substantially perpendicularly outward **42** from the ground layer **20**. Such structural support within the loops **32** can provide enhanced stability to the loops **32** to maintain their upright positioning **42**. In certain embodiments, each loop **32** can have a substantially uniform height **43** in the non-compressed configuration **40**. As a result, the loop layer **30** of the intraluminal sealing member **52** can provide a consistent contact, and thus a reliable seal, between the underlying tubular inner member **51** and the wall of a lumen into which it is implanted.

In some embodiments, the ground layer yarn of the intraluminal sealing member **52** can comprise a yarn that is substantially more shrinkable than the loop layer yarn **31**. For example, the ground layer **20** may comprise a yarn shrinkable about 40-60%, and the loop layer **30** may comprise a yarn **31** shrinkable about 5-8%. The loop yarn **31** and/or the ground yarn can comprise various yarns. A particularly useful type of yarn in either or both layers **20**, **30**, respectively, is a polyester yarn. The polyester yarn can be different in each of the ground and loop layers **20**, **30**, respectively.

In some embodiments of such a device, the loops in the intraluminal sealing member can be densely knit to further enhance the upright stability of the loop layer. For example, the loop layer can include two loops knit in every four courses of the ground layer. In certain embodiments, the loop layer can include between about 600 and 750 loops per square inch of the fabric.

In some embodiments of such a device **50**, the intraluminal sealing member **52** can be compressed from the non-compressed configuration **40** to the compressed configuration **41**. In the non-compressed configuration **40**, some embodiments of the sealing member **52** can have a thickness of about 1-5 mm. In the compressed configuration **41**, some embodiments of the sealing member **52** can have a thickness of about 0.004-0.008 inches.

In some embodiments of the present invention, the multifilament loops **32** can promote clot formation within the loops **32**. A typical clotting cascade can occur in which blood clots form first on the inside of the loops **32** and then progressively outwardly until a clot forms a solid connection between the fabric **10** and/or sealing member **52** and the adjacent anatomical structure, such as a vessel wall. In this way, the clot facilitated by the loop structure and size can help secure the fabric **10** and/or device **50** in place and prevent blood flow around the outside of the device **50**. The height of the loops **32** can vary, depending on the underlying device **50**, the target location for implantation, and the degree of loop compressibility desired. A greater height of the loops **32** provides a larger surface area for clot formation and can minimize dislodgement of the forming clots. An optimal loop height **43** can allow promotion of clot formation while allowing sufficient compressibility of the loops **32**.

In some embodiments, movement and positioning of the compressible resilient fabric **10** and/or device **50** can be monitored fluoroscopically or under CT visualization. For example, the compressible resilient fabric **10** can include radiopaque material such that positioning and expansion of the device **50** and the attached fabric **10** can be monitored. Radiopaque is defined as being opaque to radiation and especially x-rays. In certain embodiments, a plurality of radiographic markers (not shown) can be in communication with predetermined portions of the compressible resilient fabric **10** and/or implantable device **50** so that when the device **50** moves, movement and positioning of the markers—and the fabric **10** and/or device **50** in communication therewith—can be visualized.

Embodiments of the compressible resilient fabric **10**, device **50**, system, kit, and method as described herein can be utilized in medical applications, including, for example, in vascular and endovascular implants such as stents, stent-grafts, and heart valves. Some embodiments may be applicable for use in various other types of anatomical structures and locations, for example, in shunts between organs and/or in gastrointestinal, pulmonary, neurological, and/or other structures and locations of a human or animal body.

Embodiments of the compressible resilient fabric **10** and/or device **50** can have advantages over conventional fabrics and devices. For example, one advantage is that the fabric **10** and/or sealing member **52** can be sufficiently compressible for inserting into a target location and sufficiently resilient to recover to substantially its non-compressed configuration **40** when in the target location and the compression is relieved. As a result, the fabric **10** and/or sealing member **52** are adapted to promote sealing between the fabric **10** and/or sealing member **52** and an adjacent anatomical structure, such as a lumen wall. In certain embodiments, the compressible resilient fabric **10** and/or device **50** can provide frictional contact between the fabric **10** or device **50** and the adjacent anatomical structure. Such a frictional contact can help pre-

vent blood flow around the fabric **10** and/or device **50** and provide a surface for clot formation to further secure the fabric **10** and/or device **50** in the desired implant position.

Another advantage of some embodiments of the compressible resilient fabric **10** and/or device **50** is that the loops **32** can have sufficient stability in the perpendicularly extended (upright) position **42** relative to the ground layer **20** to provide a uniform loop height **43**, and thereby consistent contact with an adjacent anatomical structure. Loop stability can be advantageously provided by various aspects of embodiments of the present invention. For example, the loops **32** can be stabilized in the outwardly extended position **42** by each loop **32** being integrally knit into the ground layer **20**, by knitting the loops **32** closely together in a dense pattern, by high denier per filament yarn **31** in the loops **32**, and by the ground yarn having a high shrinkage capacity that when shrunk causes the loops **32** to become more tightly packed.

Another advantage of some embodiments of the compressible resilient fabric **10** and/or device **50** is that loops comprising high denier per filament yarn can retain resiliency when stored in fluid media.

Some embodiments of the present invention can include a system and/or kit. Such a system and/or kit can include a compressible resilient fabric **10** and/or devices **50** including a compressible resilient fabric **10** as described herein. For example, some embodiments of such a system and/or kit can include the fabric **10** and/or intraluminal sealing member **52** comprising a ground layer **20** of knitted yarn, and a loop layer **30** comprising a plurality of loops **32** of yarn **31**, each loop **32** having a point **33** knit into the ground layer **20**. The fabric **10** and/or intraluminal sealing member **52** can be compressible from an non-compressed configuration **40**, in which each loop **32** has an apex **34** extending substantially perpendicularly outward **42** from the ground layer **20**, into the compressed configuration **41**, in which each loop **32** is collapsed onto the ground layer **20**. The fabric **10** can be resilient so as to substantially resume the non-compressed configuration **40** when compression is relieved.

The loops **32** in embodiments of the fabric **10** and/or intraluminal sealing member **52** can be stabilized in the outwardly extended position **42** by various means, including by each loop **32** being integrally knit into the ground layer **20**, by knitting the loops **32** closely together in a dense pattern, by high denier per filament yarn **31** in the loops **32**, and by the ground yarn having a high shrinkage capacity that when shrunk causes the loops **32** to become more tightly packed.

The system and/or kit may further comprise additional components, for example, a delivery catheter for a device that includes the fabric **10** and/or intraluminal sealing member **52**.

Some embodiments of the present invention can include a method of making a compressible resilient fabric **10** and/or devices **50** including the compressible resilient fabric **10** as described herein. For example, one such a method can include knitting the ground layer **20** of yarn and the loop layer **30** comprising a plurality of loops **32** of yarn **31**, each loop **32** having a point **33** knit into the ground layer **20**. In the fabric **20** and/or device **50** made by such a method, the fabric **10** can be compressible from the non-compressed configuration **40**, in which each loop **32** has an apex **34** extending substantially perpendicularly outward **42** from the ground layer **20**, into the compressed configuration **41**, in which each loop **32** is collapsed onto the ground layer **20**. The fabric **10** can further be resilient so as to substantially resume the non-compressed configuration **40** when compression is relieved. In some embodiments of a method, the loop layer **30** can be knit with a multifilament yarn **31** having 5-20 denier per filament and a total denier of 60-70. A high denier per filament yarn can increase the extensibility and stability of loop positioning.

Embodiments of the compressible resilient fabric **10** and/or intraluminal sealing member **52** of the present invention can be made utilizing warp knitting techniques, for example, on a double-bar raschel knitting machine. As used herein, "warp knitting" is defined as a method of knitting fabric out of one or more sets of yarn prepared as warps on beams. The yarns are fed through one or more guide bars to knitting needles that form the yarns into interlaced loops **32**. The guide bars move the yarns around the needles and from needle to needle to create the warp knit fabric. In warp knitting, there is simultaneous yarn-feeding and loop-forming action occurring at every needle in the guide bar during the knitting cycle. All needles in the needle bar are simultaneously lapped by separate guide bars. A "warp knit fabric" is a knit fabric in which the yarns generally run lengthwise but in a zigzag patterns, which forms loops **32** in two or more wales.

In one alternative warp knitting technique to form the high pile fabric **10**, a "dummy needle" can be used to fill a needle space on a knitting machine when no needle is required for the pattern. In another alternative warp knitting technique, yarn ends can be looped around a pole to help form a loop **32** into a particular size. Use of a "pole" or pile sinker can be helpful for knitting relatively larger loops **32**.

Warp knitting can be advantageous for making the compressible resilient fabric **10** and/or intraluminal sealing member **52** in that warp knitting decreases the risk of the fabric **10** or sealing member **52** from fraying and from unraveling when cut. Warp knitting provides a manufacturing process that can result in consistent quality of knitted products.

In some embodiments of the compressible resilient fabric **10** and/or intraluminal sealing member **52**, the loops **32** can be integrally knit with the ground layer **20** utilizing a stitch design that ensures the points **33** of the loops **32** are held tightly to the ground layer **20**. Such tight loop layer **30**—ground layer **20** knitting can help the loops **32** stand upright **42** away from the ground layer **20** surface, thereby contributing to the resilience of the loops **32**.

FIG. **5** shows a knitting stitch diagram of one four-course repeat for one exemplary embodiment of the compressible resilient fabric **10**. The 3-2-1-0 designation in FIG. **5** represents spaces between needles along the direction of the wales in the fabric **10**. Courses **1-4** are indicated along the left hand side of the diagram. In this knitting pattern, four guide bars (bars **1-4**) alternate between two needle beds. While bars **3** and **4** knit in their respective courses, bars **1** and **2** each knit once in every four-course repeat. Thus, bars **1** and **2** produce open stitch loops **32** in alternating courses, providing two loops **32** in every four course repeat. The stitch notation in FIG. **5** designates the path of the yarn on each bar between the needles. For example, the yarn on bar **1** travels in course **1** starting in space **1** and forms loop ending in space **0**; stays in space **0** in courses **2** and **3**; and then moves to space **1** in course **4**. Since the yarn stays in the same space (space **0**) in courses **2** and **3**, an open stitch loop **32** is formed.

In some embodiments, selected guide bars from which the ground layer **20** is knit can be tightly spaced so as to knit the ground layer **20** more tightly to create a more densely packed loop layer **30**. In some embodiments of a method, the loop layer **30** can be knit having between about 600 and about 750 loops **32** per square inch of the fabric **10**.

Another embodiment of a method of making the compressible resilient fabric **10** and/or devices **50** can include pile knitting. In a pile knitted construction, the pile (for example, loops **32**) stand out substantially at right angles **42** from the technical back of the knitted ground layer **20**. As used herein,

"pile" refers to yarns (for example, loops **32**) that stand away, or extend outwardly **42**, from the surface of the fabric **10**. Sinker loops or underlaps can be used to produce this effect. Such a technique can be varied by using a double needle bar knitting machine, and pressing off on the second set of needles to produce the pile surface layer. Point or looped pile can be produced on a double-bar raschel knitting machine by replacing the front bar needles by a point or pin bar around which the pile yarns are overlapped. Pile knitting can produce a high pile fabric that has resistance to unraveling similar to the ravel-resistance achievable with warp knitting. A pile knitting machine also has the ability to hold slack in a stitch to create the ground layer **20** having higher tension than the loops **32**, thereby further enhancing the stability of the extended loops **32**. Pile knitting can provide for variation in the size of the loops **32**, which can be customized by changing the size of the knitting elements.

Knitted constructions of the compressible resilient fabric **10** can provide loops **32** having greater extensibility than in other construction modalities, such as weaving. Enhanced loop extensibility can allow greater height **43** of the loops **32** and thus greater contact with a vessel wall and more surface area for blood to clot between the exterior surface of a device **50** to which the fabric **10** is attached and the interior wall of the vessel into which the device **50** is implanted. Knitting also offers the advantage of providing enhanced stretch and recovery, or resiliency, of the loops **32**. In addition, warp knitting can provide a more flexible process for making a tubular device **50** with the fabric **10**, while still providing for the fabrication of the ground layer **20** and the loop layer **30**.

Although knitting may be a preferred technique for making some embodiments of the compressible resilient fabric **10**, the fabric **10** can also be made by weaving. Weaving may be utilized to produce a high pile fabric having a highly stable ground layer **20**. In addition, a thinner and more flexible fabric **10** may be made by weaving, which can facilitate production of a tubular device **50**. In woven embodiments of the fabric **10**, the loops **32** can comprise floated yarns. Thus, woven embodiments of the present invention may provide the advantages of increased stability, while including a thinner fabric **10**.

Some embodiments of a method of making the compressible fabric **10** and/or intraluminal sealing member **52** can further include washing the fabric **10** or sealing member **52** in about 90 degree C. water. Washing the fabric **10** or sealing member **52** after formation can advantageously cause some shrinkage of the fabric **10** or sealing member **52**. It may be desirable to place the fabric **10** or sealing member **52** inside a protective housing such as a mesh covering or bag to protect the loops **32** from rigorous agitation or disturbance during washing. The wash can include use of detergent(s), softener(s), and/or other additives.

After washing, the fabric **10** or sealing member **52** can be dried at about 60-65 degrees C. The fabric **10** or sealing member **52** can be dried in a tumble dryer. Drying at this temperature can cause the fabric **10** or sealing member **52** to shrink further. The ground layer **20** and the loop layer **30** can each be knit with a yarn(s) having a different degree of shrinkability. For example, the ground layer yarn can be substantially more shrinkable than the loop layer yarn **31**. In one particular embodiment, washing and drying the fabric **10** and/or intraluminal sealing member **52** can shrink the ground layer **20** about 40-60% and shrink the loop layer **30** about 7-8%.

After the washing and drying processes, the fabric **10** or sealing member **52** can be thermoset in a dry oven. Such heat-setting can improve the memory of the fibers in at least the loop layer yarns **31**. In addition, heat-setting can create pockets in the ground layer **20** that allow the loops **32** to be compressed into areas within the ground layer **20**, resulting in a thinner fabric in the compressed configuration **41**.

Certain embodiments of a method of making the fabric **10** or sealing member **52** can further include stretching the fabric **10** or sealing member **52** in the width or course-wise direction prior to drying the fabric **10** or sealing member **52** so as to heat set the fabric **10** or sealing member **52** under tension. For example, in some embodiments, each of the yarn ends of the fabric **10** or sealing member **52** can be releasably attached to pins in a pin frame. The pins in the pin frame can secure the edges of the fabric **10** or sealing member **52** to stabilize the fabric **10** or sealing member **52** with an even tension throughout the fabric **10** or sealing member **52** in order to achieve a consistent degree of final shrinkage as the fabric **10** or sealing member **52** is being heat set. Stretching the fabric **10** or sealing member **52** in the heat-setting process can thus provide a desired orientation for memory by the fabric **10** or sealing member **52** once heat set.

Some embodiments of the present invention can include a method of using the compressible resilient fabric **10** and/or devices **50** including the compressible resilient fabric **10** as described herein. For example, one such a method can include utilizing the device **50** comprising the substantially tubular inner member **51**, such as the stent **53**, and the intraluminal sealing member **52** attachable to the exterior of the inner member **51**. The sealing member **52** can include the ground layer **20** of knitted yarn and the loop layer **30** comprising a plurality of loops **32** of yarn **31**, each loop **32** having a point **33** knit into the ground layer **20**. The sealing member **52** can be compressed from the non-compressed configuration **40**, in which each loop **32** has an apex **34** extending substantially perpendicularly and radially outward **42** from the ground layer **20**, into the compressed configuration **41**, in which each loop **32** is collapsed onto the ground layer **20**. After the device **50** is implanted into a lumen in a human or animal body and compression is relieved, the sealing member **52** can recover so as to substantially resume its non-compressed configuration **40**. The intraluminal sealing member **52** can be adapted to promote sealing between the inner member **51** and a lumen wall.

Although the present invention has been described with reference to particular embodiments, it should be recognized that these embodiments are merely illustrative of the principles of the present invention. Those of ordinary skill in the art will appreciate that a compressible resilient fabric **10**, device **50**, system, kit, and methods of the present invention may be constructed and implemented in other ways and embodiments. Accordingly, the description herein should not be read as limiting the present invention, as other embodiments also fall within the scope of the present invention.

What is claimed is:

1. A fabric, comprising:

a ground layer of knitted yarn; and

a loop layer comprising a plurality of loops of yarn, each loop having a point knit into the ground layer,

wherein the fabric is compressible from a non-compressed configuration, in which each loop has an apex extending substantially perpendicularly outward from the ground layer, into a compressed configuration comprising a thickness of about 0.004-0.008 inches and in which each loop is collapsed onto the ground layer, and

wherein the fabric is resilient so as to substantially resume the non-compressed configuration by returning the loops to approximately an original, non-compressed height when compression is relieved.

2. The fabric of claim **1**, wherein the ground layer yarn comprises a yarn shrinkable substantially more than the loop layer yarn.

3. The fabric of claim **1**, wherein the ground layer yarn comprises a yarn having a higher shrinkability than the loop layer yarn.

4. The fabric of claim **1**, wherein the loop layer further comprises two loops in every four courses of the ground layer.

5. The fabric of claim **1**, wherein the loop layer further comprises between about 600 and about 750 loops per square inch of the fabric.

6. The fabric of claim **1**, wherein each loop further comprises a substantially uniform height in the non-compressed configuration.

7. The fabric of claim **1**, wherein the fabric further comprises a thickness of about 1-5 mm in the non-compressed configuration.

8. The fabric of claim **1**, wherein at least the loop yarn further comprises a polyester yarn.

9. The fabric of claim **1**, wherein the loop layer yarn comprises a multifilament yarn having 5-20 denier per filament.

10. The fabric of claim **1**, wherein the ground layer comprises a porosity sufficient to allow collapse of each loop onto the ground layer.

11. A fabric, comprising:

a ground layer of knitted yarn; and

a loop layer comprising a plurality of loops of multifilament yarn having a total denier of about 60-70, each loop having a point knit into the ground layer,

wherein the fabric is compressible from a non-compressed configuration, in which each loop has an apex extending substantially perpendicularly outward from the ground layer, into a compressed configuration comprising a thickness of about 0.008 inches and in which each loop is collapsed onto the ground layer, and

wherein the fabric is resilient so as to substantially resume the non-compressed configuration having a thickness between about 1 mm and about 2 mm by returning the loops to approximately an original, non-compressed height when compression is relieved.

* * * * *