



US 20060105485A1

(19) **United States**(12) **Patent Application Publication**
Basin et al.(10) **Pub. No.: US 2006/0105485 A1**(43) **Pub. Date: May 18, 2006**(54) **OVERMOLDED LENS OVER LED DIE****Publication Classification**(75) Inventors: **Grigoriy Basin**, San Francisco, CA (US); **Robert Scott West**, Morgan Hill, CA (US); **Paul S. Martin**, Pleasanton, CA (US); **Gerard Harbers**, Sunnyvale, CA (US); **Willem H. Smits**, Veldhoven (NL); **Robert F. M. Hendriks**, Overlangel (NL); **Frans H. Konijn**, Huizen (NL)(51) **Int. Cl.****H01L 21/00** (2006.01)(52) **U.S. Cl.** **438/27; 257/E33**

(57)


ABSTRACT

One or more LED dice are mounted on a support structure. The support structure may be a submount with the LED dice already electrically connected to leads on the submount. A mold has indentations in it corresponding to the positions of the LED dice on the support structure. The indentations are filled with a liquid optically transparent material, such as silicone, which when cured forms a lens material. The shape of the indentations will be the shape of the lens. The mold and the LED dice/support structure are brought together so that each LED die resides within the liquid silicone in an associated indentation. The mold is then heated to cure (harden) the silicone. The mold and the support structure are then separated, leaving a complete silicone lens over each LED die. This over molding process may be repeated with different molds to create concentric shells of lenses. Each concentric lens may have a different property, such as containing a phosphor, providing a special radiation pattern, having a different hardness value, or curable by a different technique (e.g., UV vs. heat).

Correspondence Address:

PATENT LAW GROUP LLP
2635 NORTH FIRST STREET
SUITE 223
SAN JOSE, CA 95134 (US)(73) Assignee: **Lumileds Lighting U.S., LLC**(21) Appl. No.: **11/069,418**(22) Filed: **Feb. 28, 2005****Related U.S. Application Data**

(63) Continuation-in-part of application No. 10/990,208, filed on Nov. 15, 2004.






FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21




FIG. 22




FIG. 23




FIG. 24




FIG. 25




FIG. 26




FIG. 27




FIG. 28




FIG. 29




FIG. 30




FIG. 31




FIG. 32




FIG. 33




FIG. 34

OVERMOLDED LENS OVER LED DIE**CROSS-REFERENCE TO RELATED APPLICATIONS**

[0001] This is a continuation-in-part of U.S. application Ser. No. 10/990,208, filed Nov. 15, 2004, by Grigoriy Basin et al., entitled "Molded Lens Over LED Die."

FIELD OF THE INVENTION

[0002] This invention relates to light emitting diodes (LEDs) and, in particular, to a technique for forming a lens over an LED die.

BACKGROUND

[0003] LED dies typically emit light in a lambertian pattern. It is common to use a lens over the LED die to narrow the beam or to make a side-emission pattern. A common type of lens for a surface mounted LED is pre-formed molded plastic, which is bonded to a package in which the LED die is mounted. One such lens is shown in U.S. Pat. No. 6,274,924, assigned to Lumileds Lighting and incorporated herein by reference.

SUMMARY

[0004] A technique for forming a lens for surface mounted LEDs is described herein.

[0005] One or more LED dice are mounted on a support structure. The support structure may be a ceramic substrate, a silicon substrate, or other type of support structure with the LED dice electrically connected to metal pads on the support structure. The support structure may be a submount, which is mounted on a circuit board or a heat sink in a package.

[0006] A mold has indentations in it corresponding to the positions of the LED dice on the support structure. The indentations are filled with a liquid, optically transparent material, such as silicone, which when cured forms a hardened lens material. The shape of the indentations will be the shape of the lens. The mold and the LED dice/support structure are brought together so that each LED die resides within the liquid lens material in an associated indentation.

[0007] The mold is then heated to cure (harden) the lens material. The mold and the support structure are then separated, leaving a complete lens over each LED die. This general process will be referred to as overmolding.

[0008] The overmolding process may be repeated with different molds to create concentric or overlapping shells of lenses. Each lens may have a different property, such as containing a phosphor, being a different material, providing a different radiation pattern, having a different hardness value, having a different index of refraction, or curable by a different technique (e.g., UV vs. heat).

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] **FIG. 1** is a side view of four LED dice mounted on a support structure, such as a submount, and a mold for forming a lens around each LED die.

[0010] **FIG. 2** is a side view of the LED dice being inserted into indentations in the mold filled with a liquid lens material.

[0011] **FIG. 3** is a side view of the LED dice removed from the mold after the liquid has been cured, resulting in a lens encapsulating each LED die.

[0012] **FIG. 4** is a perspective view of an array of LED dice on a submount or circuit board with a molded lens formed over each LED die.

[0013] **FIG. 5** is a close-up side view of a flip-chip LED die mounted on a submount, which is, in turn, mounted on a circuit board, and where a molded lens is formed over the LED die.

[0014] **FIG. 6** is a close-up side view of a non-flip-chip LED die mounted on a submount, which is, in turn, mounted on a circuit board, where wires electrically connect n and p metal on the LED die to leads on the circuit board, and where a molded lens is formed over the LED die.

[0015] **FIGS. 7, 8, 9, 10, and 11** are cross-sectional views of an LED die with different lenses formed over it.

[0016] **FIG. 12** is a cross-sectional view of a side-emitting lens molded onto the LED die using the inventive techniques.

[0017] **FIG. 13** is a cross-sectional view of a collimating lens molded onto the LED die using the inventive techniques.

[0018] **FIG. 14** is a cross-sectional view of a preformed side-emitting lens affixed over a lambertian lens that has been molded onto the LED die using the inventive techniques.

[0019] **FIG. 15** is a cross-sectional view of a backlight for a liquid crystal display or other type of display using the LED and side-emitting lens of **FIG. 14**.

[0020] **FIG. 16** is a perspective view of a cell phone with a camera that uses as a flash an LED with a molded lens.

[0021] **FIGS. 17 and 18** are cross-sectional views of two types of molded lenses. All lenses shown are symmetrical about the center axis, although the invention may apply to non-symmetrical lenses as well.

[0022] **FIGS. 19-22** illustrate surface features on an inner lens or an outer shell lens for obtaining a desired emission pattern.

[0023] **FIG. 23** illustrates the use of a high domed lens for a collimated emission pattern.

[0024] **FIGS. 24 and 25** illustrate the use of a hard outer lens and a soft inner lens to limit the stress on a wire bond.

[0025] **FIGS. 26-28** illustrate the use of an outer lens formed on various types of inner or intermediate lenses for a side-emitting pattern.

[0026] **FIG. 29** illustrates another side-emitting molded lens.

[0027] **FIG. 30** illustrates the use of molded shells, each containing a different phosphor.

[0028] **FIG. 31** illustrates forming a mold portion on the support substrate for forming a molded lens.

[0029] **FIG. 32** illustrates depositing a metal reflector over a portion of the lens for achieving a desired emission pattern.

[0030] **FIG. 33** is a side view of a liquid crystal display using LEDs with side-emitting lenses in a backlight.

[0031] **FIG. 34** is a side view of a rear projection TV using LEDs with collimating lenses as a RGB light source.

DETAILED DESCRIPTION

[0032] As a preliminary matter, a conventional LED is formed on a growth substrate. In the example used, the LED is a GaN-based LED, such as an AlInGaN LED, for producing blue or UV light. Typically, a relatively thick n-type GaN layer is grown on a sapphire growth substrate using conventional techniques. The relatively thick GaN layer typically includes a low temperature nucleation layer and one or more additional layers so as to provide a low-defect lattice structure for the n-type cladding layer and active layer. One or more n-type cladding layers are then formed over the thick n-type layer, followed by an active layer, one or more p-type cladding layers, and a p-type contact layer (for metallization).

[0033] Various techniques are used to gain electrical access to the n-layers. In a flip-chip example, portions of the p-layers and active layer are etched away to expose an n-layer for metallization. In this way the p contact and n contact are on the same side of the chip and can be directly electrically attached to the package (or submount) contact pads. Current from the n-metal contact initially flows laterally through the n-layer. In contrast, in a vertical injection (non-flip-chip) LED, an n-contact is formed on one side of the chip, and a p-contact is formed on the other side of the chip. Electrical contact to one of the p or n-contacts is typically made with a wire or a metal bridge, and the other contact is directly bonded to a package (or submount) contact pad. A flip-chip LED is used in the examples of **FIGS. 1-3** for simplicity.

[0034] Examples of forming LEDs are described in U.S. Pat. Nos. 6,649,440 and 6,274,399, both assigned to Lumileds Lighting and incorporated by reference.

[0035] Optionally, a conductive substrate is bonded to the LED layers (typically to the p-layers) and the sapphire substrate is removed. One or more LED dice may be bonded to a submount, with the conductive substrate directly bonded to the submount, to be described in greater detail with respect to **FIGS. 5 and 6**. One or more submounts may be bonded to a printed circuit board, which contains metal leads for connection to other LEDs or to a power supply. The circuit board may interconnect various LEDs in series and/or parallel.

[0036] The particular LEDs formed and whether or not they are mounted on a submount is not important for purposes of understanding the invention.

[0037] **FIG. 1** is a side view of four LED dice **10** mounted on a support structure **12**. The support structure may be a submount (e.g., ceramic or silicon with metal leads), a metal heat sink, a printed circuit board, or any other structure. In the present example, the support structure **12** is a ceramic submount with metal pads/leads.

[0038] A mold **14** has indentations **16** corresponding to the desired shape of a lens over each LED die **10**. Mold **14** is preferably formed of a metal. A very thin non-stick film **18**, having the general shape of mold **14**, is placed over mold **14**.

Film **18** is of a well known conventional material that prevents the sticking of silicone to metal.

[0039] Film **18** is not needed if the lens material does not stick to the mold. This may be accomplished by using a non-stick mold coating, using a non-stick mold material, or using a mold process that results in a non-stick interface. Such processes may involve selecting certain process temperatures to obtain the minimum stick. By not using film **18**, more complex lenses can be formed.

[0040] In **FIG. 2**, the mold indentations **16** have been filled with a heat-curable liquid lens material **20**. The lens material **20** may be any suitable optically transparent material such as silicone, an epoxy, or a hybrid silicone/epoxy. A hybrid may be used to achieve a matching coefficient of thermal expansion (CTE). Silicone and epoxy have a sufficiently high index of refraction (greater than 1.4) to greatly improve the light extraction from an AlInGaN or AlInGaP LED as well as act as a lens. One type of silicone has an index of refraction of 1.76.

[0041] A vacuum seal is created between the periphery of the support structure **12** and mold **14**, and the two pieces are pressed against each other so that each LED die **10** is inserted into the liquid lens material **20** and the lens material **20** is under compression.

[0042] The mold is then heated to about 150 degrees centigrade (or other suitable temperature) for a time to harden the lens material **20**.

[0043] The support structure **12** is then separated from mold **14**. Film **18** causes the resulting hardened lens to be easily released from mold **14**. Film **18** is then removed.

[0044] In another embodiment, the LED dice **10** in **FIG. 1** may be first covered with a material, such as silicone or phosphor particles in a binder. The mold indentations **16** are filled with another material. When the dice are then placed in the mold, the mold material is shaped over the covering material.

[0045] **FIG. 3** illustrates the resulting structure with a molded lens **22** over each LED die **10**. In one embodiment, the molded lens is between 1 mm and 5 mm in diameter. The lens **22** may be any size or shape. **FIG. 4** is a perspective view of a resulting structure where the support structure **12** supports an array of LED dice, each having a molded lens **22**. The mold used would have a corresponding array of indentations. If the support structure **12** were a ceramic or silicon submount, each LED (with its underlying submount portion) can be separated by sawing or breaking the submount **12** to form individual LED dice. Alternatively, the support structure **12** may be separated/diced to support subgroups of LEDs or may be used without being separated/diced.

[0046] The lens **22** not only improves the light extraction from the LED die and refracts the light to create a desired emission pattern, but the lens also encapsulates the LED die to protect the die from contaminants, add mechanical strength, and protect any wire bonds.

[0047] **FIG. 5** is a simplified close-up view of one embodiment of a single flip-chip LED die on a submount **24** formed of any suitable material, such as a ceramic or silicon. In one embodiment, submount **24** acted as the support structure **12** in **FIGS. 1-4**, and the die/submount of **FIG. 5**

was separated from the structure of FIG. 4 by sawing. The LED die 10 of FIG. 5 has a bottom p-contact layer 26, a p-metal contact 27, p-type layers 28, a light emitting active layer 30, n-type layers 32, and an n-metal contact 31 contacting the n-type layers 32. Metal pads on submount 24 are directly metal-bonded to contacts 27 and 31. Vias through submount 24 terminate in metal pads on the bottom surface of submount 24, which are bonded to the metal leads 40 and 44 on a circuit board 45. The metal leads 40 and 44 are connected to other LEDs or to a power supply. Circuit board 45 may be a metal plate (e.g., aluminum) with the metal leads 40 and 44 overlying an insulating layer. The molded lens 22, formed using the technique of FIGS. 1-3, encapsulates the LED die 10.

[0048] The LED die 10 in FIG. 5 may also be a non-flip-chip die, with a wire connecting the top n-layers 32 to a metal pad on the submount 24. The lens 22 may encapsulate the wire.

[0049] In one embodiment, the circuit board 45 itself may be the support structure 12 of FIGS. 1-3. Such an embodiment is shown in FIG. 6. FIG. 6 is a simplified close-up view of a non-flip-chip LED die 10 having a top n-metal contact 34 connected to a metal lead 40 on circuit board 45 by a wire 38. The LED die 10 is mounted on a submount 36, which in the example of FIG. 6 is a metal slab. A wire 42 electrically connects the p-layers 26/28 to a metal lead 44 on circuit board 45. The lens 22 is shown completely encapsulating the wires and submount 36; however, in other embodiments the entire submount or the entire wire need not be encapsulated.

[0050] A common prior art encapsulation method is to spin on a protective coating. However, that encapsulation process is inappropriate for adding a phosphor coating to the LED die since the thickness of the encapsulant over the LED die is uneven. Also, such encapsulation methods do not form a lens. A common technique for providing a phosphor over the LED die is to fill a reflective cup surrounding the LED die with a silicone/phosphor composition. However, that technique forms a phosphor layer with varying thicknesses and does not form a suitable lens. If a lens is desired, additional processes still have to create a plastic molded lens and affix it over the LED die.

[0051] FIGS. 7-11 illustrate various lenses that may be formed using the above-described techniques.

[0052] FIG. 7 illustrates an LED die 10 that has been coated with a phosphor 60 using any suitable method. One such method is by electrophoresis, described in U.S. Pat. No. 6,576,488, assigned to Lumileds Lighting and incorporated herein by reference. Suitable phosphors are well known. A lens 22 is formed using the techniques described above. The phosphor 60 is energized by the LED emission (e.g., blue or UV light) and emits light of a different wavelength, such as green, yellow, or red. The phosphor emission alone or in conjunction with the LED emission may produce white light.

[0053] Processes for coating an LED with a phosphor are time-consuming. To eliminate the process for coating the LED die with a phosphor, the phosphor powder may be mixed with the liquid silicone so as to become embedded in the lens 62, shown in FIG. 8.

[0054] As shown in FIG. 9, to provide a carefully controlled thickness of phosphor material over the LED die, an

inner lens 64 is formed using the above-described techniques, and a separate molding step (using a mold with deeper and wider indentations) is used to form an outer phosphor/silicone shell 66 of any thickness directly over the inner lens 64.

[0055] FIG. 10 illustrates an outer lens 68 that may be formed over the phosphor/silicone shell 66 using another mold to further shape the beam.

[0056] FIG. 11 illustrates shells 70, 72, and 74 of red, green, and blue-emission phosphors, respectively, overlying clear silicone shells 76, 78, and 80. In this case, LED die 10 emits UV light, and the combination of the red, green, and blue emissions produces a white light. All shells are produced with the above-described methods.

[0057] Many other shapes of lenses can be formed using the molding technique described above. FIG. 12 is a cross-sectional view of LED 10, submount 24, and a molded side-emitting lens 84. In one embodiment, lens 84 is formed of a very flexible material, such as silicone, which flexes as it is removed from the mold. When the lens is not a simple shape, the release film 18 (FIG. 1) will typically not be used.

[0058] FIG. 13 is a cross-sectional view of LED 10, submount 24, and a molded collimating lens 86. The lens 86 can be produced using a deformable mold or by using a soft lens material that compresses when being pulled from the mold and expands to its molded shape after being released from the mold.

[0059] FIG. 14 illustrates how a preformed lens 88 can be affixed over a molded lambertian lens 22. In the example of FIG. 14, lens 22 is formed in the previously described manner. Lens 22 serves to encapsulate and protect LED 10 from contaminants. A preformed side-emitting lens 88 is then affixed over lens 22 using a UV curable adhesive or a mechanical clamp. This lens-forming technique has advantages over conventional techniques. In a conventional technique, a preformed lens (e.g., a side emitting lens) is adhesively affixed over the LED die, and any gaps are filled in by injecting silicone. The conventional process is difficult to perform due to, among other reasons, carefully positioning the separated die/submount for the lens placement and gap-filling steps. Using the inventive technique of FIG. 14, a large array of LEDs (FIG. 4) can be encapsulated simultaneously by forming a molded lens over each. Then, a preformed lens 88 can be affixed over each molded lens 22 while the LEDs are still in the array (FIG. 4) or after being separated.

[0060] Additionally, the molded lens can be made very small (e.g., 1-2 mm diameter), unlike a conventional lens. Thus, a very small, fully encapsulated LED can be formed. Such LEDs can be made to have a very low profile, which is beneficial for certain applications.

[0061] FIG. 14 also shows a circuit board 45 on which submount 24 is mounted. This circuit board 45 may have mounted on it an array of LEDs/submounts 24.

[0062] FIG. 15 is a cross-sectional view of a backlight for a liquid crystal display (LCD) or other display that uses a backlight. Common uses are for televisions, monitors, cellular phones, etc. The LEDs may be red, green, and blue to create white light. The LEDs form a two-dimensional array. In the example shown, each LED structure is that shown in

FIG. 14, but any suitable lens may be used. The bottom and sidewalls **90** of the backlight box are preferably coated with a white reflectively-diffusing material. Directly above each LED is a white diffuser dot **92** to prevent spots of light from being emitted by the backlight directly above each LED. The dots **92** are supported by a transparent or diffusing PMMA sheet **94**. The light emitted by the side-emitting lenses **88** is mixed in the lower portion of the backlight, then further mixed in the upper portion of the backlight before exiting the upper diffuser **96**. Linear arrays of LEDs may be mounted on narrow circuits boards **45**.

[0063] **FIG. 16** illustrates an LED **10** with a molded lens **22** being used as a flash in a camera. The camera in **FIG. 16** is part of a cellular telephone **98**. The cellular telephone **98** includes a color screen **100** (which may have a backlight using the LEDs described herein) and a keypad **102**.

[0064] As discussed with respect to **FIG. 10**, an outer lens may be formed over the inner shell to further shape the beam. Different shell materials may be used, depending on the requirements of the various shells. **FIGS. 17-30** illustrate examples of various lenses and materials that may be used in conjunction with the overmolding process.

[0065] **FIGS. 17 and 18** illustrate two shapes of molded lenses for an inner shell formed using the molding techniques described above. Many LEDs **10** may be mounted on the same support structure **12**. The support structure **12** may be a ceramic or silicon submount with metal traces and contact pads, as previously described. Any number of LEDs may be mounted on the same support structure **12**, and all LEDs on the same support structure **12** would typically be processed in an identical manner, although not necessarily. For example, if the support structure were large and the light pattern for the entire LED array were specified, each LED lens may differ to provide the specified overall light pattern.

[0066] An underfill material may be injected to fill any gap between the bottom of the LED die **10** and the support substrate **12** to prevent any air gaps under the LED and to improve heat conduction, among other things.

[0067] **FIG. 17** has been described above with respect to **FIGS. 3-6**, where the inner molded lens **22** is generally hemispherical for a lambertian radiation pattern. The inner molded lens **106** in **FIG. 18** is generally rectangular with rounded edges. Depending on the radiation pattern to be provided by an outer lens, one of the inner molded lenses **22** or **106** may be more suitable. Other shapes of inner molded lenses may also be suitable. The top down view of each lens will generally be circular.

[0068] **FIG. 19** illustrates the structure of **FIG. 18** with the lens outer surface having a pattern that refracts light to achieve a desired radiation pattern. The outer surface pattern may be directly formed in the inner molded lens (by the mold itself), or the outer surface pattern may be formed in an outer lens that is overmolded onto the inner molded lens or is affixed to it by an adhesive (e.g., silicone, epoxy, etc.). Pattern **108** is a diffraction grating, while pattern **110** uses binary steps to refract the light. In the examples, the pattern forms a generally side-emitting lens with the radiation pattern shown in **FIG. 20**. In **FIG. 20**, the peak intensity occurs within 50-80 degrees and is significantly greater than the intensity at 0 degrees.

[0069] The requirements for the inner lens are generally different from the requirements for the outer lens. For

example, the inner lens should have good adhesion to the support structure, not yellow or become more opaque over time, have a high index of refraction (greater than 1.4), not break or stress any wires to the LED, withstand the high LED temperatures, and have a compatible thermal coefficient. The inner lens should be non-rigid (e.g., silicone) to not provide stress on the LED or any wires. In contrast, the outer lens material generally only needs to be able to be patterned with the desired pattern and adhere to the inner lens. The outer lens may overmolded or may be preformed and adhesively affixed to the inner lens. The material for the outer lens may be UV curable, while the material for the inner lens may be thermally cured. Thermal curing takes longer than UV curing.

[0070] Generally, the range of hardness for the inner lens material is Shore 00 5-90, while the range of hardness for the outer shell(s) is Shore A 30 or more.

[0071] **FIG. 21** illustrates a Fresnel lens pattern **112** formed on the outer surface of the lens for creating a generally side-emitting light pattern similar to that of **FIG. 20**. The outer surface may be the outer surface of the inner molded lens or the outer surface of an outer shell, as described with respect to **FIG. 19**. This applies to all patterns described herein.

[0072] **FIG. 22** illustrates pyramid **114** or cone shaped **116** patterns on the outer lens surface to create a collimating light pattern or another light pattern.

[0073] **FIG. 23** illustrates a high dome outer lens **118** for creating a collimating pattern.

[0074] The surface patterns of **FIGS. 19 and 21-23** may be configured (e.g., by changing the surface angles) to create any light pattern. Holographic structures, TIR, and other patterns may be formed. Collimating light patterns are typically used for rear projection TVs, while side-emitting light patterns are typically used for backlighting LCD screens.

[0075] **FIG. 24** illustrates the use of a soft (e.g., Shore XX) material, such as a silicone gel, as the inner molded lens **124** so as to not stress the wire **126** bonded to the LED **10**. The gel is typically UV cured. The outer lens **128** may be molded or preformed and affixed with an adhesive. The outer lens **128** will typically be much harder for durability, resistance to particles, etc. The outer lens **128** may be silicone, epoxy-silicone, epoxy, silicone elastomers, hard rubber, other polymers, or other material. The outer lens may be UV or thermally cured.

[0076] **FIG. 25** is similar to **FIG. 24** but with a different shaped inner molded lens **129** (like **FIG. 18**) for a different emission pattern or a lower profile. Lens **129** may be a soft silicone gel. The outer lens **130** will further shape the emission pattern and protect the soft inner lens **129**.

[0077] The LEDs in all figures may be flip-chips or wire bonded types.

[0078] **FIG. 26** illustrates an LED structure with a soft inner molded lens **132**, having the properties needed for the inner lens, a hard intermediate shell **134** to act as an interface layer and for structural stability, and an outer lens **136** for creating a side-emitting light pattern. The outer lens **136** may be soft to facilitate the molding process. Alternatively, the outer lens **136** may be preformed and adhesively affixed

to the intermediate shell **134**. The use of the intermediate shell **134** makes the choice of the outer lens material essentially independent of the inner lens material.

[0079] **FIG. 27** illustrates how the outer lens **138** may be formed on any portion of the intermediate shell **134** or inner lens **132**.

[0080] **FIG. 28** illustrates the formation of the outer lens **142** directly on the inner lens **144** material.

[0081] **FIG. 29** illustrates another shape of side-emitting lens **145** molded over an inner lens **132**. Lens **145** may be directly molded over LED die **10** without any inner lens.

[0082] **FIG. 30** illustrates an LED where each shell **146**, **147**, and **148** contains a different phosphor material, such as a red-emitting phosphor, a green-emitting phosphor, and a blue-emitting phosphor. The LED die **10** may emit UV. The gaps between phosphor particles allow the UV to pass through an inner shell to energize the phosphor in an outer shell. Alternatively, only red and green phosphor shells are used, and the LED die **10** emits blue light. The combination of red, green, and blue light create white light. The thickness of the shells, the density of the phosphor particles, and the order of the phosphor colors, among other things, can be adjusted to obtain the desired light. Any shape of lenses may be used.

[0083] **FIG. 31** illustrates the use of a mold pattern **149** on the support structure **12** itself. A high index material (e.g., a polymer) or a reflective material (e.g., aluminum or silver) is formed by either molding the pattern on the support structure **12**, using a method similar to the method shown in **FIG. 1**, or using a metallization process, or using another suitable process. The mold pattern **149** is then used as a mold for another material forming a lens **150**. In one embodiment, the lens **150** material is a liquid (e.g., silicone) that is deposited in the mold formed on the support structure **12**, then cured. The surface may then be planarized. The resulting lens collimates the light by reflecting/refracting the light impinging on the walls like a reflector cup.

[0084] **FIG. 32** illustrates a molded lens **22** with metal **151** sputtered around its side to reflect light emitted by the LED **10**. The reflected light will be scattered by the LED **10** and be eventually emitted through the top opening. The metal **151** may be any reflective material such as aluminum or silver. The metal may instead be sputtered on the top of the lens **22** to create a side-emission pattern. The lens **22** may be made any shape to create the desired light emission pattern.

[0085] **FIG. 33** is a side view of a liquid crystal display (LCD) **152** with an LCD screen **154**, having controllable RGB pixels, a diffuser **156**, and a backlight **158** for mixing light from red, green, and blue LEDs **160** to create white light. The backlight **158** is a diffusively reflective box. The LEDs **160** have side-emitting lenses made using any of the above-described techniques.

[0086] **FIG. 34** is a side view of a rear projection television **162** with a front lens **164** for brightening the image within a specified viewing angle, a set of red, green, and blue LEDs **166**, modulator/optics **170** for modulating and focusing the RGB light to produce a color TV image, and a reflector **172**. The modulator may be an array of controllable mirrors, an LCD panel, or any other suitable device. The LEDs **166** have collimating lenses made using any of the above-described techniques.

[0087] While particular embodiments of the present invention have been shown and described, it will be obvious to those skilled in the art that changes and modifications may be made without departing from this invention in its broader aspects and, therefore, the appended claims are to encompass within their scope all such changes and modifications as fall within the true spirit and scope of this invention.

What is claimed is:

1. A method for forming a lens over a light emitting diode (LED) die comprising:

providing an LED die attached to a support structure; and

molding a first lens of a first material over the die while attached to the support structure.

2. The method of claim 1 wherein molding the first lens further comprises curing the first material using a thermal or UV cure.

3. The method of claim 1 wherein molding the first lens comprises:

filling a first indentation in a first mold with a first lens material;

bringing the first mold and the support structure together so that the LED die is within the first lens material;

curing the liquid first lens material; and

removing the support structure from the first mold so that a first lens formed from the cured first lens material overlies the LED die.

4. The method of claim 1 wherein the support structure comprises a submount having metal leads in electrical contact with metal contacts on the LED die.

5. The method of claim 1 wherein the LED die is one of a plurality of LED dice affixed to the support structure.

6. The method of claim 1 wherein the first lens is formed in direct contact with the LED die.

7. The method of claim 1 wherein molding the first lens further comprises molding a pattern into a surface of the first lens for affecting an emitted light pattern.

8. The method of 7 wherein the pattern comprises a Fresnel lens, a diffraction grating, a binary pattern, pyramids, or cones.

9. The method of claim 1 further comprising providing an optical element affixed to the first lens to obtain a desired light pattern.

10. The method of claim 9 wherein the optical element comprises a second lens of a second material different from the first material.

11. The method of claim 9 wherein the optical element comprises a second lens of a second material different from the first material, and wherein providing the optical element comprises:

molding the second lens over the first lens; and

curing the second material.

12. The method of claim 9 wherein the optical element comprises a second lens of a second material different from the first material, and wherein providing the optical element comprises:

molding the second lens over the first lens, the second lens having a surface pattern comprising a Fresnel lens, a diffraction gradient, a binary pattern, pyramids, or cones.

13. The method of claim 9 wherein the optical element comprises a second lens of a second material harder than the first material.

14. The method of claim 10 wherein a range of hardness of the first lens is Shore 00 5-90, and the hardness of the second lens is greater than Shore A 30.

15. The method of claim 9 wherein providing the optical element comprises depositing a reflective material on an outer surface of the first lens.

16. The method of claim 9 wherein the optical element is a collimating lens.

17. The method of claim 9 wherein the optical element is a side-emitting lens.

18. The method of claim 9 wherein the optical element comprises a second lens of a second material different from the first material, wherein the first material and the second material comprise silicone, epoxy, or a silicone/epoxy hybrid.

19. The method of claim 9 wherein providing the optical element comprises:

providing a second mold having a second indentation filled with a second lens material;

bringing together the second mold and the support structure, having attached to it the LED die having the first lens, so that the first lens is within the second lens material in the second indentation;

curing the second lens material; and

removing the support structure from the second mold so that the second lens material forms a first shell over the first lens.

20. The method of claim 9 wherein providing the optical element comprises providing an optical element directly on the first lens.

21. The method of claim 9 wherein the optical element comprises a second lens over the first lens, the first lens containing a first phosphor, and the second lens containing a second phosphor.

22. The method of claim 21 wherein a combination of the LED light and the light emitted by the phosphors creates white light.

23. The method of claim 9 wherein the optical element comprises a second lens over the first lens, the method further comprising molding a third lens over the second lens, the first lens containing a first phosphor, the second lens containing a second phosphor, and the third lens containing a third phosphor.

24. A method for forming a lens over a light emitting diode (LED) die comprising:

providing an LED die attached to a support structure;

forming a mold on the support structure; and

molding a first lens of a first material over the die while attached to the support structure, using the mold on the support structure to define the shape of the first lens.

25. The method of claim 24 wherein molding the first lens comprises depositing a lens material in the mold on the support structure and then curing the lens material.

26. A light emitting device comprising:

a light emitting diode (LED) die attached to a support structure; and

a first lens molded over the LED die and encapsulating the LED die.

27. The device of claim 26 further comprising an optical element affixed to the first lens to obtain a desired light pattern.

28. The device of claim 27 wherein the optical element comprises a second lens of a second material different from the first material.

29. The device of claim 28 wherein the second lens is molded over the first lens.

30. The device of claim 28 wherein the second lens has a pattern molded into its surface for affecting an emitted light pattern.

31. The device of claim 30 wherein the pattern comprises a Fresnel lens, a diffraction grating, a binary pattern, pyramids, or cones.

32. The device of claim 26 wherein the first lens has a pattern molded into its surface for affecting an emitted light pattern.

33. The device of claim 32 wherein the pattern comprises a Fresnel lens, a diffraction grating, a binary pattern, pyramids, or cones.

34. The device of claim 26 wherein the LED die is one of a plurality of LED dice affixed to the support structure.

35. The device of claim 26 further comprising a backlight for a liquid crystal display, the backlight incorporating the LED and first lens.

36. The device of claim 26 further comprising a rear projection television, the television incorporating the LED and first lens.

* * * * *