



US 20240253290A1

(19) **United States**

(12) **Patent Application Publication**
Stephens et al.

(10) **Pub. No.: US 2024/0253290 A1**

(43) **Pub. Date: Aug. 1, 2024**

(54) **WOOD-GRAINED POLYMER SUBSTRATE**

B29C 48/49

(2006.01)

(71) Applicant: **Tangent Technologies LLC**, Aurora, IL (US)

B29K 23/00

(2006.01)

B29L 31/10

(2006.01)

B32B 3/26

(2006.01)

(72) Inventors: **Andrew Stephens**, Aurora, IL (US);
Francisco Morales, Plano, IL (US);
Tadeusz Rybka, Streamwood, IL (US)

B32B 27/08

(2006.01)

B32B 27/20

(2006.01)

B32B 27/32

(2006.01)

(21) Appl. No.: **18/630,723**

(52) **U.S. Cl.**

(22) Filed: **Apr. 9, 2024**

CPC **B29C 48/695** (2019.02); **B29C 48/18** (2019.02); **B29C 48/49** (2019.02); **B32B 3/263** (2013.01); **B32B 27/08** (2013.01); **B32B 27/20** (2013.01); **B32B 27/32** (2013.01); **B29K 2023/065** (2013.01); **B29K 2995/002** (2013.01); **B29L 2031/10** (2013.01); **B32B 2250/24** (2013.01); **B32B 2307/4026** (2013.01); **B32B 2419/00** (2013.01)

Related U.S. Application Data

(63) Continuation of application No. 17/505,091, filed on Oct. 19, 2021, now abandoned, which is a continuation of application No. 16/678,400, filed on Nov. 8, 2019, now Pat. No. 11,173,643, which is a continuation-in-part of application No. 15/245,948, filed on Aug. 24, 2016, now Pat. No. 10,981,350.

(60) Provisional application No. 62/208,928, filed on Aug. 24, 2015.

(57)

ABSTRACT


A wood-grained polymer substrate includes a plurality of layers of different colors. The substrate is formed into elongated boards and used in the production of various end products similar to natural wood. Methods for producing the wood-grained polymer substrate are also provided.

Publication Classification

(51) **Int. Cl.**

B29C 48/695 (2006.01)

B29C 48/18 (2006.01)






FIG. 1




FIG. 2




FIG. 3






FIG. 4






FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 15




FIG. 16





FIG. 17











FIG. 19B











FIG. 25






FIG. 27

2700




FIG. 28A




FIG. 28B

WOOD-GRAINED POLYMER SUBSTRATE

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] The present application claims the benefit of priority under 35 U.S.C. § 120 as a continuation from U.S. patent application Ser. No. 17/505,091 entitled “Wood-Grained Polymer Substrate,” filed on Oct. 19, 2021, which claims the benefit of priority as a continuation from U.S. patent application Ser. No. 16/678,400 entitled “Wood-Grained Polymer Substrate,” filed on Nov. 8, 2019, issued on Nov. 16, 2021 as U.S. Pat. No. 11,173,643, which claims the benefit of priority as a continuation-in-part from U.S. patent application Ser. No. 15/245,948 entitled “Wood-Grained Polymer Substrate,” filed on Aug. 24, 2016, issued on Apr. 20, 2021 as U.S. Pat. No. 10,981,350, which claims the benefit of U.S. Provisional Patent Application No. 62/208,928, filed Aug. 24, 2015, the disclosures of which are hereby incorporated by reference in their entirety for all purposes.

FIELD OF THE DISCLOSURE

[0002] The present disclosure relates to polymer composites and more particularly to polymer composites that are used as a natural wood substitute or replacement.

BACKGROUND

[0003] The decking industry has seen numerous introductions of composite and alternative plastic lumber decking products over the past decade. Composite decking typically comprises 50% wood fiber or particles and 50% polyethylene plastic to act as a binder to hold the wood particles together. This entire matrix is extruded into linear deck boards (TREX brand is one example). Due to undesirable qualities of this product, many companies have added a coextruded polymer cap layer around the exterior of the board, which has little or no wood fiber to protect the wood fiber/plastic matrix in the core from exposure and deterioration due to environmental exposure.

[0004] In recent years, as composite products have evolved, manufacturers have introduced several colors to the exterior coextruded layer to produce a surface which has varied color tones to emulate natural wood. This wood grain appearance is only skin deep and cutting or planing of the wood composite removes this coextruded cap layer to expose the standard fiber-filled, homogenous core.

[0005] The standard plastic extrusion process is designed to evenly mix all ingredients to produce consistent quality of product. Introducing multiple colors at the beginning of the extrusion process results in a homogeneous mixture of a single color. The industry produced multiple color tones by utilizing color concentrates (streaker colors) that have carrier resins that melt at relatively high temperatures. By keeping the temperature zones on the extrusion process at or near the temperatures of the melting point of the streaker colors, the streaker color concentrates would soften but not melt immediately whereby the streaker color concentrates would release color randomly and produce a streak effect.

[0006] This effect would produce a short string of color on the surface of the board. However, the streakers only produced a line of color in a single direction, usually along the extrusion direction, and when cut would not create a wood-grain like appearance through a core of the board. For

example, in U.S. Pat. App. Pub. No. 2004/0038002, the streak effect shows color variation that starts and stops within a short distance due to the individual color pellet softening, streaking and then being consumed in a discrete area of the board. With the board cut, pockets of color appear on the end surface, but are discontinuous and do not form a wood-grained appearance.

[0007] For co-extruded products, streakers would cause a cap layer to have varied color tones on the surface, but the core of the product remains a single color as evident when the board is cut or planed. For example, in U.S. Pat. App. Pub. No. 2011/0177291, streaker pellets are swirled in an extruder to form a “two-dimensional” cap layer for co-extrusion with a foam core. The cap layer has streaks of color at the surface, but is thin and does not extend into the core of the finished product.

[0008] Attempts have also been made to produce polymer boards having a wood-grained appearance through a core of the board. For example, in Japanese Patent No. H07-214631, different colored plastics are extruded through concentric rings, and the molten flow becomes turbulent to swirl the colors together. However, the process produces inconsistencies in the finished product due to the turbulent flow of the extrusion, and cutting the board can expose portions having minimal or irregular color patterns, such as breaks or gaps in the lines, presenting similar problems to the streakers discussed above.

[0009] Another example is French Patent No. 2,738,768 which illustrates a process for simultaneously extruding plastics of different colors to coalesce them into a single product without mixing together. However, the process has similar deficiencies to that of Japanese Patent No. H07-214631 discussed above. The patterns produced in the processes of these references are not consistent throughout the board, and post processing steps, such as cutting, can produce visible surfaces with undesirable characteristics.

SUMMARY

[0010] The present disclosure may comprise one or more of the following features and combinations thereof.

[0011] In illustrative embodiments, a high density polyethylene wood-grained substrate includes a plurality of layers of different colors. The substrate is formed into elongated boards which each include a first set of polymer layers formed that include a first colorant. The substrate includes a second set of polymer layers that include a second colorant different than the first colorant. The first and second layers alternate within the substrate to form a wood-grained appearance throughout the entire substrate.

[0012] According to certain aspects of the present disclosure, a capped polymer substrate that simulates natural wood is provided. The substrate extends along a first direction and includes a first side and a second side spaced apart from the first side along a second direction that is different than the first direction. The first side and the second side define a width of the substrate and extend along the first direction. The substrate includes a first set of polymer layers extending along the first direction and containing a first colorant. A majority of the first set of polymer layers is substantially continuous along the first direction, the substrate includes a second set of polymer layers extending along the first direction and containing a second colorant different than the first colorant. A majority of the second set of polymer layers is substantially continuous along the first direction. A core

extends between the first and the second sides and along the first direction. The core includes a first wood-grained pattern formed of the first set of polymer layers and the second set of polymer layers. The first wood-grained pattern is exposed on outer surface of the core at a first end and a second end of the core, wherein individual layers of the first and the second set of polymer layers are interspersed within the core to form the first wood-grained pattern throughout the core. A plurality of individual layers of one of the first and second sets of polymer layers extend along a substantially uninterrupted curvilinear path in the second direction originating proximate the first side and terminating proximate the second side. A cross-section of the core exposes the first wood-grained pattern. A cap is fused onto cohere surfaces of the core, wherein the cap includes a second wood-grained pattern formed of a copolymer.

[0013] In another aspect of the present disclosure, a method of producing a capped polymer substrate that simulates natural wood is provided. The method includes co-extruding a first polymer and a second polymer to form a combined core flow extrusion. The method also includes feeding the combined core flow extrusion through a core flow divider that includes a first plurality of section inserts to form a layered core flow. Each section insert of the first plurality of section inserts is predeterminedly inter-fitted with respect to each other to vary a first wood-grained pattern into the layered core flow, wherein the first wood-grained pattern includes a plurality of core grains oriented in different directions such that individual core grains of the plurality of grains are varied in thickness. The method also includes co-extruding the second polymer and a third polymer to form a combined cap flow extrusion. The method also includes feeding the combined cap flow extrusion through a cap flow divider that includes a second plurality of section inserts to form a layered cap flow. Each section insert of the second plurality of section inserts predeterminedly inter-fitted with to each other to vary a second wood-grained pattern into the layered cap flow. The method also includes receiving the layered core flow at a die to form a core. The method also includes receiving the layered cap flow at the die. The method also includes fusing the layered cap flow to cohere surfaces of the core.

[0014] In yet another aspect of the present disclosure, a machine for producing a capped polymer substrate that simulates natural wood is provided. The machine includes a first extruder and a second extruder. A core flow adapter is in communication with the first extruder and the second extruder, wherein the core flow adapter receives a first polymer from the first extruder and a second polymer from the second extruder for co-extruding the first polymer and the second polymer to form a combined core flow extrusion. A core flow divider is in communication with the core flow adapter, wherein the core flow divider receives the combined core flow extrusion from the core flow adapter to form a layered core flow comprising a first wood-grained pattern. The machine also includes a third extruder. A cap flow adapter is in communication with the second extruder and the third extruder, wherein the cap flow adapter receives the second polymer from the second extruder and a third polymer from the third extruder for co-extruding the second polymer and the third polymer to form a combined cap flow extrusion. A cap flow divider is in communication with the cap flow adapter, wherein the cap flow divider receives the combined cap flow extrusion from the cap flow adapter to

form a layered cap flow comprising a second wood-grained pattern. A die is in communication with the core flow divider and the cap flow divider, wherein the die receives the layered core flow from the core flow divider and receives the layered cap flow from the cap flow divider for fusing the layered cap flow to the layered core flow.

[0015] These and other features of the present disclosure will become more apparent from the following description of the illustrative embodiments.

BRIEF DESCRIPTION OF THE DRAWINGS

[0016] FIG. 1 illustrates a sectional view through an extrusion machine used to manufacture wood-grained polymer substrates of the present disclosure;

[0017] FIG. 2 is an exploded perspective view of a flow adapter of the extrusion machine of FIG. 1 showing that the flow adapter includes a body plate and an co-extrusion insert;

[0018] FIG. 3 is a perspective view of the flow adapter of FIG. 2;

[0019] FIG. 4 is a front elevation view of the flow adapter of FIG. 2;

[0020] FIG. 5 is a side elevation view of a set of section inserts used in the extrusion machine to form layers of different color polymers as suggested in FIGS. 5A-5G;

[0021] FIGS. 5A-5G are sectional views taken at the beginning and end of each section insert in FIG. 5;

[0022] FIG. 6 is sectional view taken through one embodiment of a polymer substrate in accordance with the present disclosure showing a wood grain pattern of the polymer substrate;

[0023] FIG. 7 is a top plan view of the polymer substrate of FIG. 6 showing colorations on a surface of the substrate form the different color polymers;

[0024] FIG. 8 is a view similar to FIG. 6 showing embossing on an outer surface of the polymer substrate;

[0025] FIG. 9 is a view similar to FIG. 6 showing a wood grain pattern of the polymer substrate after a portion of the outer surface is removed;

[0026] FIG. 10 is sectional view taken through another embodiment of a polymer substrate in accordance with the present disclosure showing a wood grain pattern of the polymer substrate;

[0027] FIG. 11 is a top plan view of the polymer substrate of FIG. 10 showing a wood grain pattern of the polymer substrate after a portion of the outer surface is removed;

[0028] FIG. 12 is a perspective view of one embodiment of an end product formed using a polymer substrate of the present disclosure;

[0029] FIG. 13 is a perspective view of another embodiment of an end product formed using a polymer substrate of the present disclosure;

[0030] FIG. 14 is a sectional view through an alternative embodiment of an extrusion machine used to manufacture capped polymer substrates that simulate natural wood, according to certain aspects of the present disclosure.

[0031] FIG. 15 is a perspective view of an alternative embodiment of a flow adapter of the extrusion machine of FIG. 14, according to certain aspects of the present disclosure;

[0032] FIG. 16 is a cross-sectional view of the flow adapter of FIG. 15 taken along line 15A-15A, according to certain aspects of the present disclosure;

[0033] FIG. 17 is a cross-sectional view of the flow adapter of FIG. 15 taken long line 15B-15B, according to certain aspects of the present disclosure;

[0034] FIG. 18 is a perspective view of a cap assembly of the extrusion machine of FIG. 14, according to certain aspects of the present disclosure;

[0035] FIG. 19A is a cross-sectional view of the cap assembly of FIG. 18 taken along line 19-19 illustrating the flow adapter of FIG. 15, a flow divider, a mixer, and a flipper arranged downstream of the mixer, according to certain aspects of the present disclosure;

[0036] FIG. 19B is a cross-sectional view of an alternative cap assembly of FIG. 18 taken along line 19-19 illustrating the flow adapter of FIG. 15, a flow divider, a mixer, and a flipper arranged upstream of the mixer, according to certain aspects of the present disclosure;

[0037] FIG. 20 is a perspective view of a gear utilized with the flow divider of FIGS. 19A-B, according to certain aspects of the present disclosure;

[0038] FIG. 21 is a perspective view of the mixer of FIGS. 19A-B, according to certain aspects of the present disclosure;

[0039] FIG. 22 is a perspective view of the flipper of FIGS. 19A-B, according to certain aspects of the present disclosure;

[0040] FIG. 23 is a perspective cross-sectional view of a die of the extrusion machine of FIG. 14 illustrating a 1-up configuration according to certain aspects of the present disclosure;

[0041] FIG. 24 is another perspective cross-sectional view of the die of FIG. 23, according to certain aspects of the present disclosure;

[0042] FIG. 25 is a perspective cross-sectional view of an alternative embodiment of the die of FIG. 23 illustrating a 4-up configuration, according to certain aspects of the present disclosure;

[0043] FIG. 26 is another perspective cross-sectional view of the die of FIG. 25 illustrating the 4-up configuration, according to certain aspects of the present disclosure;

[0044] FIG. 27 illustrates an example process for producing a capped polymer substrate that simulates natural wood for manufacturing end products using the example extrusion machine of FIG. 14, according to certain aspects of the present disclosure; and

[0045] FIGS. 28A-28B are example illustrations of various samples of the capped polymer substrates that simulate natural wood associated with the example process of FIG. 27, according to certain aspects of the present disclosure.

DETAILED DESCRIPTION OF THE DRAWINGS

[0046] For the purposes of promoting an understanding of the principles of the disclosure, reference will now be made to a number of illustrative embodiments illustrated in the drawings and specific language will be used to describe the same.

[0047] An illustrative extrusion machine 100 in accordance with the present disclosure is shown in FIG. 1. Extrusion machine 100 is used to form wood-grained polymer substrates 10, 210, as shown in FIGS. 6-11, having varying patterns of simulated wood grain which extend through and along each substrate 10, 210. Substrates 10, 210 can be made from polymer based materials, such as recycled high density polyethylene (HDPE), having at least two different colorants added thereto to define the wood-grain

patterns. Polymer substrates 10, 210 can be free of natural wood or other organic fibers. Polymer substrates 10, 210 can include additives, such as UV inhibitors, foaming agents, and color concentrates, to produce polymer substrates having desired colors and material properties, such as durability and strength.

[0048] The wood-grained polymer substrates 10, 210 can be post-processed, such as by planing or embossing, and cut to form various sized boards used to make polymer-lumber end products, such as those shown in FIGS. 12 and 13. The boards can be shipped to customers that design and build a multitude of end products, such as furniture, and they can fabricate the end products using the wood-grained polymer boards of the present disclosure just as they typically would using natural wood lumber. Fabrication using the polymer boards could include drilling, routing, and cutting to build multi-component products such as outdoor furniture, including adirondack chairs and park benches for example.

[0049] Each polymer substrate 10, 210 includes a multi-tone, simulated natural wood-grain effect that runs throughout the entire substrate (cross section) as shown in FIGS. 6 and 10. The simulated wood grains 16, 216 also extend to an outer surface, for example top surface 12, 212, of each substrate 10, 210 so that when removal of material occurs, such as through planing or cutting, the multi-tone wood grain effect remains both on the surface 12, 212 as well as with an exposed core 14, 214 of the substrates as suggested in FIGS. 9 and 11. Alternatively, or in addition to planing, outer surface 12, 212 of substrates 10, 210 can be embossed, such as with a wood grain pattern, as suggested in FIG. 8.

[0050] In one embodiment, polymer substrate 10 of the present disclosure includes continuous linear lines of color wood grain patterns 16 particularly within the core 14 and exposed core surfaces 12 to emulate wood rings or graining, as shown in FIGS. 6-9. In the illustrative embodiment, polymer substrate 10 is made using extrusion machine 100, shown in FIG. 1, from a first polymer 120 and a second polymer 124. A first extruder 118 is adapted to extrude first polymer 120, which is blended with a primary (main) base color. The first polymer 120 forms the lighter portions of polymer substrate 10. First polymer 120 includes a polymer material, such as a high density polyethylene resin. In some embodiments, the first polymer 120 is mixed with other additives, such as foaming agent, UV stabilizers, color concentrates, and other fillers such as fiberglass, minerals, etc.

[0051] A second extruder 122 of extrusion machine 100 is adapted to extrude second polymer 124 as shown in FIG. 1. Second polymer 124 includes a polymer material, such as a high density polyethylene resin. In some embodiments, the second polymer 124 is mixed with other additives, such as foaming agent, UV stabilizers, color concentrates, and other fillers such as fiberglass, minerals, etc.

[0052] Second polymer 124 is blended with an accent color used to form wood grain patterns 16 of substrate 10 as suggested in FIG. 6. The accent color for second polymer 124 and base color for first polymer 120 are different from one another. The accent color is chosen to complement the base color, and each will remain distinctive in the final extrusion. In some embodiments, the base and accent colors simulate the colors in natural wood, whether fresh cut, dried, aged, or otherwise. In some embodiments, the grains 16, 216 of substrates 10, 210 simulate natural wood grain, and the

base and accent colors used are generally not characteristic of natural wood, such as purple, orange, black, and pink, just to name a few.

[0053] In some embodiments, first and second polymers 120, 124 partially intermix, along with the main and accent colors, to produce shade and combinations of color which are identified as polymer A/B blend(s) 123 as suggested in FIG. 1. For example, first polymer 120 could be white in color and second polymer 124 could be black in color. When blended according to the present disclosure, areas that intermix showing shades of gray are defined as polymer A/B blend 123. One or more additional accent color extruders can be used to add other accent colored resins into the flow stream through extrusion machine 100.

[0054] A flow adapter 125 is coupled to first extruder 118 by securing flow adapter 125 to an adapter plate 126 by use of fasteners, such as bolts, as suggested in FIG. 1. Flow adapter 125 is positioned to receive the output flows from extruders 118, 122 and configured to initiate the combined flow of first and second polymers 120, 124 through extrusion machine 100. The combined flow of first and second polymers 120, 124 is then directed to flow divider 140 for formation of the wood grain pattern.

[0055] Flow adapter 125 includes a body plate 129 and a co-extrusion insert 127 as shown in FIGS. 2-4. Body plate 129 includes a first face 128 and a second face 130, and is formed to include a slot 121 in first face 128. A series of first apertures 132 are formed through second face 130 and into slot 121. A series of pass-through apertures 131 extend through co-extrusion insert 127 in a similar pattern to first apertures 132. Slot 121 is configured to receive co-extrusion insert 127 to align first apertures 132 of body plate 129 with pass-through apertures 131 of co-extrusion insert 127. Aligned first apertures 132 and pass-through apertures 131 allow first polymer 120 to flow through flow adapter 125 from first face 128 to second face 130 as suggested in FIGS. 1-4.

[0056] Co-extrusion insert 127 is also formed to include an internal passageway 133 that is coupled to second extruder 122 at a first end 134 and is in fluid communication with injection ports 136 at a second end 138 as shown in FIGS. 2 and 4. A series of second apertures 135 are formed through second face 130 of body plate 129 into slot 121 and are positioned between first apertures 132 such that first and second apertures 132, 135 alternate with one another around a centerline of the extrusion machine 100 as suggested in FIG. 2.

[0057] Injection ports 136 align with second apertures 135 when co-extrusion insert 127 is received in slot 121 as suggested in FIGS. 2-4. Body plate 129 and co-extrusion insert 127 cooperate so that first and second polymers 120, 124 are extruded together through flow adapter 125. In the illustrative embodiment, first apertures 132 are larger than second apertures 135. This arrangement allows second polymer 124, which is the accent color, to exit the flow adapter 125 simultaneously with first polymer 120 in a defined geometric relationship and proportional flow rate. Flow adapter 125 permits the ability to design a variety of patterns and flow rates of first and second polymers 120, 124 to associate with different profile sizes and well as different linear graining and streaking aesthetics by changing the number and size of the openings 132, 135.

[0058] The combined flow of first and second polymer 120, 124 exit from flow adapter 125 and enter a reducer 139

of extrusion machine 100 as shown in FIG. 1. Reducer 139 increases pressure of the flow by reducing a cross section of the combined extrusions. Reducer 139 directs the flow of the first and second polymers 120, 124 into flow divider 140.

[0059] Flow divider 140 includes a channel 149 formed through flow divider 140 and a plurality of section inserts 141-147 positioned within the channel 149 as shown in FIG. 1. Section inserts 141-147 are coupled to one another to form a continuous dividing element 148 as suggested in FIG. 5. In the illustrative embodiment, each section insert 141-147 is a plate having opposing ends twisted relative to one another to form a helical profile. Section inserts 141-147 are coupled to one another such that the helical profile along the combined dividing element is offset and reversed with each connected section insert 141-147.

[0060] Section inserts 141-147 cut across and redirect the combined flow of first and second polymer 120, 124 as the flow passes through channel 149 of flow divider 140 as suggested in FIGS. 1 and 5-5G. Section inserts 141-147 can be of different designs and fit together in a variety of orientations to vary the wood grain patterns 16 of polymer substrate 10. For illustrative purposes, six section inserts 141-146 are shown in FIG. 5. Seven section inserts 141-147, as shown in FIG. 1, can be included in the flow divider 140, but it is contemplated that any number of section inserts can be used to vary the grain pattern formed in the polymer substrate 10. Generally, the number of section inserts can be used to control the number of layers in the substrate. More or less section inserts can also be used depending on the size of the substrate being produced.

[0061] In the illustrative embodiment, the design, orientation, and number of section inserts 141-147 determine the linear graining and layering aesthetics for a particular profile size and shape of polymer substrate 10. For example, as suggested in FIGS. 5 and 5G, a horizontal (longitudinal to the substrate) orientation of the final end of the dividing element 148 produces horizontal layers in the flow, which leads to horizontal grains in the final polymer substrate 10 as suggested in FIG. 6. Having the final end of the dividing element 148 oriented vertically produces vertical (transverse to the substrate) layers in the flow, which leads to vertical grains in the final polymer substrate 10 as suggested in FIG. 10.

[0062] With each successive section insert 141-147, the interlayering of first polymer 120 and second polymer 124 increases the amount of linear graining between the two polymers 120, 124 as well as promote the polymer A/B blending 123 which produces multiple color combinations and layers of the two colors as depicted in FIGS. 5A-5G. The portions of the flow contacting the channel 149 and inner dividing element 148 experience less movement than other portions of the flow due to the viscosity of the material. The continuous dividing and rotation of the flow causes layers of first and second polymer 120, 124 to form on one another within the flow rather than forming a homogeneous mixture.

[0063] The combined flow of layered polymers 120, 124 exiting section insert 147 enters an expander 152 as shown in FIG. 1. Expander 152 reduces pressure of the flow by allowing the flow to expand. Expander 152 directs the flow into the entry of a die 154 for forming the general profile of polymer substrate 10. The substrate 10 enters tooling with similar dimensions to the die exit to begin cooling and forming the final product.

[0064] As shown in FIG. 6, polymer substrate 10 can be cut through the core 14 to expose the wood grain pattern 16 created by extrusion machine 100. The wood grain 16 in the core 14 of polymer substrate 10 is oriented generally horizontal and the individual grains are closely spaced to one another. The grains 16 (formed from second polymer 124) are generally thinner than the remaining layers (formed from first polymer 120) of the substrate 10. Outer surfaces 12 of polymer substrate 10 have a matte finish and limited wood grain visibility after exiting the die 154 as suggested in FIG. 7. In some embodiments, surfaces 12 of polymer substrate 10 can be further enhanced by embossing techniques applied to the surfaces 12 as suggested in FIG. 8. Embossing can provide a texture similar to natural wood lumber and add to the wood grain effect in the final product. Alternatively or in addition to embossing, a thin layer can be removed from each outer surface 12, such as by planing, to expose the wood grain pattern 16 as suggested in FIG. 9. In the illustrative embodiment, a burling effect is created due to the horizontally oriented and closely spaced grains 16.

[0065] As noted above, variations in wood grain patterns can be created depending upon the arrangement of the flow divider. A polymer substrate 210 produced by extrusion machine 100 includes vertical graining 216 in a core 214 of polymer substrate 210 as shown in FIG. 10. The wood grain 16 in the core 14 of polymer substrate 10 is oriented generally vertical and the individual grains are widely spaced from one another. The grains 216 (formed from second polymer 124) are generally thinner than the remaining layers (formed from first polymer 120) of the substrate 10. Similar post processing steps to polymer substrate 10 can be performed on polymer substrate 210. For example, planing of outer surfaces 212 of polymer substrate 210 can expose the wood grain 216 as suggested in FIG. 11. In the illustrative embodiment, the exposed grains generally align with one another along a length of the substrate 210 due to the vertically oriented and widely spaced grains 216. In some embodiments, the grains 216 mimic the organic rings of a tree.

[0066] The illustrative process can be used to form polymer substrates form 10, 210 continuously as an extrudate. As noted above, polymer substrates 10, 210 can be cut to form polymer boards used in the construction of various end products. In the illustrative embodiment, boards are created by making subsequent cuts across the extrudate to define a length of the board, with the orientation of the ends of the board defining a length direction. Various cross-sectional profiles are possible, such as round, polygonal, or other unique shapes, such as those used for molding used around windows and doors for example. These profiles can be created using the die 154, or through post processing of the boards.

[0067] The wood-grain patterns 16, 216 in the resulting boards formed from polymer substrates 10, 210 generally extend along the length of the board. In some embodiments, a majority of the wood grains 16, created by the layers of the second polymer 124, extend along the length of the entire board. Likewise, the remaining portions of the board, created by the interspersed layers of the first polymer 120, also generally extend along the length of the board. In some embodiments, a majority of the layers of the first polymer 120 extend along the length of the entire board. This creates a substantially consistent pattern along the length of the

board such that cuts various points along a length of the board will expose a substantially similar grain pattern.

[0068] As noted above, the wood grains 16, 216 can be oriented along different directions. In some embodiments, a width direction of the substrate 10 is oriented such that wood grains 16 extend between lateral sides 11, 13 of substrate 10 as suggested in FIG. 6. The layers of first and second polymers 120, 124 are stacked from a bottom surface 18 of substrate 10 toward the top surface 12. In some embodiments, a width direction of the substrate 10 is oriented such that wood grains 216 extend between top surface 212 and a bottom surface 218 of substrate 210 as suggested in FIG. 10. The layers of first and second polymers 120, 124 are stacked from a lateral surface 211 toward a lateral surface 213 of substrate 210. Generally, the width direction is perpendicular to the length direction and rotationally oriented around the length direction.

[0069] The width direction (i.e., cross-direction of the grains 16, 216) can assume various orientations to change the orientation of the grains 16, 216 to simulate natural wood grains of different patterns. For example, the exposed grain patterns in natural wood assume different orientations depending on the portion of the timber the board is cut from. The orientation of the grains 16, 216 can be changed to simulate these different patterns. In the illustrative embodiments, the grains 16, 216 extend along curvilinear paths across the width of the substrates 10, 210. In some embodiments, a majority of the grains 16, 216 extend substantially uninterrupted across the board, i.e., with minimal or no gaps in the visible grain 16, 216.

[0070] In illustrative embodiments, the other portions of the substrates 10, 210 formed by the first polymer 120 are similar to the grains 16, 216. The layers formed by the first polymer 120 extend along a length of the boards made from the substrates 10, 210 and across a width of the boards. In some embodiments, the grains 16, 216 are thinner than the layers formed by the first polymer 120.

[0071] Example of illustrative end products formed using the wood-grained polymer boards of the present disclosure are shown in FIGS. 12 and 13. A chair armrest 390 formed using polymer substrate 10, which was embossed on the outer surfaces 12, is shown in FIG. 12. The exposed wood grain 16 is clearly visible after cutting out the shape of the armrest 390 while the embossing provides the feel of natural wood. Another example of a chair armrest 490 formed using polymer substrate 210, which was embossed on the outer surfaces 212, is shown in FIG. 13. The exposed wood grain 216 is clearly visible after cutting out the shape of the armrest 490 while the embossing provides the feel of natural wood. Other structural and non-structural uses, such as decking and siding for example, are contemplated by this disclosure.

[0072] In illustrative embodiments, a wood-grained polymer substrate is provided having alternating layers of differently colored polymer material to produce a simulated natural wood grain appearance. The wood grain appearance runs through a core of the substrate such that the simulated wood grains are exposed when the substrate is cut. The wood-grained polymer substrate can be cut to length to form a wood-grained polymer board. The wood-grain polymer board is useful in the production of various end products, such as furniture and decking for example. The grain patterns are adjustable to simulate various cuts of natural wood timber. The grain patterns are substantially consistent along

a length of the board such that cuts across the board at various points along the length will expose similar patterns.

[0073] With reference to FIG. 14, an alternative embodiment extrusion machine 1000 is exemplarily illustrated in accordance with certain aspects of the present disclosure. The extrusion machine 1000 is used to form a capped polymer substrate 2810, as illustrated in FIG. 28A. In certain aspects, the capped polymer substrate 2810 simulates natural wood. As will be discussed in more detail below, the capped polymer substrate 2810 includes a core 2812 and a cap 2814 fused substantially around the core 2812. The core 2812 of the capped polymer substrate 2810 includes varying wood-grained core patterns 2816 of simulated wood grain, which extend through and along the core 2812 of the capped polymer substrate 2810. The core 2812 of the capped polymer substrate 2810 can be made from polymer based materials, such as, but not limited to, recycled high density polyethylene (HDPE) that include at least two different colorants added thereto to define the wood-grained core patterns 2816. In some aspects, the core 2812 of the capped polymer substrate 2810 can include additives, such as, but not limited to, ultraviolet (UV) inhibitors, foaming agents, color concentrates, and other well-known additives in the industry, to produce substrates having desired colors and material properties such as durability and strength.

[0074] The cap 2814 of the capped polymer substrate 2810 includes varying wood-grained cap patterns 2818 of simulated wood grain, as illustrated in FIG. 28A. As discussed previously, the cap 2814 is fused substantially around the core 2812. For example, the cap 2814 can be fused around the core 2812 in a compacted laminate manner. In certain aspects, the cap 2814 is condensed so that it does not contain any bubbles, such as gas bubbles, therethrough. In certain aspects, the cap 2814 is formed of copolymer material to provide a structural benefit to the capped polymer substrate 2810. In addition to the structural benefit, the cap 2814 is also designed so that it does not crack. In certain aspects, the cap 2814 is formed of virgin copolymer material.

[0075] The capped polymer substrate 2810 can be post-processed by various techniques, such as, but not limited to, planing, embossing, cutting, and other well-known techniques in the industry, to form various sized boards used to make polymer-lumber end products. For example, the boards can be shipped to customers who design and build a multitude of end products, such as furniture and the like. The customers can fabricate the end products using the capped polymer substrate 2810 (i.e., the board) just as they would using natural wood lumber. Fabrication using the capped polymer substrate 2810 could include, but is not limited to, drilling, routing, and cutting to build multi-component end products such as outdoor furniture including, but not limited to, Adirondack chairs, park benches, and the like, for example.

[0076] The core 2812 of the capped polymer substrate 2810 includes a multi-tone, simulated natural wood-grained effect that runs throughout the core 2812, as shown FIG. 28A. The core 2812 includes outer core surfaces 2820, which are exposed from the cap 2814 (i.e., the cap 2814 does not cover the outer core surfaces 2820 of the core 2812). As such, the wood-grained core patterns 2816 that extend through the core 2812 are visible at the outer core surfaces 2820. For example, when the capped polymer substrate 2810 is cut along a line parallel to the outer core surfaces 2820, the wood-grained core patterns 2816 are exposed and visible

at that cut. The core 2812 also includes cohere surfaces 2822 to which the cap 2814 is fused. As such, the cohere surfaces 2822 of the core 2812 are not exposed, but are instead covered by the cap 2814. In such a manner, as described above, the capped polymer substrate 2810 includes the wood-grained cap patterns 2818 that are exteriorly visible, as well as, the wood-grained core patterns 2816 that are exteriorly visible at the outer core surfaces 2820, to emulate wood rings or graining, as illustrated in FIG. 28A.

[0077] Referring back to FIG. 14, the capped polymer substrate 2810 is fabricated using the extrusion machine 1000, as will be described in more detail below. The extrusion machine 1000 includes a first extruder 1010, a second extruder 1012, a third extruder 1014, a core assembly 1016, a cap assembly 1018, and a die 1020. In particular, the core 2812 is fabricated using the first extruder 1010, the second extruder 1012, and the core assembly 1016. The core 2812 is formed of a first polymer 1022 and a second polymer 1024. The first extruder 1010 extrudes the first polymer 1022, which can be blended with a primary or main base color for the wood-grained core patterns 2816. In certain aspects, a weight scale (not shown) and a blender (not shown) can be mounted to a feed throat of the first extruder 1010 to feed the primary or main base color (i.e., pellets) into the first extruder 1010. In certain aspects, the first polymer 1022 includes a polymer material such as, for example, a high density polyethylene resin. In certain aspects, the first polymer 1022 can be any one of, but not limited to, a homopolymer, a copolymer, a virgin homopolymer, a virgin copolymer, a recycled homopolymer, and a recycled copolymer. In certain aspects, the first polymer 1022 is mixed with other additives such as, but not limited to, foaming agents, ultraviolet (UV) stabilizers, color concentrates, fiberglass, minerals, and other fillers that are well-known in the industry.

[0078] The second extruder 1012 extrudes the second polymer 1024, which can be blended with a secondary or accent color to provide accent coloring with respect to the first polymer 1022 for the wood-grained core patterns 2816. For example, the accent color of the second polymer 1024 can be selected to complement the main color of the first polymer 1022 so that each color will remain distinctive in the core 2812. In certain aspects, a weight scale (not shown) and a blender (not shown) can be mounted to a feed throat of the second extruder 1012 to feed the secondary or accent color (i.e., pellets) into the second extruder 1012. In certain aspects, the accent color of the second polymer 1024 is different from the main color of the first polymer 1022. In certain aspects, the second polymer 1024 includes a polymer material such as, for example, a high density polyethylene resin. In certain aspects, the second polymer 1024 can be any one of, but not limited to, a homopolymer, a copolymer, a virgin homopolymer, a virgin copolymer, a recycled homopolymer, and a recycled copolymer. In certain aspects, the second polymer 1024 is a material that is the same as the first polymer 1022. In certain other aspects, the second polymer 1024 is a different material than the first polymer 1022. In certain aspects, the main color of the first polymer 1022 and the accent color of the second polymer 1024 simulate the colors and patterns in natural wood, whether fresh cut, dried, aged, or otherwise. In other aspects, while the wood-grained core patterns 2816 emulate natural wood grain, the main color of the first polymer 1022 and the accent color of the second polymer 1024 can be selected from

colors that are non-characteristic of natural wood such as, for example, purple, orange, black, and pink, to name a few.

[0079] In certain aspects, the first polymer 1022 and the second polymer 1024 partially intermix, along with the main and accent colors, to produce shade and combinations of color. For example, the first polymer 1022 could be white in color and the second polymer 1024 could be black in color. When blended according to the present disclosure, areas that intermix could show shades of gray in a polymer blend of the first polymer 1022 and the second polymer 1024. In certain aspects, one or more additional accent color extruders can be used to add other accent colored resin into the flow stream through the core assembly 1016 of the extrusion machine 1000.

[0080] The first extruder 1010 and the second extruder 1012 are coupled to the core assembly 1016 to transfer the first polymer 1022 and the second polymer 1024, respectively, thereto. The core assembly 1016 includes a core flow adapter 1026, a core flow reducer 1027, a core flow divider 1028, and a core flow expander 1030. The core flow adapter 1026 is upstream of the core flow divider 1028, which is upstream of the core flow expander 1030. While the core flow adapter 1026 will be described in more detail below, it should be understood that, in certain aspects, the flow adapter 125 of FIG. 1 could be interchanged with the core flow adapter 1026.

[0081] As illustrated in FIGS. 15-17, the core flow adapter 1026 includes a first port 1032 and a second port 1034. The first port 1032 is coupled to the first extruder 1010 for receiving the first polymer 1022 from the first extruder 1010. The second port 1034 is coupled to the second extruder 1012 for receiving the second polymer 1024 from the second extruder 1012. The core flow adapter 1026 is configured to co-extrude or combine the first polymer 1022 and the second polymer 1024 into a combined core flow 1036 (see FIG. 14) that is directed to the core flow divider 1028. The core flow adapter 1026 includes a core co-extruder 1038 in communication with the first port 1032 and the second port 1034. The core co-extruder 1038 is centrally disposed through the core flow adapter 1026. The core co-extruder 1038 includes a plurality of apertures 1040 in communication with the first port 1032 to extrude the first polymer 1022 through the core flow adapter 1026 to the core flow divider 1028. In certain aspects, the plurality of apertures 1040 includes a first series of apertures 1042, a second series of apertures 1044, and a third series of apertures 1044. In such aspects, first apertures 1048 of the first series of apertures 1042 are disposed around a first circumference 1050, second apertures 1052 of the second series of apertures 1044 are disposed around a second circumference 1054, and third apertures 1056 of the third series of apertures 1046 are disposed around a third circumference 1058. In certain aspects, the first circumference 1050 is disposed radially outwardly from the second circumference 1054, which is disposed radially outwardly from the third circumference 1058.

[0082] Moreover, the core co-extruder 1038 includes a plurality of slots 1060 in communication with the second port 1034, via a duct 1062, to extrude the second polymer 1024 through the core flow adapter 1026 to the core flow divider 1028. In certain aspects, each slot of the plurality of slots 1060 are arcuate although other shapes are within the scope of the present disclosure. In certain aspects, the plurality of slots 1060 includes a first slot 1064 and a second slot 1066. The duct 1062 directs the second polymer 1024

received at the second port 1034 and delivers the second polymer 1024 to the first slot 1064 and the second slot 1066. In certain aspects, the first slot 1064 is disposed radially inward of the first series of apertures 1042 such that it is arranged between the first series of apertures 1042 and the second series of apertures 1044, and the second slot 1066 is disposed radially inward of the second series of apertures 1044 such that it is arranged between the second series of apertures 1044 and the third series of apertures 1046. Such arrangement of the plurality of apertures 1040 with respect to the plurality of slots 1060 allows the second polymer 1024, which is the accent color, to exit the core flow adapter 1026 simultaneously with the first polymer 1022, which is the main color, in a defined geometric relationship and at a proportional flow rate. Although certain designs and arrangements of the plurality of apertures 1040 and the plurality of slots 1060 of the core flow adapter 1026 are described above, it should be understood that other designs and arrangements are within the scope of the present disclosure. The plurality of apertures 1040 and the plurality of slots 1060 can be arranged in various numbers and/or sizes to vary the geometric patterns and flow rates of the first polymer 1022 and the second polymer 1024 exiting the core flow adapter 1026 to produce different linear graining and streaking aesthetics of the combined core flow 1036 entering the core flow divider 1028. While the flow adapter 125 of the extrusion machine 100 includes the co-extrusion insert 127 having the apertures 131 and the injection ports 136 that require alignment with the first apertures 132 and the second apertures 136, respectively, the core flow adapter 1026 includes the plurality of apertures 1040, which may be created through the core flow adapter 1026, such as, for example, by drilling, and does not require alignment with other apertures on another component. In view of the geometry of the plurality of apertures 1040, the core flow adapter 1026 may provide a more consistent combined core flow 1036 than the geometry of the flow adapter 125.

[0083] The combined core flow 1036 exits the core flow adapter 1026 at the core co-extruder 1038 and enters the core flow reducer 1027, such as the reducer 139 of the extrusion machine 100 of FIG. 1, which is coupled to the core flow adapter 1026. The core flow reducer 1027 receives and increases pressure of the combined core flow 1036 by reducing a cross section thereof. The core flow reducer 1027 is coupled to the core flow divider 1028 and directs the combined core flow 1036 thereto. In certain aspects, the combined core flow 1036 exits the core flow adapter 1026 at the core co-extruder 1038 and directly enters the core flow divider 1028.

[0084] Referring to FIG. 14, the core flow divider 1028 is similar to the flow divider 140 of the extrusion machine 100 of FIG. 1. The core flow divider 1028 includes a channel 1068, a tube 1070, a plurality of section inserts 1072, and a gear 1074. The channel 1068 is disposed through the core flow divider 1028 and couples the core flow reducer 1027 to the core flow expander 1030. The tube 1070 is received by the channel 1068 and is selectively movable within the channel 1068 via the gear 1074 (see FIG. 20), which is mechanically engaged with the tube 1070. The plurality of section inserts 1072 is coupled to the tube 1070. The gear 1074 is partially exposed through the core flow divider 1028 to facilitate in selectively moving the position of the tube

1070 within the channel **1068** to orientate the plurality of section inserts **1072** to effect the wood-grained core patterns **2816** of the core **2812**.

[0085] As the plurality of section inserts **1072** is similar to the plurality of section inserts **141-147** described above in reference to the extrusion machine **100** of FIG. 1, a brief description is provided below. The section inserts of the plurality of section inserts **1072** are consecutively coupled such that adjacent section inserts are coupled to each other to form a continuous dividing element. Each section insert of the plurality of section inserts **1072** is a plate having opposing ends twisted relative to one another to form a helical profile. The section inserts of the plurality of section inserts **1072** are coupled in such a manner that the helical profile along the continuous dividing element is offset and reversed with each connected section insert.

[0086] The plurality of section inserts **1072** receive the combined core flow **1036** from the core flow reducer **1027** and redirect the combined core flow **1036** through the core flow divider **1028** to produce a layered core flow **1076** upon exit of the core flow divider **1026**. The plurality of section inserts **1072** can be of different designs and fit together in a variety of orientations to vary the wood-grained core patterns **2816** of the core **2812**. Any number of section inserts can be used to vary the wood-grained core patterns **2816**. Generally, the number of section inserts can be used to selectively control the number of layers in the core **2812**. More or less section inserts can be used depending on the desired size of the capped polymer substrate **2810**.

[0087] As noted above, the design, orientation, and number of section inserts of the plurality of section inserts **1072** determine the linear graining and layering aesthetics of the wood-grained core patterns **2816** for a particular profile size and shape of the core **2812** of the capped polymer substrate **2810**. For example, orientating the final section insert of the plurality of section inserts **1072** (i.e., the section insert adjacent to the core flow expander **1030**) in a horizontal orientation produces horizontal layers in the layered core flow **1076** exiting the core flow divider **1026**. Orientating the final section insert of the plurality of section inserts **1072** in a vertical orientation produces vertical layers in the layered core flow **1076** exiting the core flow divider **1026**. By controlling the gear **1074** to selectively position the plurality of section inserts **1072**, the final section insert of the plurality of section inserts **1072** can be adjusted to a desired orientated in the horizontal orientation, the vertical orientation, and therebetween.

[0088] By increasing the number of section inserts of the plurality of section inserts **1072**, the interlayering of the first polymer **1022** and the second polymer **1024** increases. This, in turn, increases the amount of linear graining, in the core **2812**, between the first and second polymers **1022**, **1024** as well as promote the blending, which produces multiple color combinations and layers of the main and accent colors. As the combined core flow **1036** flows through the core flow divider **1028**, the portions of the combined core flow **1036** that contacts the tube **1070** and the plurality of section inserts **1072** experience less movement than other portions of the combined core flow **1036** due to the viscosity of the material. The continuous dividing and rotation of the combined core flow **1036** causes layers of the first and the second polymers **1022**, **1024** to form on one another within the combined core flow **1036** rather than forming a homogeneous mixture.

[0089] The layered core flow **1076** exits the core flow divider **1028** and enters the core flow expander **1030**, which is coupled to the core flow divider **1028**. The core flow expander **1030** reduces pressure on the layered core flow **1076** by allowing the layered core flow **1076** to expand. The core flow expander **1030** is coupled to a first inlet **1078** (see FIG. 23) of the die **1020** and directs the layered core flow **1076** to the first inlet **1078** of the die **1020** for forming the core **2812** and fusing the cap **2814** to the core **2812**.

[0090] As discussed above, the extrusion machine **1000** includes a cap assembly **1018**, which includes a cap flow adapter **1080**, a cap flow divider **1082**, a cap mixer **1084**, a cap flipper **1086**, and a cap flow reducer **1088**. With reference to FIGS. 14 and 18-19, the cap assembly **1018** is coupled to the second extruder **1012** and a third extruder **1014**. More particularly, the second extruder **1012** is coupled to, and in communication with, the cap flow adapter **1080** for transferring the second polymer **1024** to the cap assembly **1018** while the third extruder **1080** is also coupled to, and in communication with, the cap flow adapter **1080** for transferring a third polymer **1090** (see FIG. 14) to the cap assembly **1018**. The cap **2814** is formed of the second polymer **1024**, which acts as the accent color, and the third polymer **1090**, which acts as the main color. In certain aspects, the third polymer **1090** includes a polymer material that is different from the second polymer **1024** such that the cap **2814** is formed of a co-polymer.

[0091] The structure of the cap flow adapter **1080** is generally similar to the structure of the core flow adapter **1026**. As such, a first port **1092** of the cap flow adapter **1080** is coupled to the third extruder **1014** for receiving the third polymer **1090** from the third extruder **1014**. A second port **1094** of the cap flow adapter **1080** is coupled to the second extruder **1012** for receiving the second polymer **1024** from the second extruder **1012**. The cap flow adapter **1080** is configured to co-extrude or combine the second polymer **1024** and the third polymer **1090** into a combined cap flow **1096** that is directed to the cap flow divider **1082**. The cap flow adapter **1080** includes a co-extruder **1098** in communication with the first port **1092** and the second port **1094**. The cap co-extruder **1098** is centrally disposed through the cap flow adapter **1080**. In certain aspects, an expander **2000** is disposed between the first port **1092** and the cap co-extruder **1098** to facilitate in the transfer of the third polymer **1090** from the first port **1092** to the cap co-extruder **1098**.

[0092] The cap co-extruder **1098** includes a plurality of apertures **2002** in communication with the first port **1092** to extrude the third polymer **1090** through the cap flow adapter **1080** to the cap flow divider **1082**. In certain aspects, the plurality of apertures **2002** includes a first series of apertures **2004**, a second series of apertures **2006**, and a third series of apertures **2008**. In such aspects, first apertures **2010** of the first series of apertures **2004** are disposed around a first circumference **2012**, second apertures **2014** of the second series of apertures **2006** are disposed around a second circumference **2016**, and third apertures **2018** of the third series of apertures **2008** are disposed around a third circumference **2020**. In certain aspects, the first circumference **2012** is disposed radially outwardly from the second circumference **2016**, which is disposed radially outwardly from the third circumference **2020**.

[0093] The cap co-extruder **1098** includes a plurality of slots **2022** in communication with the second port **1094**, via a duct **2024**, to extrude the second polymer **1024** through the

cap flow adapter 1080. In certain aspects, each slot of the plurality of slots 2022 are arcuate although other shapes are within the scope of the present disclosure. In certain aspects, the plurality of slots 2022 includes a first slot 2026 and a second slot 2028. The duct 2024 directs the second polymer 1024 received at the second port 1094 and delivers the second polymer 1024 to the first slot 2024 and the second slot 2026. In certain aspects, the first slot 2026 is disposed radially inward of the first series of apertures 2004 such that it is arranged between the first series of apertures 2004 and the second series of apertures 2006, and the second slot 2028 is disposed radially inward of the second series of apertures 2006 such that it is arranged between the second series of apertures 2006 and the third series of apertures 2008. Such arrangement of the plurality of apertures 2002 with respect to the plurality of slots 2022 allows the second polymer 1024, which is the accent color, to exit the cap flow adapter 1080 simultaneously with the third polymer 1090, which is the main color, in a defined geometric relationship and at a proportional flow rate. Although certain designs and arrangements of the plurality of apertures 2002 are describe above, it should be understood that other designs and arrangements are within the scope of the present disclosure. The plurality of apertures 2002 and the plurality of slots 2022 can be arranged in various numbers and/or sizes to vary the geometric patterns and flow rates of the second polymer 1024 and the third polymer 1090 exiting the cap flow adapter 1080 to produce different linear graining and streaking aesthetics of the combined cap flow 1096 entering the cap flow divider 1082.

[0094] The combined cap flow 1096 exits the cap flow adapter 1080 at the cap co-extruder 1098 and enters the cap flow divider 1082. The cap flow divider 1082 is similar to the core flow divider 1028 of the core assembly 1016 described above with reference to FIG. 14. The cap flow divider 1082 includes a channel 2030, a tube 2032, a plurality of section inserts 2034, and a gear 2036. The channel 2030 is disposed through the cap flow divider 1082 and is arranged downstream of the cap co-extruder 1098 and upstream of the cap mixer 1084. In certain aspects, the combined cap flow 1096 exits the cap flow adapter 1080 at the cap co-extruder 1098 and enters a reducer 1081 before entering the cap flow divider 1082.

[0095] Referring to FIG. 19A, the tube 2032 is received by the channel 2030 and is selectively movable within the channel 2030 via the gear 2036 (see FIG. 20), which is mechanically engaged with the tube 2032. The plurality of section inserts 2034 are coupled to the tube 2032. The gear 2036 is partially exposed through the cap flow divider 1082 to facilitate in selectively moving the position of the tube 2032 within the channel 2030 to orientate the plurality of section inserts 2034 to effect the wood-grained cap patterns 2818 of the cap 2814.

[0096] As the plurality of section inserts 2034 is similar to the plurality of section inserts 1072 described above in reference to the core assembly 1016, a brief description is provided below. The section inserts of the plurality of section inserts 2034 are consecutively coupled such that adjacent section inserts are coupled to each other to form a continuous dividing element. Each section insert of the plurality of section inserts 2034 is a plate having opposing ends twisted relative to one another to form a helical profile. The section inserts of the plurality of section inserts 2034 are

coupled in such a manner that the helical profile along the continuous dividing element is offset and reversed with each connected section insert.

[0097] The plurality of section inserts 2034 receive the combined cap flow 1096 from the cap co-extruder 1098 of the cap flow adapter 1080 and redirect the combined cap flow 1096 to produce a layered cap flow 2038 upon exit of the cap flow divider 1082. The plurality of section inserts 2034 can be of different designs and can fit together in a variety of orientations to vary the wood-grained cap patterns 2818. While six (6) section inserts of the plurality of section inserts 2034 are illustrated in FIG. 19A, any number of section inserts can be used to vary the wood-grained cap patterns 2818. Generally, the number of section inserts can be used to selectively control the number of layers in the cap 2814. More or less section inserts can be used depending on the desired size of the capped polymer substrate 2810.

[0098] As noted above, the design, orientation, and number of section inserts of the plurality of section inserts 2034 determine the linear graining and layering aesthetics of the wood-grained cap patterns 2818 for a particular profile size and shape of the cap 2814 of the capped polymer substrate 2810. For example, orientating the final section insert of the plurality of section inserts 2034 (i.e., the section insert adjacent to the cap mixer 1084) in a vertical orientation produces wood-grained cap patterns 2818 that extend longitudinally in the layered cap flow 2038 exiting the cap flow divider 1082. On the other hand, orientating the final section insert of the plurality of section inserts 2034 in a horizontal orientation produces wood-grained cap patterns 2818 that extend traverse to the longitudinal direction of in the layered cap flow 2038 exiting the cap flow divider 1082. By controlling the gear 2036 to selectively position the plurality of section inserts 2034, the final section insert of the plurality of section inserts 2034 can be adjusted to a desired orientation in the horizontal orientation, the vertical orientation, and therebetween. In certain aspects, the orientation of the final section insert of the plurality of section inserts 2034 of the cap assembly 1018 is different to the orientation the final section insert of the plurality of section inserts 1074 of the core assembly 1016. For example, the final section insert of the plurality of section inserts 2034 of the cap assembly 1018 can be in the vertical orientation while the final section insert of the plurality of section inserts 1074 of the core assembly 1016 can be in the horizontal orientation.

[0099] By increasing the number of section inserts of the plurality of section inserts 2034, the interlayering of the second polymer 1024 and the third polymer 1090 increases. This, in turn, increases the amount of linear graining, in the cap 2814, between the second and third polymers 1024, 1090 as well as promote the blending, which produces multiple color combinations and layers of the main and accent colors. As the combined cap flow 1096 flows through the cap flow divider 1082, the portions of the combined cap flow 1096 that contacts the tube 2032 and the plurality of section inserts 2034 experience less movement than other portions of the combined cap flow 1096 due to the viscosity of the material. The continuous dividing and rotation of the combined cap flow 1096 causes layers of the second and the third polymers 1024, 1090 to form on one another within the combined cap flow 1096 rather than forming a homogeneous mixture.

[0100] With further reference to FIG. 19A, the cap flow divider 1082 includes a housing 2040 located downstream of

the plurality of section inserts **2034**. The housing **2040** houses the cap mixer **1084** and the cap flipper **1086**. The cap mixer **1084** is downstream of the cap flow divider **1082** and upstream of the cap flipper **1086**. The cap mixer **1084** is in communication with the cap flow divider **1086** and the cap flipper **1086**. The cap mixer **1084** is configured to receive the layered cap flow **2038** and blend the layered cap flow **2038** so that the wood-grained cap patterns **2818** are more consistent (i.e., spread out the layering within the layered cap flow **2038**). Furthermore, the cap mixer **1084** is configured to spread out the layers within the layered cap flow **2038** and make the layers smoother. In effect, the cap mixer **1084** can blur layer lines within the layered cap flow **2038** to make the layer lines less distinct. The blending of the layers together within the layered cap flow **2038**, via the cap mixer **1084**, can also remove possible imperfections from the layered cap flow **2038**.

[0101] Referring to FIG. 21, the cap mixer **1084** is substantially cylindrical in shape and includes a cylindrical wall **2042** and an opening **2044** therethrough. A grate **2046** is disposed with the opening **2044** and coupled to the cylindrical wall **2042**. The grate **2046** includes a first V-shaped member **2048** and a second V-shaped member **2050**. The first V-shaped member **2048** includes a first plurality of slats **2052** on one leg of the “V” such that a first slit **2054** is disposed between each slat of the first plurality of slats **2052**. The first V-shaped member **2048** also includes a second plurality of slats **2056** on the other leg of the “V” such that a second slit **2058** is disposed between each slat of the second plurality of slats **2056**. Similarly, the second V-shaped member **2050** includes a third plurality of slats **2060** on one leg of the “V” such that a third slit **2062** is disposed between each slat of the third plurality of slats **2064**. The second V-shaped member **2050** also includes a fourth plurality of slats **2064** on the other leg of “V” such that a fourth slit **2066** is disposed between each slat of the fourth plurality of slats **2064**. The first V-shaped member **2048** and the second V-shaped member **2050** are arranged within the opening **2044** such that each slat of the second plurality of slats **2056** of the first V-shaped member **2048** is interposed with a corresponding fourth slit **2066** of the second V-shaped member **2050**.

[0102] The layered cap flow **2038** passes through the grate **2046** of the cap mixer **1084** and is then received by the cap flipper **1086**. With reference to FIG. 22, the cap flipper **1086** is configured to receive the layered cap flow **2038** from the cap mixer **1084** and to create texture to the layered cap flow **2038** for the wood-grained cap patterns **2818** on the exterior surfaces **2824** of the cap **2814**. The cap flipper **1086** includes a cylindrical body **2068** disposed between a disperser receiver **2070** and an exit **2072**. The disperser receiver **2070** faces the cap mixer **1084** and includes a centrally located first stop **2074**. A first plurality of arteries **2076** extend radially outward from the first stop **2074** such that each artery of the first plurality of arteries **2076** is spaced evenly away from each other around a circumference of the first stop **2074**. Each artery of the plurality of arteries **2076** extends axially along the cylindrical body **2068** from the disperser receiver **2070** and terminates before the exit **2072** at a first blocker **2078**. A plurality of ribs **2080** is disposed around the cylindrical body **2068** such that each rib of the plurality of ribs **2080** extends between the first blocker **2078** and a second blocker **2082**. Each rib of the plurality of ribs **2080** includes a plurality of ridges **2084** that extend radially

outward therefrom. Moreover, a second plurality of arteries **2086** is disposed around the cylindrical body **2068** such that each artery of the second plurality of arteries **2086** extends axially along the cylindrical body **2068** from the second blocker **2082** and terminates at the exit **2072**.

[0103] During production, the disperser receiver **2070** of the cap flipper **1086** receives the layered cap flow **2038** and disperses the layered cap flow **2038** through each artery of the first plurality of arteries **2076**. The layered cap flow **2038** then travels out through the first plurality of arteries **2076** and over the plurality of ridges **2084** of the plurality of ribs **2080** to create texture in the layered cap flow **2038**, which then flows into the second plurality of arteries **2086** and out through the exit **2072** into the cap flow reducer **1088**. For example, the cap flipper **1086** receives the layered cap flow **2038** and flips the layered cap flow **2038** inside-out as it flows through the first and the second plurality of arteries **2076**, **2086** and out the exit **2072**.

[0104] With reference to FIGS. 19A and 23-24, the cap flow reducer **1088** couples the housing **2040** of the cap flow divider **1082** to the die **1020**. The cap flow reducer **1088** is in communication with the exit **2072** of the cap flipper **1086** and a first passage **2088** of the die **1020**. The first passage **2088** splits, internally in the die **1020**, into a first vein **2090** and second vein **2092**. The first vein **2090** delivers a portion of the layered cap flow **2038** to a top cap reservoir **2094** while the second vein **2092** delivers a portion of the layered cap flow **2038** to a bottom cap reservoir **2096**.

[0105] The die **1020** is also coupled to the core flow divider **1028**. In certain aspects, the core flow expander **1030** couples the core flow divider **1028** to the die **1020**. The die **1020** includes a second passage **2098** in communication with the core flow divider **1028** (via the core flow expander **1030** in some aspects) to receive the layered core flow **1076**. The second passage **2098** delivers the layered core flow **1076** to a core reservoir **2100** for forming the desired shape of the core **2812**. For example, the layered core flow **1076** enters the core reservoir **2100** and is dispersed within the core reservoir **2100** to form the core **2812**. The core **2812** is further advanced to a fuser well **2102** that is in communication with the top cap reservoir **2094** and the bottom cap reservoir **2096** for fusing the layered cap flow **2038** onto the cohere surfaces **2822** of the core **2812** to form the capped polymer substrate **2810**. The fuser well **2102** also includes side wells **2104** such that the layered cap flow **2038** flows from the top cap reservoir **2094** into the side wells **2104** for fusing the layered cap flow **2038** onto cohere sides **2826** of the cohere surfaces **2822** of the core **2812**. The capped polymer substrate **2810** then exits an outlet **2106** of the die **1020** through an exit reducer **2107** and into a cooling bath **2108** (see FIG. 14). The exit reducer **2107** increases pressure to help the cap **2814** adhere to the cohere surfaces **2822** of the core **2822**. Additionally, the exit reducer **2107** prevents voids between the cap **2814** and the core **2822**. The cooling bath **2108** can be selected to be any desired temperature. For example, the temperature of the cooling bath **2108** can be 72 degrees Fahrenheit.

[0106] Although the die **1020** is configured to produce a single capped polymer substrate **2810**, it should be understood that the die **1020** can be configured to produce multiple numbers of the capped polymer substrate at the same time. For example, with reference to FIGS. 25 and 26, a 4-up die **2110** is illustrated. Similar to the die **1020**, the 4-up die **2110** includes a first passage **2112** in communica-

tion with the cap flow reducer **1088** to receive the layered cap flow **2038** from the exit **2072** of the cap flipper **1086**. The first passage **2112** splits, internally in the 4-up die **2110**, into a first vein **2114** and a second vein **2116**. Unlike the die **1020**, however, the first vein **2114** of the 4-up die **2110** then splits into a third vein **2118** and a fourth vein **2120**. The third vein **2118** splits into a fifth vein **2122** and a sixth vein **2124** while the fourth vein **2120** splits into a seventh vein **2126** and an eighth vein **2128**. The fifth vein **2122** delivers a portion of the layered cap flow **2038** to a first top cap reservoir **2130**, the sixth vein **2124** delivers a portion of the layered cap flow **2038** to a second top cap reservoir **2132**, the seventh vein **2126** delivers a portion of the layered cap flow **2038** to a third top cap reservoir **2134**, and the eighth vein **2128** delivers a portion of the layered cap flow **2038** to a fourth top cap reservoir **2136**. In a similar manner, the second vein **2116** includes similar splits to deliver portions of the layered cap flow **2038** to a first bottom cap reservoir **2138**, a second bottom cap reservoir **2140**, a third bottom cap reservoir **2142**, and a fourth bottom cap reservoir **2144**.

[0107] The 4-up die **2110** is also coupled to the core flow divider **1028**. In certain aspects, the core flow expander **1030** couples the core flow divider **1028** to the 4-up die **2110**. Similar to the die **1020**, the 4-up die **2110** includes a second passage **2146** in communication with the core flow divider **1028** (via the core flow expander **1030** in some aspects) to receive the layered core flow **1076**. Unlike the die **1020**, however, the second passage **2146** splits a ninth vein **2148** and a tenth vein **2150**. The ninth vein **2148** splits into an eleventh vein **2152** and a twelfth vein **2154** while the tenth vein **2150** splits into a thirteenth vein **2156** and a fourteenth vein **2158**. The eleventh vein **2152** delivers a portion of the layered core flow **1076** to a first core reservoir **2160**, the twelfth vein **2154** delivers a portion of the layered core flow **1076** to a second core reservoir **2162**, the thirteenth vein **2156** delivers a portion of the layered core flow **1076** to a third core reservoir **2164**, and the fourteenth vein **2158** delivers a portion of the layered core flow **1076** to a fourth core reservoir **2166**. The first through fourth core reservoirs **2160**, **2162**, **2164**, **2166** receive portions of the layered core flow **1076** for each forming the desired shape of a corresponding core **2814**. Each core **2814** is further advanced to corresponding first through fourth fuser wells **2168**, **2170**, **2172**, **2174** that are correspondingly in communication with the first through fourth top cap reservoirs **2130**, **2132**, **2134**, **2136** and the first through fourth bottom cap reservoirs **2138**, **2140**, **2142**, **2144** for fusing corresponding layered cap flow **2038** onto corresponding cohere surfaces **2822** of corresponding core **2814** to form corresponding capped polymer substrate **2810**. The first through fourth fuser wells **2168**, **2170**, **2172**, **2174** include corresponding side wells **2176**, **2178**, **2180**, **2182**, respectively, such that corresponding layered cap flows **2038** flow from the corresponding top cap reservoirs **2130**, **2132**, **2134**, **2136** into the corresponding side wells **2176**, **2178**, **2180**, **2182** for fusing the corresponding layered cap flows **2038** onto the cohere sides **2826** of the cohere surfaces **2822** of each corresponding core **2812**. One side well of the side wells **2176** is disposed on both sides of the first fuser well **2168**. The side wells **2178**, **2180**, **2182** are similarly disposed on the second through fourth fuser wells **2170**, **2172**, **2174**, respectively. Each of the four capped wood-grained substrates **2810** then exit corresponding out-

lets **2106** of the 4-up die **2110** through a reducer, such as, for example, the exit reducer **2107** and into the cooling bath **2108**.

[0108] Referring back to FIG. **14**, the extrusion machine **1000** includes a plurality of temperature sensors **2184** disposed at strategic locations throughout the extrusion machine **1000**. The plurality of temperature sensors **2184** are strategically disposed on the extrusion machine **1000** at locations that are critical for temperatures to be monitored and maintained throughout the flow process. For example, there can be 6-8 zones associated with the core assembly **1016**, the first extruder **1010**, and the second extruder **1012**. In certain aspects, each zone generally increases by 10 degrees Fahrenheit in the downstream direction. For example, zone 1 may be 370 degrees Fahrenheit and zone 2 may be 380 degrees Fahrenheit while zone 6 may be 420 degrees Fahrenheit. The plurality of sensors **2184** can be placed within these 6-8 zones to monitor the temperatures of certain components of the extrusion machine **1000**. For example, sensors of the plurality of sensors **2184** may be disposed in zone 3 to monitor the core flow adapter **1026** and the core flow divider **1028** while another sensor of the plurality of sensors **2184** may be disposed in zone 6 to monitor the front of the die **1020**.

[0109] Furthermore, sensors of the plurality of sensors **2184** can be placed on the first extruder **1010**, the second extruder **1012**, and the third extruder **1014** to monitor the melt temperatures of the first polymer **1022**, the second polymer **1024**, and the third polymer **1090**, respectively. In certain aspects, the melt temperatures can be in a range approximately from 360 degrees Fahrenheit to 420 degrees Fahrenheit. Sensors of the plurality of sensors **2184** can also be placed to monitor the temperature of the second polymer **1024** as it flows to the core flow adapter **1026** and the cap flow adapter **1080**. In certain aspects, the temperature of the second polymer **1024** flowing to the core flow adapter **1026** and the cap flow adapter **1080** can be in a range approximately from 360 degrees Fahrenheit to 390 degrees Fahrenheit. Sensors of the plurality of sensors **2184** can also be placed in the core flow divider **1028** and the cap flow divider **1082** to monitor the temperature here, which, in certain aspects, can be in a range of approximately from 360 degrees Fahrenheit to 420 degrees Fahrenheit. Sensors of the plurality of sensors **2184** can also be placed on the die **1020** to monitor the temperature of the die **1020**, which, in certain aspects, can be approximately 400 degrees Fahrenheit.

[0110] FIG. **27** illustrates an example process **2700** for producing the capped polymer substrate **2810** for manufacturing end products using the example extrusion machine **1000** of FIG. **14**. While FIG. **27** is described with reference to FIG. **14**, it should be noted that the process steps of FIG. **27** can be performed by other aspects described throughout the disclosure.

[0111] As illustrated at block **2710**, the process **2700** includes co-extruding the first polymer **1022** and the second polymer **1024** to form the combined core flow **1036** extrusion. The process **2700** also includes, as depicted in block **2712**, feeding the combined core flow **1036** extrusion through the core flow divider **1028** that includes the first plurality of section inserts **1072** to form the layered core flow **1076**. Each section insert of the first plurality of section inserts **1072** is predeterminedly inter-fitted with respect to each other to vary the first wood-grained pattern (i.e., the core wood-grained pattern **2816** into the layered core flow

1076, wherein the first wood-grained pattern includes a plurality of core grains **2828** oriented in different directions such that individual core grains of the plurality of grains **2828** are varied in thickness.

[0112] As illustrated at block **2714**, the process **2700** includes co-extruding the second polymer **1024** and the third polymer **1090** to form the combined cap flow **1096** extrusion. The process **2700** also includes, as illustrated at block **2716**, feeding the combined cap flow **1096** extrusion through the cap flow divider **1082**, which includes the second plurality of section inserts **2034** to form the layered cap flow **2038**. Each section insert of the second plurality of section inserts **2034** is predeterminedly inter-fitted with respect to each other to vary the second wood-grained pattern (i.e., the wood-grained cap patterns **2818**) into the layered cap flow **2038**.

[0113] The process **2700** also includes, as illustrated at block **2718**, receiving the layered core flow **2038** at the die **1020** to form the core **2812**. As illustrated at block **2720**, the process **2700** includes receiving the layered cap flow **2038** at the die **1020**. The process **2700** also includes, as illustrated at block **2722**, fusing the layered cap flow **2038** to cohere surfaces **2822** of the core **2812**.

[0114] FIGS. **28A** and **28B** are example illustrations of various samples of the capped polymer substrate **2810** associated with the example process of FIG. **27**. As discussed above, the capped polymer substrate **2810** produced by the extrusion machine **1000** includes the cap **2814** fused to the cohere surfaces **2822**, including the cohere sides **2826**, of the core **2812**. The wood-grained core patterns **2816** extend throughout the core **2812** and are visible at the outer core surfaces **2820**, as the cap **2814** is not fused to the outer core surfaces **2820**. Core grains **2828** (formed of the second polymer **1024**) of the wood-grained core patterns **2816** are generally thinner than the remaining layers (formed from the first polymer **1022**) of the core **2812**. Individual core grains of the core grains **2828** can vary in thickness. In certain aspects, the core grains **2828** mimic the organic wood-graining caused by rings of a tree.

[0115] The wood-grained cap patterns **2818** extend throughout the cap **2814** and are visible on the exterior surfaces **2824** of the cap **2814**. In certain aspects, cap grains **2830** (formed of the second polymer **1024**) of the wood-grained cap patterns **2818** are generally thinner than the remaining layers (formed from the third polymer **1090**) of the cap **2814**. Moreover, the wood-grained cap patterns **2818** include texture to simulate the feel of natural wood.

[0116] The extrusion machine **1000** can form the capped polymer substrate **2810** into boards used in the construction of various end products. While the capped polymer substrate **2810** that is formed into a board includes a generally rectangular cross-section, other cross-sectional profiles are within the scope of the disclosure. For example, the die **1020** or the 4-up die **2110** can be designed to produce a capped polymer substrate that includes a cross-sectional profile such as, but not limited to, circular, polygonal, or other unique cross-sectional profiles. Moreover, such cross-sectional profiles can also be created by post-processing techniques such as cutting or planing. For example, cutting or planing the capped polymer substrate **2810** can also expose other areas of the wood-grained core patterns **2816** by removing portions of the cap **2814**.

[0117] The wood-grained core patterns **2816** in the resulting exemplary boards formed from the capped polymer

substrate **2810** generally extend along the length of the board. In some aspects, a majority of core grains **2828**, created by the layers of the second polymer **1024**, extend along the length of the entire board. Likewise, the remaining portions of the core **2812** of the board, formed by the interspersed layers of the first polymer **1022**, also generally extend along the length of the board. In certain aspects, a majority of the layers of the first polymer **1022** extend along the length of the entire board. This creates a substantially consistent pattern along the length of the board such that cuts at various point along the board will expose a substantially similar wood-grained core patterns **2816**.

[0118] As discussed above, by selectively adjusting the orientation of the final section insert of the plurality of section inserts **1072**, the core grains **2828** of the wood-grained core patterns **2816** can be oriented in various directions and orientations. For example, as illustrated in FIG. **28A**, the core grains **2828** extend a width, between lateral sides **2832**, of the capped polymer substrate **2810** (i.e., the board) and are orientated in a generally horizontal orientation. The interspersed layers of the first polymer **1022** and the second polymer **1024** are stacked from a bottom surface **2834** of the capped polymer substrate **2810** toward a top surface **2836** of the capped polymer substrate **2810**. In another example, as illustrated in FIG. **28B**, the core grains **2828** are orientated at an angle with respect to the bottom surface **2834** of the capped polymer substrate **2810**. As illustrated in these examples, the orientation of the core grains **2828** of the wood-grained core patterns **2816** can be formed in various orientations and extend along curvilinear paths across the width of the capped polymer substrate **2810**. In certain aspects, a majority of the core grains **2828** extend substantially uninterrupted across the capped polymer substrate **2810** (i.e., the board) such that the core grains **2828** have minimal or no gaps.

[0119] Moreover, as also discussed above, by selectively adjusting the orientation of the final section insert of the plurality of section inserts **2034**, the cap grains **2830** of the wood-grained cap patterns **2818** can be oriented in various directions and orientations. For example, the cap grains **2830** extend a length of the capped polymer substrate **2810** between the outer core surfaces **2820** and are generally orientated parallel to the lateral sides **2832**. The interspersed layers of the second polymer **1024** and the third polymer **1090** are stacked between the lateral sides **2832** of the capped polymer substrate **2810**. The texture of the cap **2814** simulates the feel of natural wood.

[0120] The capped polymer substrate **2810** can be used to fabricate various end products such as, but not limited to, decks, furniture, siding, playground equipment, the examples end products illustrated in FIGS. **12** and **13**, and other end products.

[0121] While the disclosure has been illustrated and described in detail in the foregoing drawings and description, the same is to be considered as exemplary and not restrictive in character, it being understood that only illustrative embodiments thereof have been shown and described and that all changes and modifications that come within the spirit of the disclosure are desired to be protected.

What is claimed is:

1. A capped polymer substrate that simulates natural wood extending along a first direction, the capped polymer substrate having a first side and a second side spaced apart from the first side along a second direction different than the first

direction, the first and the second sides defining a width of the substrate, the first and the second sides extending along the first direction, the substrate comprising:

- a first set of polymer layers extending along the first direction and containing a first colorant, a majority of the first set of polymer layers being substantially continuous along the first direction;
- a second set of polymer layers extending along the first direction and containing a second colorant different than the first colorant, a majority of the second set of polymer layers being substantially continuous along the first direction;
- a core extending between the first and the second sides and along the first direction, the core comprising a first wood-grained pattern formed of the first set of polymer layers and the second set of polymer layers, the first wood-grained pattern is exposed on outer surfaces of the core at a first end and a second end of the core, wherein individual layers of the first and the second set of polymer layers are interspersed within the core to form the first wood-grained pattern throughout the core, wherein a plurality of individual layers of one of the first and the second sets of polymer layers extend along a substantially uninterrupted curvilinear path in the second direction originating proximate the first side and terminating proximate the second side;
- a cross-section of the core exposing the first wood-grained pattern; and
- a cap fused onto cohere surfaces of the core, wherein the cap comprises a second wood-grained pattern formed of a copolymer.

2. The capped polymer substrate of claim 1, wherein the first wood-grained pattern extends uninterrupted between the first end and the second end.

3. The capped polymer substrate of claim 1, wherein the first wood-grained pattern includes a plurality of core grains oriented in different directions such that individual grains of the plurality of grains vary in thickness with respect to a third direction that is perpendicular to the first direction and the second direction.

4. The capped polymer substrate of claim 1, wherein the second wood-grained pattern comprises a plurality of cap grains extending along a path in the first direction.

5. The capped polymer substrate of claim 1, wherein the cap comprises texturized exterior surfaces.

6. The capped polymer substrate of claim 1, wherein the first and the second set of polymer layers are one of homopolymers, copolymers, virgin homopolymers, virgin copolymers, recycled homopolymers, and recycled copolymers.

7. The capped polymer substrate of claim 1, wherein the exposed portions of the first wood-grained pattern form a burled grain pattern.

8. The capped polymer substrate of claim 1, wherein the second wood-grained pattern forms a burled grain pattern.

9. The capped polymer substrate of claim 1, wherein the first and the second set of polymer layers include at least one of a UV inhibitor and a foaming agent.

* * * * *