

DECLARATION OF JUNE ANN MUNFORD

1. My name is June Ann Munford. I am over the age of 18, have personal knowledge of the facts set forth herein, and am competent to testify to the same.
2. I earned a Master of Library and Information Science (MLIS) from the University of Wisconsin-Milwaukee in 2009. I have over ten years of experience in the library/information science field. Beginning in 2004, I have served in various positions in the public library sector including Assistant Librarian, Youth Services Librarian and Library Director. I have attached my Curriculum Vitae as Appendix CV.
3. During my career in the library profession, I have been responsible for materials acquisition for multiple libraries. In that position, I have cataloged, purchased and processed incoming library works. That includes purchasing materials directly from vendors, recording publishing data from the material in question, creating detailed material records for library catalogs and physically preparing that material for circulation. In addition to my experience in acquisitions, I was also responsible for analyzing large collections of library materials, tailoring library records for optimal catalog

search performance and creating lending agreements between libraries during my time as a Library Director.

4. I am fully familiar with the catalog record creation process in the library sector. In preparing a material for public availability, a library catalog record describing that material would be created. These records are typically written in Machine Readable Catalog (herein referred to as “MARC”) code and contain information such as a physical description of the material, metadata from the material’s publisher, and date of library acquisition. In particular, the 008 field of the MARC record is reserved for denoting the date of creation of the library record itself. As this typically occurs during the process of preparing materials for public access, it is my experience that an item’s MARC record indicates the date of an item’s public availability.
5. Typically, in creating a MARC record, a librarian would gather various bits of metadata such as book title, publisher and subject headings among others and assign each value to a relevant numerical field. For example, a book’s physical description is tracked in field 300 while title/attribution is tracked in field 245. The 008 field of the MARC record is reserved for denoting the creation of the library record itself. As this is the only date reflecting the inclusion of said materials within the library’s collection, it is my experience

that an item's 008 field accurately indicates the date of an item's public availability.

6. I have reviewed LGES-1009, "Modification of Multiwall Carbon Nanotubes by Grafting from Controlled Polymerization of Styrene: Effect of the Characteristics of the Nanotubes" by Julio Albuérne, et al. as published in *Journal of Polymer Science: Part B: Polymer Physics*, 15 May 2010.
7. Attached hereto as Appendix ALBUERNE01 is a true and correct copy of the MARC record for *Journal of Polymer Science: Part B: Polymer Physics* as held by the Penn State University library. I secured this record myself from the library's public catalog. The MARC record contained within Appendix ALBUERNE01 accurately describes the title, author, publisher, and ISSN number of *Journal of Polymer Science: Part B: Polymer Physics*. The 'Dates of Publication' field of this record visible on page 2 indicates this collection includes the 15 May 2010 edition of *Journal of Polymer Science: Part B: Polymer Physics* containing "Modification of Multiwall Carbon Nanotubes by Grafting from Controlled Polymerization of Styrene: Effect of the Characteristics of the Nanotubes".

8. Attached hereto as Appendix ALBUERNE02 is a true and correct copy of “Modification of Multiwall Carbon Nanotubes by Grafting from Controlled Polymerization of Styrene: Effect of the Characteristics of the Nanotubes” as published in *Journal of Polymer Science: Part B: Polymer Physics* as held by the Penn State University library. I secured this file myself from the library’s collection. In comparing LGES-1009 to Appendix ALBUERNE02, it is my determination that LGES-1009 is a true and correct copy of “Modification of Multiwall Carbon Nanotubes by Grafting from Controlled Polymerization of Styrene: Effect of the Characteristics of the Nanotubes” by Julio Albuerne, et al. as published in *Journal of Polymer Science: Part B: Polymer Physics* 15 May 2010.
9. The 008 field of the MARC record in Appendix ALBUERNE01 indicates the date of record creation. The 008 field of Appendix ALBUERNE01 indicates the Penn State University library first acquired this journal as of April 28, 1998 and held the journal in perpetuity until December 2019. Considering this information, it is my determination that *Journal of Polymer Science: Part B: Polymer Physics* 15 May 2010 and therefore “Modification of Multiwall Carbon Nanotubes by Grafting from Controlled Polymerization of Styrene: Effect of the Characteristics of the Nanotubes” was made available to the public shortly after its initial release in May 2010.

10. I have been retained on behalf of the Petitioner to provide assistance in the above-illustrated matter in establishing the authenticity and public availability of the documents discussed in this declaration. I am being compensated for my services in this matter at the rate of \$200.00 per hour plus reasonable expenses. My statements are objective, and my compensation does not depend on the outcome of this matter.

11. I declare under penalty of perjury that the foregoing is true and correct. I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code.

Dated: 6/8/2024

A handwritten signature in black ink, appearing to read 'June Ann Munford', with a stylized flourish at the end.

June Ann Munford

Appendix CV

June A. Munford
Curriculum Vitae

Education

University of Wisconsin-Milwaukee - MS, Library & Information Science, 2009
Milwaukee, WI

- Coursework included cataloging, metadata, data analysis, library systems, management strategies and collection development.
- Specialized in library advocacy, cataloging and public administration.

Grand Valley State University - BA, English Language & Literature, 2008
Allendale, MI

- Coursework included linguistics, documentation and literary analysis.
- Minor in political science with a focus in local-level economics and government.

Professional Experience

Researcher / Expert Witness, October 2017 – present
Freelance ● Pittsburgh, Pennsylvania & Grand Rapids, Michigan

- Material authentication and public accessibility determination. Declarations of authenticity and/or public accessibility provided upon research completion. Experienced with appeals and deposition process.
- Research provided on topics of public library operations, material publication history, digital database services and legacy web resources.
- Past clients include Alston & Bird, Arnold & Porter, Baker Botts, Fish & Richardson, Erise IP, Irell & Manella, O'Melveny & Myers, Perkins-Coie, Pillsbury Winthrop Shaw Pittman and Slayden Grubert Beard.

Library Director, February 2013 - March 2015
Dowagiac District Library ● Dowagiac, Michigan

- Executive administrator of the Dowagiac District Library. Located in

Southwest Michigan, this library has a service area of 13,000, an annual operating budget of over \$400,000 and total assets of approximately \$1,300,000.

- Developed careful budgeting guidelines to produce a 15% surplus during the 2013-2014 & 2014-2015 fiscal years while being audited.
- Using this budget surplus, oversaw significant library investments including the purchase of property for a future building site, demolition of existing buildings and building renovation projects on the current facility.
- Led the organization and digitization of the library's archival records.
- Served as the public representative for the library, developing business relationships with local school, museum and tribal government entities.
- Developed an objective-based analysis system for measuring library services - including a full collection analysis of the library's 50,000+ circulating items and their records.

November 2010 - January 2013

Librarian & Branch Manager, Anchorage Public Library ● Anchorage, Alaska

- Headed the 2013 Anchorage Reads community reading campaign including event planning, staging public performances and creating marketing materials for mass distribution.
- Co-led the social media department of the library's marketing team, drafting social media guidelines, creating original content and instituting long-term planning via content calendars.
- Developed business relationships with The Boys & Girls Club, Anchorage School District and the US Army to establish summer reading programs for children.

June 2004 - September 2005, September 2006 - October 2013

Library Assistant, Hart Area Public Library

Hart, MI

- Responsible for verifying imported MARC records and original MARC

cataloging for the local-level collection as well as the Michigan Electronic Library.

- Handled OCLC Worldcat interlibrary loan requests & fulfillment via ongoing communication with lending libraries.

Professional Involvement

Alaska Library Association - Anchorage Chapter

- Treasurer, 2012

Library Of Michigan

- Level VII Certification, 2008
- Level II Certification, 2013

Michigan Library Association Annual Conference 2014

- New Directors Conference Panel Member

Southwest Michigan Library Cooperative

- Represented the Dowagiac District Library, 2013-2015

Professional Development

Library Of Michigan Beginning Workshop, May 2008

Petoskey, MI

- Received training in cataloging, local history, collection management, children's literacy and reference service.

Public Library Association Intensive Library Management Training, October 2011

Nashville, TN

- Attended a five-day workshop focused on strategic planning, staff management, statistical analysis, collections and cataloging theory.

Alaska Library Association Annual Conference 2012 - Fairbanks, February 2012

Fairbanks, AK

- Attended seminars on EBSCO advanced search methods, budgeting, cataloging, database usage and marketing.

Depositions

2019 • Fish & Richardson

Apple v. Qualcomm (IPR2018-001281, 39521-00421IP, IPR2018-01282 and 39521-00421IP2)

2019 • Erise IP

Implicit, LLC v. Netscout Systems, Inc (Civil Action No. 2:18-cv-53-JRG)

2019 • Perkins-Coie

Adobe Inc. v. RAH Color Technologies LLC (Cases IPR2019-00627, IPR2019-00628, IPR2019-00629 and IPR2019-00646)

2020 • O'Melveny & Myers

Maxell, Ltd. v. Apple Inc. (Case No. 5:19-cv-00036-RWS)

2021 • Pillsbury Winthrop Shaw Pittman LLP

Intel v. SRC (IPR2020-1449)

2022 • Perkins-Coie

Realtek v. Future Link (IPR2021-01182)

2023 • Fish & Richardson

Neuroderm Ltd. v. Abbvie, Inc (Case No. PGR2022-00040)

2023 • Fish & Richardson

Nearmap US Inc. v. Pictometry International Corp. (IPR2022-00735)

2023 • Fish & Richardson

Samsung Electronics v. MemoryWeb LLC (Case No. 39843-0136PS1)

2023 ● Pillsbury Winthrop Shaw Whitman LLP

Gravel Rating Systems v. Costco Wholesale Corp. (Civil Action No. 4:21-cv-149-ALM)

Limited Case and Clientele History

Alston & Bird

- Ericsson

v. Collision Communications (IPR2022-01233)

- Nokia

v. Neptune Subsea, Xtera (Case No. 1:17-cv-01876)

- Universal Electronics Inc

v. Roku Inc (IPR2022-00818)

Arnold & Porter

- Ivantis

v. Glaukos (Case No. 8:18-cv-00620)

- Samsung

v. Jawbone (Case No. 2:21-cv-00186)

Benesch Friedlander Coplan & Aronoff

- Voyis

v. Cathx (Case No. 5:21-cv-00077-RWS)

Erise I.P.

- Apple

- v. Ericsson Inc. (IPR2022-00715)
- v. Future Link Systems (IPRs 6317804, 6622108, 6807505, and 7917680)
- v. INVT (Case No. 20-1881)
- v. Navblazer LLC (IPR2020-01253)
- v. Qualcomm (IPR2018-001281, 39521-00421IP, IPR2018-01282, 39521-00421IP2)
- v. Quest Nettech Corp (Case No. 2:19-cv-00118-JRG)
- v. Telefonaktiebolaget LM Ericsson (IPR2022-00275)

- Fanduel

- v. CGT (Case No. 19-1393)

- Garmin

- v. Phillips North America LLC (Case No. 2:19-cv-6301-AB-KS)

- Netscout

- v. Longhorn HD LLC (Case No. 2:20-cv-00349)
- v. Implicit, LLC (Civil Action No. 2:18-cv-53-JRG)

- Sony Interactive Entertainment LLC

- v. Bot M8 LLC (IPR2020-01288)
- v. Infernal Technology LLC (Case No. 2:19-CV-00248-JRG)

- Unified Patents

v. GE Video Compression (Civil Action No. 2:19-cv-248)

Fish & Richardson

- Apple

- v. AliveCor (3:21-cv-03958)

- v. LBS Innovations (Case No. 2:19-cv-00119-JRG-RSP)

- v. Koss Corporation (IPR2021-00305)

- v. Masimo (IPR 50095-0012IP1, 50095-0012IP2, 50095-0013IP1, 50095-0013IP2, 50095-0006IP1, 50095-0135IP1)

- v. Neonode (Case No. 21-cv-08872-EMC)

- v. Qualcomm (IPR2018-001281, 39521-00421IP, IPR2018-01282, 39521-00421IP2)

- Dell

- v. Neo Wireless (IPR2022-00616)

- Dish Network

- v. Entropic Communications, LLC (Case No. 2:2023-CV-01043)

- v. Realtime Adaptive Streaming (Case No. 1:17-CV-02097-RBJ)

- v. TQ Delta LLC (Case No. 18-1798)

- Evapco Dry Cooling

- v. SPG Dry Cooling (IPR2021-00688)

- Genetec

- v. Sensormatic Electronics (Case No. 1:20-CV-00760)

- Huawei

- v. Bell Northern Research LLC (IPR2019-01174)
- Kianxis
 - v. Blue Yonder (Case No. 3:20-cv-03636)
- LG Electronics
 - v. Bell Northern Research LLC (Case No. 3:18-cv-2864-CAB-BLM)
- Metaswitch
 - v. Sonus Networks (IPR2018-01719)
- Microsoft
 - v. Throughputer Inc (IPR2022-00757)
- Mom Enterprises
 - v. Ddrops Company (Case No. 1:22-cv-00332)
- MLC Intellectual Property
 - v. MicronTech (Case No. 3:14-cv-03657-SI)
- Nearmap Inc
 - v. EagleView Technologies (IPR2022-01009)
- Neuroderm Ltd.
 - v. Abbvie, Inc (Case No. PGR2022-00040)
- Realtek Semiconductor

v. Future Link (IPR2021-01182)

- Quectel

v. Koninklijke Philips (Case No. 1:20-cv-01710)

- Samsung

v. Aire Technology (IPR2022-00877)

v. Bell Northern Research (Case No. 2:19-cv-00286-JRG)

v. Communication Technologies Inc (IPR2022-01221)

v. Jawbone Innovations (IPR2022-00865)

v. MemoryWeb LLC (IPR2022-00885)

v. Dodots Licensing Solutions (IPR2023-00701)

v. Telefonaktiebolaget LM Ericsson (IPR2021-00615)

- Texas Instruments

v. Vantage Micro LLC (IPR2020-01261)

- Xilinx

v. Sentient Sensors LCC (Case No. 1:22-cv-00173)

Irell & Manella

- Curium

O'Melveny & Myers

- Apple

v. Maxell (Case No. 5:19-cv-00036-RWS)

- Micron Technology Inc.
v. Besang Inc (IPR2023-00900)
- Samsung
v. Daedalus Prime LLC (1335 Investigation)

Perkins-Coie

- Heru Industries
v. The UAB Research Foundation (IPR2022-01148)
- Intel Corporation
v. BitMICRO (Case No. 5:23-cv-00625)
- Realtek Semiconductor
v. Future Link (IPR2021-01182)
- Twitter Inc
v. VOIP-Pal.com (Case No. 3:20-cv-02397-JD)
- TCL Industries
v. Koninklijke Philips NV (IPR2021-00495, IPR2021-00496
and IPR2021-00497)

Pillsbury Winthrop Shaw Pittman

- Intel
v. FG SRC LLC (Case No. 6:20-cv-00315)
- Gravel Rating Systems

- v. Costco (Case No. 4:21-cv-149)
- v. Lowe's Home Centers (Case No. 4:21-cv-150)
- v. T-Mobile USA (Case No. 4:21-cv-152)
- v. Kohl's Inc. (Case No. 4:21-cv-258)
- v. Under Armor (Case No. 4:21-cv-356)

Quinn Emanuel

- Wolfspeed
 - v. The Trustees of Purdue University (Case No. 1:2021-cv-00840)

Stern, Kessler, Goldstein & Fox

- Preliminary Research

Sheppard, Mullin, Richter & Hampton LLP

- Cadence Design Systems Inc.
 - v. Semiconductor Design Technologies (Case No. 3:23-cv-01001)

Appendix ALBUERNE01



Keyword

Search...

Search

Advanced search Start Over

Share

Bookmark

Report an Issue

MARC View

LEADER 02340nas a22004697a 4500

001 44406388

003 SIRSI

005 20240514090053.0

006 m o d

007 cr n

008 980428d19862019njumr pss 0 a0eng c

010 a| sn 98007464

016 7 a| 013345618 2| Uk

019 a| DO NOT EDIT this 360 MARC RECORD

022 a| 1099-0488 | 0887-6266 y| 0887-6266

035 a| (WaSeSS)ssj0009959

037 b| Wiley Subscription Services, Inc., 111 River St., Hoboken, NJ 07030-5774 USA

040 a| NSD b| eng e| pn c| NSD d| OCLCQ d| NSD d| OCL d| NSD d| MUQ d| SYB d| EEM d| OCLCQ d| UKMGB d| OCLCQ d| OCLCF d| OCLCO d| OCLCQ d| EZC d| OCLCO d| U3W d| WYU d| OCLCO d| AUD d| OCLCA d| CGU d| VT2 d| OCLCO d| OCLCQ d| OCLCO d| NJT d| CEF d| OCLCO d| OCLCQ d| SFB d| OCLCA d| UMC d| OCLCO d| IUL d| UBY d| OCLCQ d| WaSeSS

042 a| nsdp a| pcc

050 1 4 a| QC173.4.P65

060 0 0 a| W1 b| J0837PJ

082 1 0 a| 547 2| 13

130 0 a| Journal of polymer science. Part B, Polymer physics (Online)

210 0 a| J. polym. sci., Part B, Polym. phys. b| (Online)

222 0 a| Journal of polymer science. Part B, Polymer physics b| (Online)

245 1 0 a| Journal of polymer science. n| Part B, p| Polymer physics h| [electronic resource].

246 3 0 a| Polymer physics

260 a| [New York, N.Y.] : b| Wiley, c| [1986]-©2019.

310 a| Monthly

362 0 a| Vol. 24, issue 1 (Jan. 1986)-v. 57, no. 24 (15 December 2019).

500 a| Title from table of contents page (publisher's Web site viewed May 10, 2005).

538 a| Mode of access: World Wide Web.

580 a| Merged with: Journal of polymer science. Part A, Polymer chemistry (Online), to form: Journal of polymer science (2020).

650 0 a| Polymers v| Periodicals.

650 2 a| Physics.

650 2 a| Polymers.

776 0 8 i| Print version: t| Journal of polymer science. Part B, Polymer physics x| 0887-6266 w| (DLC) 86666467 w| (OCoLC)13378941

785 0 7 t| Journal of polymer science. Part A, Polymer chemistry (Online) x| 1099-0518 w| (DLC)sn 98007474 w| (OCoLC)39029246

785 0 7 t| Journal of polymer science (2020) x| 2642-4169 w| (DLC) 2019200121 w| (OCoLC)1090354499

856 4 0 u| http://SK8ES4MC2L.search.serialssolutions.com/?V=1.0&L=SK8ES4MC2L&S=JCS&C=JOURNOFPOLSC&T=marc

910 a| CONSER online

949 a| Electronic resource w| ASIS c| 1 i| 44406388-1001 | ONLINE m| ONLINE r| Y s| Y t| ONLINE u| 5/18/2024 o| .STAFF. 360 MARC

ASK
A LIBRARIAN

Copyright ©2019 The Pennsylvania State University. All rights reserved. Except where otherwise noted, this work is subject to a Creative Commons Attribution 4.0 license. Details and exceptions.

[Legal Statements](#) | [PSU Hotlines](#)**PENN STATE
UNIVERSITY LIBRARIES**[Libraries Home](#)

(814) 865-6368

[Libraries Intranet \(Staff Only\)](#)[Accessibility Help](#)[Website Feedback](#)[Policies and Guidelines](#)[Staff Directory](#)**CONNECT WITH
PENN STATE
UNIVERSITY LIBRARIES**[Facebook](#)[Twitter](#)[Instagram](#)



Keyword

Search...

Q Search

[Advanced search](#) [Start Over](#)

Share

Bookmark

Report an Issue



Journal of polymer science. Part B, Polymer physics [electronic resource].

Uniform Title: Journal of polymer science. Part B, Polymer physics (Online)
Additional Titles: J. polym. sci., Part B, Polym. phys. (Online) and Polymer physics
Published: [New York, N.Y.] : Wiley, [1986]-©2019.

Access Online

serialssolutions.com**ASK**
A LIBRARIAN

Merged to Form:

[Journal of polymer science. Part A, Polymer chemistry \(Online\)](#)
[Journal of polymer science \(2020\)](#)

Dates of Publication and/or Sequential Designation:

Vol. 24, issue 1 (Jan. 1986)-v. 57, no. 24 (15 December 2019).

Subject(s):

[Polymers—Periodicals](#)
[Physics](#)
[Polymers](#)

ISSN:

1099-0488

Publication Frequency:

Monthly

Note:

Title from table of contents page (publisher's Web site viewed May 10, 2005).

Technical Details:

Mode of access: World Wide Web.

Complexity Note:

Merged with: Journal of polymer science. Part A, Polymer chemistry (Online), to form: Journal of polymer science (2020).

[View MARC record](#) | catkey: 44406388

Copyright ©2019 The Pennsylvania State University. All rights reserved. Except where otherwise noted, this work is subject to a Creative Commons Attribution 4.0 license. Details and exceptions.

[Legal Statements](#) | [PSU Hotlines](#)

PENN STATE UNIVERSITY LIBRARIES

[Libraries Home](#) (814) 865-6368
[Libraries Intranet \(Staff Only\)](#)
[Accessibility Help](#)
[Website Feedback](#)
[Policies and Guidelines](#)
[Staff Directory](#)

CONNECT WITH PENN STATE UNIVERSITY LIBRARIES

[Facebook](#)
[Twitter](#)
[Instagram](#)

[< Back](#)

Polymer Physics

Journal of Polymer Science Part B: Polymer Physics: Volume 48, Issue 10

Pages: 1009-1125

15 May 2010

[< Previous Issue](#) | [Next Issue >](#) [GO TO SECTION](#)[" Export Citation\(s\)](#)

Articles

 [Full Access](#)

Magnetic orientation of diamagnetic amorphous polymers

Leoncio Garrido

Pages: 1009-1015 | First Published: 07 April 2010

[Abstract](#) | [Full text](#) | [PDF](#) | [References](#) | [Request permissions](#) [Full Access](#)

Polymer electrolyte membranes based on *p*-toluenesulfonic acid doped poly(1-vinyl-1,2,4-triazole): Synthesis, thermal and proton conductivity properties

Şehmus Özden, Sevim Ünügür Çelik, Ayhan Bozkurt

Pages: 1016-1021 | First Published: 07 April 2010

[Abstract](#) | [Full text](#) | [PDF](#) | [References](#) | [Request permissions](#) [Full Access](#)

Poly(bis-2,2,2-trifluoroethoxymethyl oxetane): Multiple crystal phases, crystallization-induced surface topological complexity and enhanced hydrophobicity

[< Back](#)

Pages: 1022-1034 | First Published: 07 April 2010

[Abstract](#) | [Full text](#) | [PDF](#) | [References](#) | [Request permissions](#) [Full Access](#)

Modification of multiwall carbon nanotubes by *grafting from* controlled polymerization of styrene: Effect of the characteristics of the nanotubes

Julio Albuérne, Adriana Boschetti-de-Fierro, Volker Abetz

Pages: 1035-1046 | First Published: 07 April 2010

 [Correction\(s\) for this article >](#)

Modification of multiwall carbon nanotubes by *grafting from* controlled polymerization of styrene: Effect of the characteristics of nanotubes

Julio Albuérne, Adriana Brochetti-de-Fierro, Volker Abetz

Volume 48, Issue 14, Journal of Polymer Science Part B: Polymer Physics | pages: 1683-1683 |
First Published online: June 14, 2010

[Abstract](#) | [Full text](#) | [PDF](#) | [References](#) | [Request permissions](#) [Full Access](#)

The origin of DC electrical conduction and dielectric relaxation in pristine and doped poly(3-hexylthiophene) films

Ramadhar Singh, Rajiv K. Singh, Jitendra Kumar, Rama Kant, Vikram Kumar

Pages: 1047-1053 | First Published: 07 April 2010

[Abstract](#) | [Full text](#) | [PDF](#) | [References](#) | [Request permissions](#) [Full Access](#)

Hydrophobically modified poly(vinyl alcohol) using alkoxy-substituted methyl gallate: Synthesis and rheology

Aarti S. Shedde, Prakash P. Wadgaonkar, Ashish K. Lele, Manohar V. Badiger

Pages: 1054-1063 | First Published: 07 April 2010

[Abstract](#) | [Full text](#) | [PDF](#) | [References](#) | [Request permissions](#)

[< Back](#)

nanocomposite films cast from soap-free emulsion polymerized latices

Keng-Jen Lin, Chia-Hsin Lee, King-Fu Lin

Pages: 1064-1069 | First Published: 07 April 2010

[Abstract](#) | [Full text](#) | [PDF](#) | [References](#) | [Request permissions](#)

 [Full Access](#)

Nonisothermal crystallization kinetics of poly (phenylene sulphide) in composites with a liquid crystalline polymer

Arun K. Kalkar, Vineeta D. Deshpande, Milind J. Kulkarni

Pages: 1070-1100 | First Published: 07 April 2010

[Abstract](#) | [Full text](#) | [PDF](#) | [References](#) | [Request permissions](#)

 [Full Access](#)

Stability of hierarchical lamellar morphologies formed in ABC star triblock copolymers

Yuci Xu, Weihua Li, Feng Qiu, Hongdong Zhang, Yuliang Yang, An-Chang Shi

Pages: 1101-1109 | First Published: 07 April 2010

[Abstract](#) | [Full text](#) | [PDF](#) | [References](#) | [Request permissions](#)

 [Full Access](#)

Synthesis and characterization of grafted/crosslinked proton conducting membranes based on amphiphilic PVDF copolymer

Dong Kyu Roh, Sung Hoon Ahn, Jin Ah Seo, Yong Gun Shul, Jong Hak Kim

Pages: 1110-1117 | First Published: 07 April 2010

[Abstract](#) | [Full text](#) | [PDF](#) | [References](#) | [Request permissions](#)

 [Full Access](#)

Aligned and molecularly oriented semihollow ultrafine polymer fiber yarns by a facile method

Kai Zhang, Xuefen Wang, Yin Yang, Lili Wang, Meifang Zhu, Benjamin S. Hsiao, Benjamin Chu

Pages: 1118-1125 | First Published: 07 April 2010

[< Back](#)[Submit an article](#)

More from this journal

[JPS Innovation Prize](#)

ABOUT WILEY ONLINE LIBRARY

[Privacy Policy](#)
[Terms of Use](#)
[About Cookies](#)
[Manage Cookies](#)
[Accessibility](#)

[Wiley Research DE&I Statement and Publishing Policies](#)
[Developing World Access](#)

HELP & SUPPORT

[Contact Us](#)
[Training and Support](#)
[DMCA & Reporting Piracy](#)

OPPORTUNITIES

[Subscription Agents](#)
[Advertisers & Corporate Partners](#)

CONNECT WITH WILEY

[The Wiley Network](#)
[Wiley Press Room](#)

Copyright © 1999-2024 John Wiley & Sons, Inc or related companies. All rights reserved, including rights for text and data mining and training of artificial technologies or similar technologies.

< Back



Appendix ALBUERNE02

Modification of Multiwall Carbon Nanotubes by *Grafting from* Controlled Polymerization of Styrene: Effect of the Characteristics of the Nanotubes

JULIO ALBUERNE, ADRIANA BOSCHETTI-de-FIERRO, VOLKER ABETZ

Institute of Polymer Research, GKSS Research Centre Geesthacht GmbH, Max-Planck-Str. 1, Geesthacht 21502, Germany

Received 26 September 2009; revised 5 February 2010; accepted 6 February 2010

DOI: 10.1002/polb.21992

Published online in Wiley InterScience (www.interscience.wiley.com).

ABSTRACT: Linear polystyrene chains were grown from the convex surface of two commercially available multiwall carbon nanotubes (MWCNTs) with similar diameter but different lengths. The MWCNTs were supplied from Bayer Material Science® (purity >95%, external diameter = 13–16 nm, length = 1–10 μm , denoted MWCNT_{BMS}⁹⁵) and FutureCarbon GmbH (purity >99%, external diameter = 15 nm, length = 5–50 μm , denoted MWCNT_{FC}⁹⁹). The MWCNTs were oxidized with nitric acid, consecutively reacted with thionyl chloride, glycol or poly(ethylene glycol), 2-bromo-2-methylpropionyl bromide and finally with styrene under atom transfer radical polymerization (ATRP) conditions. The content of polystyrene grafted from the surface of the MWCNTs can be controlled by adjusting the molecular weight of the poly(ethylene glycol), the initiator concentration and the monomer to carbon nanotube

weight ratio. Under comparable experimental conditions, a higher amount of polystyrene is grafted from the MWCNT_{BMS}⁹⁵ than from MWCNT_{FC}⁹⁹. The difference in dimensions and the state of aggregation of the carbon nanotubes influence the *grafting from* polymerization reactions, where relative shorter and tightly aggregated carbon nanotubes promote higher polymerizations yields than longer and less aggregated carbon nanotubes. The increase of the viscosity of the carbon nanotube dispersion decreases the polymer grafting content. © 2010 Wiley Periodicals, Inc. *J Polym Sci Part B: Polym Phys* 48: 1035–1046, 2010

KEYWORDS: atom transfer radical polymerization (ATRP); carbon nanotubes; grafting from polymerization; multiwall carbon nanotubes; polystyrene; thermogravimetric analysis (TGA)

INTRODUCTION The incorporation of carbon nanotubes in polymer matrices has become a challenge during the past decade.¹ Carbon nanotubes consist of graphene sheets rolled up into a cylindrical shape. They are classified depending on the number of graphene layers. Their dimensions range up to few hundred nanometers in diameter and tens of micrometers in length.^{2,3} They have outstanding mechanical, electrical, and thermal properties, which have inspired the design of a new generation of light weight materials,^{1,4,5} or even their use as biosensors or biocarriers,^{6–9} although their biocompatibility is still questionable.^{10–13}

One of the drawbacks of the incorporation of this type of nanofiller in polymer matrices is its tendency to aggregate due to the strong π – π stacking interactions between graphene sheets. Different strategies have been used to reduce the size of the aggregates or to improve the dispersion of individual carbon nanotubes. Sonication, centrifugation, calendaring, or intense stirring have shown promising results on single (SWCNT), double (DWCNT), and multiwall (MWCNT) carbon nanotube dispersions in solvents and different polymer matrices.^{4,5,14–16} Other approaches aim for the tuning of the surface of carbon nanotubes through the physisorption of surfactants and polymers,¹⁷ or through the direct functionalization on the surface of the nanoparticle.

Tasis et al.¹⁸ have presented a review related with the chemistry of carbon nanotubes. They have categorized the modification of carbon nanotubes into three groups: the endohedral filling of their inner empty cavity, the noncovalent adsorption or wrapping of various functional molecules, and the covalent attachment of small molecules or polymer chains through reactions onto the π -conjugated skeleton of the carbon nanotubes. In the first case, the research has been focused on the production of nanowires or on the storage of liquid fuels. The works have been mainly related with the encapsulation of fullerenes, metalofullerenes, metal salts (subsequently reduced to metals), metal oxides, inorganic salts, and biomolecules in SWCNTs and MWCNTs. There are also examples of conjugated polymers that have the ability of wrapping the carbon nanotubes, usually, with a helical conformation. There are two main approaches for the covalent attachment of polymers on carbon nanotubes, known as *grafting onto* and *grafting from*. The former consists on attaching polymer chains onto the surface of carbon nanotubes through the reaction with end or side functionalized polymer chains. Unfortunately, the efficiency of the grafting reactions is sometimes inaccurate due to the presence of nongrafted polymer.^{19–21} The *grafting from* relies on the polymerization from the carbon nanotubes through the immobilization of a polymer precursor at the particle

Correspondence to: V. Abetz (E-mail: volker.abetz@gkss.de)

Journal of Polymer Science: Part B: Polymer Physics, Vol. 48, 1035–1046 (2010) © 2010 Wiley Periodicals, Inc.

surface.¹⁸ In this case, a series of prefunctionalization reactions are required to covalently anchor groups capable to initiate the polymerization. However, the concentration of initiator groups and the final characteristics of the grafted polymer (i.e., molecular weight and weight content) can be tuned by the adjustment of the prefunctionalization reactions. The most versatile technique used on the grafting of polymer from carbon nanotubes (and other substrates) is the controlled radical polymerization^{8,22–41} because a broad number of monomers is available, it generally does not require an elaborated setup, and it accepts some level of impurities on the carbon nanotubes and the reaction system. There are diverse references regarding the grafting from carbon nanotubes where the control on the polymerization is achieved by adjusting the concentration of monomer, initiator, or deactivator.^{8,28,31,32,42} However, to the author's knowledge, the influence of the carbon nanotubes on the reactions has not been discussed so far. In comparison, for silica nanospheres their influence has been previously studied, where the success of the grafting polymerization was discussed as a function of the sphere diameter,⁴³ and the characteristics of the initiator groups attached at the surface.⁴⁴ The characteristics of the carbon nanotubes and how they could affect the surface functionalization has not been discussed until now, mainly because they vary depending on the supplier and the method of synthesis. Here, a comparison between two commercially available multiwall carbon nanotubes (MWCNTs) subjected to functionalization reactions and their influence on the *grafting from* of styrene is presented for the first time. In this work, a multistep functionalization procedure was chosen, where the carbon nanotubes have been characterized after each reaction step as a function of their characteristics and behavior after each reaction. Finally, the factor that controls the content of grafted polystyrene has been tuned and compared for the studied nanoparticles.

EXPERIMENTAL

Materials

MWCNTs were obtained from Bayer MaterialScience® (Baytubes, purity >95%, internal mean diameter = 4 nm, external mean diameter = 13–16 nm, length = 1–10 μm, number of walls = 3–15, denoted MWCNT_{BMS}⁹⁵) and FutureCarbon GmbH (purity >99%, internal mean diameter = 6 nm, external mean diameter = 15 nm, length = 10–50 μm, number of walls = 10, denoted MWCNT_{FC}⁹⁹). In the notation used here, that is, MWCNT_x^y, the subscript x indicates the MWCNT manufacturer and the superscript y the carbon purity of the nanotube. Nitric acid (HNO₃, 65% v/v), thionyl chloride (SOCl₂, ≥99%), ethylene glycol (EG), poly(ethylene glycol) of 200 g mol⁻¹ and 400 g mol⁻¹ (PEG₂₀₀ and PEG₄₀₀, respectively), 2-bromo-2-methylpropionyl bromide (2BriBr, 99%), triethyl amine (Et₃N, ≥99.5%), dimethyl amino pyridine (DMAP, 97%), copper(I) bromide (CuBr, 99%), *N,N,N',N'*-pentamethyl diethylenetriamine (PMDETA, 97%), tetrahydrofuran (THF), and anisole were used as received. Chloroform (CHCl₃) and styrene (S) were dried over calcium hydride

(CaH₂) and distilled before use. All the reagents were purchased from Aldrich.

Oxidation of the MWCNTs

In a typical experiment, 1 g of MWCNT_x^y was dispersed in 40 mL of HNO₃ in a round bottom flask. After 30 min of sonication at room temperature, the system was heated at 65 °C for 48 h under continuous stirring. The dispersion was then filtered and washed with copious amounts of distilled water until the pH reached constant values. Finally, the oxidized carbon nanotubes were dried at 60 °C under vacuum for 72 h.

Acid to Acid Chloride Conversion and Esterification I: Glycol Spacer

The oxidized MWCNTs (400 mg) were chlorinated in the presence of SOCl₂ (28 mL) for 24 h at 65 °C. After reaction, the dispersion was generously washed with THF, filtered, and dried at ambient temperature overnight. The acyl or alkyl chloride functionalized MWCNTs were heated with different amounts of EG or PEG at 120 °C for 48 h. The hydroxyl decorated carbon nanotubes were passed through a Teflon® membrane (0.2 μm pore size), washed with THF, and dried for 48 h at ambient temperature. The products were repeatedly dispersed, filtered, and dried. Details of the reaction can be appreciated in Table 1.

Anchoring of Initiator Groups

The functionalization with initiator groups suitable for the grafting of styrene was done following the work of Kong et al.³¹ In a typical reaction (see Table 1, entry 1), hydroxyl decorated MWCNTs (150 mg) were dispersed in CHCl₃ (19.2 mL) with a catalytic amount of Et₃N (228 μL) and DMAP (29 μL). The system was immersed in a sonication bath for 10 min under Ar flow. Then, the dispersion was cooled down in an ice bath and thrice vacuum filled with Ar. A diluted solution of 2BriBr (210 μL) in CHCl₃ (2.4 mL) was added drop wise for ~1 h. The reaction was kept in the ice bath for 3 h and after that at ambient temperature for 48 h. After reaction, the carbon nanotubes grafted with initiator groups were passed through a Teflon® membrane and washed with copious amounts of CHCl₃. The carbon nanotubes were redispersed, filtered, and dried three times. Elemental analysis (atomic %): C, 92.25; H, 0.49; Br, 0.57. The notation used is MWCNT_x^y-Br, where the Br indicates the anchoring of the initiator. Details of the reaction can be appreciated also in Table 1.

Grafting from Styrene Under Atom Transfer Radical Polymerization

In a Schlenk tube, MWCNT_{BMS}⁹⁵-Br or MWCNT_{FC}⁹⁹-Br, 0.7 mol % of CuBr (respect to the monomer) and S were dispersed in anisole (4 vol % respect to the monomer) under Ar flow for 60 min. After three freeze-pump-thawed cycles, 0.7 mol % of PMDETA (respect to the monomer) was added and the tube transferred into an oil bath at 90 °C. When the reaction was completed, the system was diluted in toluene and precipitated in methanol. The precipitated sample was filtered using a Teflon® membrane and dried for 48 h. After drying, the polymer grafted carbon nanotubes were again

TABLE 1 Experimental Conditions Used for the Esterification with Glycols and 2BrBr of MWCNT_{BMS}⁹⁵ and MWCNT_{FC}⁹⁹

Entry	Sample	Esterification I (EG or PEG) ^a		Esterification II Initiator Anchoring		
		Type ^a	[Glycol] (mol g ⁻¹) ^b	[2BrBr] (μL mg ⁻¹) ^c	[MWCNT] (mg mL ⁻¹) ^d	[Br] (mmol g ⁻¹) ^e
1	MWCNT _{FC} ⁹⁹ -Br ¹	EG	1.3	1.4	6.5	0.07
2	MWCNT _{FC} ⁹⁹ -Br ²	EG	1.3	2.7	6.9	0.13
3	MWCNT _{FC} ⁹⁹ -Br ³	PEG ₂₀₀	1.3	2.7	6.9	0.22
4	MWCNT _{FC} ⁹⁹ -Br ⁴	PEG ₄₀₀	1.3	5.4	6.9	0.24
5	MWCNT _{FC} ⁹⁹ -Br ⁵	PEG ₄₀₀	0.6	2.7	6.0	0.04
6	MWCNT _{FC} ⁹⁹ -Br ⁶	PEG ₄₀₀	1.3	2.7	6.9	0.14
7	MWCNT _{FC} ⁹⁹ -Br ⁷	PEG ₂₀₀	1.3	2.7	6.9	0.08
8	MWCNT _{BMS} ⁹⁵ -Br ¹	EG	1.3	1.4	15.6	0.08
9	MWCNT _{BMS} ⁹⁵ -Br ²	EG	1.3	2.7	16.0	0.62
10	MWCNT _{BMS} ⁹⁵ -Br ³	PEG ₂₀₀	1.3	1.4	15.7	0.36
11	MWCNT _{BMS} ⁹⁵ -Br ⁴	PEG ₄₀₀	1.3	1.4	15.6	0.15

^a EG: ethylene glycol; PEG₂₀₀ and PEG₄₀₀: poly(ethylene glycol) of average number molecular weight of 200 g mol⁻¹ and 400 g mol⁻¹, respectively.

^b Relation between mole of ethylene glycol or poly(ethylene glycol) and MWCNT (g) used.

^c Concentration of 2-bromo-2-methylpropionyl bromide (2BrBr, μL) respect to MWCNT (mg).

^d Relation between MWCNT (mg) and CHCl₃ (mL) used during the reaction.

^e [Br] determined by elemental analysis.

dispersed in CHCl₃ for 24 h, filtered, and dried. This procedure was repeated until no traces of polymer were collected from the filtered solution by precipitation in methanol. The polystyrene grafted carbon nanotubes are denoted PS_w^qMWNCNT_x^y, where the subscript *w* represents the weight percent of polystyrene grafted, and the superscript *q* represents the molecular weight of the grafted polymer (in kg mol⁻¹).

Characterization

Fourier transform infrared spectra (FTIR) were conducted on a Bruker Equinox 55. The samples were dispersed in potassium bromide (KBr) and compressed as disks. Thermal gravimetric analyses (TGA) were carried out on a Netzsch TG209 F1 Iris under constant Ar flow, at a rate of 20 °C min⁻¹. Scanning electron microscopy (SEM) studies were performed on a Zeiss LEO Gemini 1550VP (1 kV). Samples were carefully glued on conductive tape and sputtered with a fine Au/Pd layer. Transmission electron microscopy (TEM) observations were done on a Fei Tecnai G² F20 (200 kV). The samples were dispersed in CHCl₃ or THF and dropped on grids. Scanning force microscopy (SFM) images were taken on a "Veeco" MultimodeTM AFM (NanoScope IV controller) operating in tapping mode at ambient temperature. Silicon TM AFM tips (model MPP-12100) with a free resonance of 150 kHz and spring constant of 5 N m⁻¹ were used. The carbon nanotubes were dispersed in CHCl₃ (5% w/v) for 24 h at ambient temperature. After 24 h, the dispersions were homogenized for 1 min with an ultrasonic probe (Bandelin SONOPULS[®], frequency = 20 kHz) and one drop (5 μL) was placed on a cleaned polished silicon wafer. The silicon wafers were previously cleaned in a water-saturated UV-ozone atmosphere for at least 24 h. The viscosities of the carbon nanotubes dispersions before and after the oxidation reactions were measured using a Brookfield R/S rhe-

ometer. The experiments were performed at a constant rate (500 s⁻¹) for 2 min in a plate/plate geometry (C75-1). The carbon nanotubes (1% w/v) were dispersed in ethylene glycol for 24 h at ambient temperature. Before the measurements, the dispersions were then homogenized for 5 min with an ultrasonic probe (Bandelin SONOPULS[®], 20 kHz, amplitude = 50%).

RESULTS AND DISCUSSION

Oxidation of the MWCNTs

The scheme of the modification of MWCNTs is shown in Figure 1. A similar procedure has been adopted previously by other groups.^{31,39,42} The reactions that lead to anchoring of initiator groups able to initiate the polymerization of styrene are based on well-known organic chemistry reactions. The first step implies the oxidation of the pristine MWCNTs with HNO₃. The FTIR spectra of the pristine and oxidized MWCNTs can be appreciated in Figure 2. Many authors attribute the signals between 1650 cm⁻¹ and 1540 cm⁻¹ to the C=C stretching mode of the aromatic ring.^{45–47} Around 1460 cm⁻¹, the C–H bending alkyl vibrations can be observed. Besides these signals, other features in the pristine MWCNTs are interesting. A clear C–H stretching vibration in the vicinity of a carboxylic group (~1430 cm⁻¹) and a rocking vibration (~1380 cm⁻¹) could indicate the presence of quinones and aldehydes, respectively. The C=O vibration in both cases might be overlapped with the stretching mode of the aromatics. Another feature around 1160 cm⁻¹ is related with the C–O–C stretching from aromatic esters. The described bands show that the MWCNT skeleton is not just composed of crystalline graphene layers but have also defects coming from the synthesis or the rest of catalyst. These imperfections might have consequences on the properties of the MWCNTs, however, they may also represent an




FIGURE 1 Schematic representation of the surface modification reactions carried out on MWCNTs.

advantage if reactions on these “weak points” can improve the dispersion of the MWCNTs in solvents or polymers. After oxidation, a C=O stretching vibration related with esters is easily identified for the MWCNT_{FC}⁹⁹ (1710 cm⁻¹).⁴⁸ In the case of the MWCNT_{BMS}⁹⁵, the C=O vibration is located at a lower wavenumber (broad peak) that would indicate the presence of carboxylic acid,⁴⁹ and a relative increase in the intensity at 1575 cm⁻¹ is observed. This signal might be related with a keto-enol tautomerism. One interesting change due to the oxidation reaction is the appearance of a strong signal in MWCNTs from both suppliers around 1380 cm⁻¹. The assignment could be related again with the C—H rocking vibration of aldehydes, but this would imply a stronger signal at around 1700–1650 cm⁻¹, which is not observed. A second and more probable explanation could be the formation of phenols which present such strong signal due to the combination of O—H and C—O deformation vibrations. The oxidation favors the formation of phenol groups in MWCNTs from both suppliers; ester groups seem more favorable in case of the MWCNT_{FC}⁹⁹, whereas in the case of the MWCNT_{BMS}⁹⁵ the presence of ketones and carboxylic acid groups is predominant. The formation of carbonyl and hydroxyl groups at MWCNTs after the reaction with HNO₃ (and other carbonaceous fibers)⁵⁰ has been widely described by other groups using different characterization techniques,^{48,51–55} where a qualitative increase in FTIR signal intensity in the region of the carbonyl or hydroxyl groups is associated to a discrete increase on the concentration of oxygen atoms at the surface of the carbon nanotubes. This increment has proven to be satisfactory for further reactions of the carbon nanotubes with small molecules⁵¹ or with polymer chains.^{52,56}

It is known that, to obtain high concentrations of carboxylic acid groups (or their derivatives) on carbon nanotubes, treatments more aggressive than the one used here are required, such as combinations of HNO₃ with stronger acids (like sul-

furic acid) or air oxidation at high temperatures.^{50,54,57,58} Such treatments lead to the destruction of the graphitic structure, reduction on the carbon nanotube length, disaggregation of nanotube bundles, and improvement of the dispersion of the carbon nanotubes in organic solvents. The aim of the chosen acid treatment was to preserve the carbon nanotubes by attacking defects already present in the structure and to dissolve the catalysts and the synthesis by-products (e.g., amorphous carbon), without cutting the length of the nanotubes or loosing any of the walls.⁴⁸ Figure 3 shows transmission electron microscope images of the pristine and oxidized MWCNT_{BMS}⁹⁵. The rest of catalyst or amorphous carbon is evidenced in Figure 3(a) on the left side of the




FIGURE 2 Fourier transform infrared spectra of MWCNTs from different sources before and after the oxidation reaction: (a) pristine and (b) oxidized MWCNT_{BMS}⁹⁵, (c) pristine and (d) oxidized MWCNT_{FC}⁹⁹.




FIGURE 3 Transmission electron micrographs of (a) pristine and (b) oxidized MWCNT_{BMS}⁹⁵. Scale bar = 100 nm, insert = 10 nm.

image. These amorphous aggregates were not found on any of the images after the treatment with HNO₃. Zhang et al.⁵³ also reported the decomposition of the catalyst or amorphous carbon under comparable reaction conditions. In addition, TEM images show that the numbers of walls are preserved (see inserts in Fig. 3). In the case of the MWCNT_{FC}⁹⁹, catalyst residues were not appreciated in the pristine sample during the observations (results not shown). Some pioneering works have proposed correlation models between the nanotubes length against reaction time for different oxidation systems on SWCNT.^{57,59} Unfortunately, these results cannot be directly correlated to the ones presented here because the oxidation depends on factors related with the number of walls, purity, synthesis process, and source of the carbon nanotubes.⁵⁰ A systematic study is required to understand the effect of the oxidation on identical MWCNTs exposed to mild and aggressive oxidation conditions.

Acid to Acid Chloride Conversion and Esterification I: Glycol Spacer

Further reaction between the oxidized carbon nanotubes and thionyl chloride leads to the formation of alkyl and acyl chloride groups. Experimental and theoretical evidences have shown that carbon nanotubes could also absorb thionyl chloride and the presence of moisture gives rise to by-products that could form C—Cl bonds on the structural defects.⁶⁰ The acyl or alkyl chloride groups are highly reactive and can further form esters or ethers, respectively, in the presence of an alcohol. Glycols of different molecular weights were used in this work. These α,ω -dihydroxy-functionalized telechelics will be used as spacers between the carbon nanotubes and the initiator moieties necessary for the *grafting from* of styrene. While increasing the glycol molecular weight from 62 g mol⁻¹ (ethylene glycol) to 400 g mol⁻¹, the weight loss between 100 °C and 500 °C (determined by thermal gravimetric analysis) increases from ~5% to more than 12%, in

the case of the MWCNT_{FC}⁹⁹ and from 5 to 18% in the case of the MWCNT_{BMS}⁹⁵, as can be appreciated in Figure 4.

The MWCNT source also has an effect on the reaction product; since it was observed that the grafting content of ethylene glycol on MWCNT_{BMS}⁹⁵ is almost the double of the content obtained on MWCNT_{FC}⁹⁹. On the one hand, the concentration of reactive groups on MWCNT_{BMS}⁹⁵ and MWCNT_{FC}⁹⁹ could explain the difference in grafting efficiency; however, the characterization techniques available for the determination of the concentration are still not reliable. On the other hand, the difference in grafting could also be attributed to the differences in the dimension of the carbon nanotube and the quality of the dispersion during the reaction. The contour length of the pristine and the oxidized MWCNTs were examined by scanning force microscopy (SFM). The distribution of the MWCNTs contour lengths can




FIGURE 4 Glycol grafting content (left axes, filled symbols) and concentration of hydroxyl groups (right axes, open symbols) versus glycol molecular weight for MWCNT_{BMS}⁹⁵ (●, ○) and MWCNT_{FC}⁹⁹ (■, □).




FIGURE 5 Carbon nanotube length distribution (nm) of (a) pristine MWCNTs and (b) oxidized MWCNTs, calculated from SFM phase images. Filled bars (black) correspond to $\text{MWCNT}_{\text{BMS}}^{95}$ and contour bars (orange) correspond to $\text{MWCNT}_{\text{FC}}^{99}$.

be appreciated in Figure 5. Approximately one hundred independent length measurements were done on each case, from different positions on several silicon wafers.

Although the reported information in the technical data sheets of the products indicates that the $\text{MWCNT}_{\text{BMS}}^{95}$ are on average shorter than the $\text{MWCNT}_{\text{FC}}^{99}$, the results in Figure 5 show the contrary. The length distributions of the pristine carbon nanotubes are 370 ± 60 nm and 225 ± 30 nm, for $\text{MWCNT}_{\text{BMS}}^{95}$ and $\text{MWCNT}_{\text{FC}}^{99}$, respectively. It has to be pointed out that just the carbon nanotubes dispersed on the silicon wafers were taken into account for the measurements, longer carbon nanotubes than the ones measured could not be identified on any of the images taken. Longer carbon nanotubes are probably present on the samples included inside the aggregates. The ultrasonic probe was used to disaggregate the carbon nanotubes before dropping

the dispersion on the silicon wafer. The ultrasonic treatment could induce the cleavage of the carbon nanotubes, especially if the graphitic structure has defects. In any case, comparison can be made between the $\text{MWCNT}_{\text{BMS}}^{95}$ and the $\text{MWCNT}_{\text{FC}}^{99}$ because the carbon nanotubes were dispersed under the same conditions. After the acid treatment, the population of carbon nanotubes with shorter lengths decreases in both cases, which evidences that the HNO_3 is also able to disrupt the carbon nanotubes. The carbon nanotube length distribution is slightly shifted to higher values after the acid treatment, which could indicate that the reaction unbundles longer carbon nanotubes from the aggregates.

Although the SFM measurements give an indication of the length of the isolate carbon nanotubes, the viscosity of the dispersion of carbon nanotubes could give evidences of the state of aggregation of the nanoparticles. Table 2 shows the viscosity of the dispersion of MWCNTs in ethylene glycol before and after the acid treatment. The viscosity of the MWCNTs dispersions in ethylene glycol increases after the acid treatment. The viscosity of the dispersion of the $\text{MWCNT}_{\text{FC}}^{99}$ is more than two times higher than the $\text{MWCNT}_{\text{BMS}}^{95}$. This difference could be associated to the structure of the aggregates. It is known that the synthesis process of the $\text{MWCNT}_{\text{BMS}}^{95}$ leads to the formation of highly bundled nanoparticles, whereas the synthesis of the $\text{MWCNT}_{\text{FC}}^{99}$ leads to more loose aggregates. The results obtained could indicate that the highly aggregated MWCNTs have a minor influence on the viscosity of the dispersion whereas, on the contrary, the loose aggregate structure increases the relative viscosity of the dispersion. The increase in viscosity can be associated with the disaggregation of the MWCNTs that leads to the presence of longer carbon nanotubes or looser aggregates in the dispersion. It has to be mentioned that the error on the measurements increases for the oxidized carbon nanotubes. This might indicate that the treatment on the nanoparticles depends on the state of the particle in the dispersion and the experimental conditions used. For example, it could be expected that the HNO_3 oxidize faster nanoparticles with more structural defects or might easily unbundles loose agglomerate than compact ones. Also, the variation of the conditions of the acid treatment could lead to the homogenization of the nanoparticles (e.g., dispersion of isolate particles or homogeneous size of aggregates), however, the conditions used on this work were meant to evaluate the difference between carbon

TABLE 2 Viscosity of the Dispersion of MWCNTs in Ethylene Glycol (1% w/v)

Sample	Description	η (MPa s)
Ethylene glycol		17 ± 1
$\text{MWCNT}_{\text{BMS}}^{95}$	Pristine	63 ± 1
	Oxidized	75 ± 10
$\text{MWCNT}_{\text{FC}}^{99}$	Pristine	154 ± 1
	Oxidized	280 ± 70

Values obtained at 500 s^{-1} .

nanotubes. Nevertheless, the mean values of the viscosities obtained after the acid treatment can be very well differentiated and increases $\sim 20\%$ and 80% , in the case of the $\text{MWCNT}_{\text{BMS}}^{95}$ and $\text{MWCNT}_{\text{FC}}^{99}$, respectively. Under the previous assumptions, the oxidation reaction using HNO_3 unbundles more efficiently the $\text{MWCNT}_{\text{FC}}^{99}$ compared to the $\text{MWCNT}_{\text{BMS}}^{95}$. It is expected then that the low viscosity of the dispersion containing the acyl and alkyl chloride functionalized $\text{MWCNT}_{\text{BMS}}^{95}$ favors the grafting reaction more than the dispersion containing the acyl chloride functionalized $\text{MWCNT}_{\text{FC}}^{99}$. However, the relative low increase in viscosity of the dispersion of $\text{MWCNT}_{\text{BMS}}^{95}$ after the oxidation reaction might indicate that the disaggregation of these carbon nanotubes during the functionalization reactions is more difficult compared with the $\text{MWCNT}_{\text{FC}}^{99}$, as a consequence, the functionalization of the $\text{MWCNT}_{\text{BMS}}^{95}$ probably takes place rather on the surface of aggregates than on isolated carbon nanotubes.

Previous works have shown that noncovalent adsorption of poly(ethylene glycol) may occur during grafting.^{21,61} Although the reactions have been performed at high concentration of the glycols and in the absence of solvent, the poly(ethylene glycol)s used have relative low molecular weights, and due to the thorough washing processes no or negligible adsorption should be present.⁶² From the difference in weight loss between the MWCNTs after the acid treatment and after the *grafting onto* reaction of the glycols and the molecular weight of the glycols, one can estimate the concentration of hydroxyl groups ([OH]). This value is presented in the right axis in Figure 4. In the case of the $\text{MWCNT}_{\text{BMS}}^{95}$, the [OH] decreases dramatically when the glycol molecular weight increases. This suggests that even when the grafting content of the glycols increases with the molecular weight, the relative concentration of terminal hydroxyl group decreases. In the case of $\text{MWCNT}_{\text{FC}}^{99}$, the [OH] is lower compared with the $\text{MWCNT}_{\text{BMS}}^{95}$ and independent of the glycol used, in the range of molecular weights used in the present study. Then, the MWCNTs can be more easily dispersed in organic solvent because of the longer grafted chains, but have fewer functional groups available for the successive reactions.

The difference in [OH] between the $\text{MWCNT}_{\text{BMS}}^{95}$ and the $\text{MWCNT}_{\text{FC}}^{99}$ can be attributed to different factors. The concentration of acyl (or alkyl) chloride groups present on the $\text{MWCNT}_{\text{BMS}}^{95}$ and the $\text{MWCNT}_{\text{FC}}^{99}$ could be responsible for the difference of the grafting onto of the glycols, unfortunately, these differences are difficult to quantify using any of the existing characterization methods. The contour length of the MWCNTs estimated by the SFM measurements (Fig. 5) showed no marked difference between the dispersed nanoparticles that could infer any influence on the reaction efficiency.⁶³ However, the viscosity of the dispersion containing the MWCNTs seems to play a role on the grafting efficiency. The low viscosity of the dispersion of $\text{MWCNT}_{\text{BMS}}^{95}$ during the reaction might increase the accessibility of the hydroxyl groups to the acyl (or alkyl) chloride groups compared with the $\text{MWCNT}_{\text{FC}}^{99}$.




FIGURE 6 Fourier transform infrared spectra of MWCNTs after different sequential modification steps (a) PEG_{400} grafted $\text{MWCNT}_{\text{FC}}^{99}$, (b) $\text{MWCNT}_{\text{FC}}^{99}\text{-Br}^4$, (c) $\text{PS}_{44}\text{MWCNT}_{\text{FC}}^{99}$, and (d) $\text{PS}_{85}\text{MWCNT}_{\text{FC}}^{99}$.

A representative infrared spectrum of the MWCNTs after grafting of PEG_{400} is presented in Figure 6. Even though the symmetric C—H stretching of the methylene groups is difficult to identify due to the alkyl groups of the MWCNTs, the C—H stretching deformations at $\sim 1420\text{ cm}^{-1}$ and the C—O—C stretching deformation at 880 cm^{-1} are evident. These indicate the success of the reaction. An asymmetric C—H deformation is observed for this sample at 2970 cm^{-1} , which is only observed clearly in MWCNTs modified with poly(ethylene glycol) of 400 g mol^{-1} . The occurrence of any noncovalent interaction can be ruled out, since there is no evidence of the methylene groups related with nongrafted poly(ethylene glycol) at 2890 cm^{-1} .⁵⁶

Esterification II: ATRP Initiator

The infrared spectrum after anchoring the initiator groups for the controlled radical polymerization to the MWCNTs is also shown in Figure 6. The carboxylic acid stretching vibration located at 1740 cm^{-1} indicates the successful grafting of the initiator. Table 1 shows the initiator concentration estimated by elemental analysis. The reaction conditions were optimized to obtain comparable results of anchored initiator concentration [Br] for the MWCNTs from both used sources as a function of the 2BrBr concentration, as can be seen in Table 1 (entries 1 and 8). For this reason, the esterification reaction on the hydroxyl modified $\text{MWCNT}_{\text{FC}}^{99}$ was carried out at higher dilutions. Figure 7 shows the distribution of the average contour lengths of two MWCNTs with a comparable concentration of initiator. The length distribution of the MWCNTs shorter than $\sim 1\text{ }\mu\text{m}$ does not appreciably change with respect to the values obtained after oxidation, however, longer carbon nanotubes could be found on the samples after the esterification, which confirms the assumption that the functionalization reaction helps to disaggregate the MWCNTs. In addition, longer carbon nanotubes were found in the sample $\text{MWCNT}_{\text{FC}}^{99}\text{-Br}^6$ than in the sample




FIGURE 7 Length distribution (nm) for MWCNTs after the grafting of the ATRP initiator. [Color figure can be viewed in the online issue, which is available at www.interscience.wiley.com.]

MWCNT_{BMS}⁹⁵-Br⁴. This could also be an indication that the MWCNT_{FC}⁹⁹ are effectively longer than the MWCNT_{BMS}⁹⁵ and that they are easier to disentangle due to the looseness of the aggregates.

In the case of the ethylene glycol modified MWCNTs, the anchored initiator concentrations shown in Table 1 for MWCNT_{BMS}⁹⁵ and MWCNT_{FC}⁹⁹ are comparable when low 2BrBr concentrations are used. By increasing the concentration of 2BrBr, the [Br] increased in both cases, though it is five times higher for the MWCNT_{BMS}⁹⁵ (0.62 mmol g⁻¹) than for MWCNT_{FC}⁹⁹ (0.13 mmol g⁻¹). To the authors' knowledge, the [Br] obtained for the MWCNT_{BMS}⁹⁵ under the described conditions is the highest value found on the grafting of initiator for surface initiated radical polymerizations on carbon nanotubes.^{8,27,28,30,31,33,38,42,64,65}

The use of poly(ethylene glycol) spacers also affects the anchoring of the initiator. Under the same experimental conditions, the highest [Br] concentration is found on the MWCNTs grafted with PEG₂₀₀, followed by PEG₄₀₀ and EG. Two effects are involved in this behavior. On the one hand, it was previously discussed that the concentration of hydroxyl groups decreases if the molecular weight of the spacer increases (shown in Fig. 4) in the case of the MWCNT_{BMS}⁹⁵, whereas the concentration is rather low in the case of the MWCNT_{FC}⁹⁹. On the other hand, the stability of the carbon nanotube dispersions in organic solvents improves with the increment in spacer chain length, as well as the mobility of the hydroxyl end-groups. Therefore, as the molecular weight of the spacer increases, the esterification reaction takes place under conditions that resemble more those of a homogeneous reaction, which increases the feasibility of the reaction. Consequently, the observed tendency results from the competition between these two effects: the lower [Br] on the PEG₄₀₀ modified carbon nanotubes is assumed to be due to

lower hydroxyl concentration, whereas the lower [Br] on the EG modified MWCNTs is attributed to the heterogeneity of the reaction.

ATR Polymerization

Styrene (S) was chosen as a monomer for the *grafting from* the initiator anchored MWCNTs under controlled radical polymerization conditions. The results are summarized in Table 3. The decoration of carbon nanotubes and other substrates using this monomer has been well documented.^{18,66–68} Styrene is able to solubilize its polymer, shows slower polymerization rate than other available monomers [i.e., meth (acrylates)],⁶⁹ and thermally polymerizes under the experimental conditions described.⁴³ These characteristics allow the study of the grafting without nonbonded initiators (free initiator), or deactivator (e.g., CuBr₂)⁷⁰ and with reduced quantity of solvent, which may complicate the analysis. In the styrene *grafting from* polymerization reactions, some free chains are always generated in solution, which promotes the termination in the reaction medium rather than within the active species attached to the substrate, and supports a controlled polymer growth in the sense that crosslinking between different nanoparticles will unlikely occur. This has been described previously on polymerization from silica nanostructures.^{43,71,72}

The infrared spectra of polystyrene (PS) surface grafted MWCNTs under different reaction conditions are also shown in Figure 6. The bands corresponding to the polymer are clearly evident when the polymer content is over 70 wt %, for example, the C–H stretching vibrations between 3100 and 3000 cm⁻¹, the ring stretching vibration at ~1600 cm⁻¹, the overtones between 2000 and 1660 cm⁻¹, and the C–H out-of-plane vibration and ring out-of-plane deformation located at 760 cm⁻¹ and 690 cm⁻¹, respectively. Nuclear magnetic resonance (¹H NMR) measurements also support the presence of the grafted PS at the MWCNTs (results not shown). High polymer content is required also for the ¹H NMR measurements, because the magnetization of the MWCNT promotes first the aggregation and then the sedimentation of the nanoparticles during the measurement.

Scanning electron micrographs are presented for a representative group of samples in Figure 8. Qualitatively, the PS grafted MWCNTs are similar, independent of the source (MWCNT_{BMS}⁹⁵ or MWCNT_{FC}⁹⁹). The scanning electron micrographs show that if the polymer content is below 50 wt %, the aspect ratio of the MWCNTs does not discern from the one of unmodified filler. When the polymer content is lower than ~20 wt % it is possible to analyze the sample without being sputtered, which indicates that the MWCNTs preserve their electrical conductivity characteristics after modification. This might represent an advantage in applications like conducting polymer films, where the preservation of the electrical conductivity in the nanofillers is required and a relatively good dispersion ensures a low MWCNTs percolation threshold in the nanocomposite. The samples with polymer content higher than 50 wt % present a more homogeneous structure, where the nanotubes look like they are embedded in

TABLE 3 Conditions and Polymer Content on the Styrene *Grafting from* Reaction on MWCNT_{BMS}⁹⁵ and MWCNT_{FC}⁹⁹

Entry	Sample	Source	St ^a		<i>t</i> _{rxn} (h)	<i>f</i> _{PS} ^b (wt %)	<i>M</i> _{n,TGA} ^c (kg mol ⁻¹)	<i>T</i> _d ^d (°C)
			(wt %)	(mol %)				
1	PS ₁₉ ³ MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ¹	30	4,000	20.0	18.8	3	352
2	PS ₉ ¹ MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ²	30	2,200	20.1	9.0	1	272
3	PS ₁₁ ¹ MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ³	30	1,300	20.2	11.4	1	344
4	PS ₄₄ ³ MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ⁴	30	1,200	20.1	44.1	3	375
5	PS ₈₅ ²⁴ MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ⁴	120	4,700	19.4	85.2	24	410
6	PS ₂₈ ¹⁰ MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ⁵	30	6,700	23.7	28.1	10	361
7	PS ₂₂ ² MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ⁶	30	2,100	20.1	22.0	2	348
8	PS ₁₃ ² MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ⁷	30	3,800	20.0	12.8	2	335
9	PS ₂₃ ⁴ MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ⁷	60	7,700	20.0	22.5	4	356
10	PS ₃₁ ⁶ MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ⁷	120	15,400	20.1	30.6	6	371
11	PS ₃₂ ⁶ MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ⁷	120	15,400	20.2	32.0	6	370
12	PS ₁₁ ² MWCNT _{FC} ⁹⁹	MWCNT _{FC} ⁹⁹ -Br ⁷	30	3,800	20.2	11.1	2	331
13	PS ₃₄ ⁷ MWCNT _{BMS} ⁹⁵	MWCNT _{BMS} ⁹⁵ -Br ¹	30	3,400	21.0	34.4	7	393
14	PS ₄₃ ¹⁰ MWCNT _{BMS} ⁹⁵	MWCNT _{BMS} ⁹⁵ -Br ¹	30	3,400	26.0	43.4	10	394
15	PS ₄₇ ¹¹ MWCNT _{BMS} ⁹⁵	MWCNT _{BMS} ⁹⁵ -Br ¹	60	6,800	20.0	47.1	11	396
16	PS ₉₁ ²⁰ MWCNT _{BMS} ⁹⁵	MWCNT _{BMS} ⁹⁵ -Br ²	30	430	20.0	91.3	20	420
17	PS ₈₅ ⁹ MWCNT _{BMS} ⁹⁵	MWCNT _{BMS} ⁹⁵ -Br ²	60	870	18.0	84.7	9	418
18	PS ₇₀ ⁴ MWCNT _{BMS} ⁹⁵	MWCNT _{BMS} ⁹⁵ -Br ²	60	870	7.0	70.4	4	406
19	PS ₈₆ ¹⁷ MWCNT _{BMS} ⁹⁵	MWCNT _{BMS} ⁹⁵ -Br ³	30	740	20.0	85.8	17	410
20	PS ₄₉ ⁷ MWCNT _{BMS} ⁹⁵	MWCNT _{BMS} ⁹⁵ -Br ⁴	30	2,900	20.1	49.1	7	387

^a Weight and mole percent of styrene respect to the MWCNTs.^b Polystyrene grafting content.^c Average molecular weight of the grafted polystyrene, calculated from TGA.²⁸^d Decomposition onset temperature calculated from TGA data.

polymer. This effect has been previously observed by other groups.^{31,42}

From the transmission electron micrographs (shown as inserts in Fig. 8) one could assume that the graphitic-like structure of the nanotubes is preserved after all the functionalization reactions. The grafting of polymer takes place along the MWCNTs, not just on their tips, where the highest initiator concentration is supposed to be due to a major concentration of defects. However, as previously discussed, the infrared analysis on the pristine MWCNTs shows that defects are present along the structure. These potentially reactive locations enable the distribution of initiator groups along the MWCNTs.

The quantity of polymer grafted on the MWCNTs from both sources could be controlled by adjusting the weight ratio between the monomer and the nanofiller as a function of the initiator concentration. The results are summarized in Table 3. The weight ratios used in this work are comparable to the experimental conditions presented in other studies,^{40,42} although there is lack of agreement throughout the literature.^{22,30,31}

The results presented in Table 3 show that, in general, higher polymer content is obtained for the initiator anchored MWCNT_{BMS}⁹⁵ than for MWCNT_{FC}⁹⁹, when the grafting takes place under similar reaction conditions. The observed discrepancies are believed to depend on the intrinsic character-

istics of the carbon nanotubes used here. For example, in the case of the samples PS₁₉³MWCNT_{FC}⁹⁹ and PS₃₄⁷MWCNT_{BMS}⁹⁵ (entries 1 and 13), the polymer content for MWCNT_{BMS}⁹⁵ is almost twice of the one obtained for MWCNT_{FC}⁹⁹ under comparable reaction conditions. The interplay of two factors explains this difference. First, the distribution of anchored initiator along the MWCNTs varies with the location of the structural defects, which is predetermined from the carbon nanotubes synthesis. If the initiator moieties are close to each other, coupling or deactivation reactions will compete with the propagation of the living chain. This could be related with the critical conversion of coupling (CCC),⁸ where not just the electronic properties of the carbon nanotube may affect the polymerization, but also the location of the growing chain could induce coupling reactions. Second, as discussed before, the viscosity of the dispersions containing MWCNT_{BMS}⁹⁵ is lower than the dispersion prepared with the MWCNT_{FC}⁹⁹ due to the presence of relative compact aggregates and shorter carbon nanotubes. For this reason, the overall polymerization rate could be higher or a major reaction yield could be reached with the MWCNT_{BMS}⁹⁵-Br.

If the monomer to MWCNT weight ratio is kept constant, the amount of grafted polymer increases with the concentration of initiator anchored on MWCNT_{BMS}⁹⁵ and decreases for the initiator anchored on MWCNT_{FC}⁹⁹. The competition between polymer conversion, initiator concentration, and dispersion of the MWCNTs might explain these results. Short polymer




FIGURE 8 Scanning and transmission (inserts) electron micrographs of MWCNT grafted with PS, synthesized under the conditions indicated in Table 3. (a) $\text{PS}_9^1\text{MWCNT}_{\text{FC}}^{99}$, (b) $\text{PS}_{44}^3\text{MWCNT}_{\text{FC}}^{99}$, (c) $\text{PS}_{70}^4\text{MWCNT}_{\text{BMS}}^{95}$, and (d) $\text{PS}_{91}^{20}\text{MWCNT}_{\text{BMS}}^{95}$. TEM scale bar = 20 nm.

chains grafted from apparent shorter and more aggregated carbon nanotubes increase less dramatically the viscosity during the grafting from polymerization than apparent longer and less aggregated carbon nanotubes, as is the case of $\text{MWCNT}_{\text{FC}}^{99}\text{-Br}$. As a result, the grafting reactions on $\text{MWCNT}_{\text{BMS}}^{95}\text{-Br}$ take place probably for prolonged times before the increase in viscosity decreases the propagation rate of the reaction, and this results in higher polymer contents. This behavior has been previously observed in the literature, although a clear correlation with the results presented here is not possible since no data is given regarding the length of the carbon nanotubes.⁴²

The dispersion plays an important role on all the carbon nanotubes functionalization reactions. Before grafting, both $\text{MWCNT}_{\text{BMS}}^{95}\text{-Br}$ and $\text{MWCNT}_{\text{FC}}^{99}\text{-Br}$ are dispersed in the monomer. To obtain optically homogeneous carbon nanotube dispersions before the start of the polymerization, the minimum feasible monomer-to-nanofiller weight ratio found was 30 to 1; lower ratios lead to highly viscous dispersions before the start of the reaction. In the case of the $\text{MWCNT}_{\text{FC}}^{99}$, the variation of the monomer-to-nanofiller weight ratio influences the content of grafted polymer. For example, increasing four times the monomer concentration with respect to $\text{MWCNT}_{\text{FC}}^{99}\text{-Br}$ ⁷ (Table 3, Entries 8–11) the polystyrene weight fraction increases ~ 2.4 times. The low

solution viscosity due to the high concentration of monomer at the beginning of the reaction enhances the access of the monomer to the propagating radical and extends the reaction time. The carbon nanotubes dispersion improves during the polymerization reaction due to the growing chains, but the viscosity rises due to the monomer consumption. Then, the reaction will be controlled until the dispersion is hindered by the monomer consumption, the surface confinement between nanotubes will limit the propagation and coupling or disproportions might end the reaction. As the conversion of monomer advances, the viscosity rises and promotes the filler reaggregation, so that the deactivation of the growing radical is favored (as described above).

A common trend on the MWCNTs from both sources after ATRP reactions is the increase in grafted polymer content with the monomer concentration. The increase in polymer content with the monomer concentration has been also reported on MWCNTs³¹ and other confined systems.⁷¹ These observations can be correlated to the transmission electron micrographs (inserts in Fig. 8). If one assumes that the distribution of initiator moieties is homogeneous along the surface on both MWCNT sources, the polymer layer is relatively thinner for the $\text{PS}_{44}^3\text{MWCNT}_{\text{FC}}^{99}$ than for the sample $\text{PS}_{91}^{20}\text{MWCNT}_{\text{BMS}}^{95}$. This is in agreement with other systems, where the polymer grafting depends on the

nanoparticle surface area and its influence on the polymerization kinetics.⁴³

Another possibility to control the polystyrene content in the MWCNT_{FC}⁹⁹ is by varying the length of the glycol spacer. As can be observed in Table 3, for comparable monomer to MWCNT_{FC}⁹⁹ weight fractions and initiator concentration, the polystyrene grafting content doubles when ethylene glycol and PEG₄₀₀ are compared (PS₉¹MWCNT_{FC}⁹⁹ and PS₂₂²MWCNT_{FC}⁹⁹) and increases four times when PEG₂₀₀ is compared against PEG₄₀₀ (PS₁₁¹MWCNT_{FC}⁹⁹ and PS₄₄³MWCNT_{FC}⁹⁹). A polymer content over 80 wt % can be obtained with the MWCNT_{FC}⁹⁹ by choosing the right combination between glycol spacer, initiator concentration, and monomer to carbon nanotube ratio (e.g., PS₈₅²⁴MWCNT_{FC}⁹⁹, entry 5 in Table 3). From the obtained results one can deduce that the PEG₄₀₀ chain length promotes a more stable dispersion and lower the viscosity of the reactions compared to the other glycol spacers used, which increase the polymer grafting weight content through the increase in the polymerization rate or the increase of the yield during the time of the polymerizations.

CONCLUSIONS

Two commercially available MWCNTs were grafted with polystyrene after successive functionalization reactions. The grafting from polymerization of styrene was performed under atom transfer radical polymerization conditions. The purity and the dimension of the MWCNTs influence the grafted polystyrene content. The MWCNT with relative tighter aggregates and with apparent shorter length (MWCNT_{BMS}⁹⁵) showed a higher polystyrene weight content than the relative longer, less aggregated carbon nanotubes (MWCNT_{FC}⁹⁹), with comparable initiator concentrations. The presence of tight aggregates and shorter nanotubes decreases the viscosity of the dispersion during the functionalization reactions, which may enhance the propagation of the growing polymer chain before the polymerization slows down due to high monomer conversion. However, higher polymer contents can be achieved with the MWCNT_{FC}⁹⁹ with the right combination of poly(ethylene glycol) spacer, concentration of the anchored initiator, and monomer to carbon nanotube weight ratio.

Baytubes® were kindly supplied by Bayer MaterialScience. The authors thank Clarissa Abetz for TEM and Karen-Marita Prause for SEM investigations. J.A. acknowledges DAAD-HGF fellowship. The authors acknowledge financial support by the seventh Framework Program of the European Commission [HARCANA (NMP3-LA-2008-213277)].

REFERENCES AND NOTES

- Moniruzzaman, M.; Winey, K. I. *Macromolecules* 2006, 39, 5194–5205.
- Iijima, S. *Nature* 1991, 354, 56–58.
- Monthieux, M.; Kuznetsov, V. L. *Carbon* 2006, 44, 1621–1623.
- Gojny, F. H.; Schulte, K. *Compos Sci Technol* 2004, 64, 2303–2308.
- Sandler, J. K. W.; Kirk, J. E.; Kinloch, I. A.; Shaffer, M. S. P.; Windle, A. H. *Polymer* 2003, 44, 5893–5899.
- Shi, Q.; Yang, D.; Su, Y.; Li, J.; Jiang, Z.; Jiang, Y.; Yuan, W. *J. Nanopart Res* 2007, 9, 1205–1210.
- Kumar, N. A.; Ganapathy, H. S.; Kim, J. S.; Jeong, Y. S.; Jeong, Y. T. *Eur Polym J* 2008, 44, 579–586.
- Gao, C.; Muthukrishnan, S.; Li, W.; Yuan, J.; Xu, Y.; Muller, A. H. E. *Macromolecules* 2007, 40, 1803–1815.
- Richard, C.; Balavoine, F.; Schultz, P.; Ebbesen, T. W.; Mioskowski, C. *Science* 2003, 300, 775–778.
- Poland, C. A.; Duffin, R.; Kinloch, I.; Maynard, A.; Wallace, W. A. H.; Seaton, A.; Stone, V.; Brown, S.; MacNee, W.; Donaldson, K. *Nat Nanotechnol* 2008, 3, 423–428.
- Kane, A. B.; Hurt, R. H. *Nat Nanotechnol* 2008, 3, 378–379.
- Rausch, L. J.; Bisinger, E. C.; Sharma, A. *Regul Toxicol Pharm* 2004, 40, 28–41.
- Schipper, M. L.; Nakayama-Ratchford, N.; Davis, C. R.; Kam, N. W. S.; Chu, P.; Liu, Z.; Sun, X.; Dai, H.; Gambhir, S. S. *Nat Nanotechnol* 2008, 3, 216–221.
- Gojny, F. H.; Wichmann, M. H. G.; Fiedler, B.; Kinloch, I. A.; Bauhofer, W.; Windle, A. H.; Schulte, K. *Polymer* 2006, 47, 2036–2045.
- Sandler, J.; Shaffer, M. S. P.; Prasse, T.; Bauhofer, W.; Schulte, K.; Windle, A. H. *Polymer* 1999, 40, 5967–5971.
- Sandler, J. K. W.; Pegel, S.; Cadek, M.; Gojny, F.; van Es, M.; Lohmar, J.; Blau, W. J.; Schulte, K.; Windle, A. H.; Shaffer, M. S. P. *Polymer* 2004, 45, 2001–2015.
- Shim, M.; Shi Kam, N. W.; Chen, R. J.; Li, Y.; Dai, H. *Nano Lett* 2002, 2, 285–288.
- Tasis, D.; Tagmatarchis, N.; Bianco, A.; Prato, M. *Chem Rev* 2006, 106, 1105–1136.
- Sung, J.; Park, J. M.; Choi, U. H.; Huh, J.; Jung, B.; Min, B. G.; Ahn, C. H.; Park, C. *Macromol Rapid Commun* 2007, 28, 176–182.
- Hill, D. E.; Lin, Y.; Rao, A. M.; Allard, L. F.; Sun, Y. P. *Macromolecules* 2002, 35, 9466–9471.
- Baskaran, D.; Mays, J. W.; Bratcher, M. S. *Polymer* 2005, 46, 5050–5057.
- Chang, J. H.; Lee, Y. W.; Kim, B. G.; Kim, H.-K.; Choi, I. S.; Paik, H.-J. *Compos Interface* 2007, 14, 493–504.
- Cheng, B.; Li, Y.; Shen, C. *Polym Prepr (Am Chem Soc Div Polym Chem)* 2004, 45, 653–654.
- Chochos, C. L.; Stefopoulos, A. A.; Campidelli, S.; Prato, M.; Gregoriou, V. G.; Kallitsis, J. K. *Macromolecules* 2008, 41, 1825–1830.
- Choi, J. H.; Oh, S. B.; Chang, J.; Kim, I.; Ha, C.-S.; Kim, B. G.; Han, J. H.; Joo, S.-W.; Kim, G.-H.; Paik, H.-j. *Polym Bull* 2005, 55, 173–179.
- Fragneaud, B.; Masenelli-Varlot, K.; Gonzalez-Montiel, A.; Terrones, M.; Cavaillé, J.-Y. *Chem Phys Lett* 2006, 419, 567–573.

- 27 Gao, C.; Li, W.; Morimoto, H.; Nagaoka, Y.; Maekawa, T. *J Phys Chem B* 2006, 110, 7213–7220.
- 28 Gao, C.; Vo, C. D.; Jin, Y. Z.; Li, W.; Armes, S. P. *Macromolecules* 2005, 38, 8634–8648.
- 29 Hong, C. Y.; You, Y. Z.; Wu, D.; Li, Y.; Pan, C. Y. *Macromolecules* 2005, 38, 2606–2611.
- 30 Kong, H.; Gao, C.; Yan, D. *J Am Chem Soc* 2004, 126, 412–413.
- 31 Kong, H.; Gao, C.; Yan, D. *Macromolecules* 2004, 37, 4022–4030.
- 32 Kong, H.; Gao, C.; Yan, D. *J Mater Chem* 2004, 14, 1401–1405.
- 33 Kong, H.; Luo, P.; Gao, C.; Yan, D. *Polymer* 2005, 46, 2472–2485.
- 34 Lei, Z.; Wei, X.; Zhang, L.; Bi, S. *Colloid Surf A* 2008, 324, 131–136.
- 35 Li, W.; Gao, C.; Qian, H.; Ren, J.; Yan, D. *J Mater Chem* 2006, 16, 1852–1859.
- 36 Liu, Y. L.; Chen, W. H. *Macromolecules* 2007, 40, 8881–8886.
- 37 Matrab, T.; Chancolon, J.; L'Hermite, M. M.; Rouzaud, J.-N.; Deniau, G.; Boudou, J.-P.; Chehimi, M. M.; Delamar, M. *Colloid Surf A* 2006, 287, 217–221.
- 38 Qin, S.; Qin, D.; Ford, W. T.; Resasco, D. E.; Herrera, J. E. *J Am Chem Soc* 2004, 126, 170–176.
- 39 Qin, S.; Qin, D.; Ford, W. T.; Resasco, D. E.; Herrera, J. E. *Macromolecules* 2004, 37, 752–757.
- 40 Wu, H.-X.; Tong, R.; Qiu, X.-Q.; Yang, H.-F.; Lin, Y.-H.; Cai, R.-F.; Qian, S.-X. *Carbon* 2007, 45, 152–159.
- 41 Xiao, Q.; He, S.; Liu, L.; Guo, X.; Shi, K.; Du, Z.; Zhang, B. *Compos Sci Technol* 2008, 68, 321–328.
- 42 Baskaran, D.; Mays, J. W.; Bratcher, M. S. *Angew Chem Int Ed* 2004, 43, 2138–2142.
- 43 von Werne, T.; Patten, T. E. *J Am Chem Soc* 2001, 123, 7497–7505.
- 44 Huang, C.; Tassone, T.; Woodberry, K.; Sunday, D.; Green, D. L. *Langmuir* 2009, 25, 13351–13360.
- 45 Wang, T.-L.; Tseng, C.-G. *J Appl Polym Sci* 2007, 105, 1642–1650.
- 46 Osswald, S.; Havel, M.; Gogotsi, Y. *J Raman Spectrosc* 2007, 38, 728–736.
- 47 Shanmugharaj, A. M.; Bae, J. H.; Lee, K. Y.; Noh, W. H.; Lee, S. H.; Ryu, S. H. *Compos Sci Technol* 2007, 67, 1813–1822.
- 48 Chen, Q.; Xu, R.; Yu, D. *Polymer* 2006, 47, 7711–7719.
- 49 Sun, L.; Yang, J.-T.; Lin, G.-Y.; Zhong, M.-Q. *Mater Lett* 2007, 61, 3963–3966.
- 50 Zhang, J.; Zou, H.; Qing, Q.; Yang, Y.; Li, Q.; Liu, Z.; Guo, X.; Du, Z. *J Phys Chem B* 2003, 107, 3712–3718.
- 51 Xu, D.; Liu, H.; Yang, L.; Wang, Z. *Carbon* 2006, 44, 3226–3231.
- 52 Wu, C.-S. *J Appl Polym Sci* 2007, 104, 1328–1337.
- 53 Zhang, X.; Deng, C.; Xu, R.; Wang, D. *J Mater Sci* 2007, 42, 8377–8380.
- 54 Datsyuk, V.; Kalyva, M.; Papagelis, K.; Parthenios, J.; Tasis, D.; Siokou, A.; Kallitsis, I.; Galiotis, C. *Carbon* 2008, 46, 833–840.
- 55 Xia, W.; Wang, Y.; Bergsträsser, R.; Kundu, S.; Muhler, M. *Appl Surf Sci* 2007, 254, 247–250.
- 56 Baskaran, D.; Mays, J. W.; Bratcher, M. S. *Chem Mater* 2005, 17, 3389–3397.
- 57 Forrest, G. A.; Alexander, A. J. *J Phys Chem C* 2007, 111, 10792–10798.
- 58 Peng, F.; Zhang, L.; Wang, H.; Lv, P.; Yu, H. *Carbon* 2005, 43, 2405–2408.
- 59 Ziegler, K. J.; Gu, Z.; Peng, H.; Flor, E. L.; Hauge, R. H.; Smalley, R. E. *J Am Chem Soc* 2005, 127, 1541–1547.
- 60 Breza, M. *Chem Phys* 2006, 330, 224–230.
- 61 Sano, M.; Kamino, A.; Okamura, J.; Shinkai, S. *Langmuir* 2001, 17, 5125–5128.
- 62 Liu, Y.-X.; Du, Z.-J.; Li, Y.; Zhang, C.; Li, C.-J.; Yang, X.-P.; Li, H.-Q. *J Polym Sci Part A: Polym Chem* 2006, 44, 6880–6887.
- 63 Lin, Y.; Taylor, S.; Huang, W.; Sun, Y. P. *J Phys Chem B* 2003, 107, 914–919.
- 64 Yao, Z.; Braid, N.; Botton, G. A.; Adronov, A. *J Am Chem Soc* 2003, 125, 16015–16024.
- 65 Fan, D.-Q.; He, J.-P.; Tang, W.; Xu, J.-T.; Yang, Y.-L. *Eur Polym J* 2007, 43, 26–34.
- 66 Lan, Q.; Francis, L. F.; Bates, F. S. *J Polym Sci Part B: Polym Phys* 2007, 45, 2284–2299.
- 67 El Harrak, A.; Carrot, G.; Oberdisse, J.; Jestin, J.; Boué, F. *Polymer* 2005, 46, 1095–1104.
- 68 De Falco, A.; Fascio, M. L.; Lamanna, M. E.; Corcuera, M. A.; Mondragon, I.; Rubiolo, G. H.; D'Accorso, N. B.; Goyanes, S. *Phys B: Condens Matter* 2009, 404, 2780–2783.
- 69 Matyjaszewski, K.; Xia, J. *Chem Rev* 2001, 101, 2921–2990.
- 70 Matyjaszewski, K.; Miller, P. J.; Shukla, N.; Immaraporn, B.; Gelman, A.; Luokala, B. B.; Siclován, T. M.; Kickelbick, G.; Valant, T.; Hoffmann, H.; Pakula, T. *Macromolecules* 1999, 32, 8716–8724.
- 71 Moreno, J.; Sherrington, D. C. *Chem Mater* 2008, 20, 4468–4474.
- 72 Audouin, F.; Blas, H.; Pasetto, P.; Beaunier, P.; Boissière, C.; Sanchez, C.; Save, M.; Charleux, B. *Macromol Rapid Commun* 2008, 29, 914–921.