



US007381496B2

(12) **United States Patent**
Onnerud et al.

(10) **Patent No.:** **US 7,381,496 B2**
(45) **Date of Patent:** **Jun. 3, 2008**

(54) **LITHIUM METAL OXIDE MATERIALS AND METHODS OF SYNTHESIS AND USE**

(75) Inventors: **Per T. Onnerud**, Framingham, MA (US); **Jay Jie Shi**, Acton, MA (US); **Sharon L. Dalton**, Stoneham, MA (US); **Christina Lampe-Onnerud**, Framingham, MA (US)

(73) Assignee: **Tiax LLC**, Cambridge, MA (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 805 days.

5,518,842 A	5/1996	Fey et al.
5,531,920 A	7/1996	Mao et al.
5,591,543 A	1/1997	Peled et al.
5,629,110 A	5/1997	Kobayashi et al.
5,631,105 A	5/1997	Hasegawa et al.
5,648,057 A	7/1997	Ueda et al.
5,672,447 A	9/1997	Yamawaki et al.
5,679,481 A	10/1997	Takanishi et al.
5,693,435 A	12/1997	Amatucci et al.
5,728,367 A	3/1998	Mao
5,750,288 A	5/1998	Xie et al.
5,783,333 A	7/1998	Mayer

(Continued)

FOREIGN PATENT DOCUMENTS

EP 0 468 942 A2 1/1992

(Continued)

OTHER PUBLICATIONS

Jim, Y., et. al., "Electrochemical Characterizations of Commercial LiCoO₂ Powders with Surface Modified by Li₃ PO₄ Nanoparticles," *Electrochemical and Solid-State Letters*, 9 (6) A273-A276 (2006).

(Continued)

Primary Examiner—Laura S Weiner

(74) *Attorney, Agent, or Firm*—Lowrie, Lando & Anastasi, LLP

(21) Appl. No.: **10/850,877**

(22) Filed: **May 21, 2004**

(65) **Prior Publication Data**

US 2005/0260495 A1 Nov. 24, 2005

(51) **Int. Cl.**
H01M 4/58 (2006.01)

(52) **U.S. Cl.** **429/231.1; 429/231.3; 429/223; 429/231.6; 252/182.1; 423/592.1; 423/593.1; 423/594.4; 423/594.6; 427/58; 427/123**

(58) **Field of Classification Search** **429/231.1, 429/231.3, 223, 231.6; 252/182.1; 423/592.1, 423/593.1, 594.4, 594.6; 427/58, 123**
See application file for complete search history.

(56) **References Cited**


U.S. PATENT DOCUMENTS

4,520,084 A	5/1985	Tinker et al.
4,526,881 A	7/1985	Binder et al.
4,980,080 A	12/1990	Lecerf et al.
5,264,201 A	11/1993	Dahn et al.
5,286,582 A	2/1994	Tahara et al.

(57) **ABSTRACT**

A composition having a formula Li_xMg_yNiO₂ wherein 0.9<x<1.3, 0.01<y<0.1, and 0.91<x+y<1.3 can be utilized as cathode materials in electrochemical cells. A composition having a core, having a formula Li_xMg_yNiO₂ wherein 0.9<x<1.3, 0.01<y<0.1, and 0.9<x+y<1.3, and a coating on the core, having a formula Li_aCo_bO₂ wherein 0.7<a<1.3, and 0.9<b<1.2, can also be utilized as cathode materials in electrochemical cells.

15 Claims, 12 Drawing Sheets



US 7,381,496 B2

Page 2

U.S. PATENT DOCUMENTS

5,879,654	A	3/1999	Van Ghemen et al.
5,885,544	A	3/1999	Yamazaki et al.
5,914,094	A	6/1999	Sun et al.
5,932,632	A	8/1999	Biensan et al.
5,985,488	A	11/1999	Mitate et al.
5,993,998	A	11/1999	Yasuda
6,007,947	A	12/1999	Mayer
6,017,654	A	1/2000	Kumta et al.
6,033,807	A	3/2000	Yasuda
6,040,090	A	3/2000	Sunagawa et al.
6,045,771	A	4/2000	Matsubara et al.
6,048,643	A	4/2000	Van Ghemen et al.
6,071,645	A	6/2000	Biensan et al.
6,071,649	A	6/2000	Mao et al.
6,242,134	B1	6/2001	Fujiwara et al.
6,274,272	B1	8/2001	Peres et al.
6,277,521	B1	8/2001	Gao et al.
6,296,972	B1	10/2001	Hong et al.
6,361,822	B1	3/2002	Kurose et al.
6,372,385	B1	4/2002	Kweon et al.
6,379,842	B1	4/2002	Mayer
6,383,235	B1	5/2002	Maegawa et al.
6,436,577	B1	8/2002	Kida et al.
6,447,739	B1	9/2002	Krynitz et al.
6,482,550	B1	11/2002	Imachi et al.
6,582,854	B1	6/2003	Qi et al.
6,713,037	B2	3/2004	Van Neste
6,737,037	B2	5/2004	Ramasamy et al.
6,756,155	B1	6/2004	Kweon et al.
6,773,852	B2	8/2004	Cho et al.
6,794,085	B2	9/2004	Gao et al.
6,855,461	B2	2/2005	Lampe-Onnerud et al.
6,875,416	B1	4/2005	Benz et al.
6,881,520	B1	4/2005	Li
6,902,745	B2	6/2005	Lee et al.
6,916,579	B2	7/2005	Gorchkov et al.
6,916,580	B2	7/2005	Cho et al.
6,921,609	B2	7/2005	Lampe-Onnerud et al.
6,949,233	B2	9/2005	Kweon et al.
2001/0031311	A1	10/2001	Lee et al.
2002/0071991	A1	6/2002	Kweon et al.
2002/0119374	A1	8/2002	Yang et al.
2002/0142225	A1	10/2002	Kweon et al.
2002/0192148	A1	12/2002	Kweon et al.
2002/0192552	A1	12/2002	Lampe-Onnerud et al.
2002/0192556	A1	12/2002	Lampe-Onnerud et al.
2003/0013017	A1	1/2003	Nagayama et al.
2003/0124424	A1	7/2003	Takahashi et al.
2003/0180616	A1	9/2003	Johnson et al.
2004/0053133	A1	3/2004	Li
2004/0062993	A1	4/2004	Yanagida et al.
2004/0062995	A1	4/2004	Yanagida et al.
2004/0081889	A1	4/2004	Lee et al.
2004/0096742	A1	5/2004	Akashi et al.
2004/0110064	A1	6/2004	Kitao et al.
2004/0110065	A1	6/2004	Hamano et al.
2004/0142241	A1	7/2004	Nagayama et al.
2004/0142247	A1	7/2004	Yoshimura et al.
2004/0157124	A1	8/2004	Goh et al.
2004/0161668	A1	8/2004	Maeda et al.
2004/0180263	A1	9/2004	Kase et al.
2004/0191628	A1 *	9/2004	Inoue et al. 429/231.1
2004/0197659	A1	10/2004	Kumar et al.
2004/0265216	A1	12/2004	Nazri et al.
2005/0037263	A1	2/2005	Wang et al.
2005/0069774	A1	3/2005	Miyazaki et al.
2005/0069775	A1	3/2005	Hwang et al.
2005/0175897	A1	8/2005	Jung et al.
2005/0238956	A1	10/2005	Lee

2005/0266316	A1	12/2005	Kitao et al.
2005/0271945	A1	12/2005	Takahashi et al.

FOREIGN PATENT DOCUMENTS

EP	0 587 973	A1	3/1994
EP	0 744 780	A1	11/1996
EP	0 702 421	B1	12/1998
EP	0 468 942	B2	12/1999
EP	0 986 116	A1	3/2000
EP	1 111 701	A1	6/2001
JP	08-064209		3/1996
JP	08-064244		3/1996
JP	08-096794		4/1996
JP	08-138726		5/1996
JP	08-138734		5/1996
JP	08-148141		6/1996
JP	08-148147		6/1996
JP	08-162112		6/1996
JP	08-203561		8/1996
JP	08-213050		8/1996
JP	08-306358		11/1996
JP	09-050810		2/1997
JP	09-180720		7/1997
JP	09-245789		9/1997
JP	09-245835		9/1997
JP	09-259881		10/1997
JP	10-074516		3/1998
JP	10-074517		3/1998
JP	10-083816		3/1998
JP	10-114527		5/1998
JP	10-114528		5/1998
JP	10-139429		5/1998
JP	10-139430		5/1998
JP	10-172613		6/1998
JP	10-182157		7/1998
JP	10-182160		7/1998
JP	10-182161		7/1998
JP	10-188954		7/1998
JP	10-236826		9/1998
JP	10-255804		9/1998
JP	10-283839		10/1998
JP	10-308216		11/1998
JP	10-308219		11/1998
JP	11-067209		3/1999
JP	11-111338		4/1999
JP	11-149926		6/1999
JP	11-162454		6/1999
JP	11-176439		7/1999
JP	11-191408		7/1999
JP	11-214012		8/1999
JP	11-246225		9/1999
JP	11-278848		10/1999
JP	11-310416		11/1999
JP	2000-156230		6/2000
JP	2000-169150		6/2000
JP	2000-200604		7/2000
JP	2000-231933		8/2000
JP	2000-299133		10/2000
JP	2000-311718		11/2000
JP	2000-315524		11/2000
JP	2000-331711		11/2000
JP	2000-348729		12/2000
JP	2001-068152		3/2001
JP	2001-210316		8/2001
JP	2001-357891		12/2001
JP	2002-025556		1/2002
JP	2002-141069		5/2002
JP	2002-313422		10/2002
JP	2002-313423		10/2002
JP	2003-151626		5/2003
JP	2003-346797		12/2003
JP	2004-288579		10/2004

JP	2005-190996	7/2005
WO	WO 96/41385	12/1996
WO	WO 98/16960	4/1998
WO	WO 98/20571	5/1998
WO	WO 98/24131 A1	6/1998
WO	WO 98/54769	12/1998
WO	WO 98/54772	12/1998
WO	WO 98/54773	12/1998
WO	WO 00/11738 A1	3/2000
WO	WO 02/103823 A2	12/2002
WO	WO 02/103824 A2	12/2002
WO	WO 03/041193	5/2003
WO	WO 2005/055344 A2	6/2005
WO	WO 2005/113849	12/2005

OTHER PUBLICATIONS

Cho et al., "Annealing-Temperature Effect on Various Cutoff-Voltage Electrochemical Performances in AlPO_4 -Nanoparticle-Coated LiCoO_2 ," *Journal of The Electrochemical Society*, 152(1), 2005, pp. A32-A36.

Chung et al., "In Situ XRD Studies of the Structural Changes of ZrO_2 Coated LiCoO_2 During Cycling and Their Effects on Capacity Retention in Lithium Batteries," publication date unknown, 1 page.

Eftekhari, "Mixed-Metals Codeposition as a Novel Method for the Preparation of LiMn_2O_4 Electrodes with Reduced Capacity Fades," *Journal of The Electrochemical Society*, 150(7), 2003, pp. A966-A969.

Eftekhari, " LiMn_2O_4 electrode prepared by gold-titanium codeposition with improved cyclability," *Journal of Power Sources*, 130, 2004, pp. 260-265.

Eriksson, " LiMn_2O_4 as a Li-Ion Battery Cathode," Comprehensive Summaries of Uppsala Dissertations from the Faculty of Science and Technology 651, 2001, pp. 1-53.

Fey et al., "Electrochemical studies on LiCoO_2 coated with Al_2O_3 derived from carboxylate-alumoxane," Department of Chemical

and Materials Engineering, Department of Chemistry, National Central University, Chung-Li, Taiwan, R.O.C., publication date unknown, 1 page.

Gnanaraj et al., "Improving the high-temperature performance of LiMn_2O_4 spinel electrodes by coating the active mass with MgO via a sonochemical method," *Electrochemistry Communications* 5, 2003, pp. 940-945.

Kim et al., "Washing Effect of $\text{LiNi}_{0.83}\text{Co}_{0.15}\text{O}_2$ Cathode in Water," Abstract from *Electrochemical Solid-State Letters*, vol. 1, Issue 1, 2006, pp. A19-A23, <http://www.ecsdl.org>, printed Mar. 23, 2006.

Kim et al., "Electrochemical Properties of $\text{Li}(\text{Ni}_{1/3}\text{Co}_{1/3}\text{Mn}_{1/3})\text{O}_2$ Synthesized by Hydrothermal Process," Department of Materials and Science Engineering, Korea, publication date unknown, 1 page.

Lee et al., "Effect of AlPO_4 -Nanoparticle Coating Concentration on High-Cutoff-Voltage Electrochemical Performances in LiCoO_2 ," *Journal of The Electrochemical Society*, 151(6), 2004, pp. A801-A805.

Lee et al., "A Study of Electrochemical Kinetics of Lithium Ion in Organic Electrolytes," *Korean J. Chem. Eng.*, 19(4), 2002, pp. 638-644.

Nordlinder, "Nanotubes for Battery Applications," Digital Comprehensive Summaries of Uppsala Dissertations from the Faculty of Science and Technology 72, 2005, pp. 9-60.

Stroeve et al., "Improvement of Thermal Stability of LI-ION Batteries by Polymer Coating of LiMn_2O_4 ," Institute of Transportation Studies, University of California, Davis, May 2004, pp. 2-34, UCD-ITS-RR-04-11.

Xie et al., "Electrochemical Performances of Nanosized Intermetallic Compound CoSb_2 Prepared by the Solvothermal Route," *Journal of The Electrochemical Society*, 151 (11), 2004, pp. A1905-A1910. Search Report (miscellaneous) publication date unknown.

* cited by examiner




FIG. 1







FIG. 4

**FIG. 2**

**FIG. 3**

**FIG. 5**




FIG. 6





FIG. 7

**FIG. 8**





FIG. 9

**FIG. 10**






FIG. 11

**FIG. 12**

**FIG. 13**

LITHIUM METAL OXIDE MATERIALS AND METHODS OF SYNTHESIS AND USE

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to lithium metal oxide compositions as well as electrochemical devices utilizing such compositions and, in particular, to lithium-magnesium nickel oxide compositions suitable as components of lithium-ion electrochemical devices.

2. Description of Related Art

Rechargeable lithium and lithium-ion batteries can be used in a variety of applications, such as cellular phones, laptop computers, digital cameras and video cameras, and hybrid electric vehicles etc., due to their high energy density.

Commercially available lithium-ion batteries typically consist of graphite-based anode and LiCoO₂-based cathode materials. However, LiCoO₂-based cathode materials can be expensive and typically have relatively low capacity, approximately 150 mAh/g.

Alternatives to LiCoO₂-based cathode materials include LiNiO₂-based cathode materials, which can be less expensive. Typical LiNiO₂-based cathode materials can include compositions having a formula LiNi_{0.8}Co_{0.2}O₂ or LiNi_{0.8}Co_{0.15}Al_{0.05}O₂. These materials are relatively more expensive than cobalt-free LiNiO₂-based cathode material because of the relatively higher cost of cobalt relative to nickel. Furthermore, LiNiCoO₂-based cathode materials usually have lower safety, cyclability, and first cycle efficiency over LiCoO₂-based cathode materials because of the lower structural stability and higher surface reactivity of LiNiO₂ type cathodes.

Li(Ni, Co)O₂-based cathode materials have also been disclosed. For example, Lecerf et al., in U.S. Pat. No. 4,980,080, disclosed a process of making a cathode material for a secondary battery having a formula Li_{1-x}Ni_{2-y}O₂ or Li_{1-x}Co_xO₂. Xie et al., in U.S. Pat. No. 5,750,288, disclosed modified lithium nickel oxide compounds for electrochemical cathodes and cells based on Li_xM_yO₂ materials, where M is a non-transition metal selected from the group consisting of aluminum, gallium, tin and zinc. Mayer, in U.S. Pat. No. 5,783,333, disclosed a Li_xNi_yCo_zM_nO₂ material. Mayer also disclosed, in U.S. Pat. Nos. 6,007,947 and 6,379,842, cathode materials having a formula Li_xNi_yCo_zM_nO₂ or Li_xMn_{2-r}MI_{0.4} where M is a metal selected from the group consisting of aluminum, titanium, tungsten, chromium, molybdenum, magnesium, tantalum, silicon, and combinations thereof and MI is one of chromium, titanium, tungsten, nickel, cobalt, iron, tin, zinc, zirconium, silicon, or a combination thereof. Kumta et al., in U.S. Pat. No. 6,017,654, disclosed cathode materials having a formula Li_{1+x}Ni_{1-y}M_yN_xO_{2(1+x)}} and LiN_{1-y}M_yN_xO_p where M is a transition metal selected from the group consisting of titanium, vanadium, chromium, manganese, iron, cobalt, and aluminum and N is a Group II element selected from the group consisting of magnesium, calcium, strontium, barium, and zinc. Sunagawa et al., in U.S. Pat. No. 6,040,090, disclosed a positive electrode material based on Li—Ni—Co—Mn—O₂. Peres et al., in U.S. Pat. No. 6,274,272, disclosed an active cathode material having a formula Li_{1-x}Ni_(1-x-4M)Co_{4M}Al_{4M}Mg_MO₂. Gao et al., in U.S. Pat. No. 6,277,521, disclosed a lithium metal oxide material containing multiple dopants with a formula LiN_{1-x}CO₃M_aM'_bO₂ where M is a metal selected from the group consisting of titanium, zirconium, and combinations thereof and M' is a metal selected from the group consisting of magnesium, calcium, stron-

tium, barium, and combinations thereof. Mao et al., in U.S. Pat. No. 6,071,649, disclosed LiCoO₂-coated LiNiO₂ or Li(Ni,Co)O₂ materials. None of these disclosed Li—Mg—Ni—O₂-based cathode materials.

Matsubara et al., in U.S. Pat. No. 6,045,771, disclosed a cathode material having a formula Li_{1-x1}Ni_{1-x2}M_xO₂ where M is a metal selected from the group consisting of aluminum, iron, cobalt, manganese, and magnesium, x=x1+x2, 0<x1≤0.2, 0<x2≤0.5, 0<x≤0.5, and 0.9≤y≤1.3.

Multiple companies are also commercially fabricating cathodes utilizing materials with a general formula LiNi-CoMO₂. TODA (earlier Fuji Chemical) manufactures products CA5, CA1505N, and NCA. Honjo-FMC and Nichia (both of Japan) also provide nickel-cobalt-based cathodes. These products typically suffer from low safety properties, and relatively low rate capability.

BRIEF SUMMARY OF THE INVENTION

In accordance with one or more embodiments, the present invention relates to Li_xMg_yNiO₂ materials, which, when utilized in electrochemical applications or systems, can be characterized as being or providing systems that utilize safer, low-cost cathode materials with high capacity, long cycle life, high rate, especially high powerability, as well as high voltage. In some embodiments, the cathode materials of the present invention can be characterized as being lower cost, having improved chemically stability, and higher operating voltage while providing greater capacity especially, for example, relative to LiCoO₂- and/or LiNiO₂-based cathode materials.

In accordance with one or more embodiments, the present invention provides a composition having a formula Li_xMg_yNiO₂ wherein 0.9<x<1.3, 0.01<y<0.1, and 0.91<x+y<1.3.

In accordance with further embodiments, the present invention provides a composition comprising a core having a formula Li_xMg_yNiO₂, wherein 0.9<x<1.3, 0.01<y<0.1, and 0.91<x+y<1.3, and a coating on the core having a formula Li_aCo_bO₂, wherein 0.7<a<1.3, and 0.9<b<1.2.

In accordance with one or more embodiments, the present invention provides an electrochemical cell comprising a cathode comprising a composition having a formula Li_xMg_yNiO₂, wherein 0.9<x<1.3, 0.01<y<0.1, and 0.91<x+y<1.3.

In accordance with one or more embodiments, the present invention provides an electrochemical cell comprising a cathode comprising particles consisting of a core having a formula Li_xMg_yNiO₂, wherein 0.9<x<1.3, 0.01<y<0.1, and 0.91<x+y<1.3, and a coating on the core. The coating can have a formula Li_aCo_bO₂, wherein 0.7<a<1.3, and 0.9<b<1.2.

A method of preparing a composition comprising providing a mixture of compounds comprising a lithium source, a magnesium source, and a nickel source and reacting the mixture in an oxidizing atmosphere at a temperature and for a period sufficient to crystallize the mixture into a Li_xMg_yNiO₂ composition wherein 0.9<x<1.3, 0.01<y<0.1, and 0.91<x+y<1.3.

In accordance with one or more embodiments, the present invention provides a method of preparing coated particles. The method can comprise steps of providing a first mixture of compounds comprising lithium, magnesium, and nickel and sintering the first mixture in an oxidizing atmosphere at a first temperature and for a first period sufficient to crystallize the first mixture into core particles having a formula Li_xMg_yNiO₂, wherein 0.9<x<1.3, 0.01<y<0.1, and 0.91<x+y<1.3; and coating the core particles with a second mixture comprising compounds comprising lithium and cobalt and

3

sintering the coated core particles at a second temperature and for a second period sufficient to crystallize the coating having a formula $\text{Li}_a\text{Co}_b\text{O}_2$ wherein $0.7 < a < 1.3$, and $0.9 < b < 1.2$.

In accordance with one or more embodiments, the present invention provides a particle comprising a core material having a composition of a formula $\text{Li}_{1-y}\text{Mg}_y\text{NiO}_2$ where Mg and Li are predominantly in a crystallographic 3a site and Ni is predominantly in a crystallographic 3b site and $0.01 < y < 0.1$.

Other advantages, novel features, and objects of the invention should become apparent from the following detailed description of the invention when considered in conjunction with the accompanying drawings, which are schematic and not intended to be drawn to scale.

BRIEF DESCRIPTION OF THE DRAWINGS

Preferred, non-limiting embodiments of the present invention will be described by way of example with reference to the following, accompanying drawings. In the drawings, each identical or nearly identical component that is illustrated in various figures is typically represented by a like numeral. For clarity, not every component may be labeled in every drawing nor is every component shown where illustration is not necessary to allow those of ordinary skill in the art to understand the invention. In the drawings:

FIG. 1 is a copy of photomicrograph, representing a typical lithium-magnesium-nickel oxide composition in accordance with one or more embodiments of the present invention; here represented by spherical $\text{LiMg}_{0.025}\text{NiO}_2$;

FIG. 2 is an X-ray diffraction pattern of the composition shown in FIG. 1;

FIG. 3 is a graph showing the discharge profile, at different discharge rates, of the material shown in FIG. 1;

FIG. 4 is a copy of photomicrograph of a typical lithium-cobalt oxide-gradient coated lithium-magnesium-nickel oxide: composition in accordance with one or more embodiments of the present invention; here represented by an about 5 mol % $\text{LiCoO}_2\text{:LiMg}_{0.025}\text{NiO}_2$;

FIG. 5 is an XRD graph of the coated composition shown in FIG. 4;

FIG. 6 is a graph showing the discharge profile of the composition shown in FIG. 4 having about a 5 mol % coating level at various rates;

FIG. 7 is a graph showing the discharge profile of the composition shown in FIG. 4 having about a 10 mol % coating level at various rates;

FIG. 8 is a graph showing the discharge profile of the composition shown in FIG. 4 having about a 15 mol % coating level at various rates;

FIG. 9 is a graph showing the area specific impedance for a $\text{LiMg}_{0.025}\text{NiO}_2$ composition with about a 5 mol % LiCoO_2 gradient coating, using about a 1 s and an 18 s pulse according to protocol 3, in accordance with one or more embodiments of the invention;

FIG. 10 is a graph showing the area specific impedance for various $\text{LiMg}_{0.025}\text{NiO}_2$ compositions, using 1 s and 18 s pulses according to protocol 3, in accordance with one or more embodiments of the invention;

FIG. 11 is a graph showing the X-ray diffraction patterns showing peak profiles at about 5 mol %, 10 mol %, and 15 mol % gradient coating levels of a LiCoO_2 composition (with an enlarged portion shown in the right side), in accordance with one or more embodiments of the invention;

FIG. 12 is a graph showing the capacity retention of cells during about a 1 C discharge cycling utilizing a) LiNiO_2 , b)

4

LiMgNiO_2 , c) about 5 mol % LiCoO_2 coated $\text{LiMg}_{0.025}\text{NiO}_2$, and d) CA1505N(TODA Co., Japan); and

FIG. 13 is a graph showing the differential scanning calorimetry profile of a) $\text{LiMg}_{0.025}\text{NiO}_2$, b) about 5 mol % LiCoO_2 coated $\text{LiMg}_{0.025}\text{NiO}_2$, and c) TODANCA-02 electrodes, which have been subjected to about 4.2V charging (100% state-of-charge) and immersed in electrolyte.

DETAILED DESCRIPTION OF THE INVENTION

This invention is not limited in its application to the details of construction and the arrangement of components or compounds set forth in the following description, including the various examples, or illustrated in the drawings. The invention is capable of other embodiments and of being practiced or of being carried out in various ways. Also, the phraseology and terminology used herein is for the purpose of description and should not be regarded as limiting. The use of "including," "comprising," or "having," "containing," "involving," and variations thereof herein, is meant to encompass the items listed thereafter and equivalents thereof as well as additional items.

In accordance with one or more embodiments, the present invention provides one or more compositions and one or more methods for forming the various compositions. The compositions can be used as a cathode active material in, for example, rechargeable lithium and lithium-ion electrochemical devices, such as but not limited to, batteries. In accordance with one or more embodiments, the present invention can also provide rechargeable lithium batteries or lithium-ion batteries, as well as methods of preparation and use, utilizing, for example, the compositions of the invention. The electrochemical cells utilizing the compositions of the present invention can be characterized as, inter alia, being low cost and chemically stable while providing high capacity during a long operating life.

In accordance with some embodiments, the composition of the present invention typically exhibits improved capacity, cyclability, and safety over LiCoO_2 and LiNiO_2 materials when such materials are utilized in electrochemical devices, including, but not limited to primary and secondary batteries. The materials of the present invention can provide economic advantages because they are typically less expensive to produce and/or utilize compared to LiCoO_2 , LiNiO_2 or $\text{LiNi}_{0.8}\text{Co}_{0.2}\text{O}_2$ -based materials.

In accordance with one or more embodiments, the present invention provides a lithium metal oxide composition having a first metal substantially associated with an a-site and a second metal substantially associated with a b-site in a crystalline lattice. The a-site can be crystallographically referred to as the 3a site and the b-site can be referred to as the 3b site in a Rm crystal lattice. In accordance with some embodiments of the invention, the first metal can be associated at the 3a site along with, for example, lithium, and the second metal can be associated at the 3b site. Preferably, the first metal or, in some cases the second metal, can provide crystalline stability during lithium intercalation and de-intercalation processes when, for example, the materials or compositions of the present invention are utilized as components of electrochemical devices. By providing such a structure, the composition of the present invention can be advantageously utilized as a cathode in electrochemical devices because, it is believed, the first metal can stabilize, at least partially, the crystal lattice during lithium intercalation and de-intercalation processes.

In accordance with one or more preferred embodiments of the invention, the composition can comprise a lithium-magnesium-nickel oxide wherein lithium and magnesium are crystallographically associated with the 3a site and nickel is crystallographically associated with the 3b site.

In accordance with one or more embodiments, the present invention provides a composition having a general formula $\text{Li}_x\text{Mg}_y\text{NiO}_2$, where $0.9 < x < 1.3$, and $0.01 < y < 0.1$, $0.91 < x + y < 1.3$, preferably, $0.9 < x < 1.1$ and $0.02 < y < 0.05$. The crystal-line characteristics of the composition can be characterized as having lithium and magnesium associated with the 3a site and the nickel as being associated with the 3b site.

In accordance with further embodiments, the present invention provides a particle comprising a core or interior layer having one or more layers of a metal oxide coating applied thereon. The coating layer can comprise a second lithium intercalating material including, for example, a compound having a formula $\text{Li}_a\text{Co}_b\text{O}_2$, where $0.7 < a < 1.3$, and $0.9 < b < 1.2$. In some cases, the coating layer can be characterized as having a Co/Ni molar ratio that ranges from about 0.01 to about 1.4, relative to the amount of nickel in the core layer. In still further embodiments of the invention, $0.9 < a < 1.3$, $1.8 < b < 2.2$ and the Co/Ni molar ratio can range from about 0.02 to about 0.8. The one or more layers can be characterized as having a concentration gradient with respect to the amount of cobalt relative to distance, e.g., radial distance, from the surface of the particle. The nature of the concentration gradient of the amount cobalt, relative to distance from the surface, can range from about 100%, substantially all cobalt and none or only negligible trace amounts of nickel, at the outer surface of the particle to about 0%, substantially none or only negligible trace amounts of cobalt at the coating/core interface. The nature or shape of the gradient profile can vary. For example, the gradient profile can linearly decrease relative to radial distance from the surface.

In accordance with still further embodiments, the invention can be characterized as providing a particle comprising a lithium magnesium nickel oxide core having a lithium cobalt oxide coating layer. The amount of the coating layer can range from about 0.01 wt % to about 30 wt % of the particle.

The present invention further provides one or more synthesis techniques that provides a first metal having a preferential association with the 3a site and, in some cases, provides a second metal having a preferential association with the 3b site. In accordance with still other embodiments, the present invention provides synthesis techniques that can decrease any tendency by the second metal to associate with the 3a site.

The first metal can provide crystalline stability to the lithium mixed metal oxide material during lithium intercalation/de-intercalation cycling processes. Thus, the techniques of the present invention can provide a chemically stable material that may be suitable as components, e.g., cathodes, in electrochemical devices and be characterized as having high capacity, low cost as well as high voltage and high rate with improved cycle life.

In accordance with one or more embodiments, the techniques of the present invention can utilize precursor compounds that can form a lithium metal oxide, preferably a lithium metal oxide doped with a crystal lattice stabilizing metal. In accordance with other embodiments, the techniques of the present invention can provide or promote processing conditions that favor the formation of ionic species from precursor compounds that can preferentially become associated with specific crystallographic sites. The

processing conditions of the present invention can promote formation of metal oxide species as well as association of such species with a particular, predetermined crystallographic site. For example, the techniques of the present invention can utilize one or more lithium donor compounds, one or more metal donor compounds that preferentially can become associated with a 3a crystallographic site, and in some cases, one or more metal donor compounds that preferentially become associated with a 3b crystallographic site. Thus, in accordance with one or more embodiments, the present invention can utilize a lithium donor compound, a magnesium metal donor compound, and a nickel metal donor compound; the processing conditions can promote ionic species formation, intermingling, and crystallization to form a lithium mixed metal oxide wherein a first metal can be preferentially associated with a 3a crystallographic site and a second metal can be preferentially associated with a 3b site.

In accordance with further embodiments, the techniques of the present invention can provide a lithium magnesium nickel oxide composition. For example, one or more techniques can utilize precursor compounds including, for example, those selected from the group consisting of a lithium donor, a magnesium donor, and a nickel donor. In some cases, one or more oxidizing agents or compounds can also be utilized. Thus, the precursor compound mixture can comprise, for example, a lithium source, an oxidizing agent, a first metal donor, and a second metal donor. The lithium source, the oxidizing agent, the first metal donor, and the second metal donor, preferably, can undertake one or more phase changes or phase transitions at about the same processing conditions, e.g., at about the same processing temperature range. Preferably, the elements of the selected precursor compounds can maintain their respective predetermined valences until, or in some cases through, the phase change. Likewise, the processing conditions utilized inhibit or at least do not promote any valence changes. Thus, in accordance with one or more preferred embodiments of the present invention, the precursor compounds, or oxides of the respective donor components, can be subject to processing conditions that promote or maintain chemical stability until reaction to a desired phase.

The lithium donor or source can comprise lithium hydroxide, lithium carbonate, or mixtures thereof. The oxidizing agent can comprise lithium nitrate or nickel nitrate or mixtures thereof. In some cases, the lithium source can comprise or consist of lithium nitrate as well as lithium hydroxide. The first metal donor can comprise magnesium hydroxide, magnesium carbonate, magnesium oxide, or mixtures thereof. The second metal donor can comprise nickel hydroxide, nickel sulfate, nickel nitrate, nickel oxide, or mixtures thereof.

The precursor compounds can have any form that facilitates mixing into the precursor mixture. For example, the precursor mixture can comprise a powder mixture of each of the precursor compounds or a slurry of each of the precursor compounds. Moreover, the precursor compound can be a masterbatch comprising hydroxides of lithium, the first metal donor, and/or the second metal donor. The oxidizing agent can be incorporated into the masterbatch as desired to facilitate processing and storage before utilization. In accordance with one or more embodiments, the precursor compounds can have any desired structure that, preferably, promotes efficient utilization of the lithium metal oxide materials of the present invention. Thus, the synthesis techniques of the invention can provide morphologically desirable lithium metal oxide materials.

The precursor compounds can have a variety of shapes that can be transformed to a material that can coat or be coated to form a component of an electrochemical device. For example, one or more of the precursor powder compounds can be spherically-shaped. Other shapes can be utilized as desired to accommodate or suit an end-user preference. Preferably, the synthesis process of the present invention can maintain, at least partially, the spherical shape throughout the processing or synthesis steps to provide, for example, a lithium magnesium nickel oxide material suitable as a cathode electrode in, for example, rechargeable electrochemical devices. Thus, in accordance with one or more preferred embodiments, the precursor mixture comprises a nickel donor, such as but not limited to nickel hydroxide, having a spherical shape. However, any shape and form of the starting materials of the composition of the present invention can be utilized.

In accordance with still further embodiments, the nickel donor can comprise a high density, e.g., high tap density, nickel hydroxide.

The $\text{Li}_x\text{Mg}_y\text{NiO}_2$ compositions of the present invention can be prepared by utilizing precursor compounds with pre-defined or pre-selected particle sizes and morphologies. Any particle size can be utilized to create the composition of the present invention. For example, the particle size of a nickel donor precursor such as $\text{Ni}(\text{OH})_2$ can be in the range of about 2 μm to about 20 μm .

In accordance with one or more embodiments, the material molar ratios of the precursor compounds can be selected to provide a composition having the general material formula $\text{Li}_x\text{Mg}_y\text{NiO}_2$, where $0.1 < x < 1.3$, and $0.01 < y < 0.1$, $0.9 < x + y < 1.3$. In some cases, the ratios can be selected to so that $0.9 < x < 1.1$, and $0.02 < y < 0.05$. In still other cases, x can be about 1-y.

In yet other embodiments in accordance with the present invention, the $\text{Li}_x\text{Mg}_y\text{NiO}_2$ or $\text{Li}_{1-y}\text{Mg}_y\text{NiO}_2$ materials can have any one of the following formula: $\text{Li}_{1.05}\text{Mg}_{0.005}\text{NiO}_2$, $\text{Li}_{1.05}\text{Mg}_{0.01}\text{NiO}_2$, $\text{Li}_{1.05}\text{Mg}_{0.02}\text{NiO}_2$, $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$, $\text{Li}_{1.05}\text{Mg}_{0.030}\text{NiO}_2$, $\text{Li}_{1.05}\text{Mg}_{0.04}\text{NiO}_2$, and $\text{Li}_{1.05}\text{Mg}_{0.05}\text{NiO}_2$. Thus, the precursor compounds can be selected in such ratios that provide such compositions.

The precursor compounds are typically pre-mixed to allow homogeneous mixing. In still further embodiments, the materials of the present invention can be crystallized by, for example, heating to sinter and facilitate crystallization into the compositions of the present invention.

The synthesis process can comprise mixing the precursor compounds into a substantially homogeneous mixture. The synthesis process can further comprise heating the precursor mixture in one or more heating stages or steps, e.g., two or more heat soaks, according to a predetermined heating profile. The synthesis process typically promotes oxidation, or oxyhydroxide formation, of the corresponding donor components; mixing, typically ionic mixing, of such components; and crystallization into a lithium metal oxide composition, wherein the first metal of the composition, e.g., magnesium, is associated with a 3a site and the second metal, e.g., nickel, is associated with the 3b site. For example, in a lithium-magnesium-nickel oxide composition, the mixture can be heated to a first heating temperature that promotes preferential formation of Ni^{3+} over Ni^{2+} .

In accordance with one or more embodiments of the invention, the first heating step or stage can involve heating the green, precursor mixture to allow oxide formation and/or ion mixing without, or at least minimal, valence changes of the donor compounds. For example, the precursor mixture can be heated to a heat soak temperature of about 450° C. in

a first heating step. This first heat soaking temperature can range from about 350° C. to about 700° C. The second heating step can comprise heating to promote crystallization of the transformed oxide mixture by, for example, heat soaking at a second heat soak temperature of about 700° C. The second heat soaking temperature can range from about 600° C. to about 800° C.

Preferably, the first soaking temperature is maintained until the precursor compounds have been substantially transformed into their oxide counterparts. For example, the first soaking temperature can be maintained for about one hour but can be maintained for as long as about six hours. In accordance with other embodiments, the first heat soak condition can be maintained for any duration such that the synthesis procedure can proceed to the next heating stage to commence or promote crystallization, i.e., without maintaining a first soaking temperature. The second soaking temperature can be maintained, for example, until the lithium metal oxide has crystallized to a desired extent. Thus, for example, the second heat soak can be maintained for about one hour but can be maintained for as long as about six hours.

Heating, as well heat soaking, can be performed with exposure to an oxidizing atmosphere such as air or pure oxygen.

The first heating step can comprise raising the temperature at a rate sufficient to promote oxide formation while reducing any tendency to destabilize the precursor morphology. For example, the precursor mixture can be heated at a rate of about 20° C. per minute, about 10° C. per minute, or even about 5° C. per minute. Control of the heating rate may depend on several factors including, but not limited to, the amount being processed, the desired relative composition, as well as the effective area exposed to the oxidizing atmosphere. The second heating stage can comprise raising the temperature to be sufficient to facilitate crystallization such that the first metal tends to be associated with the 3a site and the second metal tends to be associated with the 3b site. For example, the oxide mixture can be heated at a rate of about 10° C. per minute, about 5° C. per minute, or even about 2° C. per minute.

After heat treatment, the materials can be allowed to cool naturally to room temperature by, for example, natural convection. Heat soaking can be performed in any suitable equipment. For example, a furnace or oven accommodating the mixture can be utilized. The furnace can be supplied with air and/or oxygen.

The sintered, crystallized material can be ground in any suitable grinding apparatus. For example, a mortar grinder (e.g., Model RM100 grinder available from Retsch/Brinkmann or Brinkmann Instruments, Inc., Westbury, New York) fitted with an agate mortar and pestle, can be utilized to grind the crystallized composition to render it with a desired particle size. Other suitable grinding methods or systems can include, for example, ball milling, jet milling, attritor mill, hammer mill and pin mill devices. The desired particle size can vary and can depend on the specific application or use. Thus, in accordance with one or more embodiments of the invention, the $\text{Li}_x\text{Mg}_y\text{NiO}_2$ composition can be formed as particles by grinding for about five minutes until a mean particle size of about 2 μm to about 20 μm , preferably about 5 μm to about 10 μm , is achieved.

In accordance with one or more preferred embodiments of the present invention, the $\text{Li}_x\text{Mg}_y\text{NiO}_2$ composition, typically as particles, can further comprise a coating layer that further improves a first cycle efficiency, life, and/or safety or even reduces gassing when the composition is utilized as a

cathodic material in electrochemical devices. In accordance with still further embodiments of the invention, the $\text{Li}_x\text{Mg}_y\text{NiO}_2$ particles further comprise one or more coating layers that reduces any gelling tendencies when the particles are prepared as an electrode paste. For example, the particles can be coated to reduce the likelihood of gelling in a mixture comprising NMP, PVDF, $\text{Li}_x\text{Mg}_y\text{NiO}_2$, and conductive carbon, which is yet another advantage over non-coated nickelates.

In accordance with one or more embodiments of the invention, the coating layer can comprise a composition having a formula LiCoO_2 . The coated $\text{Li}_x\text{Mg}_y\text{NiO}_2$ particles can be prepared by mixing therewith a lithium salt solution or mixture such as, but not limited to LiNO_3 , LiOH , LiAc , Li_2SO_4 , Li_2CO_3 , with a cobalt containing salt solution. In accordance with one or more embodiments of the invention, the lithium salt can comprise LiNO_3 and the cobalt salt can comprise $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$. The molar ratio of Li/Co can vary but typically ranges from about 0.6 to about 1.4. Preferably, the Li/Co molar ratio ranges from about 0.95 to about 1.05 so that the molar ratio of the Co content, in the coating layer, to the Ni content, in the core layer, ranges from about 0.01 to about 0.4, more preferably from about 0.05 to about 0.15.

If any water, which is typically carried with the salts, is present, it is preferably allowed to evaporate utilizing any suitable techniques. For example the mixture can be heated on a hot plate with stirring until dry, or in a rotating drying oven.

The precursor-coated material can then be heated or sintered in air using any suitable apparatus, such as a muffle furnace to facilitate oxidation and/or crystallization of the coating layer on the core. For example, the coating layer can be synthesized by raising the temperature of the precursor coated $\text{Li}_x\text{Mg}_y\text{NiO}_2$ particles at any suitable rate, such as about 5°C . per minute, and maintained or soaked at a temperature of about 450°C . for about one hour. A second soaking temperature can be utilized by raising the temperature at a rate of about 2°C . per minute and maintained at a temperature of about 700°C . for about two hours to promote crystallization of the coating layer. Such an exemplary sintering treatment can provide a coated material having a concentration gradient structure wherein more cobalt can be present at or near the outer surface compared to the region at or near the core layer. Other techniques may be utilized that provides a coated core material having the composition of the present invention.

The drying stage can be performed until the mixture is sufficiently dry. For example, drying can be performed by heating at a rate of about 2°C . per minute to a temperature of about 110°C . The drying temperature can be maintained as long as necessary and may last from 0 minutes to one or more hours.

The first heating rate to produce the one or more coating layers can vary and may range from about 2°C . per minute to about 10°C . per minute. The first heat soaking temperature can range from about 300°C . to about 500°C . This first heat soaking temperature can be maintained until the sufficient or desired oxide conversion has been achieved. It can be maintained from 0 minutes to one or more hours. The second heating rate can vary from about 2°C . per minute to about 10°C . per minute. The second heat soaking temperature can range from about 650°C . to about 750°C . It is believed that higher soaking temperatures may promote degradation of the core layer to other than the preferred crystallographic arrangement. The coated particles can be allowed to cool to room temperature.

Any suitable equipment may be utilized in the drying/heating/soaking process including, for example, any oven or furnace that provides an appropriate oxidizing atmosphere.

The sintered, coated material can be further processed to obtain a particle sized between about $8\text{ }\mu\text{m}$ to about $12\text{ }\mu\text{m}$. For example, the sintered, coated material can be ground for about five minutes in a mortar grinder fitted with an agate mortar and pestle.

EXAMPLES

The function and advantages of these and other embodiments of the present invention can be more fully understood from the examples below. The following examples illustrate the benefits and/or advantages of the compositions and techniques of the present invention but do not exemplify the full scope of the invention.

In the examples, the following test protocols were performed.

Protocol 1. Rate Capability Test and Formation—1st Cycle Efficiency

A coin cell was used for material life test utilizing lithium metal as the counter electrode. The positive electrode of the coin cell was made from a composite cathode prepared in accordance with Example 2. The electrolyte was EC/DEC (1:1)- LiPF_6 , 1 M (available from EM Industries, Inc., Hawthorne, N.Y.) and the separator was a glass fiber material (available from Fisher Scientific).

The cell was fully charged and discharged at a rate of C/20 for first cycle efficiency measurements, which is the ratio of the discharge capacity vs. the charge capacity. Thereafter the cell was cycled at rates of about C/5, C/2, 1C, 2C, 3C, and 5C from about 2.7 volts to about 4.2 volts. 1C rate was defined as about 150 mAh/g discharge in 1 hour.

Protocol 2. Life Cycle Test.

A coin cell was used for material life test. The positive electrode of the coin cell was made from a composite cathode, and the negative electrode was made from a composite anode, consisting of graphite as mesophase carbon microbeads (MCMB 2528, 90 wt %), PVDF binder (7 wt %) and carbon black (3 wt %). The electrolyte was EC/DEC (1:1)- LiPF_6 , 1 M (available from EM Industries, Inc., Hawthorne, New York) and the separator was a glass fiber material (available from Fisher Scientific).

The cell was initially fully charged and discharged for 3 cycles at about C/5 rate, deep cycle. The deep cycles consisted of charging to about 4.2 V (fully charged) and discharging to about 2.7 V (fully discharged). The cell was fully charged, to about 4.2 V (100% state-of-charge (SOC)); the cell was then discharged to about 20% of full capacity at about 1C rate current to reach about an 80% SOC. Then the cell was cycled: discharging about 10% (to about 70% SOC) and charged 10% (to about 80% SOC) at about 1C rate current, typically referred to as a shallow cycle.

A deep cycle was performed after every 200 shallow cycles. This test provided an indication of the effective life of the cell under evaluation.

Protocol 3. Area Specific Impedance (ASI) Measurement.

The ASI, in Ωcm^2 , at various starting SOC conditions was determined by pulse discharging a coin cell. ASI was calculated according to:

$$ASI = A \cdot (\Delta V / I),$$

where A is the electrode area in cm^2 , where I is the discharge current pulse at a rate of about 6C. The voltage variation (ΔV) is the voltage change during the discharge pulse.

11

For example, at a SOC=90%, the initial voltage is measured. The cell is discharged at a rate of 6C and the final voltage is measured after 18 sec.

ASI can correlate to the potential available power and allows for a comparison of power capability between materials and formulations for Li-ion cells. This can be particularly important for high pulse power applications.

Example 1

Synthesis of $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ Composition

A $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ composition was prepared and evaluated. The composition was prepared by dry mixing:

about 242.91 g $\text{Li}(\text{OH})_2$ (anhydrous fine powder available from Sigma-Aldrich, Inc., St. Louis, Mo.)

about 14.79 g $\text{Mg}(\text{OH})_2$ (fine powder available from Alfa Aesar, Ward Hill, Mass.)

about 34.97 g LiNO_3 (crystals available from Alfa Aesar, Ward Hill, Mass.)

The mixed materials were added to about 940.31 g $\text{Ni}(\text{OH})_2$ (#543 high density spherical powder available from OM Group, Inc., Cleveland, Ohio) in a 1 liter jar. The compounds were mixed by shaking in the jar.

The homogeneous precursor powders (precursor compounds) were placed in alumina crucibles and sintered.

Sintering was performed by heating at a rate of about 5° C./minute to about 450° C. and held at about 450° C. for about four hours. The temperature was then raised at about 2° C./minute to about 700° C. and held for about four hours.

The sample was then allowed to cool naturally to room temperature. The cooled sample was ground for about five minutes to break up any agglomerates. The powder material was sieved through a No. 270 mesh to remove larger particles and to ensure a desired 10 μm particle size.

FIG. 1 is a copy of scanning electron micrograph showing the morphology of the about 10 μm spherical core material. An X-ray diffraction pattern (XRD) analysis was performed and showed that the produced composition was phase-pure with no visible impurities. FIG. 2 is a copy of the XRD plot of the resultant composition. The XRD data shows that the resulting powder is essentially free of impurities.

Example 2

Fabrication and Electrochemical Performance Evaluation of $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ -Based Electrochemical Cells

A $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ cathode was fabricated by mixing about 90 wt % active cathode material powder produced as described in Example 1, about 6 wt % carbon black (AB 100% available from Chevron Phillips Chemical Company LP, The Woodlands, Tex.), and about 4 wt % K1120 binder containing 12% PVDF in NMP (available from Kureha Chemical of Japan). Additional NMP (n-methyl pyrrolidone) was added to produce a desired viscosity and promote mixing.

The solution was mixed in a 250 ml jar with about 50 steel balls on a paint shaker for about 30 minutes. The mixed slurry was coated onto an aluminum foil, about 20 μm thick, with a doctor blade having about a 100 μm micron coating gap.

The coated foil was dried at about 130° C. for about thirty minutes. The dried, coated foil was then densified by passing the dried, coated foil through pressurized calender rolls, about 3 inch diameter, set at about 100 psi. The densified,

12

dried, coated foil was cut into about 2 cm^2 disks for use as electrodes. The active material weight on the disk electrodes was typically about 20 mg. The disk electrode was dried at about 80° C. under vacuum for about sixteen hours before cell assembly.

A coin cell (Hosen type #2025) was assembled by utilizing the disk electrode as the cathode. The coin cell was comprised of a glass fiber separator containing EC/DEC (1:1)- LiPF_6 , 1 M electrolyte (available from EM Industries, Inc., Hawthorne, N.Y.) and a lithium metal anode. All assembly operations were performed in an argon-filled glove box wherein water and oxygen levels were less than about 2 ppm.

The assembled coin cell was evaluated using a cycler/tester (available from Maccor, Inc., Tulsa, Okla.) for capacity, efficiency, rate capability, power and cyclability, according to protocols 1, 2, and 3, described above. The electrochemical performance of the $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ composition (i.e., 0% coating) data are listed in Table 1 below. The discharge voltage profiles at different discharge rates are shown in FIG. 3, which shows that the capacity of the $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ composition was typically about 190 mAh/g.

TABLE 1

Electrochemical performance of $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ -based cell.						
Coating Level mol %	1 st Cycle Efficiency %	Specific Capacity at Specified Rate				
		C/5 mAh/g	1C mAh/g	2C mAh/g	3C mAh/g	5C mAh/g
0%	87	203	192	185	180	172
5%	92	202	194	186	181	165
10%	89	197	190	179	175	162
15%	90	191	184	173	169	141

Example 3

Safety Testing of $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ Cathode

Coated cathodes were prepared and evaluated. The densified electrode prepared as described in Example 2 was cut into flag-shaped electrodes of about 60×50 mm^2 . The active material weight on the electrode was typically about 300 mg. Similar to the cathode, an anode was prepared with formulation of MCMB:PVDF (93:7) was coated on a copper foil and cut to form 60×50 mm^2 flag electrodes. These were similarly densified by calendering at 175 psi. The flag electrodes were dried at about 80° C., under vacuum for about sixteen hours.

A two-electrode bag cell was assembled. The cell was comprised of the dried anode and cathodes, separated by a glass fiber separator with a rectangular size of about 65×55 mm^2 . About 1.6 ml of EC/DEC (1:1)- LiPF_6 , 1 M electrolyte was allowed to soak into the electrodes and separator and the assembly was compressed between two 70×60 mm^2 glass plates. The whole assembly was put into an aluminum-laminated bag, approximately 80×70 mm^2 , and sealed under vacuum.

All assembly operations were performed in an argon-filled glove box wherein water and oxygen levels were less than about 2 ppm.

13

The bag cells were charged and discharged at about C/10 current rate, between about 4.1 V to about 2.7 V, then charged at about C/5 current rate to a capacity of about 180 mAh/g to about 200 mAh/g.

The cells with charged composite cathode were disassembled in an argon-filled glove box. The composite cathode powder was removed from the aluminum current collector. The composite electrode powder, with EC/DEC(1:1)-LiPF₆, 1 M electrolyte in a weight ratio of powder/electrolyte of 1:1, was loaded into a sealed pressure tight DSC pan. DSC measurements were performed with a continuous scan rate of about 5° C./minute up to about 450° C.

The safety data shown in FIG. 13 shows DSC curves of Li_{1.05}Mg_{0.025}NiO₂ and 5% LiCoO₂ coated material compared to LiNi_{0.8}Co_{0.15}Al_{0.005}O₂ (CA1505N cell available from TODA Co., Japan). The DSC curves provide a signature of chemical reactivity during exothermic reactions.

Example 4

Comparison to Li_{1.05}NiO₂-Based Electrochemical Cells

A Li_{1.05}NiO₂ composition was prepared by dry mixing: about 244.42 g Li(OH)₂ (anhydrous fine powder) about 35.18 g LiNO₃ (crystals)

The mixed materials were added to about 946.15 g Ni(OH)₂ (OM Group, Inc. #543 High density spherical powder) in a 1 liter jar. The precursor powder mixture was mixed by shaking.

The precursor powders were placed in alumina crucibles and sintered. Sintering was performed by heating at a rate of about 5° C./minute to about 450° C. and held at about 450° C. for about four hours. The temperature was raised at about 2° C./minute to about 700° C. and held for about four hours.

The sample was then allowed to cool naturally to room temperature.

The cooled sample was ground for about five minutes to break up any agglomerates. The powder material was sieved through a No. 270 mesh to remove large particles and to ensure the desired 10 μm particle size. When subjected to XRD analysis, this material was shown to be phase-pure with no visible impurities. Electrochemical measurements of this powder were performed in accordance with the procedure described in Example 2. The performance results are listed in Table 2 (i.e., 0% coating).

TABLE 2

Electrochemical performance of LiNiO ₂ -based cell.						
Coating Level atom %	1 st Cycle Efficiency %	Specific Capacity at Specified Rate				
		C/5 mAh/g	1C mAh/g	2C mAh/g	3C mAh/g	5C mAh/g
0%	89	211	192	184	178	154
5%	88	214	203	197	190	166
10%	90	209	196	192	184	168
15%	89	197	185	179	172	151

14

The data show that the performance, as quantified by specific capacity, of the LiMg_yNiO₂-based electrochemical cells of the present invention (see Table 1) are amongst the highest when comparing to the performance of typical lithium-nickel oxide materials.

Example 5

Comparison to LiCoO₂-Based Electrochemical Cells

A comparable composite cathode in an electrochemical cell was prepared using LiCoO₂ (C-5 grade available from Nippon Chemical Industrial Co., LTD., Tokyo, Japan) as the active material. Similar coin cells were prepared as in the previous example for evaluation.

The electrochemical data of this material are listed in Table 3.

TABLE 3

Electrochemical performance of LiCoO ₂ -based cell.						
Sample	1 st Cycle Efficiency %	Specific Capacity at Specified Rate				
		C/5 mAh/g	1C mAh/g	2C mAh/g	3C mAh/g	5C mAh/g
LiCoO ₂	97	157	143	127	108	71

The data show that the electrochemical performance of the Li_{1.05}Mg_{0.025}NiO₂-based electrochemical cell of the present invention (see Table 1) exceeds the performance of typical lithium-cobalt oxide-based cells, which is the dominating material in the market presently.

Example 6

Performance of Varying Dopant Levels in Li_{1.05}Mg_yNiO₂ Material (y=0.005, 0.01, 0.02, 0.025, 0.03, 0.04, and 0.05)

Seven Li_{1.05}Mg_yNiO₂ compositions were prepared and evaluated where y varied from 0.005, 0.01, 0.02, 0.03, 0.04 and to 0.05. The synthesis procedure for these compositions were substantially similar to the procedure described in Example 1 except that the levels of Mg(OH)₂ were varied accordingly to obtain the various dopant levels.

When subjected to XRD analyses, all samples except for the sample having y=5% were shown to be phase-pure with no visible impurities. For this latter composition, Li_{1.05}Mg_{0.05}NiO₂, impurities were detected that indicated the presence of mixed magnesium oxides.

All samples were then tested electrochemically in coin cells prepared similar to the procedure described in Example 2. The results are listed in Table 4.

TABLE 4

Electrochemical Properties of $\text{LiMg}_y\text{NiO}_2$ at varying Mg doping levels.							
Mg Doping Level in $\text{LiMg}_y\text{NiO}_2$	1 st Cycle Efficiency %	Specific Capacity at Specified Rate					
		C/20 mAh/g	C/5 mAh/g	1C mAh/g	2C mAh/g	3C mAh/g	5C mAh/g
0	89	227	211	192	184	178	154
0.005	90	226	210	191	183	176	166
0.01	90	223	207	191	184	178	169
0.02	89	218	204	189	183	178	169
0.025	87	214	203	192	185	180	172
0.03	87	210	199	187	181	176	167

The data in Table 4 show that the electrochemical performance, e.g., at specific capacity at 1C rate, of the $\text{LiMg}_y\text{NiO}_2$ -based cells of the present invention was better when compared to the performance of LiNiO_2 -based cells, and superior to the performance of LiCoO_2 -based cells.

Example 7

Synthesis of $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ Core Particles Coated with a LiCoO_2 Layer

In this example, a lithium-magnesium-nickel oxide composition, substantially prepared as described in Example 1, was coated with a lithium-cobalt oxide layer.

To synthesize the coating layer, about 105.55 g LiNO_3 (crystalline powder, available from Alfa Aesar, Ward Hill, Mass.) and about 445.50 g $\text{Co}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ (crystalline aggregates, also available from Alfa Aesar) were dissolved in about 200-300 ml distilled water. To which, about 1000 g of the $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ powder substantially prepared as described in Example 1 was added.

The excess water was removed by evaporation on a hot plate with stirring until the mixture became a thick slurry. The slurry was poured into an alumina crucible and sintered under the following heating profile: heat at a rate of about 2°C./min to about 110°C. , hold for about one hour at about 110°C. , heat at a rate of 5°C./min to about 450°C. , heat soak for about one hour at about 450°C. , heat at a rate of about 2°C./min to about 700°C. , and heat soak for about two hours at about 700°C.

The prepared sample was allowed to cool naturally to room temperature. Once cooled, it was ground for about five minutes to break up any agglomerates and sieved through a No. 270 mesh screen.

XRD analysis shows that the prepared coated composition had a gradient profile, with no visible impurities, as can be seen in the copy of the XRD plot presented in FIG. 5 represented here by 5 mol % LiCoO_2 coated $\text{LiMg}_{0.025}\text{NiO}_2$. A copy of an SEM photomicrograph for the same sample, FIG. 4, shows that the coated powder composition maintained its spherical, about 10 μm , morphology.

Table 1 lists rate capability and first cycle efficiency of $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ core materials coated with various levels of LiCoO_2 coating. FIGS. 6-8 are graphs showing the discharge profile of the LiCoO_2 -coated $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ -based core composition having, respectively, about 5 mol % coating, about 10 mol % coating, and about 15 mol % coating. The profiles show that the lithium-magnesium-nickel composition can be coated with up to about 15 mol % lithium-cobalt oxide layer and retain about the same elec-

trochemical performance. FIG. 11 is an XRD comparison of these samples showing increasing gradients with amount of LiCoO_2 coating.

Example 8

Evaluation of LiCoO_2 -Coated $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ Core Material

Two gradient coated $\text{Li}_{1.05}\text{Mg}_{0.025}\text{NiO}_2$ materials were synthesized and coated with about 10% and about 15% LiCoO_2 using the method in Examples 1 and 7. The gradient coating was detected by studying the increasing degree of asymmetry in the Bragg reflections. In particular, the peak 104 at about 44.4 degrees in 2-theta was used (FIG. 11) to show how the asymmetry of peak 104 continuously increased with the amount of LiCoO_2 . The respective XRD patterns in FIG. 11 have been adjusted for 2-theta zero point position and normalized in intensity for comparison (shown in the insert in the right side of FIG. 11). The gradient coated samples were also evaluated electrochemically for rate capability and first cycle efficiency as listed in Table 1, according to protocol 1.

Example 9

Comparison of LiCoO_2 -coated $\text{Li}_{1.05}\text{NiO}_2$ Core Material

Three gradient coated $\text{Li}_{1.05}\text{NiO}_2$ materials were synthesized and coated with 5%, 10% and 15% LiCoO_2 using the methods as substantially described in Examples 4 and 7. The coated samples were tested electrochemically for rate capability and first cycle efficiency as described above and protocol 1. The specific capacity results, listed in Table 2, show that lithium cobalt oxide coated lithium nickel oxide compounds of the present invention can provide better or at least equal performance capacity compared to non-coated compounds.

FIG. 9 shows the ASI of a cell utilizing the LiCoO_2 -coated $\text{Li}_{1.05}\text{NiO}_2$ material, measured according to protocol 3 above and FIG. 10 shows several ASI measurements of a cell utilizing uncoated LiMgNiO_2 material. As shown in FIGS. 9 and 10, the performance, in terms of potential available power, of the lithium-cobalt-oxide coated lithium-nickel-oxide cells is comparable, if not better than cells utilizing the uncoated lithium-nickel-oxide materials. FIG. 12 shows the capacity retention at a discharge rate of about 1C of cells utilizing various active materials including lithium-nickel oxide, lithium magnesium nickel oxide,

17

lithium-cobalt-oxide coated lithium magnesium nickel oxide, $\text{LiN}_{1.08}\text{Co}_{0.15}\text{Al}_{0.05}\text{O}_2$ (CA1505 cell available from TODA Co., Japan), and LiCoO_2 (C-5 grade available from Nippon Chemical Industrial Co., LTD., Tokyo, Japan). The results presented in FIG. 12 indicate that the cells utilizing the coated and uncoated lithium-magnesium-nickel oxides of the invention can have better performance compared to cells utilizing lithium cobalt oxide. FIG. 13 is a graph showing the differential scanning calorimetry of the uncoated and lithium-cobalt oxide-coated lithium-magnesium-nickel oxide material of the present invention compared to a commercially available lithium-nickel-cobalt oxide material at about a 100% state of charge and shows that the coated and uncoated materials are more thermally stable.

Those skilled in the art should appreciate that the parameters and configurations described herein are exemplary and that actual parameters and/or configurations will depend upon the specific application in which the systems and methods of the present invention are used. Those skilled in the art should recognize or be able to ascertain, using no more than routine experimentation, equivalents to the specific embodiments of the invention. For example, the shape of the particles of the present invention, in either the coated or uncoated embodiments, can include particles shaped to facilitate packing and/or increase packing and/or tap density such as, but not limited to, plates or having one dimension substantially greater than a second and/or third dimension. Further, a range or combination of particle sizes can also be utilized. For example, a mixture of lithium cobalt oxide coated lithium magnesium nickel oxide particles with uncoated lithium magnesium nickel oxide particles can be utilized in the systems, device, and techniques of the present invention wherein the mixture can have a first type or kind of particle, e.g. uncoated, having a first particle size and a second type or kind of particle, e.g. coated and/or a different Mg loading, having a second particle size. It is therefore to be understood that the foregoing embodiments are presented by way of example only and that, within the scope of the appended claims and equivalents thereto, the invention may be practiced otherwise than as specifically described. Further, it is to be appreciated various alterations, modifications, and improvements will readily occur to those skilled in the art. Such alterations, modifications, and improvements are intended to be part of this disclosure, and are intended to be within the spirit and scope of the invention. Moreover, the present invention is directed to each feature, system, or method described herein and any combination of two or more features, systems, and/or methods, if such features, systems, or methods are not mutually inconsistent, is considered to be within the scope of the present invention as embodied in the claims. The use of the clarifiers such as "first" and "second" or even "third" and "fourth" is intended to modify an element and does not create an implication of priority, precedent, sequence, or temporal order, over another but is intended as labels.

18

What is claimed is:

1. An electrode composition comprising:

a first material having a formula consisting of $\text{Li}_x\text{Mg}_y\text{NiO}_2$ wherein $0.9 < x < 1.3$, $0.01 < y < 0.1$, and $0.91 < x + y < 1.3$; and

a second material applied upon the first material, the second material having a formula $\text{Li}_a\text{Co}_b\text{O}_2$ wherein $0.7 < a < 1.3$, and $0.9 < b < 1.2$.

2. The composition of claim 1 wherein $0.9 < a < 1.3$ and $0.9 < b < 1.2$.

3. The composition of claim 1 wherein the molar ratio of Co:Ni ranges between about 0.01 to about 0.8.

4. The composition of claim 1 wherein $0.9 < x < 1.1$ and $0.02 < y < 0.05$.

5. The composition of claim 4 wherein $x = 1.05$ and $y = 0.025$.

6. The composition of claim 1, wherein Li and Mg are predominantly associated with a crystallographic 3a site and Ni is predominantly associated with a crystallographic 3b site.

7. The composition of claim 1, wherein the second material has a concentration gradient with respect to the amount of cobalt therein.

8. An electrochemical cell comprising an electrode comprising particles comprising a first material having a formula consisting of $\text{Li}_x\text{Mg}_y\text{NiO}_2$, wherein $0.9 < x < 1.3$, $0.01 < y < 0.1$, and $0.91 < x + y < 1.3$, and a second material having a formula $\text{Li}_a\text{Co}_b\text{O}_2$, wherein $0.7 < a < 1.3$, and $0.9 < b < 1.2$.

9. The electrochemical cell of claim 8 wherein $0.9 < x < 1.1$, $0.02 < y < 0.05$, $0.9 < a < 1.3$, and $0.9 < b < 1.2$.

10. The electrochemical cell of claim 9 wherein $x = 1.05$ and $y = 0.025$, and $a = 1$.

11. The electrochemical cell of claim 8, wherein Li and Mg are predominantly associated with a crystallographic 3a site and Ni is predominantly associated with a crystallographic 3b site.

12. The electrochemical cell of claim 8, wherein the second material has a concentration gradient with respect to the amount of cobalt therein.

13. The electrochemical cell of claim 8, wherein the first material is formed by heating a first mixture comprising sources of lithium, magnesium, and nickel in an oxidizing atmosphere at a temperature of about 350°C to 800°C .

14. The electrochemical cell of claim 13, wherein the first material is formed by heating the first mixture for a period sufficient to crystallize the first mixture such that lithium and magnesium are predominantly associated with a crystallographic 3a site and nickel is predominantly associated with a crystallographic 3b site.

15. The electrochemical cell of claim 13, wherein the second material is formed by heating the first mixture and a second mixture comprising sources of lithium and cobalt at a temperature of about 300°C to 900°C .

* * * * *