



(51) International Patent Classification:
H01L 27/146 (2006.01) **H01L 27/148** (2006.01)

(21) International Application Number:
PCT/US2010/049375

(22) International Filing Date:
17 September 2010 (17.09.2010)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
61/243,434 17 September 2009 (17.09.2009) US
61/311,004 5 March 2010 (05.03.2010) US
61/311,107 5 March 2010 (05.03.2010) US

(71) Applicant (for all designated States except US):
SIONYX, INC. [—/US]; 100 Cummings Ctr., Suite 243-F, Beverly, MA 01915-6506 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **HADDAD, Homayoon** [—/US]; 16460 Sanderling CT., Beaverton, OR 97007 (US). **JIANG, Jutao** [CN/US]; 15121 Sw Kenton Dr., Tigard, OR 97224 (US). **MCKEE, Jeffrey** [US/US]; 22850 Sw Eno PL., Tualatin, OR 97224 (US). **MILLER, Drake** [US/US]; 13052 Sw Jacob CT., Tigard, OR 97224 (US). **FORBES, Leonard** [US/US]; 7340 Nw Mountain View Drive, Corvallis, OR 97330 (US). **PALSULE, Chintamani** [US/US]; 100 Cummings CTR., Suite 243-F, Beverly, MA 01915-6506 (US).

(74) Agents: **ALDER, Todd, B.** et al.; Thorpe North & Western, LLP, Po Box 1219, Sandy, UT 84091-1219 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report (Rule 48.2(g))

(54) Title: PHOTSENSITIVE IMAGING DEVICES AND ASSOCIATED METHODS




FIG. 1

(57) Abstract: Photosensitive devices and associated methods are provided. In one aspect, for example, a photosensitive imager device can include a semiconductor substrate having multiple doped regions forming at least one junction, a textured region coupled to the semiconductor substrate and positioned to interact with electromagnetic radiation, and an electrical transfer element coupled to the semiconductor substrate and operable to transfer an electrical signal from the at least one junction. In one aspect, the textured region is operable to facilitate generation of an electrical signal from the detection of infrared electromagnetic radiation. In another aspect, interacting with electromagnetic radiation further includes increasing the semiconductor substrate's effective absorption wavelength as compared to a semiconductor substrate lacking a textured region.



WO 2011/035188 A2

PHOTOSENSITIVE IMAGING DEVICES AND ASSOCIATED METHODS

PRIORITY DATA

This application claims the benefit of U.S. Provisional Patent Application
5 Serial No. 61/243,434, filed on September 17, 2009, U.S. Provisional Patent
Application Serial No. 61/311,004 filed on March 5, 2010, and U.S. Provisional
Patent Application Serial No. 61/311,107, filed on March 5, 2010, each of which is
incorporated herein by reference.

10 BACKGROUND

The interaction of light with semiconductor materials has been a significant
innovation. Silicon imaging devices are used in various technologies, such as digital
cameras, optical mice, video cameras, cell phones, and the like. Charge-coupled
devices (CCDs) were widely used in digital imaging, and were later improved upon
15 by complementary metal-oxide-semiconductor (CMOS) imagers having increased
performance. CMOS sensors are typically manufactured from silicon and can convert
visible incident light into a photocurrent and ultimately into a digital image. Silicon-
based technologies for detecting infrared incident electromagnetic radiation have been
problematic, however, because silicon is an indirect bandgap semiconductor having a
20 bandgap of about 1.1 eV. Thus the absorption of electromagnetic radiation having
wavelengths of greater than about 1100 nm is, therefore, very low in silicon.

SUMMARY

The present disclosure provides photosensitive devices and associated
25 methods. In one aspect, for example, a photosensitive imager device can include a
semiconductor substrate having multiple doped regions forming at least one junction,
a textured region coupled to the semiconductor substrate and positioned to interact
with electromagnetic radiation, and an electrical transfer element coupled to the
semiconductor substrate and operable to transfer an electrical signal from the at least
30 one junction. In one aspect, the textured region is operable to facilitate generation of
an electrical signal from the detection of infrared electromagnetic radiation. In
another aspect, interacting with electromagnetic radiation further includes increasing
the semiconductor substrate's effective absorption length as compared to a
semiconductor substrate lacking a textured region. In one specific aspect, the transfer

element is selected from the group consisting of a transistor, a sensing node, a transfer gate, and combinations thereof.

The textured region can be positioned in a variety of locations relative to the doped regions. In one aspect, for example, the textured region is positioned on a surface of the semiconductor substrate that is opposite the multiple doped regions. In one specific aspect, the textured region has a surface morphology operable to direct electromagnetic radiation into or out of the semiconductor substrate. The surface morphology of the textured region relative to the semiconductor substrate can include a variety of configurations, including, without limitation, sloping, pyramidal, inverted pyramidal, spherical, parabolic, asymmetric, symmetric, and the like, including combinations thereof.

In another aspect, the textured region can be positioned on a surface of the semiconductor substrate that is adjacent the multiple doped regions. In a more specific aspect, an additional textured region can be positioned on a surface of the semiconductor substrate that is opposite the multiple doped regions. In this manner, textured regions can thus be positioned adjacent to multiple doped regions and opposite the multiple doped regions.

Various aspects of the textured region can vary depending on the desired configuration of the device. In one aspect, however, the textured region includes surface features having a size selected from the group consisting of micron-sized, nano-sized, and combinations thereof. Numerous surface feature morphologies are contemplated, nonlimiting examples of which include cones, pillars, pyramids, microlenses, quantum dots, inverted features, and combinations thereof. Additionally, the textured region can be formed by a variety of processes. Nonlimiting examples of such texturing processes can include lasing, chemical etching (e.g. anisotropic etching, isotropic etching), nanoimprinting, material deposition, and combinations thereof.

Additional layers and/or structures can be included in various devices according to aspects present disclosure. In one aspect, for example, a reflective layer can be coupled to the semiconductor substrate and positioned to maintain the electromagnetic radiation in the semiconductor substrate. In another aspect, a lens can be optically coupled to the semiconductor substrate and positioned to focus incident electromagnetic radiation into the semiconductor substrate.

In another aspect of the present disclosure, a method of making a photosensitive imager device is provided. Such a method can include forming a textured region on a semiconductor substrate having multiple doped regions forming a least one junction, wherein the textured region is formed in a position to interact with electromagnetic radiation and coupling an electrical transfer element to the semiconductor substrate such that the electrical transfer element is operable to transfer an electrical signal from the at least one junction.

In one aspect, the photosensitive imager device can be tuned to be selected to filter out specific electromagnetic radiation wavelengths. In one specific aspect, tuning includes forming surface features to have dimensions that selectively diffuse or selectively absorb a desired wavelength of electromagnetic radiation. In another aspect, tuning is accomplished through a factor selected from the group consisting of placement of the textured region, material type and/or thickness of the textured region, dopant type of the textured region, doping profile of the texture region, dopant profile of the semiconductor substrate, material type and/or thickness of the semiconductor substrate, and combinations thereof.

In another aspect of the present disclosure, a photosensitive imager device is provided. Such a device can include a semiconductor substrate having multiple doped regions forming a least one junction, a textured region coupled to the semiconductor substrate and positioned to interact with electromagnetic radiation, and at least 4 transistors coupled to the semiconductor substrate and with at least one of the transistors electrically coupled to the at least one junction.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic view of a photosensitive device in accordance with one aspect of the present disclosure;

FIG. 2 is a schematic view of a photosensitive device in accordance with another aspect of the present disclosure;

FIG. 3 is a schematic view of a photosensitive device in accordance with yet another aspect of the present disclosure;

FIG. 4 is a schematic view of a photosensitive device in accordance with a further aspect of the present disclosure;

FIG. 5 is a schematic view of a photosensitive device in accordance with yet a further aspect of the present disclosure;

FIG. 6 is a schematic view of a photosensitive device in accordance with another aspect of the present disclosure;

FIG. 7 is a schematic view of a photosensitive pixel device in accordance with yet another aspect of the present disclosure;

5 FIG. 8 is a schematic view of a photosensitive pixel device in accordance with a further aspect of the present disclosure;

FIG. 9 is a schematic view of a photosensitive pixel device in accordance with yet a further aspect of the present disclosure;

10 FIG. 10 is a schematic view of a photosensitive pixel device in accordance with another aspect of the present disclosure;

FIG. 11 is a schematic view of a photosensitive pixel device in accordance with yet another aspect of the present disclosure;

FIG. 12 is a schematic view of a photosensitive pixel device in accordance with a further aspect of the present disclosure;

15 FIG. 13 is a schematic view of a photosensitive pixel device in accordance with another aspect of the present disclosure;

FIG. 14 is a schematic view of a photosensitive imager device in accordance with yet another aspect of the present disclosure;

20 FIG. 15 is a schematic view of a photosensitive pixel device in accordance with a further aspect of the present disclosure;

FIG. 16 is a schematic view of a photosensitive pixel device in accordance with another aspect of the present disclosure; and

FIG. 17 is a depiction of a method of making a photosensitive imager device in accordance with yet another aspect of the present disclosure.

25

DETAILED DESCRIPTION

Before the present disclosure is described herein, it is to be understood that this disclosure is not limited to the particular structures, process steps, or materials disclosed herein, but is extended to equivalents thereof as would be recognized by those ordinarily skilled in the relevant arts. It should also be understood that terminology employed herein is used for the purpose of describing particular embodiments only and is not intended to be limiting.

30

Definitions

The following terminology will be used in accordance with the definitions set forth below.

It should be noted that, as used in this specification and the appended claims,
5 the singular forms “a,” and, “the” include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to “a dopant” includes one or more of such dopants and reference to “the layer” includes reference to one or more of such layers.

As used herein, the term “low oxygen content” refers to any material having
10 an interstitial oxygen content that is less than or equal to about 60 ppm atomic.

As used herein, the terms “disordered surface” and “textured surface” can be used interchangeably, and refer to a surface having a topology with nano- to micron-sized surface variations formed by the irradiation of laser pulses. While the characteristics of such a surface can be variable depending on the materials and
15 techniques employed, in one aspect such a surface can be several hundred nanometers thick and made up of nanocrystallites (e.g. from about 10 to about 50 nanometers) and nanopores. In another aspect, such a surface can include micron-sized structures (e.g. about 2 μm to about 60 μm). In yet another aspect, the surface can include nano-sized and/or micron-sized structures from about 5 nm and about 500 μm .

As used herein, the term “fluence” refers to the amount of energy from a
20 single pulse of laser radiation that passes through a unit area. In other words, “fluence” can be described as the energy density of one laser pulse.

As used herein, the terms “surface modifying” and “surface modification” refer to the altering of a surface of a semiconductor material using laser radiation. In
25 one specific aspect, surface modification can include processes using primarily laser radiation or laser radiation in combination with a dopant, whereby the laser radiation facilitates the incorporation of the dopant into a surface of the semiconductor material. Accordingly, in one aspect surface modification includes doping of a semiconductor material.

As used herein, the term “target region” refers to an area of a semiconductor
30 material that is intended to be doped or surface modified using laser radiation. The target region of a semiconductor material can vary as the surface modifying process progresses. For example, after a first target region is doped or surface modified, a second target region may be selected on the same semiconductor material.

As used herein, the term “detection” refers to the sensing, absorption, and/or collection of electromagnetic radiation.

As used herein, the term “substantially” refers to the complete or nearly complete extent or degree of an action, characteristic, property, state, structure, item, or result. For example, an object that is “substantially” enclosed would mean that the object is either completely enclosed or nearly completely enclosed. The exact allowable degree of deviation from absolute completeness may in some cases depend on the specific context. However, generally speaking the nearness of completion will be so as to have the same overall result as if absolute and total completion were obtained. The use of “substantially” is equally applicable when used in a negative connotation to refer to the complete or near complete lack of an action, characteristic, property, state, structure, item, or result. For example, a composition that is “substantially free of” particles would either completely lack particles, or so nearly completely lack particles that the effect would be the same as if it completely lacked particles. In other words, a composition that is “substantially free of” an ingredient or element may still actually contain such item as long as there is no measurable effect thereof.

As used herein, the term “about” is used to provide flexibility to a numerical range endpoint by providing that a given value may be “a little above” or “a little below” the endpoint.

As used herein, a plurality of items, structural elements, compositional elements, and/or materials may be presented in a common list for convenience. However, these lists should be construed as though each member of the list is individually identified as a separate and unique member. Thus, no individual member of such list should be construed as a de facto equivalent of any other member of the same list solely based on their presentation in a common group without indications to the contrary.

Concentrations, amounts, and other numerical data may be expressed or presented herein in a range format. It is to be understood that such a range format is used merely for convenience and brevity and thus should be interpreted flexibly to include not only the numerical values explicitly recited as the limits of the range, but also to include all the individual numerical values or sub-ranges encompassed within that range as if each numerical value and sub-range is explicitly recited. As an illustration, a numerical range of “about 1 to about 5” should be interpreted to include

not only the explicitly recited values of about 1 to about 5, but also include individual values and sub-ranges within the indicated range. Thus, included in this numerical range are individual values such as 2, 3, and 4 and sub-ranges such as from 1-3, from 2-4, and from 3-5, etc., as well as 1, 2, 3, 4, and 5, individually.

5 This same principle applies to ranges reciting only one numerical value as a minimum or a maximum. Furthermore, such an interpretation should apply regardless of the breadth of the range or the characteristics being described.

The Disclosure

10 Electromagnetic radiation can be present across a broad wavelength range, including visible range wavelengths (approximately 350nm to 800nm) and non-visible wavelengths (longer than about 800nm or shorter than 350 nm). The infrared spectrum is often described as including a near infrared portion of the spectrum including wavelengths of approximately 800 to 1300 nm, a short wave infrared
15 portion of the spectrum including wavelengths of approximately 1300 nm to 3 micrometers, and a mid to long wave infrared (or thermal infrared) portion of the spectrum including wavelengths greater than about 3 micrometers up to about 30 micrometers. These are generally and collectively referred to herein as “infrared” portions of the electromagnetic spectrum unless otherwise noted.

20 Traditional silicon photodetecting imagers have limited light absorption/detection properties. For example, infrared light is mostly transparent to such silicon based detectors. While other materials (e.g. InGaAs) can be used to detect infrared electromagnetic radiation having wavelengths greater than about 1000 nm, silicon is still commonly used because it is relatively cheap to manufacture and can be
25 used to detect wavelengths in the visible spectrum (i.e. visible light, 350 nm – 800 nm). Traditional silicon materials require substantial absorption depths to detect photons having wavelengths longer than approximately 700 nm. While visible light can be absorbed at relatively shallow depths in silicon, absorption of longer wavelengths (e.g. 900 nm) in silicon of a standard wafer depth (e.g. approximately
30 750 μ m) is poor if at all. The devices of the present disclosure increase the absorption of semiconductor materials by decreasing the effective absorption length to longer wavelengths as compared to traditional materials. For example, the absorption depth of silicon can be reduced such that these longer wavelengths can be absorbed at depths of less than or equal to about 850 μ m. In other words, by decreasing the

effective absorption length these devices are able to absorb longer wavelengths (e.g. >1000 nm for silicon) within a thin semiconductor material. In addition to increasing the effective absorption length, the response rate or response speed can also be increased using thinner semiconductor materials.

5 The present disclosure additionally provides broadband photosensitive diodes, pixels, and imagers capable of detecting visible as well as infrared electromagnetic radiation, including associated methods of making such devices. A photosensitive diode can include a semiconductor substrate having multiple doped regions forming at least one junction, and at least one textured region coupled to the semiconductor
10 substrate and positioned to interact with electromagnetic radiation. In one aspect the multiple doped regions can include at least one cathode region and at least one anode region. In some aspects, doped regions can include an n-type dopant and/or a p-type dopant as is discussed below, thereby creating a p-n junction. In other aspects, a photosensitive device can include an i-type region to form a p-i-n junction.

15 A photosensitive pixel can include a semiconductor substrate having multiple doped regions forming at least one junction, at least one textured region coupled to the semiconductor substrate and positioned to interact with electromagnetic radiation, and an electrical transfer element coupled to the semiconductor substrate and operable to transfer an electrical signal from the at least one junction. A photosensitive imager
20 can include multiple photosensitive pixels. Additionally, an electrical transfer element can include a variety of devices, including without limitation, transistors, sensing nodes, transfer gates, transfer electrodes, and the like.

 Photosensitive or photodetecting imagers include photodiodes or pixels that are capable of absorbing electromagnetic radiation within a given wavelength range.
25 Such imagers can be passive pixel sensors (PPS), active pixel sensors (APS), digital pixel sensor imagers (DPS), or the like, with one difference being the image sensor read out architecture. For example, a semiconducting photosensitive imager can be a three or four transistor active pixel sensor (3T APS or 4T APS). Various additional components are also contemplated, and would necessarily vary depending on the
30 particular configuration and intended results. As an example, a 4T configuration can additionally include, among other things, a transfer gate, a reset, a source follower, and row select transistors. Additionally, devices having greater than 4 transistors are also within the present scope.

Photosensitive imagers can be front side illumination (FSI) or back side illumination (BSI) devices, and there are advantages and disadvantages to both architecture types. In a typical FSI imager, incident light enters the semiconductor device by first passing by transistors and metal circuitry. The light, however, can
5 scatter off of the transistors and circuitry prior to entering the light sensing portion of the imager, thus causing optical loss and noise. A lens can be disposed on the top side of a FSI pixel to direct and focus the incident light to the light sensing active region of the device, thus partially avoiding the circuitry. In one aspect the lens can be a lens. BSI imagers, on the other hand, are configured to have the depletion region of the
10 junction extending to the opposite side of the device. In one aspect, for example, incident light enters the device via the light sensing portion and is mostly absorbed prior to reaching the circuitry. BSI designs allow for smaller pixel architecture and a high fill factor for the imager. As mentioned, the present disclosure can be adapted for either configuration. It should also be understood that devices according to
15 aspects of the present disclosure can be incorporated into complementary metal-oxide-semiconductor (CMOS) imager architectures or charge-coupled device (CCD) imager architectures.

In one aspect, as is shown in FIG. 1, a photosensitive diode 10 can include a semiconductor substrate 12 having multiple doped regions 14, 16 forming at least one
20 junction, and at least one textured region 18 coupled to the semiconductor substrate and positioned to interact with electromagnetic radiation. The different doped regions can have the same doping profile or different doping profiles, depending on the device. Such an architecture is a FSI design where light enters the semiconductor substrate from the direction of the multiple doped regions. While the device shown in
25 FIG. 1 contains three doped regions, it should be noted that aspects containing one or more doped regions are considered to be within the present scope. Additionally, the semiconductor substrate can be doped, and thus can be considered to be a doped region in some aspects. It should also be noted that the photosensitive diode can be configured with a BSI architecture, and thus electromagnetic radiation would enter the
30 semiconductor substrate from the direction of the textured region.

The various devices according to aspects of the present disclosure can exhibit increased quantum efficiency over traditional photosensitive devices. Any increase in the quantum efficiency makes a large difference in the signal to noise ratio. More complex structures can provide not only increased quantum efficiency but also good

uniformity from pixel to pixel. In addition, devices of the present disclosure exhibit increased responsivity as compared to traditional photosensitive devices. For example, in one aspect the responsivity can be greater than or equal to 0.8A/W for wavelengths greater than 1000 nm for semiconductor substrate that is less than 100
5 μm thick.

Photosensitive imagers can be maintained under constant conditions (fixed voltage or current) to provide enhanced linearity and uniformity. Connections between the imager and the underlying device layers can be achieved using vias fabricated from a refractory metal, such as tungsten or tantalum. Placing storage
10 elements under the imager may provide various photonic benefits. For example, the entire pixel array may be dedicated to signal processing. This may enable higher performance by permitting access to low level pixel signals. Furthermore, massively parallel operations can be performed by pixel processors. For example, analog to digital conversion, noise reduction (ie., true correlated double sampling), power
15 conditioning, nearest neighbor pixel processing, compression, fusion, and color multiplexing operations can be performed.

A variety of semiconductor materials are contemplated for use with the devices and methods according to aspects of the present disclosure. Non-limiting examples of such semiconductor materials can include group IV materials,
20 compounds and alloys comprised of materials from groups II and VI, compounds and alloys comprised of materials from groups III and V, and combinations thereof. More specifically, exemplary group IV materials can include silicon, carbon (e.g. diamond), germanium, and combinations thereof. Various exemplary combinations of group IV materials can include silicon carbide (SiC) and silicon germanium (SiGe). In one
25 specific aspect, the semiconductor material can be or include silicon. Exemplary silicon materials can include amorphous silicon (a-Si), microcrystalline silicon, multicrystalline silicon, and monocrystalline silicon, as well as other crystal types. In another aspect, the semiconductor material can include at least one of silicon, carbon, germanium, aluminum nitride, gallium nitride, indium gallium arsenide, aluminum
30 gallium arsenide, and combinations thereof.

Exemplary combinations of group II-VI materials can include cadmium selenide (CdSe), cadmium sulfide (CdS), cadmium telluride (CdTe), zinc oxide (ZnO), zinc selenide (ZnSe), zinc sulfide (ZnS), zinc telluride (ZnTe), cadmium zinc

telluride (CdZnTe, CZT), mercury cadmium telluride (HgCdTe), mercury zinc telluride (HgZnTe), mercury zinc selenide (HgZnSe), and combinations thereof.

Exemplary combinations of group III-V materials can include aluminum antimonide (AlSb), aluminum arsenide (AlAs), aluminum nitride (AlN), aluminum phosphide (AlP), boron nitride (BN), boron phosphide (BP), boron arsenide (BAs),
 5 gallium antimonide (GaSb), gallium arsenide (GaAs), gallium nitride (GaN), gallium phosphide (GaP), indium antimonide (InSb), indium arsenide (InAs), indium nitride (InN), indium phosphide (InP), aluminum gallium arsenide (AlGaAs, $\text{Al}_x\text{Ga}_{1-x}\text{As}$), indium gallium arsenide (InGaAs, $\text{In}_x\text{Ga}_{1-x}\text{As}$), indium gallium phosphide (InGaP),
 10 aluminum indium arsenide (AlInAs), aluminum indium antimonide (AlInSb), gallium arsenide nitride (GaAsN), gallium arsenide phosphide (GaAsP), aluminum gallium nitride (AlGaN), aluminum gallium phosphide (AlGaP), indium gallium nitride (InGaN), indium arsenide antimonide (InAsSb), indium gallium antimonide (InGaSb), aluminum gallium indium phosphide (AlGaInP), aluminum gallium arsenide
 15 phosphide (AlGaAsP), indium gallium arsenide phosphide (InGaAsP), aluminum indium arsenide phosphide (AlInAsP), aluminum gallium arsenide nitride (AlGaAsN), indium gallium arsenide nitride (InGaAsN), indium aluminum arsenide nitride (InAlAsN), gallium arsenide antimonide nitride (GaAsSbN), gallium indium nitride arsenide antimonide (GaInNAsSb), gallium indium arsenide antimonide
 20 phosphide (GaInAsSbP), and combinations thereof.

The semiconductor material can be of any thickness that allows electromagnetic radiation detection and conversion functionality, and thus any such thickness of semiconductor material is considered to be within the present scope. In some aspects the laser processed region of the semiconductor increases the efficiency
 25 of the device such that the semiconductor material can be thinner than has previously been possible. Decreasing the thickness of the semiconductor reduces the amount of semiconductor material required to make such a device. In one aspect, for example, the semiconductor material has a thickness of from about 500 nm to about 50 μm . In another aspect, the semiconductor material has a thickness of less than or equal to
 30 about 500 μm . In yet another aspect, the semiconductor material has a thickness of from about 1 μm to about 10 μm . In a further aspect, the semiconductor material can have a thickness of from about 5 μm to about 750 μm . In yet a further aspect, the semiconductor material can have a thickness of from about 5 μm to about 100 μm .

Additionally, various types of semiconductor material are contemplated, and any such material that can be incorporated into an electromagnetic radiation detection device is considered to be within the present scope. In one aspect, for example, the semiconductor material is monocrystalline. In another aspect, the semiconductor material is multicrystalline. In yet another aspect, the semiconductor material is microcrystalline. It is also contemplated that the semiconductor material can be amorphous. Specific nonlimiting examples include amorphous silicon or amorphous selenium.

The semiconductor materials of the present disclosure can also be made using a variety of manufacturing processes. In some cases the manufacturing procedures can affect the efficiency of the device, and may be taken into account in achieving a desired result. Exemplary manufacturing processes can include Czochralski (Cz) processes, magnetic Czochralski (mCz) processes, Float Zone (FZ) processes, epitaxial growth or deposition processes, and the like. Whether or not low oxygen content is desired in the device can also affect the choice of a manufacturing process for the semiconductor material. Various processes produce semiconductor materials containing varying amounts of oxygen, and as such, some applications having more stringent tolerances with respect to oxygen levels may benefit more from specific manufacturing procedures as compared to others. For example, during CZ crystal growth oxygen from the containment vessel, usually a quartz crucible, can become incorporated into the crystal as it is pulled. Additionally, other sources of oxygen contamination are also possible with the CZ process. Such contamination may be reduced, however, through the use of non oxygen-containing crucible materials, as well as the development of other crystal growth methods that do not utilize a crucible. One such process is the FZ process.

Materials grown with the CZ method can also be made to have lowered oxygen concentration through enhancements to the crystal growth process, such as growing the crystal in the presence of a magnetic field (i.e. the mCz process). Also, gettering techniques can be employed to reduce the impact of oxygen or other impurities on the finished device. These gettering techniques can include thermal cycles to liberate or nucleate impurities, or selective ion implantation of species to serve as gettering sites for the impurities. For example, oxygen concentrated in the semiconductor can be removed by the performing a furnace cycle to form a denuded zone. During heating with an inert gas, oxygen near the surface of the semiconductor

diffuses out of the material. During the furnace cycle but after the denuding step, nucleating and growing steps may be performed. Nucleating sites for precipitates are formed during the nucleating step, and the precipitates are grown from the nucleating sites during a growing step. The precipitates are formed from interstitial oxygen
5 within the bulk of the semiconductor material and beneath the denuded zone. The precipitation of oxygen in the bulk of the semiconductor material can be desired because such precipitates can act as gettering sites. Such precipitate formation can also be performed to “lock up” interstitial oxygen into the precipitates and reduce the likelihood that such oxygen can migrate from the bulk of the semiconductor material
10 into the denuded zone.

In those aspects where low oxygen content of the device is desired, further processing of the semiconductor material can be performed so as to minimize the introduction of oxygen. Oxygen can exist in different states or at different sites (for example, interstitially or substitutionally) within a semiconductor such as silicon,
15 dependent upon the thermal processing the semiconductor has received. If the semiconductor is subjected to temperatures higher than, for example, about 1000° C, oxygen can form aggregates or clusters that serve as defect sites in the crystal lattice. These sites may result in trap states and a reduction in carrier lifetime within the semiconductor material and device can occur. At lower temperatures (for example,
20 around 400° C to 700° C), oxygen can behave as electrically active thermal donors. Thus, oxygen can have a negative impact on carrier lifetime and on carrier mobility. In a device fabricated to have photoconductive gain, the presence of oxygen causing reduced carrier lifetime may result in reduced levels of photoconductive gain.

It may be beneficial, therefore, to produce semiconductor devices such that a
25 low oxygen content is obtained or maintained. This can be accomplished in a variety of ways, including using semiconductor materials having low levels of oxygen contained therein to begin with, processing these materials in a manner that minimizes the uptake of oxygen into the semiconductor lattice, and utilizing techniques that eliminate or reduce oxygen that may be present in the semiconductor. Such processes
30 and techniques can include, for example, annealing the semiconductor material and any laser treated region to lower temperatures as compared to previous annealing procedures. Annealing processes are discussed more fully below.

Additionally, texture processing of the semiconductor material and/or any annealing process can be performed in a substantially oxygen-depleted environment

in order to minimize the introduction of oxygen into the semiconductor. An oxygen-depleted or substantially oxygen-depleted environment can include a variety of environments. In one aspect, for example, the oxygen-depleted environment can be an environment whereby oxygen from the air or other sources has been replaced with
5 a gas or other fluid containing little to no oxygen. In another aspect, processing can occur in a vacuum environment, and thus contain little to no oxygen. Additionally, oxygen-containing materials or materials that introduce oxygen into the semiconductor, such as, for example, quartz crucibles, can be avoided. As a practical matter, the term "oxygen-depleted environment" can be used to describe an
10 environment with low levels of oxygen, provided a semiconductor material can be processed therein within the desired tolerances. Thus, environments having low oxygen, or little to no oxygen, are environments in which a semiconductor can be processed as a low-oxygen content semiconductor while maintaining oxygen levels within the tolerances of the present disclosure. In one aspect, an oxygen-depleted
15 environment can be an oxygen-free environment. Further details regarding low-oxygen content semiconductor materials can be found in US Patent Application No. 12/771848, filed on April 30, 2010, which is incorporated herein by reference.

The semiconductor material can have varying levels of interstitial oxygen depending on the desired efficiency of the device. In some aspects, oxygen content
20 may be of no concern, and thus any level of oxygen within the lattice is acceptable. In other aspects, a low oxygen content is desired. In one aspect a semiconductor material can have an oxygen content that is less than or equal to about 50 ppm atomic. In another aspect, a semiconductor material can have an oxygen content that is less than or equal to about 30 ppm atomic. In yet another aspect, the semiconductor
25 material can have an oxygen content less than or equal to about 10 ppm atomic. In another aspect the semiconductor can have an oxygen content less than about 5 ppm atomic. In yet another aspect the semiconductor can have an oxygen content less than about 1 ppm atomic.

As has been described, the textured region can function to diffuse
30 electromagnetic radiation, to redirect electromagnetic radiation, and to absorb electromagnetic radiation, thus increasing the quantum efficiency of the device. The textured region can include surface features to increase the effective absorption length of the photosensitive pixel. The surface features can be cones, pyramids, pillars, protrusions, microlenses, quantum dots, inverted features and the like. Factors such

as manipulating the feature sizes, dimensions, material type, dopant profiles, texture location, etc. can allow the diffusing region to be tunable for a specific wavelength. In one aspect, tuning the device can allow specific wavelengths or ranges of wavelengths to be absorbed. In another aspect, tuning the device can allow specific
5 wavelengths or ranges of wavelengths to be reduced or eliminated via filtering.

Tuning can also be accomplished through the location of the texture region within the device, modifying the dopant profile(s) of regions within the device, dopant selection, and the like. Additionally, material composition near the textured region can create a wavelength specific photosensing pixel device. It should be noted that a
10 wavelength specific photosensing pixel can differ from one pixel to the next, and can be incorporated into an imaging array. For example a 4 x 4 array can include a blue pixel, a green pixel, a red pixel, and infrared light absorbing pixel, or a blue pixel, two green pixels, and a red pixel.

Textured regions according to aspects of the present disclosure can allow a
15 photosensitive device to experience multiple passes of incident electromagnetic radiation within the device, particularly at longer wavelengths (i.e. infrared). Such internal reflection increases the effective absorption length to be greater than the thickness of the semiconductor substrate. This increase in absorption length increases the quantum efficiency of the device, leading to an improved signal to noise ratio.

The textured region can be formed by various techniques, including lasing, chemical etching (e.g. anisotropic etching, isotropic etching), nanoimprinting, additional material deposition, and the like. For example, pillar features can be incorporated into pixels by thinning or removing material from the backside of a FSI semiconductor substrate by using deep trench isolation and etching techniques. In
20 one aspect material can be removed to a thickness of about 20 μm . Anisotropic etching can be used to produce a sloping backside pyramid structure, spherical, structure parabolic structure, a lens structure with reflectors, and the like. Such features on the backside of pillars will also serve to diffuse and reflect electromagnetic radiation.

In one aspect, the texturing process can be performed during the manufacture
30 of the photosensitive device. In another aspect, the texturing process can be performed on a photosensitive device that has previously been made. For example, a CMOS, CCD, or other photosensitive element can be textured following manufacture. In this case, material layers may be removed from the photosensitive element to

expose the semiconductor substrate or bulk material upon which a textured region may be formed.

One effective method of producing a textured region is through laser processing. Such laser processing allows discrete locations of the semiconductor substrate to be textured. A variety of techniques of laser processing to form a textured region are contemplated, and any technique capable of forming such a region should be considered to be within the present scope. Laser treatment or processing can allow, among other things, enhanced absorption properties and thus increased electromagnetic radiation focusing and detection. The laser treated region can be associated with the surface nearest the impinging electromagnetic radiation, or the laser treated surface can be associated with a surface opposite in relation to impinging electromagnetic radiation, thereby allowing the radiation to pass through the semiconductor material before it hits the laser treated region.

In one aspect, for example, a target region of the semiconductor material can be irradiated with laser radiation to form a textured region. Examples of such processing have been described in further detail in U.S. Patents 7,057,256, 7,354,792 and 7,442,629, which are incorporated herein by reference in their entireties. Briefly, a surface of a semiconductor material is irradiated with laser radiation to form a textured or surface modified region. Such laser processing can occur with or without a dopant material. In those aspects whereby a dopant is used, the laser can be directed through a dopant carrier and onto the semiconductor surface. In this way, dopant from the dopant carrier is introduced into the target region of the semiconductor material. Such a region incorporated into a semiconductor material can have various benefits in accordance with aspects of the present disclosure. For example, the target region typically has a textured surface that increases the surface area of the laser treated region and increases the probability of radiation absorption via the mechanisms described herein. In one aspect, such a target region is a substantially textured surface including micron-sized and/or nano-sized surface features that have been generated by the laser texturing. In another aspect, irradiating the surface of semiconductor material includes exposing the laser radiation to a dopant such that irradiation incorporates the dopant into the semiconductor. Various dopant materials are known in the art, and are discussed in more detail herein.

Thus the surface of the semiconductor material is chemically and/or structurally altered by the laser treatment, which may, in some aspects, result in the

formation of surface features appearing as microstructures or patterned areas on the surface and, if a dopant is used, the incorporation of such dopants into the semiconductor material. In some aspects, the features or microstructures can be on the order of 50 nm to 20 μm in size and can assist in the absorption of electromagnetic radiation. In other words, the textured surface can increase the probability of incident radiation being absorbed by the semiconductor material.

The type of laser radiation used to surface modify a semiconductor material can vary depending on the material and the intended modification. Any laser radiation known in the art can be used with the devices and methods of the present disclosure. There are a number of laser characteristics, however, that can affect the surface modification process and/or the resulting product including, but not limited to the wavelength of the laser radiation, pulse width, pulse fluence, pulse frequency, polarization, laser propagation direction relative to the semiconductor material, etc. In one aspect, a laser can be configured to provide pulsatile lasing of a semiconductor material. A short-pulsed laser is one capable of producing femtosecond, picosecond and/or nanosecond pulse durations. Laser pulses can have a central wavelength in a range of about from about 10 nm to about 8 μm , and more specifically from about 200 nm to about 1200 nm. The pulse width of the laser radiation can be in a range of from about tens of femtoseconds to about hundreds of nanoseconds. In one aspect, laser pulse widths can be in the range of from about 50 femtoseconds to about 50 picoseconds. In another aspect, laser pulse widths can be in the range of from about 50 picoseconds to 100 nanoseconds. In another aspect, laser pulse widths are in the range of from about 50 to 500 femtoseconds.

The number of laser pulses irradiating a target region can be in a range of from about 1 to about 2000. In one aspect, the number of laser pulses irradiating a semiconductor target region can be from about 2 to about 1000. Further, the repetition rate or frequency of the pulses can be selected to be in a range of from about 10 Hz to about 10 μHz , or in a range of from about 1 kHz to about 1 MHz, or in a range from about 10 Hz to about 1 kHz. Moreover, the fluence of each laser pulse can be in a range of from about 1 kJ/m^2 to about 20 kJ/m^2 , or in a range of from about 3 kJ/m^2 to about 8 kJ/m^2 .

A variety of dopant materials are contemplated, and any such material that can be used in the laser treatment process to surface modify a semiconductor material according to aspects of the present disclosure is considered to be within the present

scope. It should be noted that the particular dopant utilized can vary depending on the semiconductor material being laser treated, as well as the intended use of the resulting semiconductor material. For example, the selection of potential dopants may differ depending on whether or not tuning of the photosensitive device is desired.

5 A dopant can be either electron donating or hole donating. In one aspect, non-limiting examples of dopant materials can include S, F, B, P, N, As, Se, Te, Ge, Ar, Ga, In, Sb, and combinations thereof. It should be noted that the scope of dopant materials should include, not only the dopant materials themselves, but also materials in forms that deliver such dopants (i.e. dopant carriers). For example, S dopant
10 materials includes not only S, but also any material capable being used to dope S into the target region, such as, for example, H₂S, SF₆, SO₂, and the like, including combinations thereof. In one specific aspect, the dopant can be S. Sulfur can be present at an ion dosage level of between about 5×10^{14} and about 1×10^{16} ions/cm². Non-limiting examples of fluorine-containing compounds can include ClF₃, PF₅, F₂
15 SF₆, BF₃, GeF₄, WF₆, SiF₄, HF, CF₄, CHF₃, CH₂F₂, CH₃F, C₂F₆, C₂HF₅, C₃F₈, C₄F₈, NF₃, and the like, including combinations thereof. Non-limiting examples of boron-containing compounds can include B(CH₃)₃, BF₃, BCl₃, BN, C₂B₁₀H₁₂, borosilica, B₂H₆, and the like, including combinations thereof. Non-limiting examples of phosphorous-containing compounds can include PF₅, PH₃, and the like, including
20 combinations thereof. Non-limiting examples of chlorine-containing compounds can include Cl₂, SiH₂Cl₂, HCl, SiCl₄, and the like, including combinations thereof. Dopants can also include arsenic-containing compounds such as AsH₃ and the like, as well as antimony-containing compounds. Additionally, dopant materials can include mixtures or combinations across dopant groups, i.e. a sulfur-containing compound
25 mixed with a chlorine-containing compound. In one aspect, the dopant material can have a density that is greater than air. In one specific aspect, the dopant material can include Se, H₂S, SF₆, or mixtures thereof. In yet another specific aspect, the dopant can be SF₆ and can have a predetermined concentration range of about 5.0×10^{-8} mol/cm³ to about 5.0×10^{-4} mol/cm³. SF₆ gas is a good carrier for the incorporation
30 of sulfur into the semiconductor material via a laser process without significant adverse effects on the semiconductor material. Additionally, it is noted that dopants can also be liquid solutions of n-type or p-type dopant materials dissolved in a solution such as water, alcohol, or an acid or basic solution. Dopants can also be solid materials applied as a powder or as a suspension dried onto the wafer.

The semiconductor substrate can be annealed for a variety of reasons, including dopant activation, semiconductor material damage repair, and the like. In those aspects including a laser textured region, the semiconductor material can be annealed prior to laser treatment, following laser treatment, during laser treatment, or both prior to and following laser treatment. Annealing can enhance the semiconductive properties of the device, including increasing the photoresponse properties of the semiconductor materials. Additionally, annealing can reduce damage done by the lasing process. Although any known anneal can be beneficial and would be considered to be within the present scope, annealing at lower temperatures can be particularly useful. Such a "low temperature" anneal can greatly enhance the photoconductive gain and external quantum efficiency of devices utilizing such materials. In one aspect, for example, the semiconductor material can be annealed to a temperature of from about 300° C to about 1100 C°. In another aspect, the semiconductor material can be annealed to a temperature of from about 500° C to about 900° C. In yet another aspect, the semiconductor material can be annealed to a temperature of from about 700° C to about 800° C. In a further aspect, the semiconductor material can be annealed to a temperature that is less than or equal to about 850° C.

The duration of the annealing procedure can vary according to the specific type of anneal being performed, as well as according to the materials being used. For example, rapid annealing processes can be used, and as such, the duration of the anneal may be shorter as compared to other techniques. Various rapid thermal anneal techniques are known, all of which should be considered to be within the present scope. In one aspect, the semiconductor material can be annealed by a rapid annealing process for a duration of greater than or equal to about 1 μ s. In another aspect, the duration of the rapid annealing process can be from about 1 μ s to about 1 ms. As another example, a baking or furnace anneal process can be used having durations that may be longer compared to a rapid anneal. In one aspect, for example, the semiconductor material can be annealed by a baking anneal process for a duration of greater than or equal to about 1 ms to several hours. As has been described, if low oxygen content semiconductor materials are used it may be beneficial to anneal such materials in a substantially oxygen-depleted environment.

As has been described, annealing can help reduce defects inherent to the semiconductor substrate and otherwise reduce electron/hole recombination. In other

words, the annealing can help create electron states that effectively reduce the undesirable recombination processes. Annealing the semiconductor material may also improve the responsivity or photoconductive gain of the device. Photoconductive devices can have dopants, impurities, or defects that can introduce energy levels that can trap carriers. Trapping carriers and reducing recombination of photocarriers can lead to an increase in photoconductive gain of the device. The relationship of photoconductive gain and trapping time can be represented by Equation (I):

$$\text{Gain} = \tau_L / \tau_t \quad (I)$$

where “ τ_L ” is the lifetime of an excess carrier and “ τ_t ” is the transit time of the carriers across the device. It is understood that the lifetime of an excess carrier can be increased by trapping a carrier species and reducing the recombination rate. An increase in gain can be achieved by trapping centers in the semiconductor that have millisecond trapping times at room temperature and short transit times in thinned lightly doped wafers. These trapping locations can decrease the recombination of carriers and therefore improve or increase the photoconductive gain of the device by allowing more electrons to traverse the different regions without being recombined.

Turning to FIG. 2, a reflecting layer 20 can be coupled to the semiconductor substrate 12. The reflecting layer can be coupled to any side or portion of the semiconductor substrate in order to reflect electromagnetic radiation back into the device. Accordingly, in one aspect the reflecting layer can be located on the semiconductor substrate opposite the incoming electromagnetic radiation. Thus, as is shown in FIG. 2, electromagnetic radiation passing through the semiconductor substrate and the textured region 16 can be reflected back into the semiconductor substrate. Additionally, a passivation layer 22 can be coupled to the semiconductor substrate. The passivation layer is shown coupled to the side of the semiconductor substrate facing the incoming electromagnetic radiation, however a passivation layer can be located anywhere on the device and still be within the present scope.

As has been described, location of the textured region can be used to provide enhancement and/or filtering of the incoming electromagnetic radiation. For example, a textured region located at the point of entry of the electromagnetic radiation into the photosensitive device tends to bend the electromagnetic radiation, particularly the blue wavelengths. Accordingly, one level of tuning can be accomplished by locating

the textured region on the surface adjacent the incident electromagnetic radiation to purposely effectuate the filtering of blue wavelengths. Additionally, absorption of particular wavelengths of electromagnetic radiation occurs at different depths in the semiconductor layer and/or textured region. By increasing the absorption to green wavelengths, for example, the electrical signal as a result of green wavelengths can be increased in a diode or pixel. Certain traditional 4 pixel imagers have one red, one blue, and two green pixels, with the greater number of green pixels to account for increased sensitivity of the human eye to green colors. Thus in one aspect, a 4 pixel imager can have one blue, one red, and one green pixel having an increased green wavelength absorption. The fourth pixel can be used for an IR or other wavelength selective pixel depending on the desired application of the imager.

FIG. 3 shows a photosensitive device having textured regions 30 located on the sides of the semiconductor substrate 12. Such a configuration allows electromagnetic radiation normally exiting through the sides of the device to be further defused and absorbed within semiconductor substrate. The textured region(s) can be located on one or more sides to facilitate the enhanced absorption.

FIG. 4 shows a photosensitive device having a textured region 40 having a nonparallel surface with respect to the semiconductor substrate 12. Thus the overall configuration of the textured region can be designed to further enhance absorption and/or selectively tune the device. As has been described, the nonparallel surface can have a variety of configurations, such as, without limitation, nonparallel slope, a pyramid, an inverted pyramid, a concave shape, a convex shape, and the like. In some cases the configuration of the textured region can function to direct or focus electromagnetic radiation into the semiconductor substrate, and in other cases the configuration of the textured region can function to direct or focus electromagnetic radiation away from the semiconductor substrate.

As is shown in FIG. 5, a lens 50 can be coupled to the semiconductor substrate 12 on a side facing incoming electromagnetic radiation. Thus the lens can focus the electromagnetic radiation into the semiconductor substrate. In those aspects having circuitry or other structures disposed on the incoming electromagnetic radiation surface, the lens can further focus light around such structures, thereby reducing optical scattering and noise.

As is shown in FIG. 6, a textured region 60 is located on the semiconductor substrate 12 adjacent to the multiple doped regions 14, 16. The textured region can be

associated with at least one of the doped regions as is shown, or the textured region can be distinct from the doped regions (not shown). Electromagnetic radiation can enter the photosensitive device at the side adjacent the doped regions, or alternatively at the side opposite the doped regions.

5 FIGs. 7-11 show various steps in the manufacture of a photosensitive pixel according to aspects of the present disclosure. FIG. 7 shows a cross-section of a front side illumination (FSI) photosensitive pixel device. The photosensitive pixel device can include a semiconductor substrate 72, and can be referred to as bulk semiconductor material. The semiconductor substrate includes at least one doped region 74 that can be doped with an electron donating or hole donating species to
10 cause the region to become more positive or negative in polarity as compared to the semiconductor substrate. In one aspect, for example, the doped region can be p doped. In another aspect the doped region can be n doped. A highly doped region 76 can be formed on or near the doped region to create a pinned diode. In one example,
15 the semiconductor substrate can be negative in polarity, and the doped region and the highly doped region can be doped with p⁺ and n⁻ dopants respectively. In some aspects, variations of n(--), n(-), n(+), n(++), p(--), p(-), p(+), or p(++ type doping of the regions can be used. It should be noted that in one aspect the highly doped region can be the textured region. In other words, textured surface features can be formed on
20 or in the highly doped region.

 The device of FIG. 7 can further include various metal regions 78, at least one via 80, a passivation layer 82, trench isolation 84, and an electrical transfer element 86. Trench isolation elements can maintain pixel to pixel uniformity by reducing optical and electrical crosstalk. The trench isolation can be shallow (FIG. 7) or deep
25 (FIG. 12) trench isolation. The trench isolation can include various materials, including, without limitation, dielectric materials, reflective materials, conductive materials, light diffusing features, and the like. These trench isolation regions can be configured to reflect incident light until it is absorbed, thereby increase the effective absorption length of the device.

30 As is shown in FIG. 8, a carrier substrate or carrier wafer 88 can be coupled to the photosensing pixel. In one aspect, the carrier substrate can be disposed on the passivation layer 82, although the carrier substrate can be disposed on any surface of the device. In one aspect, for example, the carrier substrate can be disposed on the semiconductor substrate (not shown). The carrier substrate can be coupled to the

photosensing pixel by various techniques, and any such coupling mechanism is within the present scope. In one aspect, for example, the coupling can occur by way of a bonding layer or adhesive layer disposed on the device, for example, on the passivation layer. The support substrate can provide support to the semiconductor device both during and after manufacture, depending on whether or not the support is removed. The carrier substrate can be made of a semiconductor material that is the same or similar to the bulk semiconductor material, or it can be made of a different material.

As is shown in FIG. 9, a textured region 90 is coupled to the semiconductor substrate 72 opposite the doped regions 74,76. Thus light entering from the direction of the doped regions passes through the semiconductor substrate prior to contacting the textured region. The textured region can be disposed across an entire surface of the semiconductor substrate, as is shown in FIG. 9, or it can be disposed on one or more discrete regions (not shown).

As is shown in FIG. 10, an additional carrier support substrate 100 can be coupled to the device on an opposing side from the carrier support substrate 88. The additional carrier support substrate can be utilized for a variety of purposes, including providing additional support to the device, facilitating the removal of the first carrier support substrate, and the like. A reflective layer 102 can be disposed between the textured region 90 and the carrier support substrate. Thus the reflective layer can reflect electromagnetic radiation that passes through the textured region back toward the semiconductor substrate 72, thus reducing optical loss and backscattering. Thus, in some aspects a reflective layer can increase the quantum efficiency of the device. The reflective layer material can be any reflective material that can be incorporated into such a device. Nonlimiting examples can include materials such as silver, aluminum, and the like.

As is shown in FIG. 11, the carrier support substrate can be removed to expose the passivation layer 82 or any other material layer that was previously covered by the carrier support substrate. The additional carrier substrate 100 can be maintained in the device, removed from the device, or thinned to reduce the thickness of the substrate depending on the intended use of the device. The removal of material from the device, including the carrier support substrate and the additional carrier substrate, can be accomplished by a variety of methods including, without limitation, etching, chemical mechanical polishing, ion implanting (i.e. smart cut), and the like.

Various types of trench isolation are contemplated, and any such isolation is considered to be within the present scope. As has been described, trench isolation can be shallow (FIG. 7, 84) or deep (FIG. 12, 120) trench isolation. The trench isolation can also include depths between shallow and deep, depending on the device design.

5 Trench isolation can include dielectric materials, reflective materials, conductive materials, and combinations thereof, including textured regions and other light diffusing features. Thus the trench isolation layer can be configured to reflect incident electromagnetic radiation, in some cases until it is absorbed, thereby increasing the effective absorption length of the device. Additionally, in some aspects
10 pillar features can be incorporated into pixels by thinning or removing material from the semiconductor substrate using deep trench isolation and etching techniques. As is shown in FIG. 13, the textured region 130 can have a nonparallel surface with respect to the semiconductor substrate 72 as has been described. This nonparallel morphology, when included with the deep trench isolation 120, can effectively focus
15 electromagnetic radiation into the semiconductor substrate from multiple sides.

It is also contemplated, that a non-bulk material can be formed or disposed near a doped region in the device. The addition of the non-bulk material can allow for electromagnetic radiation diffusing features to be formed on or in the non-bulk material. A metal layer defining an aperture can also be included in one aspect of the
20 present disclosure. The metal layer can be formed near the doped regions and can have a light entering region that defines an aperture. This light entering region can also include an antireflecting material.

Fig. 14 shows a photosensitive imager comprising two photosensitive pixels 140. Each photosensitive pixel includes a boundary region 142 that can include metal
25 circuitry and a textured region 144. Each photosensitive pixel can include at least one transistor 146 or other electrical transfer element. Additional read out and circuitry elements 148 can be utilized and shared by both photosensitive pixels.

Turning to FIG. 15, a backside illuminated (BSI) photosensitive pixel according to one aspect present disclosure is provided. A lens 150 and an anti-
30 reflective coating 152 are disposed on the backside of the pixel following thinning and trench isolation. A color filter 154 can be optically coupled to the lens to allow specific wavelengths filtering of the electromagnetic radiation. A textured region 156 can be coupled to the semiconductor substrate 72 opposite the lens in order to provide diffusive scattering and reflection of the incident electromagnetic radiation that passes

through to the front side of the pixel. Thus the electromagnetic radiation can be focused within the semiconductor substrate to the combined action of the textured region and the trench isolation 120

Fig. 16 shows a front side illuminated (FSI) imager according to another aspect of the present disclosure. A lens 160 and an antireflecting passivation layer on 5 62 are coupled to the front side of the pixel. A textured region 90 and a reflecting layer 102 are coupled to the semiconductor substrate 72 opposite the lens to provide diffusive scattering and reflection of the incident electromagnetic radiation that passes through the semiconductor substrate. An aperture 164 formed in a metal or other 10 reflective material layer 166 can increase the effectiveness of the optical cavity. Thus the lens focuses electromagnetic radiation through the aperture.

In other aspects of the present disclosure, various methods of making photosensitive diodes, pixels, and imagers, are contemplated. In one aspect, as is shown in FIG. 17, a method of making a photosensitive imager device can include 15 forming a textured region on a semiconductor substrate having multiple doped regions forming a least one junction, wherein the textured region is formed in a position to interact with electromagnetic radiation 170. The method also includes coupling an electrical transfer element to the semiconductor substrate such that the electrical transfer element is operable to transfer an electrical signal from the at least one 20 junction 172. In one aspect, multiple pixels can be associated together to form an imager. A passivation layer can also be disposed on the photosensitive imager device to protect and/or reduce the dark current of the device.

In another aspect of the present disclosure, a method for making a photosensitive diode is provided. Such a method can include forming at least one 25 cathode and at least one anode on a surface of a semiconductor substrate, coupling a textured region to the semiconductor substrate, and coupling a support substrate to the semiconductor substrate. The textured region can be located adjacent to the anode and cathode, opposite the anode and cathode, or both adjacent and opposite the anode and cathode. An electrical transfer on the can be electrically coupled to at least one of 30 the anode and cathode to form a photosensitive pixel. In another aspect, the semiconductor substrate can be thinned to improve the response rate and/or speed of the device. A passivation layer can also be disposed on the photosensitive diode to protect and/or reduce the dark current of the device. An additional support substrate can be attached to the device to provide additional support. In one aspect, the

additional support substrate can be located on the opposite side of the photosensitive diode from the support substrate. The support substrate can subsequently be removed to allow for further processing.

Of course, it is to be understood that the above-described arrangements are
5 only illustrative of the application of the principles of the present disclosure.
Numerous modifications and alternative arrangements may be devised by those
skilled in the art without departing from the spirit and scope of the present disclosure
and the appended claims are intended to cover such modifications and arrangements.
Thus, while the present disclosure has been described above with particularity and
10 detail in connection with what is presently deemed to be the most practical
embodiments of the disclosure, it will be apparent to those of ordinary skill in the art
that numerous modifications, including, but not limited to, variations in size,
materials, shape, form, function and manner of operation, assembly and use may be
made without departing from the principles and concepts set forth herein.

15

CLAIMS

What is claimed is:

- 5 1. A photosensitive imager device, comprising:
a semiconductor substrate having multiple doped regions forming a least one
junction;
a textured region coupled to the semiconductor substrate and positioned to
interact with electromagnetic radiation; and
10 an electrical transfer element coupled to the semiconductor substrate and
operable to transfer an electrical signal from the at least one junction.
2. The device of claim 1, wherein the textured region is operable to facilitate
generation of an electrical signal from the detection of infrared electromagnetic
15 radiation.
3. The device of claim 1, wherein interacting with electromagnetic radiation further
includes increasing the semiconductor substrate's effective absorption length as
compared to a semiconductor substrate lacking a textured region.
20
4. The device of claim 1, wherein the transfer element is selected from the group
consisting of a transistor, a sensing node, a transfer gate, and combinations thereof.
5. The device of claim 1, further comprising a reflective layer coupled to the
25 semiconductor substrate and positioned to maintain the electromagnetic radiation in
the semiconductor substrate.
6. The device of claim 1, wherein the textured region is positioned on a surface of the
semiconductor substrate that is opposite the multiple doped regions.
30
7. The device of claim 6, wherein the textured region has a surface morphology
operable to direct electromagnetic radiation into or out of the semiconductor substrate.

8. The device of claim 7, wherein the surface morphology of the textured region relative to the semiconductor substrate is a member selected from the group consisting of sloping, pyramidal, inverted pyramidal, spherical, parabolic, asymmetric, symmetric, and combinations thereof.

5

9. The device of claim 1, wherein the textured region is positioned on a surface of the semiconductor substrate that is adjacent the multiple doped regions.

10. The device of claim 9, further comprising an additional textured region positioned on a surface of the semiconductor substrate that is opposite the multiple doped regions.

11. The device of claim 1, wherein the textured region is coupled directly to at least one of the multiple doped regions.

15

12. The device of claim 1, wherein the textured region includes surface features having a size selected from the group consisting of micron-sized, nano-sized, and combinations thereof.

20 13. The device of claim 12, wherein surface features include a member selected from the group consisting of cones, pillars, pyramids, microlenses, quantum dots, inverted features, and combinations thereof.

25 14. The device of claim 1, wherein the textured region has been formed by a process selected from the group consisting of lasing, chemical etching, nanoimprinting, material deposition, and combinations thereof.

30 15. The device of claim 1, further comprising a lens optically coupled to the semiconductor substrate and positioned to focus incident electromagnetic radiation into the semiconductor substrate.

16. A photosensitive imager array, comprising at least two photosensitive imager devices of claim 1.

17. The array of claim 16, further comprising at least one trench isolation positioned between the at least two photosensitive imager device.

18. A method of making a photosensitive imager device, comprising:

- 5 forming a textured region on a semiconductor substrate, wherein the semiconductor substrate has multiple doped regions forming a least one junction, and wherein the textured region is formed in a position to interact with electromagnetic radiation; and
- coupling an electrical transfer element to the semiconductor substrate such that
- 10 the electrical transfer element is operable to transfer an electrical signal from the at least one junction .

19. The method of claim 18, wherein forming the textured region is by a process selected from the group consisting of lasing, chemical etching, nanoimprinting,

15 material deposition, and combinations thereof.

20. The method of claim 18, wherein forming the textured region includes irradiating a target region with laser radiation to form surface features having a size selected from the group consisting of micron-sized, nano-sized, and combinations thereof.

20

21. The method of claim 20, wherein irradiating the target region includes exposing the laser radiation to a dopant such that the irradiation incorporates the dopant into the textured region.

25 22. The method of claim 20, wherein the irradiation is performed using a pulsed laser including a member selected from the group consisting of a femtosecond laser, a picosecond laser, a nanosecond laser, and combinations thereof.

23. The method of claim 18, further comprising tuning an electrical response of the

30 photosensitive imager device.

24. The method of claim 23, wherein tuning includes forming surface features to have dimensions that selectively diffuse or selectively absorb a desired wavelength of electromagnetic radiation.

25. The method of claim 23, wherein tuning is accomplished through a factor selected from the group consisting of placement of the textured region, material type of the textured region, thickness of the textured region, dopant type of the textured
5 region, doping profile of the texture region, doping profile of the semiconductor substrate, thickness of the substrate, and combinations thereof.

26. The method of claim 18, wherein the transfer element is selected from the group consisting of a transistor, a sensing node, a transfer gate, and combinations thereof.

10

27. The method of claim 18, further comprising annealing the semiconductor substrate to a temperature of from about 300° C to about 1100° C.

28. A photosensitive imager device, comprising:
15 a semiconductor substrate having multiple doped regions forming a least one junction;
a textured region coupled to the semiconductor substrate and positioned to interact with electromagnetic radiation; and
at least 4 transistors coupled to the semiconductor substrate and with at least
20 one of the transistors electrically coupled to the at least one junction.

1/14




FIG. 1




FIG. 2

2/14




FIG. 3




FIG. 4

3/14




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9

7/14




FIG. 10




FIG. 11




FIG. 12




FIG. 13

11/14




FIG. 14




FIG. 15




FIG. 16

14/14




FIG. 17