



US 20120068255A1

(19) **United States**(12) **Patent Application Publication****LEE et al.**(10) **Pub. No.: US 2012/0068255 A1**(43) **Pub. Date: Mar. 22, 2012**(54) **THREE-DIMENSIONAL SEMICONDUCTOR
MEMORY DEVICES**(75) Inventors: **Changhyun LEE**, Suwon-si (KR);
Byoungkeun SON, Suwon-si (KR);
Hyejin CHO, Anyang-si (KR)(73) Assignee: **Samsung Electronics Co., Ltd.**(21) Appl. No.: **13/220,376**(22) Filed: **Aug. 29, 2011**(30) **Foreign Application Priority Data**

Sep. 16, 2010 (KR) 10-2010-0091140

Publication Classification(51) **Int. Cl.**
H01L 29/792 (2006.01)(52) **U.S. Cl. 257/324; 257/E29.309**(57) **ABSTRACT**

Three-dimensional (3D) nonvolatile memory devices include a substrate having a well region of second conductivity type (e.g., P-type) therein and a common source region of first conductivity type (e.g., N-type) on the well region. A recess is provided, which extends partially (or completely) through the common source region. A vertical stack of nonvolatile memory cells are provided on the substrate. This vertical stack of nonvolatile memory cells includes a vertical stack of spaced-apart gate electrodes and a vertical active region, which extends on sidewalls of the vertical stack of spaced-apart gate electrodes and on a sidewall of the recess. Gate dielectric layers are provided, which extend between respective ones of the vertical stack of spaced-apart gate electrodes and the vertical active region. The gate dielectric layers may include a composite of a tunnel insulating layer, a charge storage layer, a relatively high bandgap barrier dielectric layer and a blocking insulating layer having a relatively high dielectric strength.




Fig. 1A




Fig. 1B




Fig. 1C




Fig. 2B




Fig. 3A




Fig. 3B




Fig. 3C




Fig. 3D




Fig. 4A




Fig. 4B




Fig. 5A




Fig. 5B




Fig. 6A




Fig. 6B




Fig. 6C




Fig. 6D




Fig. 6E




Fig. 6F




Fig. 6G




Fig. 6H




Fig. 7A




Fig. 7B




Fig. 7C




Fig. 7D




Fig. 8A




Fig. 8B




Fig. 8C




Fig. 8D




Fig. 8F




Fig. 9A




Fig. 9C





Fig. 9D






Fig. 10B




Fig. 10C




Fig. 11




Fig. 12B




Fig. 12D




Fig. 12E




Fig. 12F




Fig. 13A




Fig. 13C




Fig. 13D




Fig. 13E




Fig. 14




Fig. 15B




Fig. 15D




Fig. 15F




Fig. 16A




Fig. 16B




Fig. 17





Fig. 18



THREE-DIMENSIONAL SEMICONDUCTOR MEMORY DEVICES

REFERENCE TO PRIORITY APPLICATION

[0001] This U.S. non-provisional patent application claims priority under 35 U.S.C. §119 to Korean Patent Application 10-2010-0091140, filed Sep. 16, 2010, the entire contents of which are hereby incorporated herein by reference.

BACKGROUND

[0002] The present disclosure herein relates to a semiconductor device and a method of fabricating the same and, more particularly, to a three-dimensional (3D) semiconductor memory device and a method of fabricating the same.

[0003] Due to characteristics such as miniaturization, multifunction and/or low-fabricating cost, semiconductor devices are getting the spotlight as an important factor in electronic industries. With the advance of electronic industries, requirements for the superior performances and/or low costs of semiconductor devices are increasing. For satisfying such requirements, high-integrating of semiconductor devices is growing. Particularly, high-integrating of semiconductor memory devices storing logical data is growing more.

[0004] In a degree of integration of typical Two-Dimensional (2D) semiconductor memory devices, planar areas that unit memory cells occupy may be main factors for deciding the degree of integration. Therefore, a degree of integration of the typical 2D semiconductor memory devices may be largely affected by the level of a technology for forming fine patterns. However, the technology for forming the fine patterns may be gradually reaching limitations, and also, the fabricating costs of semiconductor memory devices may increase because high-cost equipment is required. For solving such limitations, 3D semiconductor memory devices including three dimensionally-arranged memory cells have been proposed.

SUMMARY

[0005] Three-dimensional (3D) nonvolatile memory devices according to embodiments of the invention include a substrate having a well region of second conductivity type (e.g., P-type) therein and a common source region of first conductivity type (e.g., N-type) on the well region. A recess is provided in the substrate. In some embodiments of the invention, the recess extends partially through the common source region. A vertical stack of nonvolatile memory cells are provided on the substrate. This vertical stack of nonvolatile memory cells includes a vertical stack of spaced-apart gate electrodes and a vertical active region, which extends on sidewalls of the vertical stack of spaced-apart gate electrodes and on a sidewall of the recess. Gate dielectric layers are provided, which extend between respective ones of the vertical stack of spaced-apart gate electrodes and the vertical active region.

[0006] In other embodiments of the invention, the recess extends entirely through the common source region, which forms a P-N rectifying junction with the well region, and a sidewall of the recess defines an interface between the vertical active region and the well region. In addition, each of the gate dielectric layers may include a composite of: (i) a tunnel insulating layer in contact with the vertical active region, (ii) a charge storage layer on the tunnel insulating layer, (iii) a barrier dielectric layer on the charge storage layer; and (iv) a blocking insulating layer extending between the barrier

dielectric layer and a respective gate electrode. In some of these embodiments of the invention, the barrier dielectric layer may be formed of a material having a greater bandgap relative to the blocking insulating layer. According to still further embodiments of the invention, a protective dielectric layer is provided on a sidewall of the recess. This protective dielectric layer extends between the vertical active region and the common source region. A bottom of the recess may also define an interface between the vertical active region and the well region. This vertical active region, which may have a cylindrical shape, may include a plurality of concentrically-arranged semiconductor layers of first conductivity type having equivalent or different dopant concentrations therein.

[0007] According to additional embodiments of the invention, the vertical stack of spaced-apart gate electrodes has an opening extending therethrough that is aligned to the recess. In addition, the gate dielectric layers may have a cylindrical shape, and may be concentrically-arranged relative to the plurality of concentrically-arranged semiconductor layers.

[0008] According to still further embodiments of the invention, the vertical active region includes an active region plug filling the recess and a cylindrically-shaped active layer on the active region plug. The cylindrically-shaped active layer includes a plurality of concentrically-arranged semiconductor layers of first conductivity type having equivalent or different doping concentrations therein. A vertical stack of at least two spaced-apart gate electrodes of respective ground selection transistors may also be provided, which extend opposite the active region plug. These ground selection transistors include respective gate dielectric layers that extend on sidewalls of the active region plug. The gate dielectric layers of the vertical stack of nonvolatile memory cells may be formed of different materials relative to the gate dielectric layers of the stacked ground selection transistors.

[0009] Methods of forming three-dimensional (3D) nonvolatile memory devices according to embodiments of the invention may include forming a vertical stack of a plurality of sacrificial layers and a plurality of insulating layers arranged in an alternating sequence, on a substrate. A selective etching step is then performed to etch through the vertical stack to define a first opening therein and a recess in the substrate. The recess is filled with an electrically conductive active region plug, which is electrically connected to a well region in the substrate. A sidewall of the first opening is then lined with a first vertical active layer before the first opening is filled with a dielectric pattern that extends on the first vertical active layer. Another selective etching step is performed to selectively etch through the vertical stack to define a second opening therein that exposes the substrate. Portions of the sacrificial layers extending between each of the plurality of insulating layers in the vertical stack are then replaced with gate dielectric layers and gate electrodes of respective memory cells. The step of lining a sidewall of the first opening may include lining a sidewall of the first opening with a first vertical active layer that contacts an upper surface of the active region plug. The step of filling the recess with an active region plug may also include filling the recess with an active region plug having an upper surface that is elevated relative to surface of the substrate. In particular, the substrate may include a well region of second conductivity type and a common source region of first conductivity type extending between the well region and a surface of the substrate, and the recess containing the active region plug may extend entirely through the common source region.

[0010] According to still further embodiments of the invention, the step of lining a sidewall of the first opening with a first vertical active layer may be preceded by a step of lining the sidewall of the first opening with a first electrically insulating sub-layer that contacts an upper surface of the active region plug. A step may also be performed to selectively etching through the first vertical active layer and the first electrically insulating sub-layer in sequence to expose the upper surface of the active region plug. In addition, the step of filling the first opening with a dielectric pattern may be preceded by lining an inner sidewall of the first vertical active layer with a second vertical active layer that contacts the upper surface of the active region plug. These first and second vertical active layers may be formed as doped or undoped cylindrically-shaped silicon layers.

BRIEF DESCRIPTION OF THE DRAWINGS

[0011] The accompanying drawings are included to provide a further understanding of the inventive concept, and are incorporated in and constitute a part of this specification. The drawings illustrate exemplary embodiments of the inventive concept and, together with the description, serve to explain principles of the inventive concept. In the drawings:

[0012] FIG. 1A is a plan view illustrating a three-dimensional (3D) semiconductor memory device according to an embodiment of the inventive concept;

[0013] FIG. 1B is a cross-sectional view taken along line I-I' of FIG. 1A;

[0014] FIG. 1C is a magnified view of a portion A of FIG. 1B;

[0015] FIG. 2A is a cross-sectional view taken along line I-I' of FIG. 1A for describing a modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept;

[0016] FIG. 2B is a cross-sectional view taken along line I-I' of FIG. 1A for describing other modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept;

[0017] FIG. 3A is a cross-sectional view taken along line I-I' of FIG. 1A for describing still other modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept;

[0018] FIG. 3B is a magnified view of a portion B of FIG. 3A;

[0019] FIG. 3C is a magnified view of a portion B of FIG. 3A for describing even other modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept;

[0020] FIG. 3D is a magnified view of a portion B of FIG. 3A for describing yet other modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept;

[0021] FIG. 4A is a cross-sectional view taken along line I-I' of FIG. 1A for describing further modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept;

[0022] FIG. 4B is a magnified view of a portion C of FIG. 4A;

[0023] FIG. 5A is a plan view illustrating still further modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept;

[0024] FIG. 5B is a cross-sectional view taken along line II-II' of FIG. 5A;

[0025] FIGS. 6A to 6H are cross-sectional views taken along line I-I' of FIG. 1A for describing a method of fabricating 3D semiconductor memory device according to an embodiment of the inventive concept;

[0026] FIGS. 7A to 7D are cross-sectional views taken along line I-I' of FIG. 1A for describing a modification example of a method of fabricating 3D semiconductor memory device according to an embodiment of the inventive concept;

[0027] FIGS. 8A to 8F are cross-sectional views taken along line I-I' of FIG. 1A for describing other modification example of a method of fabricating 3D semiconductor memory device according to an embodiment of the inventive concept;

[0028] FIGS. 9A to 9D are cross-sectional views taken along line I-I' of FIG. 1A for describing still other modification example of a method of fabricating 3D semiconductor memory device according to an embodiment of the inventive concept;

[0029] FIGS. 10A to 10C are cross-sectional views taken along line I-I' of FIG. 1A for describing even other modification example of a method of fabricating 3D semiconductor memory device according to an embodiment of the inventive concept;

[0030] FIG. 11 is a cross-sectional view illustrating a 3D semiconductor memory device according to another embodiment of the inventive concept;

[0031] FIG. 12A is a cross-sectional view illustrating a modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept;

[0032] FIG. 12B is a cross-sectional view illustrating other modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept;

[0033] FIG. 12C is a cross-sectional view illustrating still other modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept;

[0034] FIG. 12D is a cross-sectional view illustrating even other modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept;

[0035] FIG. 12E is a cross-sectional view illustrating yet other modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept;

[0036] FIG. 12F is a cross-sectional view illustrating further modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept;

[0037] FIGS. 13A to 13E are cross-sectional views for describing a method of fabricating 3D semiconductor memory device according to another embodiment of the inventive concept;

[0038] FIG. 14 is a cross-sectional view illustrating a modification example of a method of fabricating 3D semiconductor memory device according to another embodiment of the inventive concept;

[0039] FIGS. 15A to 15F are cross-sectional views illustrating other modification example of a method of fabricating 3D semiconductor memory device according to another embodiment of the inventive concept;

[0040] FIGS. 16A and 16B are cross-sectional views illustrating still other modification example of a method of fabri-

cating 3D semiconductor memory device according to another embodiment of the inventive concept;

[0041] FIG. 17 is a block diagram schematically illustrating an example of an electronic system including a 3D semiconductor memory device according to an embodiment of the inventive concept; and

[0042] FIG. 18 is a block diagram schematically illustrating an example of a memory card including a 3D semiconductor memory device according to an embodiment of the inventive concept.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0043] The present invention now will be described more fully with reference to the accompanying drawings, in which preferred embodiments of the invention are shown. This invention may, however, be embodied in many different forms and should not be construed as being limited to the embodiments set forth herein; rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art. Like reference numerals refer to like elements throughout.

[0044] It will be understood that when an element or layer is referred to as being “on,” “connected to” or “coupled to” another element or layer (and variants thereof), it can be directly on, connected or coupled to the other element or layer or intervening elements or layers may be present. In contrast, when an element is referred to as being “directly on,” “directly connected to” or “directly coupled to” another element or layer (and variants thereof), there are no intervening elements or layers present. Like reference numerals refer to like elements throughout.

[0045] It will be understood that, although the terms first, second, third, etc. may be used herein to describe various elements, components, regions, layers and/or sections, these elements, components, regions, layers and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer or section from another region, layer or section. Thus, a first element, component, region, layer or section discussed below could be termed a second element, component, region, layer or section without departing from the teachings of the present invention.

[0046] Spatially relative terms, such as “beneath,” “below,” “lower,” “above,” “upper” and the like, may be used herein for ease of description to describe one element or feature’s relationship to another element(s) or feature(s) as illustrated in the figures. It will be understood that the spatially relative terms are intended to encompass different orientations of the device in use or operation in addition to the orientation depicted in the figures. For example, if the device in the figures is turned over, elements described as “below” or “beneath” other elements or features would then be oriented “above” the other elements or features. Thus, the term “below” can encompass both an orientation of above and below. The device may be otherwise oriented (rotated 90 degrees or at other orientations) and the spatially relative descriptors used herein interpreted accordingly.

[0047] The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the present invention. As used herein, the singular forms “a,” “an” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise. It will be further understood that the terms “compris-

ing,” “including,” “having” and variants thereof, when used in this specification, specify the presence of stated features, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, steps, operations, elements, components, and/or groups thereof. In contrast, the term “consisting of” when used in this specification, specifies the stated features, steps, operations, elements, and/or components, and precludes additional features, steps, operations, elements and/or components.

[0048] Embodiments of the present invention are described herein with reference to cross-section and perspective illustrations that are schematic illustrations of idealized embodiments (and intermediate structures) of the present invention. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments of the present invention should not be construed as limited to the particular shapes of regions illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a sharp angle may be somewhat rounded due to manufacturing techniques/tolerances.

[0049] Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which the present invention belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

[0050] FIG. 1A is a plan view illustrating a 3D semiconductor memory device according to an embodiment of the inventive concept. FIG. 1B is a cross-sectional view taken along line I-I' of FIG. 1A. FIG. 1C is a magnified view of a portion A of FIG. 1B. Referring to FIGS. 1A and 1B, a well region **102** doped with a first conductive dopant may be disposed in a semiconductor substrate **100** (hereinafter referred to as a substrate). The substrate **100** may be a silicon substrate, a germanium substrate or a silicon-germanium substrate, for example a common source region **105** doped with a second conductive dopant may be formed in the well region **102**. An upper surface of the common source region **105** may be disposed on the substantially same level as that of the upper surface of the substrate **100**. A lower surface of the common source region **105** may be disposed on a level higher than that of a lower surface of the well region **102**. One of the first and second conductive dopants may be an n-type dopant, and the other may be a p-type dopant. For example, the well region **102** may be doped with a p-type dopant, and the common source region **105** may be doped with an n-type dopant.

[0051] A stack-structure, including insulation patterns **110a** and gate patterns **155L**, **155a1**, **155a** and **155U** that are stacked alternately and repeatedly, may be disposed on the common source region **105**. A plurality of the stack-structures may be disposed on the common source region **105**. As illustrated in FIG. 1A, the stack-structures may be extended side by side in a first direction. The stack-structures may be spaced apart in a second direction perpendicular to the first direction. The first and second directions may be parallel with the upper surface of the substrate **100**.

[0052] A vertical active pattern **130** may pass through the stack-structure. The vertical active pattern **130** may be extended into a recess region **120** that is formed in the common source region **105** under the vertical active pattern **130**.

Therefore, the vertical active pattern **130** may be connected to the well region **102** under the vertical active pattern **130**. As illustrated in FIG. 1B, the recess region **120** may vertically pass through the common source region **105**. A bottom surface of the recess region **120** may be disposed on a level lower than that of the lower surface of the common source region **105**. The vertical active pattern **130** may contact the bottom surface of the recess region **120**. Accordingly, the vertical active pattern **130** may contact the well region **102**. Also, the vertical active pattern **130** may contact a sidewall of the recess region **120**. As a result, the vertical active pattern **130** may directly contact the common source region **105**.

[0053] According to an embodiment of the inventive concept, a portion **122** of the well region **102** just under the bottom surface of the recess region **120** may have a high dopant concentration. In other words, the first conductive dopant concentration of the portion **122** of the well region **102** may be higher than the first conductive dopant concentration of another portion of the well region **102**.

[0054] According to an embodiment of the inventive concept, the vertical active pattern **130** may have a hollow pipe shape or a macaroni shape. Herein, the lower end of the vertical active pattern **130** may be in a closed state. The inside of the vertical active pattern **130** may be filled with a filling dielectric pattern **132**.

[0055] A gate dielectric layer **150** may be disposed between a sidewall of the vertical active pattern **130** and each of the gate patterns **155L**, **155a1**, **155a** and **155U**. According to an embodiment of the inventive concept, as illustrated in FIG. 1B, the gate dielectric layer **150** may be extended to cover an upper surface and a lower surface of each of the gate patterns **155L**, **155a1**, **155a** and **155U**. That is, the extended portion of the gate dielectric layer **150** may be disposed between each of the gate patterns **155L**, **155a1**, **155a** and **155U** and the insulation pattern **110a** adjacent to each of the gate patterns **155L**, **155a1**, **155a** and **155U**.

[0056] The gate dielectric layer **150** will be described below in more detail with reference to FIG. 1C. Referring to FIG. 1C, according to an embodiment of the inventive concept, the gate dielectric layer **150** may include a tunnel dielectric layer **141**, a charge storage layer **142** and a blocking dielectric layer **143**. The tunnel dielectric layer **141** may be adjacent to the sidewall of the vertical active pattern **130**, and the blocking dielectric layer **143** may be adjacent to each of the gate patterns **155L**, **155a1**, **155a** and **155U**. The charge storage layer **142** may be disposed between the tunnel dielectric layer **141** and the blocking dielectric layer **143**. According to an embodiment of the inventive concept, as illustrated in FIG. 1C, the entirety of the gate dielectric layer **150** (i.e., the tunnel dielectric layer **141**, the charge storage layer **142** and the blocking dielectric layer **143**) may be extended to cover the upper and lower surfaces of each of the gate patterns **155L**, **155a1**, **155a** and **155U**.

[0057] The tunnel dielectric layer **141** may include oxide and/or oxynitride. The tunnel dielectric layer **141** may be single-layered or multi-layered. The charge storage layer **142** may include a dielectric material having traps for storing electric charges, for example, the charge storage layer **142** may include nitride and/or metal-oxide. The blocking dielectric layer **143** may include a high-k dielectric layer having a dielectric constant higher than that of the tunnel dielectric layer **141**. For example, the high-k dielectric layer in the blocking dielectric layer **143** may include metal-oxide such as aluminum-oxide or hafnium-oxide. Furthermore, the

blocking dielectric layer **143** may further include a barrier dielectric layer. The barrier dielectric layer in the blocking dielectric layer **143** may include a dielectric material having a greater band gap than the high-k dielectric layer in the blocking dielectric layer **143**. For example, the barrier dielectric layer may include oxide. The barrier dielectric layer may be disposed between the high-k dielectric layer and the charge storage layer **142**.

[0058] A lowermost gate pattern **155L** in the stack-structure may correspond to a ground selection gate. A ground selection transistor including the lowermost gate pattern **155L** may include a vertical channel region that is defined in the sidewall of the vertical active pattern **130**. As illustrated in FIGS. 1A and 1B, the entire lower surface of the lowermost gate pattern **155L** may substantially overlap with the common source region **105**.

[0059] An uppermost gate pattern **155U** in the stack-structure may correspond to a string selection gate. Gate patterns **155a1** and **155a** between the uppermost gate pattern **155U** and the lowermost gate pattern **155L** may correspond to cell gates. A string selection transistor including the uppermost gate pattern **155U** and cell transistors including the cell gates may also include vertical channel regions that are defined in the sidewall of the vertical active pattern **130a**. The vertical channel regions of the ground selection transistor, the cell transistor and the string selection transistor configuring one cell string may be defined in the vertical active pattern **130**.

[0060] According to an embodiment of the inventive concept, among gate patterns used as the cell gates in the stack-structure, a gate pattern most adjacent to the lowermost gate pattern **155L** may correspond to a dummy cell gate. For example, the gate pattern **155a1** disposed just on the lowermost gate pattern **155L** may be a dummy gate pattern. For example, the gate pattern **155a1** that is stacked secondly from the substrate **100** may be a dummy cell gate. Naturally, one of the insulation pattern **110a** is disposed between the lowermost gate pattern **155L** and the secondly-stacked gate pattern **155a1**. For example, a dummy cell transistor including the secondly-stacked gate pattern **155a1** may have the same shape as that of a cell transistor storing data, but may not serve as the cell transistor. For example, the dummy cell transistor may perform only a turn-on/off function. Thus, the secondly-stacked gate pattern **155a1** may be a second ground selection gate. In this case, the cell string may include a plurality of stacked ground selection transistors.

[0061] A plurality of the vertical active patterns **130** may pass through each of the stack-structures. As illustrated in FIG. 1A, the vertical active patterns **130** passing through each of the stack-structures may be arranged in the first direction to form one column. Alternatively, the vertical active patterns **130** passing through each of the stack-structures may be arranged in a zigzag shape in the first direction.

[0062] The vertical active pattern **130** may include a semiconductor material. For example, the vertical active pattern **130** may include the same semiconductor material as that of the substrate **100**. The vertical active pattern **130** may have an undoped state, or may be doped with the first conductive dopant. The vertical active pattern **130** may have a polycrystalline state or a single crystalline state. The gate patterns **155L**, **155a1**, **155a** and **155U** include a conductive material. For example, the gate patterns **155L**, **155a1**, **155a** and **155U** may include at least one of a doped semiconductor (for example, doped silicon and others), a metal (for example, tungsten, aluminum, copper and others), a transition metal

(for example, titanium, tantalum and others) or a conductive metal nitride (for example, a titanium nitride, a tantalum nitride and others). The insulation patterns **110a** may include oxide.

[0063] A device isolation pattern **160a** may be disposed between the stack-structures. An upper surface of the device isolation pattern **160a** and an upper surface of the stack-structure may substantially be coplanar. An interlayer dielectric **165** may be disposed on the substrate **100**. A contact plug **167** may be connected to an upper end of the vertical active pattern **130** through the interlayer dielectric **165**. A drain being doped with the second conductive dopant may be formed in the upper portion of the vertical active pattern **130**. A lower surface of the drain may be disposed on a level adjacent to an upper surface of the uppermost gate pattern **155U**. A bit line **170** may be disposed on the interlayer dielectric **165**, and may be connected to the contact plug **167**. The bit line **170** may be extended in the second direction and cross over the stack-structure. The interlayer dielectric **165** may include oxide. The contact plug **167** includes a conductive material. For example, the contact plug **167** may include tungsten. The bit line **170** also includes a conductive material. As an example, the bit line **170** may include tungsten, copper, aluminum or the like.

[0064] According to the above-described 3D semiconductor memory device, the vertical active pattern **130** may be disposed in the recess region **120** passing through the common source region **105** and be connected to the well region **102**. Moreover, the common source region **105** may be disposed under the lowermost gate pattern **155L**. Therefore, a distance between the vertical active pattern **130** and the common source region can be minimized, and also the vertical active pattern **130** can be connected to the well region **102**. Consequently, a current flowing through the vertical active pattern **130** can quickly flow to the common source region **105**. Accordingly, the reduction of an amount of current in a cell transistor can be minimized. Also, the vertical active pattern **130** is connected to the well region **102**, such that the erasing operation of cell transistors is very easy. As a result, the 3D semiconductor memory device can be implemented which has excellent reliability and is optimized for high integration.

[0065] Next, the modification examples of the 3D semiconductor memory device according to an embodiment of the inventive concept will be described below with reference to the accompanying drawings. In the modification examples, a description on the same elements as the above-described elements will be omitted for avoiding a repetitive description.

[0066] FIG. 2A is a cross-sectional view taken along line I-I' of FIG. 1A for describing a modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept. Referring to FIG. 2A and according to the modification example, protection dielectric patterns **173a** may be disposed between the insulation patterns **110a** and the vertical active pattern **130** and between the inner sidewall of the recess region **120** and the vertical active pattern **130**. The protection dielectric pattern **173a** may include a dielectric material for protecting the vertical active pattern **130** in a fabricating process. For example, the protection dielectric pattern **173a** may include oxide. According to the modification example, a capping semiconductor pattern **175** may be disposed on the vertical active pattern **130**. The capping semiconductor pattern **175** may also be disposed on the protection dielectric pattern **173a** that is disposed between an uppermost insulation pattern **110a** and the vertical active

pattern **130**. The upper end of the vertical active pattern **130** may be disposed on a level lower than an upper surface of the uppermost insulation pattern **110a**. The upper surface of the capping semiconductor pattern **175** and the upper surface of the uppermost insulation pattern **110a** may be substantially coplanar. The capping semiconductor pattern **175** may include the same semiconductor material as that of the vertical active pattern **130**. The capping semiconductor pattern **175** may be doped with the second conductive dopant. The contact plug **167** may be connected to the capping semiconductor pattern **175**.

[0067] FIG. 2B is a cross-sectional view taken along line I-I' of FIG. 1A for describing other modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept. Referring to FIG. 2B and according to the modification example, a bottom surface of the recess region **120** may be disposed on a level higher than the lower surface of the common source region **105**. In this case, a region **122a** being counter-doped with the first conductive dopant may be disposed under the bottom surface of the recess region **120a**. The counter-doped region **122a** may contact the vertical active pattern **130** and the well region **102**. Therefore, the vertical active pattern **130** may be connected to the well region **102** through the counter-doped region **122a**.

[0068] FIG. 3A is a cross-sectional view taken along line I-I' of FIG. 1A for describing still other modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept. FIG. 3B is a magnified view of a portion B of FIG. 3A. Referring to FIG. 3A, a gate dielectric layer **150a** according to the modification example may be disposed between a vertical active pattern **130a** and each of the gate patterns **155L**, **155a1**, **155a** and **155U**. The gate dielectric layer **150a** may include a first sub-layer **147** and a second sub-layer **149**. The first sub-layer **147** may be substantially extended vertically and be disposed between the vertical active pattern **130a** and the insulation pattern **110a**. The second sub-layer **149** may be substantially extended horizontally and cover the lower surface and upper surface of each of the gate patterns **155L**, **155a1**, **155a** and **155U**. The gate dielectric layer **150a** may include the tunnel dielectric layer, the charge storage layer and the blocking dielectric layer. Herein, the first sub-layer **147** may include at least a portion of the tunnel dielectric layer, and the second sub-layer **149** may include at least a portion of the blocking dielectric layer. One of the first and second sub-layers **147** and **149** may include the charge storage layer. In other words, a portion of the gate dielectric layer **150a** including the tunnel dielectric layer, the charge storage layer and the blocking dielectric layer may be extended vertically, and another portion of the gate dielectric layer **150a** may be extended horizontally.

[0069] The vertical active pattern **130a** may include first and second semiconductor patterns **123** and **124**. The first semiconductor pattern **123** may be disposed between the second semiconductor pattern **124** and the first sub-layer **147**. The first semiconductor pattern **123** may contact the first sub-layer **147**. According to an embodiment of the inventive concept, the first semiconductor pattern **123** may have a macaroni shape or a pipe shape where an upper end and a lower end are opened. The first semiconductor pattern **123** may not contact the inner surface of the recess region **120** by the first sub-layer **147**. The second semiconductor pattern **124** may contact the first semiconductor pattern **123** and the inner surface of the recess region **120**. The second semiconductor pattern **124** may have a macaroni shape or a pipe shape where

a lower end is closed. A filling dielectric pattern **132** may fill the inside of the second semiconductor pattern **124**. The first and second semiconductor patterns **123** and **124** may have an undoped state or be doped with a dopant (i.e., the first conductive dopant) having the same type as that of the well region **102**.

[0070] According to an embodiment of the inventive concept, as illustrated in FIG. 3B, the first sub-layer **147** of the gate dielectric layer **150a** may include a tunnel dielectric layer **141**, a charge storage layer **142** and a barrier dielectric layer **144**. In this case, the second sub-layer **149** may include a high-k dielectric material (for example, metal-oxide such as aluminum oxide or hafnium oxide) having a dielectric constant higher than that of the tunnel dielectric layer **141**. The barrier dielectric layer **144** may include a dielectric material having a greater band gap than that of the high-k dielectric material. For example, the barrier dielectric layer **144** may include oxide. The second sub-layer **149** and the barrier dielectric layer **144**, disposed between the charge storage layer **142** and each of the gate patterns **155L**, **155a1**, **155a** and **155U**, may be included in the blocking dielectric layer. In other words, the first sub-layer **147** may include the tunnel dielectric layer **141**, the charge storage layer **142** and a portion (i.e., the barrier dielectric layer **144**) of the blocking dielectric layer, and the second sub-layer **149** may include another portion (i.e., the high-k dielectric layer) of the blocking dielectric layer. However, an embodiment of the inventive concept is not limited thereto. The first and second sub-layers of the gate dielectric layer may be combined differently.

[0071] FIG. 3C is a magnified view of a portion B of FIG. 3A for describing even other modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept. Referring to FIG. 3C, a first sub-layer **147a** of a gate dielectric layer **150b** according to the modification example may include a tunnel dielectric layer **141** and a charge storage layer **142**, and a second sub-layer **149a** of the gate dielectric layer **150b** may include a barrier dielectric layer **144** and a high-k dielectric layer **146**. The high-k dielectric layer **146** may be formed of the same material as the high-k dielectric material that has been described above with reference to FIG. 3B. According to the modification example, the second sub-layer **149b** may correspond to a blocking dielectric layer. According to the modification example, the first sub-layer **147a** may include the tunnel dielectric layer **141** and the charge storage layer **142**, and the second sub-layer **149a** may include the blocking dielectric layer.

[0072] FIG. 3D is a magnified view of a portion B of FIG. 3A for describing yet other modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept. Referring to FIG. 3D, a first sub-layer **147b** of a gate dielectric layer **150c** according to the modification example may include the tunnel dielectric layer, and a second sub-layer **149b** of the gate dielectric layer **150c** may include the charge storage layer **142** and the blocking dielectric layer **143**. According to the modification example, the tunnel dielectric layer in the gate dielectric layer **150c** may be extended vertically and be disposed between the vertical active pattern **130a** and the insulation pattern **110a**, and the charge storage layer **142** and the blocking dielectric layer **143** in the gate dielectric layer **150c** may be extended horizontally and cover the upper surface and lower surface of each of the gate patterns **155L**, **155a1**, **155a** and **155U**.

[0073] The first and second sub-layers according to an embodiment of the inventive concept are not limited to the modification examples that have been described above with reference to FIGS. 3B, 3C and 3D. The first and second sub-layers may be combined differently.

[0074] FIG. 4A is a cross-sectional view taken along line I-I' of FIG. 1A for describing further modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept. FIG. 4B is a magnified view of a portion C of FIG. 4A. Referring to FIGS. 4A and 4B, the entirety of a gate dielectric layer **150d** between the vertical active pattern **130a** and each of the gate patterns **155L**, **155a1**, **155a** and **155U** may be substantially extended vertically. That is, the tunnel dielectric layer **141**, charge storage layer **142** and blocking dielectric layer **143** of the gate dielectric layer **150d** may be substantially extended vertically. An extended portion of the gate dielectric layer **150d** may be disposed between the vertical active pattern **130a** and the insulation pattern **110a**. The stack-structure of FIGS. 1A and 1B may have a line shape that is extended in the first direction. Unlike this, the stack-structure may include gate patterns having a flat plate shape. This will be described below with reference to the accompanying drawings.

[0075] FIG. 5A is a plan view illustrating still further modification example of a 3D semiconductor memory device according to an embodiment of the inventive concept. FIG. 5B is a cross-sectional view taken along line II-II' of FIG. 5A. Referring to FIGS. 5A and 5B, a stack-structure according to the modification example may include gate patterns **220L**, **220a**, **220** and **220U** and insulation patterns **210** and **210U** that are stacked alternately and repeatedly. A lowermost gate pattern **220L** in the stack-structure may be a ground selection gate, and an uppermost gate pattern **220U** in the stack-structure may be a string selection gate. The gate pattern **220a** just on the lowermost gate pattern **220L** may be used as a cell gate, a dummy cell gate or a second ground selection gate. The gate patterns **220** between the gate pattern **220a** just on the lowermost gate pattern **220L** and the upper gate pattern **220U** may be used as cell gates.

[0076] The gate patterns **220L**, **220a** and **220** under a string selection gate, as illustrated in FIGS. 5A and 5B, may have a flat plate shape. The uppermost gate pattern **220U** corresponding to the string selection gate may have a line shape that is extended in the first direction. The uppermost gate pattern **220U** may be provided in plurality, and the uppermost gate patterns **220U** may be extended side by side in the first direction. The bit line **170** may be extended in the second direction and cross over the uppermost gate pattern **220U**. Like the uppermost gate pattern **220U**, an uppermost insulation pattern **210U** on the uppermost gate pattern **220U** may also be extended in the first direction.

[0077] The vertical active pattern **130a** may pass through the stack-structure and be extended into the recess region **120** under it. The lowermost gate pattern **220L** corresponding to the ground selection gate may be disposed on the common source region **105** in the substrate **100**. The entire lower surface of the lowermost gate pattern **220L** may substantially overlap with the common source region **105**. According to the modification example, the gate dielectric layer **150d** may be disposed between the vertical active pattern **130a** and the inner sidewall of an opening **115** passing through the stack-structure. The gate dielectric layer **150d** may be substantially extended vertically. The opening **115** and the recess region **120** may be self-aligned. The gate dielectric layer **150d** may

be extended into the recess region **120**. According to an embodiment of the inventive concept, the lower end of the gate dielectric layer **150d** in the recess region **120** may be disposed on a level higher than the lower surface of the recess region **120**.

[0078] A lower interlayer dielectric **163** may be disposed between the uppermost gate patterns **220U**. An upper surface of the lower interlayer dielectric **163** may be coplanar with an upper surface of the uppermost insulation pattern **210U**. An upper interlayer dielectric **165** may be disposed on the lower interlayer dielectric **163** and the uppermost gate patterns **220U**. The insulation patterns **210** and **210U** may include oxide, nitride and/or oxynitride. The gate patterns **220L**, **220a**, **220** and **220U** may include at least one of a doped semiconductor (for example, doped silicon), a metal (for example, tungsten and others) or a conductive metal nitride (for example, a titanium nitride, a tantalum nitride and others).

[0079] The elements of the above-described modification examples may be combined or replaced. For example, the capping semiconductor pattern **175** of FIG. **2A** may be disposed on the vertical active pattern **130** or **130a** that has been disclosed in FIG. **1B**, **3A**, **4A** or **5B**.

[0080] FIGS. **6A** to **6H** are cross-sectional views taken along line I-I' of FIG. **1A** for describing a method of fabricating 3D semiconductor memory device according to an embodiment of the inventive concept. Referring to FIG. **6A**, a well region **102** may be formed by providing a first conductive dopant into the substrate **100**. A common source region **105** may be formed by providing a second conductive dopant into the upper portion of the well region **102**. Insulation layers **110** and sacrificial layers **112** may be alternately and repeatedly stacked on the common source region **105**. For example, the insulation layers **110** may be formed as oxide layers. The sacrificial layers **112** may be formed of materials having an etch selectivity with respect to the insulation layers **112**. For example, the sacrificial layers **112** may be formed as nitride layers.

[0081] Referring to FIG. **6B**, an opening **115** and a recess region **120** may be formed by sequentially patterning the insulation layers **110**, sacrificial layers **112** and the substrate **100**. The opening **115** may pass through the insulation layers **110** and sacrificial layers **112**, and the recess region **120** may be formed in the common source region **102** under the opening **115** (i.e., in a portion of the substrate **100**). The recess region **120** is self-aligned in the opening **115** by sequentially patterning the insulation layers **110** and sacrificial layers **112** and the substrate **100**. The recess region **120** may pass through the common source region **105**, and the bottom surface of the recess region **120** may be disposed on a level lower than the lower surface of the common source region **105**. Therefore, the well region **102** may be exposed to the bottom surface of the recess region **120**, and the common source region **105** may be exposed to the inner sidewall of the recess region **120**. A high concentration region **122** may be formed by providing the first conductive dopant into the well region **102** through the bottom surface of the recess region **120**. The high concentration region **122** of the first conductive dopant may be higher than another portion of the well region **102**. That is, due to the high concentration region **122**, the well region **102** may partially have a high dopant concentration.

[0082] Referring to FIG. **6C**, a semiconductor layer may be conformally formed on the substrate **100** having the opening **115** and the recess region **120**. Therefore, the semiconductor

layer may be formed to have a substantially uniform thickness on the inner surface of the recess region **120** and an inner sidewall of the opening **115**. The semiconductor layer may contact the inner surface (i.e., an inner sidewall and a bottom surface) of the recess region **120**. The semiconductor layer may be formed in a chemical vapor deposition process and/or an atomic layer deposition process. A filling dielectric layer may be formed on the semiconductor layer to fill the opening **115**. For example, the filling dielectric layer may be formed as an oxide layer. By planarizing the filling dielectric layer and the semiconductor layer until the uppermost insulation layer **110** is exposed, a vertical active pattern **130** and a filling dielectric pattern **132** may be formed in the opening **115** and the recess region **120**.

[0083] Referring to FIG. **6D**, a trench **135** may be formed by sequentially patterning the insulation layers **110** and sacrificial layers **112**, such that insulation patterns **110a** and the sacrificial patterns **112a** being alternately and repeatedly stacked may be formed at a side of the trench **135**. The insulation patterns **110a** and sacrificial patterns **112a** may include the opening **115**. That is, the vertical active patterns **130** may sequentially pass through the insulation patterns **110a** and the sacrificial patterns **112a** being alternately and repeatedly stacked on the substrate **100**. Sidewalls of the sacrificial patterns **112a** and the insulation patterns **110a** are exposed to the trench **135**.

[0084] Referring to FIG. **6E**, empty regions **140** may be formed by removing the sacrificial patterns **112a** exposed to the trench **135**. Each of the empty regions **140** corresponds to a region from which the each sacrificial pattern **112a** is removed. The empty regions **140** may expose some portions of the sidewall of the vertical active pattern **130**, respectively.

[0085] Referring to FIG. **6F**, a gate dielectric layer **150** may be conformally formed on the substrate **100** having the empty regions **140**. Therefore, the gate dielectric layer **150** may be conformally formed on the inner surfaces of the empty regions **140**. The gate dielectric layer **150**, as described above with reference to FIGS. **1B** and **1C**, may include the tunnel dielectric layer, the charge storage layer and the blocking dielectric layer.

[0086] A gate conductive layer **155** filling the empty regions **140** may be formed on the substrate **100** having the gate dielectric layer **150**. The gate conductive layer **155** may also be formed in the trench **135**. Herein, the gate conductive layer **155** may partially fill the trench **135**. Therefore, a space surrounded by the gate conductive layer **155** may be formed in the trench **135**. A bottom surface of the space may be lower than an inner-upper surface of the lowermost empty region **140**.

[0087] Referring to FIG. **6G**, the gate patterns **155L**, **155a1**, **155a** and **155U** respectively filling the empty regions **140** may be formed by etching the gate conductive layer **155**. The gate patterns **155L**, **155a1**, **155a** and **155U** are separated by the etching process of the gate conductive layer **155**. According to an embodiment of the inventive concept, the etching process of the gate conductive layer **155** may be an isotropic etching process. The insulation patterns **110a** and the gate patterns **155L**, **155a1**, **155a** and **155U**, being alternately and repeatedly stacked on the substrate **100**, may be included in a stack-structure. Subsequently, a device isolation insulation layer **160** may be formed to fill the trench **135**.

[0088] Referring to FIG. **6H**, the device isolation insulation layer **160** and the gate dielectric layer **150** may be planarized until the uppermost insulation pattern among the insulation

patterns 110a is exposed. Therefore, a device isolation pattern 160a may be formed in the trench 135. Subsequently, by forming the interlayer dielectric 165, contact plug 167 and bit line 170 of the FIG. 1B on the substrate 100, the 3D semiconductor memory device that has disclosed in FIGS. 1A, 1B and 1C may be implemented. According to the above-described 3D semiconductor memory device, the opening 115 and the recess region 120 can be formed in self-alignment by sequentially patterning the insulation layers 110, the sacrificial layers 112 and the substrate 100 (i.e. the common source region 105). Therefore, the 3D semiconductor memory device can be implemented which has excellent reliability and is optimized for high integration. Next, a method of fabricating the 3D semiconductor memory device that has been disclosed in FIG. 2A will be described below with reference to the accompanying drawings. The method may include the methods that have been described above with reference to FIGS. 6A and 6B.

[0089] FIGS. 7A to 7D are cross-sectional views taken along line I-I' of FIG. 1A for describing a modification example of a method of fabricating 3D semiconductor memory device according to an embodiment of the inventive concept.

[0090] Referring to FIGS. 6B and 7A, a protection dielectric layer 173 may be conformally formed on the substrate 100 having the opening 115 and the recess region 120, and the protection dielectric layer 173 may be etched by a blanket anisotropic etching process until the bottom surface of the recess region 120 is exposed. As illustrated in FIG. 7A, therefore, the protection dielectric layer 173 may be formed on the sidewalls of the recess region 120 and the opening 115. The protection dielectric layer 173 may include a dielectric material having an etch selectivity with respect to the sacrificial layer 112. For example, the protection dielectric layer 173 may be formed of oxide.

[0091] Subsequently, a semiconductor layer may be formed, a filling dielectric layer may be formed on the semiconductor layer, and the filling dielectric layer and the semiconductor layer may be planarized. Therefore, the vertical active pattern 130 and the filling dielectric pattern 132 may be formed in the opening 115 and the recess region 120. The vertical active pattern 130 may contact the bottom surface of the recess region 120. The protection dielectric layer 173 may be disposed between the vertical active pattern 130 and the inner sidewalls of the opening 115 and the recess region 120.

[0092] Referring to FIG. 7B, the upper ends of the vertical active pattern 130, filling dielectric pattern 132 and protection dielectric layer 175 may be recessed lower than the upper surface of the uppermost insulation layer 110. Subsequently, a capping semiconductor layer filling the opening 110 may be formed on the substrate 100, and a capping semiconductor pattern 175 may be formed by planarizing the capping semiconductor layer until the uppermost insulation layer 110 is exposed. The capping semiconductor pattern 175 may cover the recessed upper ends of the vertical active pattern 130, filling dielectric pattern 132 and protection dielectric layer 175.

[0093] Subsequently, the trench 135 may be formed by sequentially patterning the insulation layers 110 and the sacrificial layers 112. In this case, as described above, the insulation patterns 110 and the sacrificial patterns 112a that are alternately and repeatedly stacked may be formed at a side of the trench 135.

[0094] Referring to FIG. 7C, the sacrificial patterns 112a exposed to the trench 135 may be removed. Therefore, the empty regions 140 may be formed which respectively exposes some portions of the protection dielectric layer 173 disposed on the sacrificial patterns 112a and the vertical active patterns 130. As described above, the protection dielectric layer 173 has an etch selectivity with respect to the sacrificial patterns 112a, and thus it can protect the vertical active pattern 130 from a process of removing the sacrificial patterns 112a. The protection dielectric layer 173 may be used as an etch stop layer in the process of removing the sacrificial patterns 112a. Subsequently, the exposed portions of the protection dielectric layer 173 may be removed. Therefore, the empty regions 140 may expose some portions of the side wall of the vertical active pattern 130, respectively. When removing the exposed portions of the protection dielectric layer 173, the protection dielectric patterns 173a may be formed between the vertical active pattern 130 and the insulation patterns 110a and between the vertical active pattern 130 and the inner sidewall of the recess region 120. The protection dielectric patterns 173a correspond to remaining portions of protection dielectric layer 173.

[0095] Referring to FIG. 7D, the gate dielectric layer 150 may be conformally formed on the substrate 100 having the empty regions 140, and the gate patterns 155L, 155a1, 155a and 155U respectively filling the empty regions 140 may be formed. Afterwards, the device isolation pattern 160a filling the trench 135 may be formed. Subsequently, by forming the interlayer dielectric 165, contact plug 167 and bit line 170 of FIG. 2A, the 3D semiconductor memory device of FIG. 2A can be implemented.

[0096] The features of a method, that fabricates the 3D semiconductor memory device that has been disclosed in FIG. 2B, may have a process of forming the lower surface of the recess region 120 higher than the lower surface of the common source region 105 and a process of forming the counter-doped region 122a by counter-doping the common source region 105 under the bottom surface of the recess region 120 with the first conductive dopant. Other processes may be the same as the processes that have been described above with reference to FIGS. 7A to 7D.

[0097] Next, a method of fabricating the 3D semiconductor memory device that has been disclosed in FIG. 3A will be described below with reference to the accompanying drawings. The method may include the methods that have been described above with reference to FIGS. 6A and 6B.

[0098] FIGS. 8A to 8F are cross-sectional views taken along line I-I' of FIG. 1A for describing other modification example of a method of fabricating 3D semiconductor memory device according to an embodiment of the inventive concept.

[0099] Referring to FIGS. 6B and 8A, a first sub-layer 147 may be conformally formed on the substrate 100 having the opening 115 and the recess region 120. The first sub-layer 147 may be conformally formed on the inner sidewall of the opening 115 and the inner surface of the recess region 120. A first semiconductor layer 121 may be conformally formed on the substrate 100 having the first sub-layer 147.

[0100] Referring to FIG. 8B, portions of the first sub-layer 147 and the first semiconductor layer 121 disposed on the bottom surface of the recess region 120 may be removed. At this point, portions of the first sub-layer 147 and the first semiconductor layer 121 disposed outside opening 115 may also be removed. Therefore, the first sub-layer 147 and the

first semiconductor pattern 123 that are sequentially stacked on the sidewalls of the recess region 120 and opening 115 may be formed, the first semiconductor pattern 123 correspond to a portion of the first semiconductor layer 121. According to an embodiment of the inventive concept, by blanket-anisotropic-etching the first semiconductor layer 121 and the first sub-layer 147 until the bottom surface of the recess region 120 is exposed, the first semiconductor pattern 123 may be formed. The first semiconductor pattern 123 may not contact the inner surface of the recess region 120 by the first sub-layer 147.

[0101] Referring to FIG. 8C, subsequently, by isotropic-etching the first sub-layer 147, at least one portion of the inner sidewall of the recess region 120 may be exposed. At this point, a portion of the first semiconductor pattern 123 in the recess region 120 may also be etched.

[0102] Referring to FIG. 8D, subsequently, a second semiconductor layer may be conformally formed on the substrate 100, a filling dielectric layer filling the opening 115 may be formed on the second semiconductor layer. The second semiconductor layer may contact the first semiconductor pattern 123, and also the second semiconductor layer may contact the bottom surface and exposed inner sidewall of the recess region 120. By planarizing the second semiconductor layer and the filling dielectric layer, a second semiconductor pattern 124 and a filling dielectric pattern 132 may be formed in the opening 115 and the recess region 120. The second semiconductor pattern 124 may contact the bottom surface and inner sidewall of the recess region 120 and the first semiconductor pattern 123. The first and second semiconductor patterns 123 and 124 may configure a vertical active pattern 130a.

[0103] Referring to FIG. 8E, subsequently, the trench 135, the insulation patterns 110a and the sacrificial patterns 112 may be formed by sequentially patterning the insulation layers 110 and the sacrificial layers 112. The empty regions 140 may be formed by removing the sacrificial patterns 112. At this point, the empty regions 140 may expose some portions of the first sub-layer 147, respectively.

[0104] Referring to FIG. 8F, a second sub-layer 149 may be conformally formed on the substrate 100 having the empty regions 140. The second sub-layer 149 may be conformally formed on the inner surfaces of the empty regions 140. The second sub-layer 149 may contact the first sub-layer 147 exposed to the empty regions 140. The first and second sub-layers 147 and 149 may be included in the gate dielectric layer 150a. The first sub-layer 147 may include at least a portion of the tunnel dielectric layer, and the second sub-layer 149 may include at least a portion of the blocking dielectric layer. Herein, one of the first and second sub-layers 147 and 149 may include the charge storage layer. According to an embodiment of the inventive concept, the first and second sub-layers 147 and 149 may be the same as the layers that have been described above with reference to FIG. 3B. Unlike this, the first and second sub-layers 147 and 149 may be replaced with the first and second sub-layers 147a and 149a of the FIG. 3C, respectively. Unlike this, the first and second sub-layers 147 and 149 may be replaced with the first and second sub-layers 149b and 149c of the FIG. 3C, respectively. Subsequently, the gate patterns 155L, 155a1, 155a and 155U respectively filling the empty regions 140 may be formed, and the device isolation pattern 160a filling the trench 135 may be formed. Subsequently, the interlayer dielectric 165, the contact plug 167 and the bit line 170 that have been disclosed in FIG. 3A may be formed. Next, a method of fabricating the 3D

semiconductor memory device that has been disclosed in FIGS. 4A and 4B will be described below with reference to the accompanying drawings. The method may include the methods that have been described above with reference to FIGS. 6A and 6B.

[0105] FIGS. 9A to 9D are cross-sectional views taken along line I-I' of FIG. 1A for describing still other modification example of a method of fabricating 3D semiconductor memory device according to an embodiment of the inventive concept. Referring to FIGS. 6B to 9A, a gate dielectric layer 150d may be conformally formed on the substrate 100 having the opening 115 and the recess region 120. A first semiconductor layer may be conformally formed on the gate dielectric layer 150d. Subsequently, the first semiconductor layer and the gate dielectric layer 150d may be etched by a blanket-anisotropic-etching process until the bottom of the recess region 120 is exposed, such that a first semiconductor pattern 123 may be formed in the opening 115 and the recess region 120. At this point, the gate dielectric layer 150d may also be restrictively disposed in the opening 115 and the recess region 120. The first semiconductor pattern 123 may not contact the side wall of the opening 115 and the inner surface of the recess region 120 by the gate dielectric layer 150d.

[0106] Referring to FIG. 9B, subsequently, a second semiconductor may be conformally formed over the substrate 100, and a filling dielectric layer may be formed on the second semiconductor layer. By planarizing the filling dielectric layer and the second semiconductor layer, a second semiconductor pattern 124 and a filling dielectric pattern 132 may be formed in the opening 115 and the recess region 120. The first and second semiconductor patterns 123 and 124 may configure a vertical active pattern 130a. Subsequently, a trench 135, insulation patterns 110a and sacrificial patterns 112a may be formed by sequentially patterning the insulation layers 110 and the sacrificial layers 112. According to the modification example, a portion of the lowermost insulation layer among the insulation layers 110 may remain under the trench 135.

[0107] Referring to FIG. 9C, empty regions 140 may be formed by removing the sacrificial patterns 112a. The empty regions 140 may expose the gate dielectric layer 150d. Particularly, the blocking dielectric layer 143 (see FIG. 4B) in the gate dielectric layer 150d may be exposed. Subsequently, a gate conductive layer 155 filling the empty regions 140 may be formed on the substrate 100.

[0108] Referring to FIG. 9D, by removing the gate conductive layer outside the empty regions 140, gate patterns 155L, 155a1, 155a and 155U filling the empty regions 140 may be formed. Subsequently, the device isolation pattern 160a filling the trench 135 may be formed, and the interlayer dielectric 165, contact plug 167 and bit line 170 of FIG. 4A may be formed. Thus, the 3D semiconductor memory device of FIGS. 4A and 4B can be implemented. Next, a method of fabricating the 3D semiconductor memory device of FIGS. 5A and 5B will be described below with reference to the accompanying drawings.

[0109] FIGS. 10A to 10C are cross-sectional views taken along line I-I' of FIG. 1A for describing even other modification example of a method of fabricating 3D semiconductor memory device according to an embodiment of the inventive concept. Referring to FIG. 10A, insulation layers 210 and gate layers 220 may be alternately and repeatedly stacked on the common source region 105 in the substrate 100. The insulation layers 210 and gate layers 220L, 220a and 220 may have a flat plate shape. Referring to FIG. 10B, an uppermost

gate pattern 220U and an uppermost insulation pattern 210U may be formed by patterning an uppermost insulation layer and an uppermost gate layer. The uppermost gate pattern 220U and the uppermost insulation pattern 210U may have a line shape that is extended in one direction as illustrated in FIG. 5A. A lower interlayer dielectric 163 may be formed on the substrate 100, and the lower interlayer dielectric 163 may be planarized. An opening 115 and a recess region 120 may be formed by sequentially patterning the uppermost insulation pattern 210U, the uppermost gate pattern 220U, the insulation layers 210, the gate layers 220L, 220a and 220 and the common source region 105. The recess region 120 may be formed in self-alignment in the opening 115. By providing a first conductive dopant through the bottom surface of the recess region 120, a high concentration region 122 may be formed. Subsequently, a gate dielectric layer 150d may be conformally formed over the substrate 100, and a first semiconductor layer may be conformally formed on the gate dielectric layer 150d. By blanket-isotropic-etching the first semiconductor layer and the gate dielectric layer 150d until the bottom surface of the recess region 120 is exposed, a first semiconductor pattern 123 may be formed in the opening 115 and the recess region 120.

[0110] Referring to FIG. 10C, a second semiconductor layer may be conformally formed over the substrate 100, and a filling dielectric layer may be formed on the second semiconductor. By planarizing the filling dielectric layer and the second semiconductor layer, a second semiconductor pattern 124 and a filling dielectric pattern 132 may be formed in the opening 115 and the recess region 120. The first and second semiconductor patterns 123 and 124 may configure a vertical active pattern 130a. Subsequently, the tipper dielectric layer 165, contact plug 167 and bit line 170 of FIG. 5B may be formed. Thus, the 3D semiconductor memory device of FIGS. 5A and 5B can be implemented. According to the above-described method, the uppermost gate pattern 220U may be formed, and thereafter the vertical active pattern 130a may be formed. Unlike this, after the opening 115, the recess region 120 and the vertical active pattern 130a may be formed, and then the uppermost gate pattern 220U may be formed.

[0111] When forming the uppermost gate pattern 220U, a stack-structure having a line shape may be formed by sequentially patterning the gate layers 220, 220a and 220L and insulation layers 110 under the uppermost gate pattern 220U. In this case, the 3D semiconductor memory device of FIGS. 4A and 4B can be implemented. In other words, the 3D semiconductor memory device of FIGS. 4A and 4B may be implemented in the method that has been described above with reference to FIGS. 9A to 9D or a modified method of a portion of the fabricating method of FIGS. 10A to 10C.

[0112] FIG. 11 is a cross-sectional view illustrating a 3D semiconductor memory device according to another embodiment of the inventive concept. Referring to FIG. 11, a well region 102 doped with a first conductive dopant may be disposed in a substrate 100. A stack-structure may be disposed on the well region 102. The stack-structure may include insulation patterns 110a and gate patterns 155L, 155a1, 155a and 155U that are alternately and repeatedly stacked on the well region 102. A plurality of the stack-structures may be disposed on the well region 102. The stack-structures may be spaced apart from each other. As illustrated in FIG. 1a, the stack-structures may be extended in parallel.

[0113] A vertical active pattern 280 may pass through the stack-structure. Also, the vertical active pattern 280 may be extended into a recess region 120 that is formed in the substrate 100 under the vertical active pattern 280. The vertical active pattern 280 may include a lower active pattern 250 and an upper active pattern 270 that are sequentially stacked. The lower active pattern 250 may fill the recess region 120. The upper active pattern 270 may contact the inner surface (i.e., inner sidewall and bottom surface) of the recess region 120. The lower active pattern 250 is disposed in the recess region 120 and contacts the well region 102. The upper surface of the lower active pattern 250 may be disposed on a level higher than that of the upper surface of the substrate 100. According to an embodiment of the inventive concept, as illustrated in FIG. 11, the upper surface of the lower active pattern 250 may be higher than the lower surface of the lowermost gate pattern 155L and lower than the upper surface of the lowermost gate pattern 155L. However, the inventive concept is not limited thereto.

[0114] The upper active pattern 270 contacts the upper surface of the lower active pattern 250. According to an embodiment of the inventive concept, the lower active pattern 250 may have a pillar shape, and the upper active pattern 270 may have a pipe shape or a macaroni shape. In this case, the inside of the upper active pattern 270 may be filled with a filling dielectric pattern 132. The lower and upper active patterns 250 and 270 may include a semiconductor material. For example, the lower and upper active patterns 250 and 270 may include the same semiconductor material as that of the substrate 100. As an example, when the substrate 100 is a silicon substrate, the lower and upper active patterns 250 and 270 may include silicon. According to an embodiment of the inventive concept, the lower active pattern 250 may have a single crystalline state. The upper active pattern 270 may have a poly-crystalline state. The lower active pattern 250 may be doped with a dopant having the same type as that of the well region 102. The upper active pattern 270 may be doped with a dopant having the same type as that of the well region 102, or may have an undoped state.

[0115] A high concentration region 122 may be disposed under the bottom surface of the recess region 120. The high concentration region 122 may correspond to a portion of the well region 102, and it may have a higher dopant concentration than another portion of the well region 102. A gate dielectric layer 150 may be disposed between a sidewall of the vertical active pattern 280 and each of the gate patterns 155L, 155a1, 155a and 155U. As described above in first embodiment of the inventive concept, the gate dielectric layer 150 may be extended horizontally and cover the upper surface and lower surface of each of the gate patterns 155L, 155a1, 155a and 155U.

[0116] According to an embodiment of the inventive concept, a common source regions 105a may be disposed in the substrate 100 of the both sides of the stack-structure, respectively. The common source region 105a may be laterally separated from the lower active pattern 250. The common source region 105a is doped with a second conductive dopant. A device isolation pattern 160a may be disposed between the stack-structures. The common source region 105a may be disposed under the device isolation pattern 160a. In operating of the 3D semiconductor memory device, a horizontal channel may be generated in the well region 102 under the lowermost gate pattern 155L. The common source region 105a may

be electrically connected to vertical channels that are formed in the vertical active pattern 280 by the horizontal channel in the well region 102.

[0117] A contact plug 167 passing through the interlayer dielectric 165 may be connected to the upper end of the upper active pattern 270. A drain doped with the second conductive dopant may be disposed in the upper portion of the upper active pattern 270. The lower surface of the drain may be disposed on a level adjacent to the upper surface of the uppermost gate pattern 155U in the stack-structure.

[0118] According to the above-described 3D semiconductor memory device, the lower active pattern 250 included in the vertical active pattern 280 fills the recess region 120 to contact the well region 102. Therefore, reliability for the operations of a vertical cell string can be improved. Particularly, reliability for the erasing operation of cell transistors can be enhanced. Also, the vertical active pattern 280 may be divided into the lower active pattern 250 and the upper active pattern 270. Accordingly, an independent and additional process may be performed in the lower active pattern 250. For example, a dopant concentration may be adjusted in the lower active pattern 250. Thus, it is very easy to control the characteristic of the 3D semiconductor memory device. As a result, the 3D semiconductor memory device can be implemented which has excellent reliability and is optimized for high integration.

[0119] Next, the modification examples of the 3D semiconductor memory device will be described below with reference to the accompanying drawings.

[0120] FIG. 12A is a cross-sectional view illustrating a modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept. Referring to FIG. 12A, a common source region 105 may be extended to the substrate 100 under the stack-structures. For example, the entire lower surface of the lowermost gate pattern 155L may substantially overlap with the common source region 105. In this case, the bottom of the recess region 120 may be disposed on a level lower than the lower surface of the common source region 105. The common source region 105 may contact a sidewall of the lower active pattern 250.

[0121] FIG. 12B is a cross-sectional view illustrating other modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept. Referring to FIG. 12B, a vertical active pattern 280a may include a lower active pattern 250 and an upper active pattern 270a that are sequentially stacked. A gate dielectric layer 150a may be disposed between the upper active pattern 270a and each of the gate patterns 155a1, 155a and 155U disposed next to the upper active pattern 270a. The gate dielectric layer 150a may include a first and a second sub-layers 147 and 149. As described above in first embodiment of the inventive concept, the first sub-layer 147 may be extended vertically and be disposed between the upper active pattern 270a and the insulation pattern 110a. The second sub-layer 149 may be extended horizontally and cover the lower surface and upper surface of each of the gate patterns 155a1, 155a and 155U.

[0122] When the upper surface of the lower active pattern 250 is disposed on a level between the levels of the lower and upper surfaces of the lowermost gate pattern 155L, the first sub-layer 147 may not exist between the lower active pattern 250 and the lowermost gate pattern 155L. The upper active pattern 270a may include a first semiconductor pattern 265 and a second semiconductor pattern 267. The first semiconductor pattern 265 may be disposed between the first sub-

layer 147 and the second semiconductor pattern 267. The first semiconductor pattern 265 may be separated from the upper surface of the lower active pattern 250 by a portion of the first sub-layer 147. The second semiconductor pattern 267 contacts the first semiconductor pattern 265. Also, the second semiconductor pattern 267 contacts the upper surface of the lower active pattern 250.

[0123] The upper surface of the lower active pattern 250 may be divided into a center portion 252c contacting the second semiconductor pattern 267 and an edge portion 252e contacting the first sub-layer 147. Herein, the center portion 252c of the upper surface of the lower active pattern 250 may be disposed on a level lower than that of the edge portion 252e. The upper active pattern 270a including the first and second semiconductor patterns 265 and 267 may have a pipe shape or a macaroni shape. In this case, the inside of the upper active pattern 270a may be filled with a filling dielectric pattern 132. The first and second semiconductor patterns 265 and 267 may have a poly-crystalline state. In the modification example, the first and second sub-layers 147 and 149 may be replaced by the first and second sub-layers 147a and 149a of FIG. 3C or the first and second sub-layers 147b and 149b of FIG. 3C. Unlike this, as described above in first embodiment of the inventive concept, the first and second sub-layers 147 and 149 may be formed by another combination of a tunnel dielectric layer, a charge storage layer and a blocking dielectric layer.

[0124] FIG. 12C is a cross-sectional view illustrating still other modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept. Referring to FIG. 12C, at least edge portion of the upper surface of the lower active pattern 250 may be disposed on a level higher than the upper surface of the lowermost gate pattern 155L. In this case, an oxide layer 255 may be disposed between the sidewall of the lower active pattern 250 and the lowermost gate pattern 155L. The oxide layer 255 may include oxide formed by oxidizing the sidewall of the lower active pattern 250. Therefore, the width of a first portion of the lower active pattern 250 next to the oxide layer 255 may be less than that of a second portion of the lower active pattern 250 disposed in the recess region 120.

[0125] When the gate dielectric layer 150a includes the first and second sub-layers 147 and 149, the oxide layer 255 and a portion of the second sub-layer 149 may be disposed between the sidewall of the lower active pattern 250 and the lowermost gate pattern 155L. In other words, the first sub-layer 147 may not exist between the sidewall of the lower active pattern 250 and the lowermost gate pattern 155L. According to an embodiment of the inventive concept, when the first sub-layer 147 includes a charge storage layer, the charge storage layer may not exist between the sidewall of the lower active pattern 250 and the lowermost gate pattern 155L. Therefore, the reliability of a ground selection transistor including the lowermost gate pattern 155L can be improved. Moreover, the lower active pattern 250 may have a single crystalline state. Accordingly, the reliability of the ground selection transistor can be more enhanced.

[0126] FIG. 12D is a cross-sectional view illustrating even other modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept. Referring to FIG. 12D, at least the edge portion of the upper surface of a lower active pattern 250 may be disposed on a level higher than the upper surface of a gate pattern 155a1 that is stacked secondarily from the substrate 100 and

lower than the lower surface of a gate pattern that is stacked thirdly from the substrate **100**. The secondarily-stacked gate pattern **155a1** and the thirdly-stacked gate pattern are disposed over the lowermost gate pattern **155L**. In this case, an oxide layer **255** may also be disposed between the secondarily-stacked gate pattern **155a1** and the side wall of the lower active pattern **250**.

[0127] According to the modification example, a transistor including the secondarily-stacked gate pattern **155a1** may be used as a dummy transistor or a second ground selection transistor. In this case, a cell gate (for example, the thirdly-stacked gate pattern **155a**) adjacent to the secondarily-stacked gate pattern **155a1** may correspond to a dummy cell gate. As described above, a dummy cell transistor including the dummy cell gate has the same type as that of a cell transistor storing data, but it may not serve as a cell transistor. As an example, in operating of the cell string, the dummy cell transistor may perform only a turn-on/off function. However, the inventive concept is not limited thereto. The thirdly-stacked gate pattern may be used as a cell transistor.

[0128] FIG. 12E is a cross-sectional view illustrating yet other modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept. Referring to FIG. 12E, the entirety of a gate dielectric layer **150d** between the sidewall of the upper active pattern **270a** and each of the gate patterns **155a1**, **155a** and **155U** may be substantially extended vertically and be disposed between an upper active pattern **270a** and an insulation pattern **110a**. In this case, only an oxide layer **255** may be disposed between the sidewall of the lower active pattern **250** and the lowermost gate pattern **155L**.

[0129] FIG. 12F is a cross-sectional view illustrating further modification example of a 3D semiconductor memory device according to another embodiment of the inventive concept. Referring to FIG. 12F, protection dielectric patterns **173a** may be disposed between the upper active pattern **270a** and the insulation patterns **110a**. In a fabricating process, the protection dielectric pattern **173a** may include a dielectric material for protecting the upper active pattern **270**. According to an embodiment of the inventive concept, the protection dielectric pattern **173a** may not exist between the lower active pattern **250** and the inner sidewall of the recess region **120**.

[0130] The elements of the above-described modification examples may be combined without clash or replaced. For example, the common source region **105a** of FIG. 11 may be replaced with the common source region **105** of FIGS. 12B to 12F. For example, in the 3D semiconductor memory devices of FIGS. 11 and 12A to 12F, the heights of the upper surfaces of the lower active patterns **250** may be replaced.

[0131] FIGS. 13A to 13E are cross-sectional views for describing a method of fabricating 3D semiconductor memory device according to another embodiment of the inventive concept. Referring to FIG. 13A, a well region **102** may be formed by providing a first conductive dopant to the substrate **100**. Insulation layers **110** and sacrificial layers **112** that are alternately and repeatedly stacked may be formed on the well region **102**. A recess region **120** and an opening **115** that are sequentially stacked may be formed by sequentially patterning the insulation layers **110**, the sacrificial layers **112** and the substrate **100**. The opening **115** may pass through the insulation layers **110** and the sacrificial layers **112**, and the recess region **120** may be self-aligned in the opening **115** and be formed in the substrate **100**. The recess region **120** may expose the well region **102**.

[0132] Referring to FIG. 13B, a high concentration region **122** may be formed by providing the first conductive dopant through the bottom of the recess region **120**.

[0133] A lower active pattern **250** filling the recess region **120** may be formed. The upper surface of the lower active pattern **250** may be higher than the upper surface of the substrate **100**. Therefore, a portion of the lower active pattern **250** may fill the lower portion of the opening **115**. The lower active pattern **250** contacts the well region **102**. The lower active pattern **250** may be formed in a selective epitaxial growth process that uses the substrate **100** exposed by the recess region **120** as a seed layer. Therefore, the lower active pattern **250** may be formed in a single crystalline state. The lower active pattern **250** may be doped with the first conductive dopant. The lower active pattern **250** may be doped by an in-situ process when the selective epitaxial growth process is performed. Unlike this, the lower active layer **250** may be doped by an ion-implanting process.

[0134] Referring to FIG. 13C, a semiconductor layer may be conformally formed on the substrate **100** having the lower active pattern **250**, and a filling dielectric layer filling the opening **115** may be formed on the semiconductor layer. The semiconductor layer may be conformally formed on the inner sidewall of the opening **115** and the upper surface of the lower active pattern **250**. The semiconductor layer may contact the lower active pattern **250**. The semiconductor layer may be formed in a chemical vapor deposition process and/or an atomic layer deposition process. Therefore, the semiconductor layer may be formed in a poly-crystalline state.

[0135] By planarizing the filling dielectric layer and the semiconductor layer, an upper active pattern **270** and a filling dielectric pattern **132** may be formed in the opening **115**. The lower and upper active patterns **250** and **270** may configure a vertical active pattern **280**. Subsequently, a trench **135**, insulation patterns **110a** and sacrificial patterns **110a** may be formed by sequentially patterning the insulation layers **110** and the sacrificial layers **112**. The vertical active pattern **280** passes through the insulation patterns **110a** and the sacrificial patterns **112a**. Subsequently, by providing a second conductive dopant into the well region **102** under the trench **135**, a common source region **105a** may be formed.

[0136] Referring to FIG. 13D, by removing sacrificial patterns **112a** exposed to the trench **135**, empty regions **140** may be formed. According to an embodiment of the inventive concept, at least a portion of an lowermost empty regions **140** may expose a portion of the sidewall of the lower active pattern **250**. A gate dielectric layer **150** may be conformally formed on the substrate **100** having the empty regions **140**, and a gate conductive layer **155** filling the empty regions **140** may be formed.

[0137] Referring to FIG. 13E, gate patterns **155L**, **155a1**, **155a** and **155U**, that are respectively disposed in the empty regions **140**, may be formed by etching the gate conductive layer **155**. Subsequently, a device isolation pattern **160a** filling the trench **135** may be formed. The 3D semiconductor memory device of FIG. 11 may be implemented by forming the interlayer dielectric **165**, contact plug **167** and bit line **170** of FIG. 11.

[0138] According to the above-described 3D semiconductor memory device, the opening **115** and the recess region **120** are formed in self-alignment, and the lower active pattern **250** fills the recess region **120** to contact the well region **102**. After, the lower active pattern **250** is formed, and then the

upper active pattern **270** may be formed. Therefore, the doping concentration of the lower active pattern **250** may be independently adjusted. As a result, the 3D semiconductor memory device having superior reliability can be implemented. The features of the method of fabricating 3D semiconductor memory device that is illustrated in FIG. **12A** will be described below with reference to FIG. **14**.

[0139] FIG. **14** is a cross-sectional view illustrating a modification example of a method of fabricating 3D semiconductor memory device according to another embodiment of the inventive concept. Referring to FIG. **14**, a second conductive dopant is injected into a substrate **100** having a well region **102**, such that a common source region **105** may be formed. Insulation layers **110** and sacrificial layers **112** that are alternately and repeatedly stacked may be formed on the common source region **105**. An opening **115** and a recess region **120** may be formed by sequentially patterning the insulation layers **110**, the sacrificial layers **112** and the substrate **100**. The recess region **120** may pass through the common source region **105**, and thus the bottom surface of the recess region **120** may be lower than the lower surface of the common source region **105**. The bottom surface of the recess region **120** may expose the well region **102**, and the inner sidewall of the recess region **120** may expose the common source region **105**. Successive processes may be performed identically to the process that has been described above with reference to FIG. **13A** through FIG. **13E**. However, the process of forming the common source region **105a** that has been described above with reference to FIG. **13C** may be omitted.

[0140] FIGS. **15A** to **15F** are cross-sectional views illustrating other modification example of a method of fabricating 3D semiconductor memory device according to another embodiment of the inventive concept. A fabricating method according to the modification example may include the method that has been described above with reference to FIG. **14**. Referring to FIGS. **14** and **15A**, a lower active pattern **250** filling the recess region **120** may be formed on the substrate **100** having the opening **115** and the recess region **120**. The lower active pattern **250** may be formed identically to the process that has been described above with reference to FIG. **13B**. The level of the upper surface of the lower active pattern **250** may be adjusted. In FIG. **15A**, the upper surface of the lower active pattern **250** may be higher than the level of the upper surface of a lowermost sacrificial layer and lower than the level of the lower surface of a sacrificial layer just on the lowermost sacrificial layer. A first sub-layer **147** may be conformally formed on the substrate **100** having the lower active pattern **250**. A first semiconductor layer **264** may be conformally formed on the first sub-layer **147**. The first semiconductor layer **264** may be formed in a chemical vapor deposition process and/or an atomic layer deposition process. The first semiconductor layer **264** may be formed in a polycrystalline state.

[0141] Referring to FIG. **15B**, the first semiconductor layer **264** and the first sub-layer **147** may be blanket-anisotropically etched until the upper surface of the lower active pattern **250** is exposed. Therefore, a first semiconductor pattern **265** may be formed in the opening **115**. According to an embodiment of the inventive concept, the center portion of the exposed upper surface of the lower active pattern **250** may be recessed lower than the edge portion of the upper surface of the lower active pattern **250**.

[0142] Referring to FIG. **15C**, a second semiconductor layer may be conformally formed on the substrate **100** having

the first semiconductor pattern **265**, and a filling dielectric layer may be formed on the second semiconductor layer. The second semiconductor layer may contact the first semiconductor pattern **265** and the center portion of the upper surface of the lower active pattern **250**. By planarizing the filling dielectric layer and the second semiconductor layer, a second semiconductor pattern **267** and a filling dielectric pattern **132** may be formed in the opening **115**. The first and second semiconductor patterns **265** and **267** may configure an upper active pattern **270a**, and the lower and upper active patterns **250** and **270a** may configure a vertical active pattern **280a**. Subsequently, a trench **135**, insulation patterns **110a** and sacrificial patterns **112a** may be formed by sequentially patterning the insulation layers **110** and the sacrificial layers **112**.

[0143] Referring to FIG. **15D**, empty regions **140** may be formed by removing the sacrificial patterns **112a**. According to an embodiment of the inventive concept, the lowermost empty region of the empty regions **140** may expose the sidewall of the lower active pattern **250**, and empty regions on the lowermost empty region may expose the first sub-layer **147**. However, the inventive concept is not limited thereto. The number of empty regions for exposing the sidewall of the lower active pattern **250** may vary with the height of the edge portion of the upper surface of the lower active pattern **250**.

[0144] Referring to FIG. **15E**, an oxide layer **255** may be formed by performing an oxidizing process in the exposed sidewall of the lower active pattern **250**. When the lower active pattern **250** is formed of silicon, the oxide layer **255** may be formed of a silicon oxide. The sidewall of the upper active pattern **270a** may not be oxidized by the first sub-layer **147**.

[0145] Referring to FIG. **15F**, subsequently, a second sub-layer **149** may be conformally formed over the substrate **100**, and gate patterns **155L**, **155a1**, **155a** and **155U** respectively filling the empty regions **140** may be formed. Subsequently, an isolation pattern **160a**, an interlayer dielectric layer **165**, a contact plug **167** and a bit line **170** may be formed. Therefore, the 3D semiconductor memory device of FIG. **12C** can be implemented. In the fabricating method of FIGS. **15A** to **15F**, the level of the upper surface of the lower active pattern **250** may be higher than the level of the upper surface of a sacrificial layer that is stacked secondarily from the upper surface of the substrate **100** and lower than the level of the lower surface of a thirdly-stacked sacrificial layer. In this case, the 3D semiconductor memory device of FIG. **12D** can be implemented. In the fabricating method of FIGS. **15A** to **15F**, when the first sub-layer **147** is replaced by the gate dielectric layer **150d** and forming of the second sub-layer **149** is omitted, the 3D semiconductor memory device of FIG. **12E** can be implemented. Next, a method of fabricating the 3D semiconductor memory device that is illustrated in FIG. **12F** will be described below with reference to the accompanying drawings. The method may include the method that has been described above with reference to FIG. **14**.

[0146] FIGS. **16A** and **16B** are cross-sectional views illustrating still other modification example of a method of fabricating 3D semiconductor memory device according to another embodiment of the inventive concept. Referring to FIGS. **14** and **16A**, after a lower active pattern **250** may be

formed, a protection dielectric layer may be conformally formed on the substrate **100**. The protection dielectric layer may be blanket-anisotropic-etched until the upper surface of the lower active pattern **250** is exposed. Therefore, a protection dielectric layer **173** may be formed to have a spacer shape in the sidewall of the opening **115**. Subsequently, a semiconductor layer may be conformally formed, and a filling dielectric layer may be formed. The filling dielectric layer and the semiconductor layer may be planarized, such that an upper active pattern **270** and a filling dielectric pattern **132** may be formed in the opening **115**.

[0147] Subsequently, the upper ends of the protection dielectric layer **173**, upper active pattern **270** and filling dielectric pattern **132** may be recessed, and then a capping semiconductor pattern **175** may be formed. The capping semiconductor pattern **175** may be formed in the same process as the process that has been described above with reference to FIG. 7B. Referring to FIG. 16B, a trench **135**, insulation patterns **110a** and sacrificial patterns **112a** may be formed by sequentially patterning insulation layers **110** and sacrificial layers **112**. Empty regions **140** may be formed by removing the sacrificial patterns **112a**. At this point, the protection dielectric layer **173** may be used as an etch stop layer. Subsequently, by removing some portions of the protection dielectric layer **173** exposed to the empty regions **140**, some portions of the sidewall of the upper active pattern **270** may be exposed. Subsequently, the 3D semiconductor memory device of FIG. 12F can be implemented by performing the method that has been described above with reference to FIGS. 13D and 13E. According to an embodiment of the inventive concept, after forming the empty regions **140** of FIG. 16B and before forming a gate dielectric layer, an oxidizing process may be performed in the exposed sidewall of the lower active pattern **250**.

[0148] The 3D semiconductor memory devices according to embodiments of the inventive concept may be implemented as various types of packages. For example, the 3D semiconductor memory devices according to embodiments of the inventive concept may be packaged in a package type such as Package on Package (PoP), Ball Grid Arrays (BGAs), Chip Scale Packages (CSPs), Plastic Leaded Chip Carrier (PLCC), Plastic Dual In-Line Package (PDIP), Die In Waffle Pack (DIWP), Die In Wafer Form (DIWF), Chip On Board (COB), Ceramic Dual In-Line Package (CERDIP), Plastic Metric Quad Flat Pack (MQFP), Thin Quad Flat Pack (TQFP), Small Outline Package (SOP), Shrink Small Outline Package (SSOP), Thin Small Outline Package (TSOP), Thin Quad Flat Pack (TQFP), System In Package (SIP), Multi Chip Package (MCP), Wafer Level Stack Package (WLSP), Die In Wafer Form (DIWF), Die On Waffle Package (DOWP), Wafer-level Fabricated Package (WFP) and Wafer-Level Processed Stack Package (WSP).

[0149] A package on which the 3D semiconductor memory device according to embodiments of the inventive concept is mounted may further include at least one semiconductor device (for example, a controller, a memory device and/or a hybrid device) performing another function.

[0150] FIG. 17 is a block diagram schematically illustrating an example of an electronic system including a 3D semiconductor memory device according to an embodiment of the inventive concept. Referring to FIG. 17, an electronic system **1100** according to an embodiment of the inventive concept may include a controller **1110**, an input/output (I/O) unit **1120**, a memory device **1130**, an interface **1140**, and a bus

1150. The controller **1110**, the input/output (I/O) unit **1120**, the memory device **1130** and/or the interface **1140** may be connected through the bus **1150**. The bus **1150** corresponds to a path for transferring data.

[0151] The controller **1110** may include at least one of a microprocessor, a digital signal processor, a microcontroller, and logical devices for performing a function similar to the functions of the elements. The input/output unit **1120** may include a keypad, a keyboard, a display device and others. The memory device **1130** may store data and/or commands. The memory device **1130** may include at least one of the 3D semiconductor memory devices according to embodiments of the inventive concept. Also, the memory device **1130** may further include another type of semiconductor memory device (for example, Phase-change Random Access Memory (PRAM), Magnetoresistive Random Access Memory (MRAM), Dynamic Random Access Memory (DRAM) and/or Static Random Access Memory (SRAM)). The interface **1140** may transmit data to a communication network or receive data from the communication network. The interface **1140** may have a wired type or a wireless type. For example, the interface **1140** may include an antenna or a wired/wireless transceiver. Although not shown, the electronic system **1100** is a working memory device for improving the function of the controller **1110**, and may further include a high-speed DRAM and/or a high-speed SRAM.

[0152] The electronic system **1100** may be applied to Personal Digital Assistants (PDAs), portable computers, web tablets, wireless phones, mobile phones, digital music players, memory cards, and all electronic devices for transmitting/receiving information at a wireless environment.

[0153] FIG. 18 is a block diagram schematically illustrating an example of a memory card including a 3D semiconductor memory device according to an embodiment of the inventive concept. Referring to FIG. 18, a memory card **1200** according to an embodiment of the inventive concept may include a memory device **1210**. The memory device **1210** may include at least one of the 3D semiconductor memory devices according to embodiments of the inventive concept. Also, the memory device **1210** may further include another type of semiconductor memory device (for example, PRAM, MRAM, DRAM and/or SRAM). The memory card **1200** may include a memory controller **1220** for controlling data exchange between a host and the memory device **1210**.

[0154] The memory controller **1220** may include a processing unit **1222** for controlling the overall operation of the memory card **1200**. Also, the memory controller **1220** may include an SRAM **1221** that is used as the working memory of the processing unit **1222**. Furthermore, the memory controller **1220** may further include a host interface **1223** and a memory interface **1225**. The host interface **1223** may include a data exchange protocol between the memory card **1200** and the host. The memory interface **1225** may connect the memory controller **1220** and the memory device **1210**. In addition, the memory controller **1220** may further include an error correction block (ECC) **1224**. The error correction block **1224** may detect and correct the error of data that is read from the memory device **1210**. Although not shown, the memory card **1200** may further include a ROM that stores code data for interfacing with the host. The memory card **1200** may be used as a portable data memory card. On the contrary, the memory card **1200** may be implemented as a Solid State Disk (SSD) that may replace the hard disk of a computer system.

[0155] According to the above-described 3D semiconductor memory device, the vertical active pattern can be disposed in the recess region of the common source region and be connected to the well region. Therefore, the distance between the vertical active pattern and the common source region can be minimized, and also, the vertical active pattern can be connected to the well region. As a result, the 3D semiconductor memory device which has excellent reliability and is optimized for high integration can be implemented.

[0156] The above-disclosed subject matter is to be considered illustrative and not restrictive, and the appended claims are intended to cover all such modifications, enhancements, and other embodiments, which fall within the true spirit and scope of the inventive concept. Thus, to the maximum extent allowed by law, the scope of the inventive concept is to be determined by the broadest permissible interpretation of the following claims and their equivalents, and shall not be restricted or limited by the foregoing detailed description.

1. A nonvolatile memory device, comprising:

- a substrate having a well region of second conductivity type therein and a common source region of first conductivity type on the well region;
- a recess in said substrate, said recess extending at least partially through the common source region; and
- a vertical stack of nonvolatile memory cells on said substrate, said vertical stack of nonvolatile memory cells comprising:
 - a vertical stack of spaced-apart gate electrodes on said substrate;
 - a vertical active region on sidewalls of the vertical stack of spaced-apart gate electrodes and on a sidewall of the recess; and
 - gate dielectric layers extending between respective ones of the vertical stack of spaced-apart gate electrodes and said vertical active region.

2. The memory device of claim 1, wherein said recess extends entirely through the common source region; wherein the common source region forms a rectifying junction with the well region; and wherein at least one of a sidewall and bottom of said recess defines an interface between said vertical active region and the well region.

3. The memory device of claim 1, wherein each of said gate dielectric layers comprises a composite of a tunnel insulating layer in contact with said vertical active region, a charge storage layer on the tunnel insulating layer, a barrier dielectric layer on the charge storage layer and a blocking insulating layer extending between the barrier dielectric layer and a respective gate electrode; and wherein the barrier dielectric layer comprises a material having a greater bandgap relative to the blocking insulating layer.

4. The memory device of claim 1, wherein said recess has a protective dielectric layer on a sidewall thereof; and wherein the protective dielectric layer extends between said vertical active region and the common source region.

5. The memory device of claim 4, wherein a bottom of said recess defines an interface between said vertical active region and the well region.

6. The memory device of claim 1, wherein said vertical active region has a cylindrical shape.

7. The memory device of claim 6, wherein said vertical active region comprises a plurality of concentrically-arranged semiconductor layers of first conductivity type having equivalent or different dopant concentrations therein.

8. The memory device of claim 7, wherein each of said gate dielectric layers comprises a composite of a tunnel insulating layer in contact with said vertical active region, a charge storage layer on the tunnel insulating layer, a barrier dielectric layer on the charge storage layer and a blocking insulating layer extending between the barrier dielectric layer and a respective gate electrode; and wherein the barrier dielectric layer comprises a material having a greater bandgap relative to the blocking insulating layer.

9. The memory device of claim 7, wherein said vertical stack of spaced-apart gate electrodes has an opening extending therethrough that is aligned to said recess; wherein said gate dielectric layers have a cylindrical shape; and wherein said gate dielectric layers are concentrically-arranged relative to the plurality of concentrically-arranged semiconductor layers.

10. The memory device of claim 1, wherein said vertical active region comprises an active region plug filling the recess and a cylindrically-shaped active layer on the active region plug.

11. The memory device of claim 10, wherein the cylindrically-shaped active layer comprises a plurality of concentrically-arranged semiconductor layers of first conductivity type having equivalent or different doping concentrations therein.

12. The memory device of claim 10, further comprising a vertical stack of at least two spaced-apart gate electrodes of ground selection transistors extending opposite the active region plug.

13. The memory device of claim 12, wherein the ground selection transistors have respective gate dielectric layers on a side of the active region plug; and wherein the gate dielectric layers of said vertical stack of nonvolatile memory cells comprise different materials relative to the gate dielectric layers of the ground selection transistors.

14. The memory device of claim 10, further comprising at least one gate electrode of a ground selection transistor extending opposite the active region plug.

15. The memory device of claim 14, wherein the ground selection transistor has a gate dielectric layer on a sidewall of the active region plug; and wherein the gate dielectric layers of said vertical stack of nonvolatile memory cells comprise different materials relative to the gate dielectric layer of the ground selection transistor.

16. A nonvolatile memory device, comprising:

- a substrate having a well region of second conductivity type therein;
- a recess in said substrate, said recess extending into the well region;
- an electrically conductive plug in said recess, said electrically conductive plug having an upper surface that is elevated relative to a surface of said substrate;
- a vertical stack of nonvolatile memory cells on said substrate, said vertical stack of nonvolatile memory cells comprising:
 - a vertical stack of spaced-apart gate electrodes on said substrate;
 - a vertical active region on sidewalls of the vertical stack of spaced-apart gate electrodes and on a sidewall of the recess; and
 - gate dielectric layers extending between respective ones of the vertical stack of spaced-apart gate electrodes and said vertical active region; and

a first selection transistor extending between said vertical stack of nonvolatile memory cells and said substrate, said selection transistor having a gate electrode extending opposite a side of said electrically conductive plug.

17. The memory device of claim **16**, wherein the gate dielectric layers of said vertical stack of nonvolatile memory cells comprise different materials relative to a gate dielectric layer of said first selection transistor.

18. The memory device claim **17**, wherein each of the gate dielectric layers comprises a composite of a tunnel insulating layer, a charge storage layer on the tunnel insulating layer, a barrier dielectric layer on the charge storage layer and a blocking insulating layer on the barrier dielectric layer; and

wherein the barrier dielectric layer comprises a material having a greater bandgap relative to the blocking insulating layer.

19. The memory device claim **16**, wherein said substrate comprises a common source region of first conductivity type on the well region; and wherein said recess extends through the common source region and into the well region.

20. The memory device claim **16**, further comprising a second selection transistor extending between said vertical stack of nonvolatile memory cells and said first selection transistor, said second selection transistor having a gate electrode extending opposite the side of said electrically conductive plug.

21.-30. (canceled)

* * * * *