



(19) **United States**

(12) **Patent Application Publication**

Park et al.

(10) **Pub. No.: US 2003/0141811 A1**

(43) **Pub. Date: Jul. 31, 2003**

(54) **ACTIVE MATRIX ORGANIC LUMINESCENCE DISPLAY DEVICE AND MANUFACTURING METHOD FOR THE SAME**

(75) Inventors: **Jae-Yong Park**, Anyang-si (KR); **Juhn Suk Yoo**, Incheon-kwangyokshl (KR)

Correspondence Address:
Brinks Hofer Gilson & Lione
Post Office Box 10395
Chicago, IL 60610 (US)

(73) Assignee: **LG. PHILIPS LCD CO., LTD.**

(21) Appl. No.: **10/330,918**

(22) Filed: **Dec. 27, 2002**

(30) **Foreign Application Priority Data**

Dec. 29, 2001 (KR) P 2001-88537


Publication Classification

(51) Int. Cl.⁷ **H01J 1/62**

(52) U.S. Cl. **313/506**

(57) **ABSTRACT**

An active matrix organic electro luminescent display (ELD) device comprises a substrate, first and second active layers formed of polycrystalline silicon on the substrate, first source and drain regions and second source and drain regions, the first source and drain regions neighboring the first active layer and the second source and drain regions neighboring the second active layer, a gate insulating layer on the first and second active layers, first and second gate electrodes on the gate insulating layer, a first inter layer on the first and second gate electrodes, an anode electrode and a capacitor electrode on the first inter layer, a first passivation layer on the anode electrode and the capacitor electrode, a power line on the first passivation layer, first source and drain electrodes on the first passivation layer, the first source electrode being connected to the first source region and the first drain electrode being connected to the first drain region, second source and drain electrodes on the first passivation layer, the second source electrode being connected to the second source region, the power line and the capacitor electrode being connected to the second drain region and the anode electrode, and a second passivation layer on the first source and drain electrodes and the second source and drain electrodes, the second passivation layer having a bank that exposes the anode electrode.






FIG. 1
(RELATED ART)




FIG. 3B
(RELATED ART)




FIG. 3C
(RELATED ART)




FIG. 3D
(RELATED ART)




FIG. 4
(RELATED ART)




FIG. 6B




FIG. 6C




FIG. 6D




FIG. 6E




FIG. 6F




FIG. 7




FIG. 8A




FIG. 8B




FIG. 8C




FIG. 8D




FIG. 8E




FIG. 8F

ACTIVE MATRIX ORGANIC LUMINESCENCE DISPLAY DEVICE AND MANUFACTURING METHOD FOR THE SAME

[0001] This application claims the benefit of Korean Patent Application No. 2001-88537, filed on Dec. 29, 2001 in Korea, which is hereby incorporated by reference for all purposes as if fully set forth herein.

BACKGROUND THE INVENTION

[0002] 1. Field of the Invention

[0003] The present invention relates to a flat panel display device and more particularly, to an active matrix electro luminescence display (ELD) device having thin film transistors and manufacturing method for the same.

[0004] 2. Discussion of the Related Art

[0005] As the information age has been evolved rapidly, the necessity for flat panel display, which has advantages such as thinness, lightweight and lower power consumption, has been increased. Accordingly, various flat panel display devices such as liquid crystal display (LCD) devices, plasma display panels (PDPs), field emission display devices and electro luminescence display (ELD) devices have been researched. The electro luminescence display (ELD) device makes use of electro luminescence phenomenon in which light is generated when an electric field of certain intensity is applied to a fluorescent substance. The electro luminescence display (ELD) devices can be classified into inorganic electro luminescence display (ELD) devices and organic electro luminescent display (ELD) devices depending on the source that excites carriers. Attention recently has focused on the organic electro luminescent display (ELD) device as a displaying device for natural colors because it can display every colors in the visible range and has a high brightness and a low action voltage. In addition, because the organic electro luminescence display (ELD) device is self-luminescent, it has a high contrast ratio and is suitable for an ultra-thin type display device. Moreover, because it has a simple manufacturing process, the degree of environmental contamination is relatively low. Besides, the organic electro luminescence display (ELD) device has a few microseconds (ps) response time so that it is suitable for displaying moving images. The organic electro luminescence display (ELD) device has no limit in a viewing angle and is stable in low temperature conditions. Because it is driven with a relatively low voltage between 5V and 15V, manufacturing and design of a driving circuit is easy. A structure of the organic electro luminescent display (ELD) device is similar to that of the inorganic electro luminescence display (ELD) device but the light-emitting theory is different from that of the inorganic electro luminescence display (ELD) device. That is, the organic electro luminescence display (ELD) device emits light by recombination of an electron and a hole and thus it is referred to as an organic light emitting diode (OLED). Recently, an active matrix type display in which a plurality of pixels is arranged in a matrix form and a thin film transistor is connected thereto has been widely applied to the flat panel display devices. The active matrix type display is also applied to the organic electro luminescent display (ELD) device and this is transferred to as an active matrix organic electro luminescent display (ELD) device.

[0006] FIG. 1 is a circuit diagram illustrating a pixel of a related art active matrix organic electro luminescent display

device. In FIG. 1, a pixel of the active matrix organic electro luminescent display device has a switching thin film transistor 4, a driving thin film transistor 5, a storage capacitor 6 and a light emitting diode (LED) 7. The switching thin film transistor 4 and the driving thin film transistor 5 are formed of p type polycrystalline silicon thin film transistor. A gate electrode of the switching thin film transistor 4 is connected to the gate line 1 and a source electrode is connected to the data line 2. A drain electrode of the switching thin film transistor 4 is connected to a gate electrode of the driving thin film transistor 5 and a drain electrode of the driving thin film transistor 5 is connected to an anode electrode of the light emitting diode (LED) 7. A source electrode of the driving thin film transistor 5 is connected to a power line 3 and a cathode electrode of the light emitting diode (LED) 7 is grounded to earth. A storage capacitor 6 is connected to the gate electrode and the source electrode of the driving thin film transistor 5. If a signal is applied to the gate line 1, the switching thin film transistor 4 is turned on. If a signal of the data line 2 is applied to the gate electrode of the driving thin film transistor 5, the driving thin film transistor 5 is turned on and thus the light emitting diode (LED) 7 emits light. The storage capacitor 6 serves to keep a gate voltage of the driving thin film transistor 5 constant while the switching thin film transistor 4 is turned off.

[0007] FIG. 2 is a cross-sectional view of the related art active matrix organic electro luminescent display device. In FIG. 2, a polycrystalline silicon layer 11, 12, 13, 14, 15 and 16 having an island shape is formed on a substrate 10. The polycrystalline silicon layer 11, 12, 13, 14, 15 and 16 is divided into an active layer 11 and 14 of the thin film transistor and source and drain regions 12, 13, 15 and 16 on which impurities doped. A gate insulating layer 20 is formed on the polycrystalline silicon layer 11, 12, 13, 14, 15 and 16. First and second gate electrodes 21 and 22 are formed on the gate insulating layer 20 over the active layer 11 and 14. An inter layer 30 is then formed on the first and second gate electrodes 21 and 22. The inter layer 30 and the gate insulating layer 20 has first, second and third contact holes 30a, 30b and 30c that respectively exposes a portion of a first source region 12, a second drain region 15 and a second source region 16. A first source electrode 41, a second drain electrode 42 and a second source electrode 43 are formed of conductive metal material on the inter layer 30. The first source electrode 41 is connected to the first source region 12 through the first contact hole 30a, the second drain electrode 42 to the second drain region 15 through the second contact hole 30b and the second source electrode 43 to the second source region 16 through the third contact hole 30c. A first drain electrode (not shown in the figure) is further formed of same material as the first source electrode 41 over the first drain region 13 and connected to the first drain region 13. The first drain electrode (not shown) is also connected to the second gate electrode 22. The second source electrode 43 is connected to the power line 3 of FIG. 3 and it may be extended from the power line 3 of FIG. 1 or be a portion of the power line 3 of FIG. 1. A portion of the second source electrode 43 is overlapped with the second gate electrode 22 and thus forms the storage capacitor C_{st} . The first gate electrode 21, the first source electrode 41 and the first drain electrode (not shown) constitutes the switching thin film transistor 4 of FIG. 1 and the second gate electrode 22, the second source electrode 43 and the second drain electrode 42 constitutes the driving thin film transistor 5 of FIG. 1. A

first passivation layer **50** is formed on the first source electrode **41**, the second drain electrode **42** and the second source electrode **43** and the first passivation layer **50** has a fourth contact hole **50a** that exposes a portion of the second drain electrode **42**. An anode electrode **60** is formed of transparent conductive material on the first passivation layer **50** and the anode electrode **60** is connected to the second drain electrode **42** through the fourth contact hole **50a**. A second passivation layer **70** is then formed on the anode electrode **60** and the second passivation layer **70** has a bank **71** that exposes the anode electrode **60**.

[0008] FIGS. 3A to 3G are cross-sectional views illustrating a fabricating sequence of the related art active matrix organic electro luminescent display device. In FIG. 3A, a semiconductor layer **17** and **18** are formed by forming a polycrystalline silicon layer and patterning it with a first mask on the substrate **10**. A buffer layer (not shown) may further be formed of material such as silicon oxide (SiO_2) between the substrate **10** and the semiconductor layer **17** and **18**.

[0009] In FIG. 3B, the gate insulating layer **20** is formed on the semiconductor layer **17** and **18**. The first and second gate electrodes **21** and **22** are formed by depositing material such as metal and patterning it with a second mask. The active layers **11** and **14** and the source and drain regions **12**, **13**, **15** and **16** are formed by doping impurities into the semiconductor layer **17** and **18** of FIG. 3A using the first and second gate electrodes **21** and **22** as a mask. The impurities are not doped into the active layer **11** and **14**.

[0010] In FIG. 3C, the inter layer **30** is formed on the first and second gate electrodes **21** and **22** and the first, second and third contact holes **30a**, **30b** and **30c** are formed by patterning the inter layer **30** with a third mask. The first contact hole **30a** exposes the first source region **12**, the second contact hole **30b** the second drain region **15** and the third contact hole **30c** the second source region **16**.

[0011] In FIG. 3D, the first source electrode **41**, the second drain electrode **42** and the second source electrode **43** are formed by depositing conductive material such as metal on the inter layer **30** and patterning it with a fourth mask. The first source electrode **41** is connected to the first source region **12** through the first contact hole **30a**, the second drain electrode **42** to the second drain region **15** through the second contact hole **30b** and the second source electrode **43** to the second source region **16** through the third contact hole **30c**. The second source electrode **43** forms the storage capacitor C_{st} by overlapping with the second gate electrode **22**. In addition, the first drain electrode (not shown) and the power line (not shown) are formed at this time. The first drain electrode is connected to the first drain region **13** and the second gate electrode **22**, and the power line is connected to the second source electrode **43**.

[0012] In FIG. 3E, the first passivation layer **50** is formed on the first source electrode **41**, the second drain and source electrodes **42** and **43**. The fourth contact hole **50a**, which exposes a portion of the second drain electrode **42**, is formed by patterning the first passivation layer **50** with a fifth mask.

[0013] In FIG. 3F, the anode electrode **60**, which contacts the second drain electrode **42** through the fourth contact hole **50a**, is formed by depositing transparent conductive material on the first passivation layer **50** and patterning it with a sixth

mask. The anode electrode **60** becomes a pixel electrode of the active matrix organic electro luminescent display device.

[0014] In FIG. 3G, the second passivation layer **70** is formed on the anode electrode **60** and the bank **71** is formed in the second passivation layer **70** by patterning the second passivation layer **70** with a seventh mask. After forming an array substrate of the active matrix organic electro luminescent display device as stated above, the active matrix organic electro luminescent display device is completed by further forming organic luminescent layer over the bank **71** and forming a cathode electrode thereon.

[0015] The storage capacitor C_{st} is for keeping a gate driving voltage of the driving thin film transistor stable and is an important element for displaying high quality images by restraining a pixel voltage fluctuation that is induced by a kick-back voltage of the switching thin film transistor and a leakage current. A storage capacitance of the storage capacitor is proportional to an area of electrodes and a dielectric constant of a dielectric substance between two electrodes, and inverse proportional to a distance between the two electrodes, i.e., a thickness of the dielectric substance. The inter layer **30** is usually formed of silicon oxide (SiO_2) and its thickness is about 7,000 Å (angstrom). If the thickness of the inter layer **30** is small, the power line becomes winding and thus electric resistance is increased. Besides, the power line may be broken. Accordingly, there is a limit in reducing the thickness of the inter layer **30**. If the area of the electrode of the storage capacitor is increased, it results in a decrease of an area of the pixel electrode, i.e., the anode electrode **60**, and thus an aperture ratio is decreased. An active matrix organic electro luminescent display device has been suggested to overcome this problem and it is illustrated in FIG. 4. FIG. 4 is a cross-sectional view of other related art active matrix organic electro luminescent display device. Because the active matrix organic electro luminescent display device of FIG. 4 has a similar structure with that of the above mentioned one of FIG. 2 except a storage capacitor portion, a detailed explanation on a same structure will be omitted. In FIG. 4, a first inter layer **31** is formed on the first and second gate electrodes **21** and **22**. A capacitor electrode **80** that is overlapped with the second gate electrode **22** is formed on the first inter layer **31**. A second inter layer **32** is formed on the capacitor electrode **80**. The second inter layer **32** together with the first inter layer **31** and the gate insulating layer **20** has first, second, third and fourth contact holes **32a**, **32b**, **32c** and **32d**. The first contact hole **32a** exposes a portion of the first source region **12**, the second contact hole **32b** the second drain region **15**, the third contact hole **32c** the capacitor electrode **80** and the fourth contact hole **32d** the second source region **16**. The first source electrode **41**, the second drain electrode **42** and the second source electrode **43** are formed on the second inter layer **32**. The first source electrode **41** is connected to the first source region **12** through the first contact hole **32a** and the second drain electrode **42** is connected to the second drain region **15** through the second contact hole **32b**. The second source electrode **43** is connected to the capacitor electrode **80** and the second source region **16** respectively through the third and fourth contact holes **32c** and **32d**. The first and second inter layers **31** and **32** are usually formed of silicon oxide (SiO_2). A thickness of the first inter layer **31** is about 3,000 Å (angstrom) and a thickness of the second inter layer **32** is about 4,000 Å (angstrom). A summation of the thickness of

the first inter layer **31** and the thickness of the second inter layer **32** has a similar value with that of the inter layer **30** of **FIG. 2**. Because the capacitor electrode **80** is formed between the first and second inter layers **31** and **32** and the capacitor electrode **80** and the second gate electrode **22** form the storage capacitor, a thickness of the dielectric substance is reduced and thus the storage capacitance of the storage capacitor can be increased. However, this active matrix organic electro luminescent display device is manufactured by iterating a photolithographic masking process several times. Because the photolithographic masking process includes many minor processes such as cleaning, deposition of the photoresist layer, exposure, development and etching, manufacturing time and cost depends on the number of masks needed. That is, if only one mask can be omitted for the total manufacturing process, the manufacturing time and cost can be greatly saved. The active matrix organic electro luminescent display device of **FIG. 2** needs seven masks and the active matrix organic electro luminescent display device needs **8** masks because the capacitor electrode **80** must be formed of separate metal material. Accordingly, the manufacturing time and cost are increased according to the related arts.

SUMMARY OF THE INVENTION

[0016] Accordingly, the present invention is directed to an active matrix organic electro luminescent display (ELD) device and manufacturing method for the same that substantially obviates one or more of problems due to limitations and disadvantages of the related art.

[0017] An advantage of the present invention is to provide an active matrix organic electro luminescent display (ELD) device in which a storage capacitance of a storage capacitor is increased without reducing an aperture ratio and number of masks needed is reduced.

[0018] Another advantage of the present invention is to provide a manufacturing method for the active matrix organic electro luminescent display (ELD) device in which a storage capacitance of a storage capacitor is increased without reducing an aperture ratio and a number of needed masks is reduced.

[0019] Additional features and advantages of the invention will be set forth in the description, which follows, and in part will be apparent from the description, or may be learned by practice of the invention. The objectives and other advantages of the invention will be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

[0020] To achieve these and other advantages and in accordance with the purpose of the present invention, as embodied and broadly described, an active matrix organic electro luminescent display (ELD) device comprises a substrate, first and second active layers formed of polycrystalline silicon on the substrate, first source and drain regions and second source and drain regions, the first source and drain regions neighboring the first active layer and the second source and drain regions neighboring the second active layer, a gate insulating layer on the first and second active layers, first and second gate electrodes on the gate insulating layer, a first inter layer on the first and second gate electrodes, an anode electrode and a capacitor electrode on

the first inter layer, a first passivation layer on the anode electrode and the capacitor electrode, a power line on the first passivation layer, first source and drain electrodes on the first passivation layer, the first source electrode being connected to the first source region and the first drain electrode being connected to the first drain region, second source and drain electrodes on the first passivation layer, the second source electrode being connected to the second source region, the power line and the capacitor electrode and the second drain electrode being connected to the second drain region and the anode electrode, and a second passivation layer on the first source and drain electrodes and the second source and drain electrodes, the second passivation layer having a bank that exposes the anode electrode. The capacitor electrode is overlapped with the second gate electrode and forms a storage capacitor together with the second gate electrode. The capacitor electrode is overlapped with the first drain region and forms a storage capacitor together with the first drain region. The capacitor electrode is formed of same material as the anode electrode. The anode electrode is formed one of indium tin oxide (ITO) and indium zinc oxide (IZO). The power line is formed of same material as the second source and drain electrodes. The active matrix organic electro luminescent display (ELD) device further comprise a second inter layer on the first inter layer. The second inter layer is formed of silicon nitride (SiN_x).

[0021] A manufacturing method for an active matrix organic electro luminescent display (ELD) device comprises forming first and second semiconductor layers on a substrate with polycrystalline silicon, forming a gate insulating layer on the first and second semiconductor layers, forming first and second gate electrodes on the gate insulating layer, forming first source and drain regions and second source and drain regions by inputting ions into the first and second semiconductor layers using the first and second gate electrodes as a mask, forming a first inter layer on the first and second gate electrodes, forming an anode electrode on the first inter layer, forming a capacitor electrode on the first inter layer, forming a first passivation layer on the anode electrode and the capacitor electrode, the first passivation layer having a plurality of contact holes, forming a power line on the first passivation layer, forming first source and drain electrodes on the first passivation layer, the first source electrode being connected to the first source region and the first drain electrode being connected to the first drain region, forming second source and drain electrodes on the first passivation layer, the second source electrode being connected to the second source region, the power line and the capacitor electrode and the second drain electrode being connected to the second drain region and the anode electrode, and forming a second passivation layer on the first source and drain electrodes and the second source and drain electrodes, the second passivation layer having a bank that exposes the anode electrode. The capacitor electrode is overlapped with the second gate electrode and forms a storage capacitor together with the second gate electrode. The capacitor electrode is overlapped with the first drain region and forms a storage capacitor together with the first drain region. The capacitor electrode forming is performed in a same process for forming the anode electrode. The anode electrode is formed one of indium tin oxide (ITO) and indium zinc oxide (IZO). The power line forming is performed in a same process for forming the second source and drain electrodes. The manufacturing method for the active

matrix organic electro luminescent display (ELD) device further comprise forming a second inter layer on the first inter layer. The second inter layer is formed of silicon nitride (SiNx).

[0022] It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

BRIEF DESCRIPTION OF THE DRAWINGS

[0023] The accompanying drawings, which are included to provide a further understanding of the invention and are incorporated in and constitute a part of this specification, illustrate embodiments of the invention and together with the description serve to explain the principles of the invention.

[0024] In the drawings:

[0025] FIG. 1 is a circuit diagram illustrating a pixel of a related art active matrix organic electro luminescent display device;

[0026] FIG. 2 is a cross-sectional view of the related art active matrix organic electro luminescent display device;

[0027] FIGS. 3A to 3G are cross-sectional views illustrating a fabricating sequence of the related art active matrix organic electro luminescent display device;

[0028] FIG. 4 is a cross-sectional view of other related art active matrix organic electro luminescent display device;

[0029] FIG. 5 is a cross-sectional view of an active matrix organic electro luminescent display device according to a first embodiment of the present invention;

[0030] FIGS. 6A to 6F are cross-sectional views illustrating a fabricating sequence of the active matrix organic electro luminescent display device according to the first embodiment of the present invention;

[0031] FIG. 7 is a cross-sectional view of an active matrix organic electro luminescent display device according to a second embodiment of the present invention; and

[0032] FIGS. 8A to 8F are cross-sectional views illustrating a fabricating sequence of the active matrix organic electro luminescent display device according to the second embodiment of the present invention.

DETAILED DESCRIPTION OF THE ILLUSTRATED EMBODIMENTS

[0033] Reference will now be made in detail to the illustrated embodiment of the present invention, which is illustrated in the accompanying drawings.

[0034] FIG. 5 is a cross-sectional view of an active matrix organic electro luminescent display device according to a first embodiment of the present invention. In FIG. 5, a polycrystalline silicon layer 111, 112, 113, 114, 115 and 116 is formed on a transparent insulating substrate 100. The polycrystalline silicon layer 111, 112, 113, 114, 115 and 116 is divided into two regions that one has an active layer 111, a first source region 112 and a first drain region 113 and the other has an active layer 114, a second drain region 115 and a second source region 116. Impurities are doped onto the first source and drain regions 112 and 113 and the second

source and drain regions 116 and 115. A gate insulating layer 120 is formed on the polycrystalline silicon layer 111, 112, 113, 114, 115 and 116. First and second gate electrodes 121 and 122 are formed on the gate insulating layer 120 respectively over the active area 111 and 114. The gate insulating layer 120 is formed one of silicon nitride (SiNx) and silicon oxide (SiO_2) and has a thickness about 1,500 Å (angstrom). First and second inter layers 130 and 140 are sequentially formed on the first and second gate electrodes 121 and 122. Thicknesses of the first and second inter layers 130 and 140 are respectively about 2,500 Å (angstrom) and 1,500 Å (angstrom). The first inter layer 130 may be formed of silicon oxide (SiO_2) and the second inter layer 140 may be formed of silicon nitride (SiNx). On the other hand, the second inter layer 140 may be omitted. An anode electrode 151 and a capacitor electrode 152 are formed of transparent conductive material such as indium tin oxide (ITO) on the second inter layer 140. A first passivation layer 160 is formed of material such as silicon oxide (SiO_2) on the anode electrode 151 and the capacitor electrode 152. The first passivation layer 160 has first, second, third, fourth and fifth contact holes 161, 162, 163, 164 and 165. The first, third and fifth contact holes 161, 163 and 165 are formed all the way to the gate insulating layer 120. The first contact hole 161 exposes a portion of the first source region 112, the second contact hole 162 the anode electrode 151, the third contact hole 163 the second drain region 115, the fourth contact hole 164 the capacitor electrode 152 and the fifth contact hole 165 the second source region 116. A first source electrode 171, a second drain electrode 172 and a second source electrode 173 are formed on the first passivation layer 160. In addition, a first drain electrode (not shown), which is connected to the first drain region 113, and a power line (not shown), which is connected to the second source electrode 173, are also formed on the first passivation layer 160. The second source electrode 173 may be extended from the power line (not shown) or may be formed of a portion of the power line. The first source electrode 171 is connected to the first source region 112 through the first contact hole 161. The second drain electrode 172 is connected to the anode electrode 151 and the second drain region 115 respectively through the second and third contact holes 162 and 163. The second source electrode 173 is connected to the capacitor electrode 152 and the second source region 116 through the fourth and fifth contact holes 164 and 165. The capacitor electrode 152 forms a storage capacitor C_{stl} together with the second gate electrode 122. Though it is not shown in the figure, the second gate electrode 122 is electrically connected to the first drain region 113. The first gate electrode 121, the first source electrode 171 and the first drain electrode (not shown), form a switching thin film transistor, and the second gate electrode 122, the second source electrode 173 and the second drain electrode 172 form a driving thin film transistor. A second passivation layer 180 is formed on the first source electrode 171, the second drain electrode 172 and the second source electrode 173. A bank 181, which exposes anode electrode 151 is formed through the first and second passivation layers 160 and 180. Because the capacitor electrode 152 is formed of separate conductive material and connected to the power line according to the first embodiment of the present invention, a thickness of the first and second inter layer 130 and 140, i.e., a dielectric substance of the storage capacitor C_{stl} can be deduced. As state above, the second inter layer 140 may be formed of silicon nitride

(SiNx) and the silicon nitride (SiNx) has a relatively high dielectric constant compared to the silicon oxide (SiO₂). Accordingly, a storage capacitance of the storage capacitor C_{st1} can be further increased. Therefore, a reduction of the storage capacitance of the storage capacitor C_{st1} can be avoided even when an area of the storage capacitor C_{st1} is reduced and thus an area of the anode electrode 151, which becomes a pixel electrode, is increased. An aperture ratio is subsequently increased as the area of the pixel electrode is increased. Because the capacitor electrode 152 is formed with same material as that of the anode electrode 151 and the source and drain electrodes 171, 172 and 173 are formed thereon, the number of manufacturing processes can be reduced according to the first embodiment of the present invention. A manufacturing sequence of the active matrix organic electro luminescent display (ELD) device according to the first embodiment will be described hereinafter with reference to FIGS. 6A to 6F.

[0035] In FIG. 6A, first and second semiconductor layer 117 and 118 are formed by forming polycrystalline silicon layer on the transparent substrate 100 and patterning it with a first mask. The polycrystalline silicon layer may be formed in many different ways and particularly be formed by depositing amorphous silicon and crystallizing it with a laser. A buffer layer (not shown) may further be formed between the substrate 100 and the semiconductor layers 117 and 118 with material such as silicon oxide (SiO₂) to prevent impurities from penetrating into the semiconductor layers 117 and 118 from the substrate 100.

[0036] In FIG. 6B, the gate insulating layer 120 is formed on the semiconductor layers 117 and 118. The first and second gate electrodes 121 and 122 are formed by depositing material such as metal on the gate insulating layer 120 and patterning it with a second mask. The active layer 111 and 114 and the source and drain regions 112, 113, 115 and 116 are formed by inputting impurities into the semiconductor layers 117 and 118 of FIG. 6A using the first and second gate electrodes 121 and 122 as a mask. The gate insulating layer 120 may be formed one of silicon nitride (SiNx) and silicon oxide (SiO₂) and has a thickness about 1,500 Å (angstrom).

[0037] In FIG. 6C, the first and second inter layers 130 and 140 are sequentially formed on the first and second gate electrodes 121 and 122. The first inter layer 130 is formed of silicon oxide (SiO₂) and has a thickness about 2,500 Å (angstrom). The second inter layer 140 is formed of silicon nitride (SiNx) and has a thickness about 1,500 Å (angstrom). The anode electrode 151 and the capacitor electrode 152 are formed by depositing transparent conductive material on the second inter layer 140 and patterning it with a third mask. The capacitor electrode 152 and the second gate electrode 122 form the storage capacitor C_{st1}. A thickness of the storage capacitor C_{st1} is the summation of the thickness of the first and second inter layer 130 and 140.

[0038] In FIG. 6D, the first passivation layer 160 is then formed on the anode electrode 151 and the capacitor electrode 152 by depositing material such as silicon oxide (SiO₂). A thickness of the first passivation layer 160 is about 4,000 Å (angstrom). The first, second, third, fourth and fifth contact holes 161, 162, 163, 164 and 165 are formed by patterning the gate insulating layer 120, the first and second inter layers 130 and 140 and the first passivation layer 160 with a fourth mask.

[0039] In FIG. 6E, the first source electrode 171, the second drain electrode 172 and the second source electrode 173 are formed by depositing conductive material such as metal on the first passivation layer 160 and patterning it with a fifth mask. Though it is not shown in the figure, a first drain electrode (not shown), which is connected to the first drain region 113, and a power line (not shown), which is connected to the second source electrode 173, are also formed on the first passivation layer 116. The second source electrode 173 may be extended from the power line (not shown) or may be formed of a portion of the power line. As stated above, the first source electrode 171 is connected to the first source region 112 through the first contact hole 161. The second drain electrode 172 is connected to the anode electrode 151 and the second drain region 115 respectively through the second and third contact holes 162 and 163. The second source electrode 173 is connected to the capacitor electrode 152 and the second source region 110 through the fourth and fifth contact holes 164 and 165.

[0040] In FIG. 6F, the second passivation layer 180 is formed on the first source electrode 171, the second drain electrode 172 and the second source electrode 173 by depositing material such as silicon oxide (SiO₂). The bank 181, which exposes the anode electrode 151, is formed by patterning the first and second passivation layers 160 and 180 with a sixth mask.

[0041] As stated above, six masks are used in the first embodiment of the present invention to manufacture the active matrix organic electro luminescent display (ELD) device and thus the manufacturing time and cost can be saved. The gate electrode of the driving thin film transistor, i.e., the second gate electrode 122, is used as an electrode of the storage capacitor C_{st1} according to the first embodiment of the present invention but the drain region of the switching thin film transistor, i.e., the first drain region 113, which is electrically connected to the gate electrode of the driving thin film transistor, may be used as one of the electrode of the storage capacitor C_{st1} according to a second embodiment of the present invention.

[0042] A structure of an active matrix organic electro luminescent display (ELD) device and manufacturing method for the same will be described hereinafter with reference to attached figures. FIG. 7 is a cross-sectional view of an active matrix organic electro luminescent display device according to a second embodiment of the present invention. In FIG. 7, a polycrystalline silicon layer 211, 212, 213, 214, 215 and 216 is formed on a transparent insulating substrate 210. The polycrystalline silicon layer 211, 212, 213, 214, 215 and 216 comprises an active layer 211 and 214 and source and drain regions 212, 213, 215 and 216 into which impurities are doped. A gate insulating layer 220 is formed on the polycrystalline silicon layer 211, 212, 213, 214, 215 and 216. First and second gate electrodes 221 and 222 are then formed on the gate insulating layer 220 over the active layer 211 and 214. The gate insulating layer 220 may be formed one of silicon nitride (SiNx) and silicon oxide (SiO₂) and has a thickness about 1,500 Å (angstrom). First and second inter layers 230 and 240 are then formed on the first and second gate electrodes 221 and 222. The first inter layer 230 has thickness about 2,500 Å (angstrom) and the second inter layer 240 about 1,500 Å (angstrom). The first inter layer 230 may be formed of silicon oxide (SiO₂), and the second inter layer 240 may be formed of silicon nitride

(SiNx) or may be omitted. An anode electrode **251** and a capacitor electrode **252** are formed of transparent conductive material such as indium tin oxide (ITO) on the second inter layer **240**. A first passivation layer **260** is formed of silicon oxide (SiO₂) on the anode electrode **251** and the capacitor electrode **252**. First, second, third, fourth and fifth contact holes **261**, **262**, **263**, **264** and **265** are formed by patterning the gate insulating layer **220**, the first and second inter layer **230** and **240** and the first passivation layer **260**. The first, third and fourth contact holes **261**, **263** and **264** are formed to the gate insulating layer **220**. The first contact hole **261** exposes a partial first source region **212**, the second contact hole **262** the capacitor electrode **252**, the third contact hole **263** a second source region **215**, the fourth contact hole **264** a second drain region **216** and the fifth contact hole **265** the anode electrode **252**. A first source electrode **271**, a second source electrode **272** and a second drain electrode **273** are formed on the first passivation layer **260**. Though it is not shown in the figures, a first drain electrode (not shown) and a power line (not shown) are also formed on the first passivation layer **260**. The first drain electrode is connected to the first drain region **213** and the power line is connected to the second source electrode **272**. The second source electrode **272** may be extended from the power line or may be a portion of the power line. The first source electrode **271** is connected to the first source region **212** through the first contact hole **261**. The second source electrode **272** is connected to the capacitor electrode **252** and the second source region **215** respectively through the second and third contact holes **262** and **263**. The second drain electrode **273** is connected to the second drain region **216** and the anode electrode **251** respectively through the fourth and fifth contact holes **264** and **265**. The capacitor electrode **252** forms a storage capacitor C_{st2} by being overlapped with the first drain region **213**. Though it is not shown in the figure, the second gate electrode **222** is electrically connected to the first drain region **213**. The first gate electrode **221**, the first source electrode **271** and the first drain electrode (not shown) form a switching thin film transistor, and the second gate electrode **222** and the second source and drain electrodes **272** and **273** form a driving thin film transistor. A second passivation layer **280** is formed on the first source electrode **271** and the second source and drain electrodes **272** and **273**. A bank **281** is formed through the first and second passivation layers **260** and **280** to expose the anode electrode **251**. As stated above, the first drain region **213**, i.e., a drain region of the switching thin film transistor, and the capacitor electrode **252** form the storage capacitor C_{st2}. A dielectric substance of the storage capacitor comprises the gate insulating layer **220** and the first and second inter layers **230** and **240**. Because the gate insulating layer **220** is relatively thin, an increase of the thickness of the dielectric substance is not so big. Besides, because the capacitor electrode **252** is formed with separate conductive material, the thickness of the first and second inter layers **230** and **240** can be formed thin. In addition, because the second inter layer **240** formed of silicon nitride (SiNx), a storage capacitance of the storage capacitor C_{st2} can be increased and an aperture ratio can be increased by increasing an area of the anode electrode **251**.

[0043] FIGS. 8A to 8F are cross-sectional views illustrating a fabricating sequence of the active matrix organic electro luminescent display device according to the second embodiment of the present invention. In FIG. 8A, first and

second semiconductor layers **217** and **218** are formed by forming polycrystalline silicon on the transparent insulating substrate **210** and patterning it with a first mask. The polycrystalline silicon forming may be executed in many different ways and particularly it may be executed by depositing amorphous silicon and crystallizing it with a laser. A buffer layer (not shown) may further be formed between the substrate **210** and the semiconductor layers **217** and **218** with material such as silicon oxide (SiO₂).

[0044] In FIG. 8B, the gate insulating layer **220** is formed on the first and second semiconductor layers **217** and **218**. The first and second gate electrodes **221** and **222** are sequentially formed by depositing material such as metal on the gate insulating layer **220** and patterning it with a second mask. The active layer **211** and **214**, the first source and drain regions **212** and **213** and the second source and drain regions **215** and **216** are formed by inputting impurities into the semiconductor layers **217** and **218** of FIG. 8A using the first and second gate electrodes **221** and **222**. The gate insulating layer **220** may be formed of material such as silicon oxide (SiO₂) and has a thickness about 1,500 Å (angstrom).

[0045] In FIG. 8C, the first inter layer **230** is formed on the first and second gate electrodes **221** and **222** with silicon oxide (SiO₂) and a thickness of the first inter layer **230** is about 2,500 Å (angstrom). The second inter layer **240** is sequentially formed on the first inter layer **230** with silicon nitride (SiNx) and a thickness of the second inter layer **240** is about 1,500 Å (angstrom). The anode electrode **251** and the capacitor electrode **252** are formed by depositing transparent conductive materials such as indium tin oxide (ITO) and patterning it with a third mask. The capacitor electrode **252** is overlapped with the first drain region **213** and forms the storage capacitor C_{st2} together with the first drain region **213**. A thickness of the dielectric substance of the storage capacitor C_{st2} is a sum of the thickness of the gate insulating layer **220**, the first inter layer **230** and the second inter layer **240**.

[0046] In FIG. 8D, the first passivation layer **260** is formed by depositing material such as silicon oxide (SiO₂) on the anode electrode **251** and the capacitor electrode **252** and a thickness of the passivation layer **260** is about 4,000 Å (angstrom). The first, third and fourth contact holes **261**, **263** and **264** are formed through the gate insulating layer **220**, the first and second inter layers **230** and **240** and the first passivation layer **260** by a photolithographic masking technique with a fourth mask. The second and fifth contact holes **262** and **265** are formed through the first passivation layer **260** in a same way and at the same time as the first, third and fourth contact holes **261**, **263** and **264**.

[0047] In FIG. 8E, the first source electrode **271**, the second source electrode **272** and the second drain electrode **273** are formed by depositing material such as metal on the first passivation layer **260** and patterning it with a fifth mask. As stated before, the first drain electrode (not shown) and the power line (not shown) are also formed on the first passivation layer **260**. The first drain electrode is connected to the first drain region **213** and the power line is connected to the second source electrode **272**. The second source electrode **272** may be extended from the power line or may be a portion of the power line. The first drain electrode is connected to the first drain region **213** and the power line is connected to the second source electrode **272**. The second

source electrode **272** may be extended from the power line or may be a portion of the power line. The first source electrode **271**, is connected to the first source region **212** through the first contact hole **261**. The second source electrode **272** is connected to the capacitor electrode **252** and the second source region **215** respectively through the second and third contact holes **262** and **263**. The second drain electrode **273** is connected to the second drain region **215** and the anode electrode **251** respectively through the fourth and fifth contact holes **264** and **265**.

[0048] In FIG. 8F, the second passivation layer **280** is formed by depositing material such as silicon oxide (SiO₂) on the first source electrode **271** and the second source and drain electrodes **272** and **273**. The bank **281** is then formed by patterning the first and second passivation layers **260** and **280** with a sixth mask to expose the anode electrode **251**.

[0049] As stated above, because the capacitor electrode of the storage capacitor is formed with separate conductive material and connected to the power line according to the present invention, the thickness of the dielectric substance may be controlled to be thin. In addition, the storage capacitance of the storage capacitor can further be increased by forming the dielectric substance with silicon nitride (SiNx), which has a high dielectric constant. Accordingly, even if an area of the storage capacitor is reduced, a decrease of the storage capacitance can be prevented and the aperture ratio can be increased by increasing an area of the anode electrode. Furthermore, a manufacturing process and cost can be decreased by forming the capacitor electrode with same material as the anode electrode and forming the source and drain electrodes thereon.

[0050] It will be apparent to those skilled in the art that various modifications and variations can be made in the fabrication and application of the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention cover the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

1. An active matrix organic electro luminescent display (ELD) device, comprising:

- a substrate;
- first and second active layers formed of polycrystalline silicon on the substrate;
- first source and drain regions and second source and drain regions, the first source and drain regions neighboring the first active layer and the second source and drain regions neighboring the second active layer;
- a gate insulating layer on the first and second active layers;
- first and second gate electrodes on the gate insulating layer;
- a first inter layer on the first and second gate electrodes;
- an anode electrode and a capacitor electrode on the first inter layer;
- a first passivation layer on the anode electrode and the capacitor electrode;
- a power line on the first passivation layer;

first source and drain electrodes on the first passivation layer, the first source electrode being connected to the first source region and the first drain electrode being connected to the first drain region;

second source and drain electrodes on the first passivation layer, the second source electrode being connected to the second source region, the power line and the capacitor electrode and the second drain electrode being connected to the second drain region and the anode electrode; and

a second passivation layer on the first source and drain electrodes and the second source and drain electrodes, the second passivation layer having a bank that exposes the anode electrode.

2. The device according to claim 1, wherein the capacitor electrode is overlapped with the second gate electrode and forms a storage capacitor together with the second gate electrode.

3. The device according to claim 2, wherein the capacitor electrode is formed of same material as the anode electrode.

4. The device according to claim 3, wherein the anode electrode is formed one of indium tin oxide (ITO) and indium zinc oxide (IZO).

5. The device according to claim 2, wherein the power line is formed of same material as the second source and drain electrodes.

6. The device according to claim 2, further comprising a second inter layer on the first inter layer.

7. The device according to claim 6, wherein the second inter layer is formed of silicon nitride (SiNx).

8. The device according to claim 1, wherein the capacitor electrode is overlapped with the first drain region and forms a storage capacitor together with the first drain region.

9. The device according to claim 8, wherein the capacitor electrode is formed of same material as the anode electrode.

10. The device according to claim 9, wherein the anode electrode is formed one of indium tin oxide (ITO) and indium zinc oxide (IZO).

11. The device according to claim 8, wherein the power line is formed of same material as the second source and drain electrodes.

12. The device according to claim 8, further comprising a second inter layer on the first inter layer.

13. The device according to claim 9, wherein the second inter layer is formed of silicon nitride (SiNx).

14. A manufacturing method for an active matrix organic electro luminescent display (ELD) device, comprising:

forming first and second semiconductor layers on a substrate with polycrystalline silicon;

forming a gate insulating layer on the first and second semiconductor layers;

forming first and second gate electrodes on the gate insulating layer;

forming first source and drain regions and second source and drain regions by inputting ions into the first and second semiconductor layer using the first and second gate electrodes as a mask;

forming a first inter layer on the first and second gate electrodes;

forming an anode electrode on the first inter layer;

forming a capacitor electrode on the first inter layer;

forming a first passivation layer on the anode electrode and the capacitor electrode, the first passivation layer having a plurality of contact holes;

forming a power line on the first passivation layer;

forming first source and drain electrodes on the first passivation layer, the first source electrode being connected to the first source region and the first drain electrode being connected to the first drain region;

forming second source and drain electrodes on the first passivation layer, the second source electrode being connected to the second source region, the power line and the capacitor electrode and the second drain electrode being connected to the second drain region and the anode electrode; and

forming a second passivation layer on the first source and drain electrodes and the second source and drain electrodes, the second passivation layer having a bank that exposes the anode electrode.

15. The method according to claim 14, wherein the capacitor electrode is overlapped with the second gate electrode and forms a storage capacitor together with the second gate electrode.

16. The method according to claim 15 wherein the capacitor electrode forming is performed in a same process as a process for forming the anode electrode.

17. The method according to claim 16, wherein the anode electrode is formed one of indium tin oxide (ITO) and indium zinc oxide (IZO).

18. The method according to claim 15 wherein, the power line forming is performed in a same process as a process for forming the second source and drain electrodes.

19. The method according to claim 15, further comprising forming a second inter layer on the first inter layer.

20. The method according to claim 19, wherein the second inter layer is formed of silicon nitride (SiN_x).

21. The method according to claim 14, wherein the capacitor electrode is overlapped with the first drain region and forms a storage capacitor together with the first drain region.

22. The method according to claim 21, wherein the capacitor electrode forming is performed in a same process as a process for forming the anode electrode.

23. The method according to claim 22, wherein the anode electrode is formed one of indium tin oxide (ITO) and indium zinc oxide (IZO).

24. The method according to claim 21, wherein the power line forming is performed in a same process as a process for forming the second source and drain electrodes.

25. The method according to claim 21, further comprising forming a second inter layer on the first inter layer.

26. The method according to claim 25, wherein the second inter layer is formed of silicon nitride (SiN_x).

* * * * *