



US 20050121711A1

(19) **United States**(12) **Patent Application Publication** (10) Pub. No.: US 2005/0121711 A1

Pogge et al.

(43) Pub. Date:

Jun. 9, 2005(54) **CHIP AND WAFER INTEGRATION PROCESS
USING VERTICAL CONNECTIONS****Publication Classification**(76) Inventors: **H. Bernhard Pogge**, Hopewell
Junction, NY (US); **Roy Yu**,
Poughkeepsie, NY (US); **Chandrika
Prasad**, Wappingers Falls, NY (US);
Chandrasekhar Narayan, Hopewell
Junction, NY (US)(51) Int. Cl.⁷ **H01L 21/8234**; **H01L 27/108**;
H01L 29/76; **H01L 31/119**;
H01L 23/48
(52) U.S. Cl. **257/296**; **438/597**; **438/598**;
438/238; **257/734**Correspondence Address:
**INTERNATIONAL BUSINESS MACHINES
CORPORATION**
DEPT. 18G
BLDG. 300-482
2070 ROUTE 52
HOPEWELL JUNCTION, NY 12533 (US)(57) **ABSTRACT**

A process is described for semiconductor device integration at chip level or wafer level, in which vertical connections are formed through a substrate. A metallized feature is formed in the top surface of a substrate, and a handling plate is attached to the substrate. The substrate is then thinned at the bottom surface thereof to expose the bottom of the feature, to form a conducting through-via. The substrate may comprise a chip having a device (e.g. DRAM) fabricated therein. The process therefore permits vertical integration with a second chip (e.g. a PE chip). The plate may be a wafer attached to the substrate using a vertical stud/via interconnection. The substrate and plate may each have devices fabricated therein, so that the process provides vertical wafer-level integration of the devices.

(21) Appl. No.: **11/033,926**(22) Filed: **Jan. 12, 2005****Related U.S. Application Data**

(62) Division of application No. 10/465,506, filed on Jun. 19, 2003, now Pat. No. 6,856,025, which is a division of application No. 10/026,103, filed on Dec. 19, 2001, now Pat. No. 6,599,778.




FIG. 1A
PRIOR ART




FIG. 1B
PRIOR ART




FIG. 2A




FIG. 2B




FIG. 2C




FIG. 2D




FIG. 2E




FIG. 2F




FIG. 3A




FIG. 3B




FIG. 3C





FIG. 3D






FIG. 3F




FIG. 3G




FIG. 4A




FIG. 4B




FIG. 4C





FIG. 4E



CHIP AND WAFER INTEGRATION PROCESS USING VERTICAL CONNECTIONS

FIELD OF THE INVENTION

[0001] This invention relates to the manufacture of integrated circuit devices. More particularly, this application relates to a process for chip-level and wafer-level integration in which vertical interconnections are formed.

BACKGROUND OF THE INVENTION

[0002] The need for greater functionality and performance in semiconductor devices has resulted in the development of larger and more complex chips. In addition, it is often desirable to include several different functions on a single chip to obtain a "system on a chip," which generally results in both an increased chip size and a more complicated manufacturing process. These factors both tend to depress manufacturing yield. It is estimated that many such complex chips, with areas greater than 400 mm², will generally have very poor manufacturing yield (perhaps under 10%).

[0003] One method of maintaining acceptable yields is to manufacture smaller chips, and then to interconnect those chips using lateral and vertical connections on the chips or on support substrates. The interconnected chips thus form a single larger chip which is mounted on another chip, on a substrate or on a chip carrier. Besides improved manufacturing yield, another major advantage of this approach is that the individual chips may be of different sizes, perform different functions, or be fabricated by different or incompatible methods.

[0004] A system constructed according to this approach is illustrated schematically in FIG. 1A. The substrate or bottom chip 11 has several chips 10 mounted thereon, with lateral spacing Δx and Δy . For example, the bottom chip 11 may be a DRAM chip while the four chips 10 are processor ("processor engine" or PE) chips.

[0005] To realize the advantages offered by the system-on-a-chip (SOC) concept, the different chips are preferably in very close proximity and have very precise alignment with respect to each other. For example, spacing Δx and Δy between chips 10 is preferably about 50 μm or less.

[0006] Chips 10 may be placed on the substrate or bottom chip 11 with very high accuracy (within about 1 μm) by using a stud/via interconnection, shown schematically in FIG. 1B. In FIG. 1B, chip 10 has metal studs 12 formed on the terminal surface of the chip, with a layer 16 of a low-melting-point alloy material deposited on the surface of the stud. Dielectric layer 17 (often designed and fabricated as a multilayer structure of polyimide), on the surface of bottom chip 11, has embedded therein high-density wiring 18 (generally several levels of Cu conductors, as shown schematically in FIG. 1B), and has electrical joining pads 15 on the surface of layer 17. A dielectric layer 14 overlies the wiring layer 17; layer 14 may be formed of a polyimide material typically used in thin film packaging processing. Layer 14 has vias 13 formed therein (e.g. by reactive-ion etching, by photolithography or by an excimer laser), so that a terminal metal joining pad 15 is at each via bottom. The vias may be formed with a sloped wall angle as a guide for high-accuracy, self-aligned placement of the studs 12 in the vias 13. A thin coating 19 of thermoplastic polymer adhesive

may be deposited on the top of the dielectric layer 14, to ensure reliable bonding to the chip surface. Details of this stud/via alignment and joining process are provided in U.S. patent application Ser. No. 09/669,531, entitled "Process for making fine pitch connections between devices and structure made by the process," the disclosure of which is incorporated herein by reference. The use of self-aligning stud/via interconnections permits a significantly higher wiring density compared to current C4 interconnection schemes.

[0007] In the SOC shown in FIG. 1A, the wiring layer extends laterally outside the area of chips 10. External connections are generally made at the perimeter 11a of the top surface of bottom chip 11. The overall size of the SOC therefore limits the space available for wirebonding to make the external connections. It is desirable that the external connections instead be made through the backsides of the chips, so that the connections are not restricted by wirebonding space requirements. Formation of a connection pad (e.g. C4 pad) on the backside 10b of a chip would require that electrical connections be made vertically through the chip body, to the device side (surface 10a) of the chip. Furthermore, building vertical interconnections through a device chip would facilitate vertical stacking of chips, effectively extending the SOC concept to three dimensions.

[0008] Accordingly, there is a need for a process for fabricating vertical interconnections in a multi-chip device such as an SOC, which permits three-dimensional chip interconnection and which can be practiced with high manufacturing yield.

SUMMARY OF THE INVENTION

[0009] The present invention addresses the above-described need by providing a process for vertical integration at chip level or wafer level, in which vertical connections are formed using a through-via in a chip. According to a first aspect of the invention, a method is provided for fabricating a semiconductor structure. A feature is formed in the top surface of the substrate, and metal is deposited in the feature to make a conducting path. A liner may first be deposited in the feature to isolate the metal from the semiconductor material. A layer is then formed which overlies the top surface of the substrate; the layer includes an electrical conductor and a first conducting pad on a top surface of the layer, so that the first conducting pad is electrically connected to the feature. A plate is attached to this layer, and the substrate is then thinned at the bottom surface thereof to expose the bottom of the feature. A second conducting pad is formed on the bottom surface of the substrate to make an electrical connection to the bottom of the feature, so that the first conducting pad and the second conducting pad are electrically connected through the feature.

[0010] The substrate may comprise a chip having a device (e.g. DRAM) fabricated therein. Formation of a conducting path in a through-via in this chip therefore permits vertical integration with a second chip (e.g. a PE chip).

[0011] The plate may be a temporary handling plate to facilitate thinning of the substrate. If the plate is transparent to ablating radiation, it may be conveniently removed by ablating an interface between the layer and the plate.

[0012] According to another aspect of the invention, the plate is a semiconductor wafer which is not removed from

the substrate; this wafer is attached to the substrate using a vertical stud/via interconnection. A second layer is formed on the above-described layer overlying the substrate, and a via is formed in the second layer exposing the first conducting pad. A stud is formed on the semiconductor wafer and aligned to the via; the wafer is then contacted to the second layer so that the stud makes electrical connection with the first conducting pad. Accordingly, the substrate and plate (semiconductor wafer) form a wafer system, and the substrate and plate may each have devices fabricated therein (e.g. DRAM and PE devices respectively). This process thus provides vertical wafer-level integration of the devices.

[0013] According to another aspect of the invention, a semiconductor structure is provided which includes a substrate; a first layer overlying the top surface of the substrate; conducting pads on top of the first layer and on the bottom surface of the substrate; a second layer on the first layer; and a plate contacting the first layer. The substrate has a via extending therethrough, with a first electrical conductor formed in the via. The first layer includes a second electrical conductor connecting the first electrical conductor with the conducting pad on top of the layer. The conducting pad on the bottom surface of the substrate is electrically connected to the first electrical conductor, so that the first conducting pad and the second conducting pad are electrically connected. The second layer has a via formed therein exposing the conducting pad on top of the first layer. The plate has a stud formed thereon, aligned to the via and making electrical contact with the conducting pad.

[0014] The present invention offers a significant advantage in that the through-via is formed in the substrate without an expensive deep-via etching process. Via dimensions may be maintained with very high fidelity, which in turn permits a high density of through-vias. Furthermore, the use of vertical stud/via interconnections allows for highly accurate chip placement in the third dimension, similar to the highly accurate lateral chip placement described above.

BRIEF DESCRIPTION OF THE DRAWINGS

[0015] FIG. 1A is a schematic illustration of system on a chip in which smaller chips are arranged on a larger chip and are integrated and connected in close proximity.

[0016] FIG. 1B illustrates a high accuracy, self-aligning stud/via interconnection scheme for the chips of FIG. 1A.

[0017] FIGS. 2A-2F illustrate steps in a process for forming a vertical interconnection through the body of a chip, in accordance with an embodiment of the invention.

[0018] FIGS. 3A-3F illustrate steps in a process for obtaining chip-level integration of DRAM chips and processor (PE) chips using vertical interconnections, in accordance with an embodiment of the invention.

[0019] FIG. 3G illustrates an alternative chip-level integration using the vertical interconnections of FIG. 3F.

[0020] FIGS. 4A-4E illustrate steps in a process for obtaining wafer-level integration of DRAM and PE wafers using vertical interconnections, in accordance with another embodiment of the invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0021] In accordance with the present invention, a semiconductor device is fabricated which includes vertical elec-

trical connections through a chip. These vertical connections are formed by constructing metallized through-vias in the chip, without the need for expensive deep via etching.

[0022] In the embodiments discussed below, two different types of chips are vertically connected. Specifically, in the examples shown, a DRAM chip (or silicon DRAM device wafer) is vertically connected to a plurality of PE chips (or a silicon PE device wafer). It will be appreciated that these types of chips are discussed for purposes of illustration only, and that the present invention may be practiced with a wide variety of chips and wafer types.

[0023] Formation of Metallized vias

[0024] A metallized through-via in a semiconductor substrate, such as a silicon wafer, may be formed by depositing metal in a trench and thinning the wafer to open the bottom of the trench, as detailed below.

[0025] In a silicon wafer 1, prior to the fabrication of devices therein, trenches 2 are etched where the vertical connections are desired. As shown in FIG. 2A, the trenches do not extend through the wafer, but should extend into the bulk Si below the depth of the devices. An oxide layer 21 is grown or deposited on the wafer and in the trenches. A trench liner 22, typically of tungsten, is deposited on the oxide, preferably by chemical vapor deposition (CVD). A layer 23 of copper is then deposited on the liner. (As is understood by those skilled in the art, a liner is necessary when copper is used to metallize the trench; numerous alternative metallization schemes are possible which do not require a liner.) The deposition process for layer 23 is ionized physical vapor deposition (IPVD), to ensure a thin, conformal coating of the interior of the trench.

[0026] A layer 24 of copper is formed on layer 23 (e.g. by electroplating) in the trench and on top of the wafer. Layer 24 is built up on the sidewalls of the trench until it reaches a thickness such that the upper part of the trench is closed, as shown in FIG. 2C. With this structure, a conducting path is established between the bottom of the trench and the top surface of the wafer, while a void 25 remains near the bottom of the trench. It should be noted that the void 25 has an important function in relieving stresses caused by differences in the thermal coefficient of expansion (TCE) of the various materials in and around the feature.

[0027] The wafer is then planarized, preferably by chemical-mechanical polishing (CMP), to remove layers 21-24 from the top surface of the wafer. The resulting structure is shown in FIG. 2D. The copper at the top of the trench is then etched away (by reactive sputtering or some other convenient process) to a depth of about 5 μm , to yield the structure shown in FIG. 2E. A layer of tungsten is deposited on the wafer (preferably by CVD) and the wafer is again planarized using CMP, leaving a tungsten layer 26 at the top of each trench and an exposed surface 1p of the silicon wafer (FIG. 2F). The trench structure 20 thus has copper metallization encased in tungsten.

[0028] The wafer is then ready to have devices formed therein near surface 1p, and to be further processed to obtain either chip-level or wafer-level integration.

[0029] Chip-Level Integration

[0030] Devices 30, shown schematically in FIG. 3A, are fabricated in wafer 1 after the metallized trench structure 20

is completed. As shown in **FIG. 3A**, the devices are located in a region of wafer **1** adjacent to the top surface of the wafer. In this embodiment, devices **30** are DRAM devices. Dielectric layer **31** (typically polyimide) is then formed on top of the wafer; layer **31** has embedded therein high-density wiring **32a-32c**, and has on its top surface electrical joining pads **33** for making external connections (e.g. to PE chips on top of the DRAM chip). Examples of possible connections are shown schematically in **FIG. 3A**. The electrical wiring may connect a metallized via to a joining pad (conductor **32a**); a device to a joining pad (conductor **32b**); or a device to a via and/or a joining pad (conductor **32c**). Although layer **31**, including the conductors, is shown as a single layer, it will be appreciated that for ease of manufacturing it is often designed and fabricated as a multilayer structure. Pads **33** are typically formed as a multilayer structure including a Ti—W alloy, Ni, and Au, but may also include Cu, Co or other combinations of metals.

[0031] Wafer **1** is then thinned, by grinding, CMP, or some other convenient process, so that the interior of metallized via structure **20** is exposed at the bottom surface **1b** or backside of wafer **1** (**FIG. 3B**). The thinned wafer may be difficult to handle or be incompatible with the equipment used in subsequent wafer processing. Accordingly, it may be desirable to attach a temporary handling plate to the wafer before the thinning process is performed, particularly if the final thickness of the wafer is less than 150 μm . In this embodiment, the wafer thickness is reduced to about 100 μm or less. As shown in **FIG. 3B**, a glass plate **35** is attached to the top surface of layer **31** using a layer of adhesive **36**.

[0032] Each via structure **20** at this point is a through-via with tungsten layer **22** exposed on the bottom surface **1b** of the wafer. An insulating layer **37** (e.g. polyimide) is deposited on surface **1b**, and openings **38** are formed therein, at the locations of the vias **20**. A metal layer (or combination of layers) is then deposited on layer **37** and patterned so that metal pads **39** are formed in and around the openings **38**. Pads **39** typically have a structure similar to pads **33**; that is, a multilayer structure including a Ti—W alloy, Ni, and Au. The resulting structure is shown in **FIG. 3C**.

[0033] Solder bumps **41** are then formed on the back side of the wafer on pads **39**, using methods known in the art. For example, a solder paste may be applied to the wafer through a screen, and the deposited solder subjected to a reflow process. **FIG. 3D** shows the wafer structure ready for dicing and joining to a carrier.

[0034] In this embodiment, the wafer is diced into chips **44** while the glass handling plate **35** is kept intact, as shown in **FIG. 3E**. Alternatively, the dicing process may include dicing of plate **35** (thus requiring handling of individual chips in the joining process). The chips are joined to a carrier **45**; solder bumps **41** are typically connected to metal pads (not shown) at the top surface of the carrier. Carrier **45** may be another chip, a ceramic substrate, a circuit board, etc.

[0035] After the joining process, the temporary handling plate **35** is removed from the chips. This may be conveniently done by a laser ablation process, as shown schematically in **FIG. 3E**. Laser radiation **46**, incident on glass plate **35**, penetrates the plate and ablates the interface between the plate and the adhesive layer **36**. This results in delamination of the plate from layer **36**, so that plate **35** may be removed. The remaining adhesive is then cleaned away so that joining pads **33** are exposed.

[0036] As shown in **FIG. 3F**, vertical integration of DRAM chips **44** and PE chips **54** is accomplished by bonding the PE chips to the joining pads **33** of the DRAM chips. In the PE chips **54**, processing devices **50** are fabricated in the wafer; otherwise the PE chips are prepared according to the same method as described above, with similar structures indicated by repeated reference numerals in **FIG. 3F**. In particular, it should be noted that the joining pads **33** on the top surface of chips **54** may be used to make external connections to the vertically integrated structure **55**, which includes a DRAM chip and a plurality of PE chips.

[0037] Alternatively, as shown in **FIG. 3G**, the PE chips may be conventional chips **56** (having devices **51** in substrate **52** and wiring layer **31**) without vertical through-via connections. In this case the PE chips **56** are joined to chips **44** (which have vertical through-via connections) to form integrated structure **57**.

[0038] Wafer-Level Integration

[0039] In this embodiment of the invention, a metallized through-via is formed in a wafer, and another wafer is joined thereto using stud/via interconnections.

[0040] In **FIG. 4A**, wafer **1** has metallized trench structures **20** and devices **30** (e.g. DRAM devices) fabricated therein, with a dielectric layer **31** on top of the wafer containing electrical wiring and having pads **33** thereon (compare **FIG. 3A**). The trench structures are formed as described above with reference to **FIGS. 2A-2F**. The wafer has a dielectric layer **61**, typically of polyimide, overlying layer **31**. Layer **61** has via openings **62** formed therein, to expose pads **33**. Another wafer **65**, having devices **60** (e.g. PE devices) near front surface **65f**, has a dielectric layer **63** formed thereon, with high-density wiring **64** for electrical connection to studs **66**. As shown in **FIG. 4A**, devices **60** are connected to studs **66**, and the studs correspond with the vias **62**.

[0041] Wafer **1** and wafer **65** are then bonded together with studs **66** making electrical connection to pads **33**, as shown in **FIG. 4B**. (The bonding may be facilitated by using a solder layer on the studs and/or an adhesive on the polyimide layer, as discussed above with reference to **FIG. 1B**.) The resulting wafer structure **70** thus contains interconnected devices; it should be noted that wafers **1** and **65** may have different device types (such as DRAM and PE devices) and/or be of different materials (Si, SiGe, GaAs, etc.).

[0042] Wafer **1** is then thinned so that the trench structure **20** becomes a through-via, as in the previous embodiment (**FIG. 4C**; compare **FIG. 3B**). It should be noted that wafer **65** can function as a handling wafer while wafer **1** is thinned. Alternatively, wafer **65** may also be processed to have through-vias extending to back surface **65b**; in this case wafer **65** may require bonding to a temporary handling plate (not shown) which is subsequently removed, prior to bonding of wafer **65** to wafer **1**.

[0043] An insulating layer **37** (e.g. polyimide) is deposited on surface **1b**, and openings **38** are formed therein, as in the previous embodiment. Pads **39** are then formed to make connections to the through-vias, and solder bumps **41** are attached to the pads (**FIG. 4D**).

[0044] The wafer structure **70** is then diced to produce combined chips **74** (e.g. combined DRAM/PE chips), which

are then joined to carrier **45**, as shown in **FIG. 4E**. Any temporary handling plate used for wafer **65** is removed at this point. It will be appreciated that if wafer **65** has through-vias to back surface **65b**, electrical connections may be made to the top surface of chip **74**. Accordingly, further vertical integration may be accomplished.

[0045] While the invention has been described in terms of specific embodiments, it is evident in view of the foregoing description that numerous alternatives, modifications and variations will be apparent to those skilled in the art. Accordingly, the invention is intended to encompass all such alternatives, modifications and variations which fall within the scope and spirit of the invention and the following claims.

1-20. (canceled)

21. A semiconductor structure comprising:

- a first substrate having a first semiconductor device formed therein and having a top surface and a bottom surface;
- a dielectric layer overlying the top surface of the first substrate, the dielectric layer having embedded therein an electrical conductor extending through the dielectric layer; and
- a second substrate having a second semiconductor device formed therein, the second substrate overlying the dielectric layer so that the electrical conductor forms an electrical connection between the second semiconductor device and the first semiconductor device.

22. A semiconductor structure according to claim 21, wherein

the dielectric layer includes a first layer having an electrical conductor extending therethrough and making contact with the first semiconductor device and a second layer having an electrical conductor extending therethrough and making contact with the second semiconductor device, and

the first layer and the second layer are joined by a stud/via interconnection to form said electrical connection.

23. A semiconductor structure according to claim 21, wherein at least one of the first substrate and the second substrate has an opening extending therethrough with an electrical conductor disposed in the opening and contacting the electrical conductor embedded in the dielectric layer.

24. A semiconductor structure according to claim 23, wherein each of the first substrate and the second substrate has an opening extending therethrough with an electrical conductor disposed in the opening and contacting the electrical conductor embedded in the dielectric layer, thereby forming a conducting path from the bottom surface of the first substrate to a top surface of the second substrate.

25. A semiconductor structure according to claim 23, further comprising a conducting pad on the bottom surface of the first substrate electrically connected to an electrical conductor disposed in an opening extending through the first substrate, so that said conducting pad is electrically connected to at least one of the first semiconductor device and the second semiconductor device.

26. A semiconductor structure according to claim 21, wherein the first semiconductor device and the second semiconductor device are of different types.

27. A semiconductor structure according to claim 26, wherein the different types of devices include DRAM devices and processor devices.

28. A semiconductor structure according to claim 21, wherein the first substrate and the second substrate are of different materials.

29. A semiconductor structure according to claim 26, wherein the first semiconductor device and the second semiconductor device form a vertically integrated device.

30. A semiconductor structure according to claim 21, wherein at least one of the first substrate and the second substrate has a thickness not greater than about 100 μm .

31. A semiconductor structure comprising:

- a plurality of substrates having devices formed therein, each of said substrates having a front surface and a back surface extending in a first direction; and

at least one dielectric layer separating said substrates one from another, the dielectric layer having electrical conductors extending through the interior of the layer in a second direction normal to the first direction, said conductors connecting devices disposed in respective substrates separated by the dielectric layer, wherein the substrates and the dielectric layer form an integrated chip having electrical connections between devices through the interior of the integrated chip.

32. A semiconductor structure according to claim 31, wherein at least one of the substrates has an electrical conductor extending through the interior of the substrate.

33. A semiconductor structure according to claim 32, wherein the front surface of a first substrate forms a top surface of the integrated chip and the back surface of a second substrate forms a bottom surface of the integrated chip, a device in the first substrate is electrically connected to a device in the second substrate through the interior of the integrated chip, and the integrated chip has electrical connections thereto on the top surface and the bottom surface.

34. A semiconductor structure according to claim 32, wherein the dielectric layer has a conductor forming an electrical connection between a device in a substrate and the electrical conductor extending through that substrate.

35. A semiconductor structure according to claim 32, further comprising conducting pads on at least one of the top surface and the bottom surface of the integrated chip.

36. A semiconductor structure according to claim 31, wherein a device in a first substrate and a device in a second substrate are of different types.

37. A semiconductor structure according to claim 36, wherein the different types of devices include DRAM devices and processor devices.

38. A semiconductor structure according to claim 31, wherein the substrates are of different materials.

39. A semiconductor structure according to claim 31, wherein at least one dielectric layer comprises a plurality of layers joined by stud/via interconnections.

40. A semiconductor structure according to claim 31, wherein at least one of the substrates has a thickness not greater than about 100 μm .

41. A semiconductor structure comprising:

a plurality of semiconductor layers arranged in a vertical stack, each of said semiconductor layers having electrical devices therein; and

an electrical connection for electrically connecting devices in separate semiconductor layers, said electrical connection including at least one electrical conductor extending vertically through a body of a semiconductor layer.

* * * * *