

Evaluation of the Near Infrared (NIR) Sorting Potential of a Whole Plastic Article

Introduction – Scope, significance and use - This test is one in the series of “Sorting Potential Test Methods” developed by the Association of Plastics Recyclers (APR).

The sorting potential test methods describe laboratory-scale representations of the most commonly used collection and Material Recovery Facility (MRF) processes for handling single-stream post consumer recyclables. The test methods assume that these co-mingled recyclables are collected curbside, compacted in a typical recycling collection truck, transported to and processed through an automated MRF into bales of similar plastics, then further processed at the plastics reclaimer in their original form before being reduced in size.

These tests do not consider the plastics recycling process starting from or after size reduction at the plastics reclaimer. Nor do they represent other processes that may use different methods of collection and separation with different results. Furthermore, plastic sorting processes have some degree of variability in commercial practice. It is not the intent of this protocol to model every possible process outcome but to choose a common set of parameters widely employed and which fall squarely within those used in industry.

The sorting potential tests are intended to identify specific design features that may cause an entire package to be lost in the recycling process. The consequences of a plastic article being mis-sorted prior to size reduction are more significant than in processes that follow size reduction, since the entire package is lost to the plastics recycling stream rather than a mere component of the package. The modeling of sorting behavior in this test enables design engineers to focus their improvement efforts and is designed to complement the wide range of tests offered by APR that form the foundation of APR’s Design Guidance for plastic package recyclability.

Typically, today’s newer single stream MRFs and PET reclaimers employ automated equipment that sort plastic packaging and other items by their NIR (near infrared) signature, either in transmission or reflection. For this equipment to operate effectively it must accurately identify the plastic article and direct it to the correct location. Otherwise, the article is either directed to the waste stream or becomes a contaminant in another recyclable stream where it is likely to not be recycled.

This specific NIR sorting potential test method provides a means of evaluating whether a plastic article can be accurately identified and sorted on pilot scale NIR sortation equipment that performs similarly to that used in production facilities. Good results in this screening test indicate that a plastic article has the potential to be sorted well in production conditions. Poor results indicate that an improvement in plastic product design is desirable to promote recovery. An optional, second part of this test method incorporates a means of determining whether the pilot equipment & software has the ability to be adjusted to correctly identify and sort this article and if so, to capture this adjustment in production facilities.

The test involves establishing the baseline performance of a pilot NIR sorting machine by processing a known blend of material while targeting the polymer of the test article. Then, 20 samples of the test article are added

Multi-Color 1010

and the mix is reprocessed. Sorting efficiency of the test articles is compared to the baseline efficiency. Five passes through the NIR unit are used to develop repeat values for the test articles

Disclaimer: *This document has been prepared by the Association of Plastic Recyclers as a service to the plastic industry to promote the most efficient use of the nation's plastic recycling infrastructure and to enhance the quality and quantity of recycled postconsumer plastic. The information in this document is offered without warranty of any kind, either expressed or implied, including WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, which are expressly disclaimed. APR and its members accept no responsibility for any harm or damages arising from the use of or reliance upon this information by any party. Participation in the Recognition Program is purely voluntary and does not guarantee compliance with any U.S. law or regulation or that a package or plastic article incorporating the innovation is recyclable or will be recycled.*

Reference Documents:


- Compression Practice:
https://plasticsrecycling.org/images/pdf/design-guide/test-methods/Compression_Practice_for_Sorting.pdf
- APR Candidate Laboratories for Testing:
https://plasticsrecycling.org/images/pdf/design-guide/Resources/Candidate_Test_Labs.pdf

Test/Method Summary and Flow Diagram

Safety Statement: *APR Test and Practice documents do NOT CLAIM TO ADDRESS ALL OF THE SAFETY ISSUES, IF ANY, ASSOCIATED WITH THEIR USE. These Tests and Practices may require the use of electrically powered equipment, heated equipment and molten polymers, rotating motors and drive assemblies, hydraulic powered equipment, high pressure air, and laboratory chemicals. IT IS THE RESPONSIBILITY OF THE USER TO ESTABLISH AND FOLLOW APPROPRIATE SAFETY AND HEALTH PROCEDURES WHEN UNDERTAKING THESE TESTS AND PRACTICES THAT COMPLY WITH APPLICABLE FEDERAL, STATE AND LOCAL REGULATORY REQUIREMENTS. APR and its members accept no responsibility for any harm or damages arising from the use of or reliance of these Tests and Practice documents by any party.*

The flow diagram below outlines the test process. First, the baseline sorting efficiency for the polymer in question is established by running a mix of known items through the NIR sorter and recording the sortation results. Then, 20 of the candidate article are added to the mix and it is processed through the NIR sorter. This is repeated five times. The results of the baseline sorting efficiency and the candidate article sorting efficiency are then compared.

Flow diagram:



Equipment required:

1. Bottle compression device built per the instructions found at [https://plasticsrecycling.org/images/pdf/design-guide/test-methods/Compression Practice for Sorting.pdf](https://plasticsrecycling.org/images/pdf/design-guide/test-methods/Compression%20Practice%20for%20Sorting.pdf)
2. Binary NIR bottle sorter operating in representative (reflective or transmissive) mode of typical field equipment, with applicable feed belt and discharge chutes. This test is conducted on pilot plant scale NIR sortation equipment. Please refer to "APR Recognized Laboratories for Testing" found at [https://plasticsrecycling.org/images/pdf/design-guide/Resources/Candidate Test Labs.pdf](https://plasticsrecycling.org/images/pdf/design-guide/Resources/Candidate_Test_Labs.pdf) for a list of potential test locations.

These businesses each maintain and operate pilot scale sorting equipment. There may be a service fee for pilot evaluations.

Materials required:

1. 20 identical candidate test articles provided by the test applicant. These articles should be fully decorated ie with label, closures, etc. as if they were placed in a curbside bin after consumer use. Note that these articles are empty whereas some residual product may remain in the articles found in the actual recycling stream. Sorting machines are generally programmed to minimize the effects of common amounts of residual product so this test does not consider residual product.
2. Mix of plastic articles representing the plastic material commonly processed through a container line at a MRF. This mix should be of sufficient quantity to operate the trial sorting machine at 50% nameplate throughput or greater for at least 1 minute (a general rule of thumb for nameplate capacity is 1 ton/hr per meter of machine width which equates to 34 lbs per minute or approximately 733 bottles per

minute but this ratio is dependent on manufacturer). These articles are normally provided and maintained by the test lab, should be previously compressed through the actual collection system and include labels and attachments. By weight percent the mix should consist of:

- 7-12% Polypropylene containers between 8 oz. and 2 liters
- 12-17% HDPE natural containers between 8 oz. and 1 gallon
- 16 – 21% HDPE colored containers between 8 oz. and 1 gallon
- 45-50% PET containers between 8 oz. and 2 liters, insuring that at least 20 of the following are represented:
 - o clear or light blue single serve water
 - o clear 2 liter carbonated soft drink
 - o green 2 liter carbonated soft drink
 - o clear with shrink sleeve label less than 75% label coverage
- 2-3% PETG containers
- 10-15% Other plastic containers, insuring that PS, PVC and black items are represented

Method steps:

1. Take pictures of all articles for submission including:
 - a. One candidate test article before compression
 - b. All candidate test articles after compression (one collective picture)
 - c. The mix of other articles (one collective picture)
2. Compress the candidate articles according to the APR compression practice found at:
https://plasticsrecycling.org/images/pdf/design-guide/test-methods/Compression_Practice_for_Sorting.pdf

Note: This is an extremely important step since compression helps flatten the articles, making them less likely to slide on the conveyor belt. Successful optical sorting requires articles to remain stable on the conveyor belt so the ejector can be timed with the sensor. Sorting tests performed on rounded items that are not compressed may have poor results.

3. Collect and classify the material mix (it is anticipated that the testing lab maintains this mix in its facility for use as required and the classification has already been completed):
 - a. Complete the attached form classifying the mix with the weight and count of each article type.
 - b. Insure the mix is of sufficient size to feed the sorter at 50% rated throughput or greater for at least 1 minute. It is permissible and expected to adjust the usable width of the sorter to fall within these parameters.
4. Establish the baseline:
 - a. Set ALL sorter parameters to represent the typical machines installed in the field.
 - i. For a candidate article primarily made from PET these parameters should represent the settings at a PET reclaimer since these machines typically represent the most stringent criteria in the process.

- ii. For a candidate article primarily made from PP or HDPE these parameters should represent the settings at a MRF since they are typically the only automatic sorters in the recycling process.
 - b. Using the manufacturers operating procedure, set the sorter to positively sort the polymer which represents the candidate article. DO NOT USE THE TEST ARTICLE TO ADJUST THE SETTINGS. Note: The purpose of this test is to represent the performance of the machines in the field, not the capabilities of the latest machine version. Therefore, this test is not an appropriate brand-to-brand or machine-to-machine comparison.
 - c. Blend the material mix without the candidate articles in a container so they are randomly mixed.
 - d. Meter the mixed articles onto the accelerating belt (or vibratory feeder – depending on test facility) at a rate at least 50% of the sorters nameplate throughput.
 - e. Record the number and percent of the target polymer articles correctly/ positively sorted on the form below.
5. Test the candidate article.
- a. To the material mix, reintroduce the items positively sorted from the baseline sort.
 - b. Add the candidate articles to the material mix and blend in a container so they are randomly mixed.
 - c. Meter the mixed articles onto the accelerating belt (or vibratory feeder – depending on test facility) at a rate at least 50% of the sorters nameplate throughput.
 - d. Record the number of candidate articles positively sorted on the form below.
 - e. Repeat 5 times

Measurements: For each run, record the count of the “positively” ejected test articles per the report form.

Report Form: Found in Annex 1

Assessment:

Variance = The difference between the sorting efficiency of the test polymer established in the baseline test, minus the sorting efficiency of the test article in aggregate of the following tests (see calculations in the report form and example)

Capture rate = The percentage of test articles correctly sorted in the aggregate of the tests. (see calculations in the report form and example)

If:

Variance is $\leq 5\%$: The candidate article is most likely to be sorted correctly by NIR and the APR Design Guidance category for the design feature of “optical sorting potential” is preferred

Variance is $>5\%$ and Capture rate is $\geq 51\%$ A high percentage of the test articles will be missorted by NIR, but will most likely get sorted into the appropriate bale. The APR Design Guidance category for the design feature “optical sorting potential” is detrimental


Capture rate % is $< 51\%$: The candidate article will most likely be missorted by NIR and therefore the APR Design Guidance category for the design feature “optical sorting potential” renders the package unrecyclable per the APR definition of recyclability.

Optional, Part Two:

Introduction – Scope, significance and use: It is possible that a candidate article doesn’t perform well in the test described above, not due to the machine capabilities, but the programming. This may be the case when new materials are introduced into the plastics recycling stream. It is not APR’s intent to stifle innovation that may be otherwise beneficial to the plastics recycling industry and as such, offers a method for these items to be integrated into it. The second part of this test evaluates the sorting machines capability of sorting these types of test articles and if applicable, to encourage industry-wide software updates to capture them. Since the predominant installed equipment base must be capable of correctly sorting these articles the test must be repeated at other test facilities to prove the concept.

Test/Method Summary and Flow Diagram: This test method involves adjusting the sorter to the candidate article and rerunning the test described above.

Flow Diagram:



Method steps.

1. Snap the NIR Signature of the Candidate Article:
 - a. Using the method appropriate to the specific sorter, place one candidate article at a time under the sensor and take a snap shot of the article
 - b. If possible, adjust the sorter to incorporate that profile into the correct polymer classification.
2. If the sorter was capable of identifying the test article, test the candidate article using the adjusted machine.
 - a. Add the candidate articles to the material mix and blend in a container so they are randomly mixed.

- b. Meter the mixed articles onto the accelerating belt (or vibratory feeder – depending on test facility) at a rate at least 50% of the sorters nameplate throughput.
 - c. Record the number of candidate articles positively sorted on the form below.
 - d. Repeat 5 times
3. Given positive results with the adjustments (variation <5% from the baseline) the applicant must then perform the test at all the test facilities listed so that the adjustments can be implemented throughout the majority of the industry. One report per equipment manufacturer should be used in this case.

Measurements: For each run, record the count of the “positively” ejected test articles per the report form below

Report Form: Found in Annex 3

Assessment:

If, at least three of the 4 facilities:

Variance is <5%: Current NIR sorting machinery has the ability to sort the candidate article correctly if adjusted but the installed machinery base has not been adjusted to do so. Through this test protocol sorting companies are aware of these adjustments and can implement them in the field. The APR is optimistic that the adjustments are implemented in the installed machinery base so that APR Design Guidance category for the design feature of “optical sorting potential” is preferred in the future.

Variance is >5% and Capture rate is $\geq 51\%$: Current NIR sorting machinery has the ability to meet the basic standards of recoverability if adjusted but a high percentage will be missorted by NIR. The installed machinery base has not been adjusted to sort the candidate article. Through this test protocol sorting companies are aware of these adjustments and can implement them in the field. The APR is optimistic that the adjustments are implemented in the installed machinery base so that APR Design Guidance category for the design feature of “optical sorting potential” is detrimental in the future.

Capture rate % is < 51%: The candidate article will most likely be missorted by NIR now and in the near future and therefore the APR Design Guidance category for the design feature “optical sorting potential” renders the package unrecyclable per the APR definition of recyclability.

Annexes:

1. **Report form: Near Infrared Sorting Potential of a Whole Plastic Article**
2. **Sample completed report form and calculations**
3. **Part 2 report form: Near Infrared Sorting Potential of a Whole Plastic Article, Sorter Capability**

Table and Figures – None

DOCUMENT VERSION HISTORY

Version	Publication Date
1	December 11, 2017
2	May 15, 2018



Annex 1: Report Form

NEAR INFRARED SORTING POTENTIAL OF A WHOLE PLASTIC ARTICLE Record Sheet 27 APR Test

BACKGROUND

TESTING FACILITY _____

TESTING FACILITY TECHNICIAN _____

DATE _____

CANDIDATE ARTICLE DESCRIPTION

Volume _____

Color _____

Label Material _____

Closure Material _____

Body Material _____

(target polymer)

Brand/Description _____

MACHINERY

NAME PLATE THROUGHPUT FOR THE WIDTH USED lbs/hr _____

WEIGHT OF MATERIAL REQUIRED FOR 50% RATED THROUGHPUT FOR 1 MINUTE: lbs _____

MATERIAL MIX

Material	Target % by weight	Actual weight	Count
PP Containers	7-12%		
HDPE Natural Containers	12-17%		
HDPE Colored Containers	16-21%		
PET Containers	45-50%		
PETG Containers	2-3%		
Other Plastic Containers	10-15%		
Total			

% of material required for 1 minute run



BASELINE TEST

Target Polymer Name _____

of Target Polymer Items Rejected _____

% of Target Polymer Items Rejected _____

CANDIDATE ARTICLE TESTS

	RUN 1	RUN 2	RUN 3	RUN 4	RUN 5	TOTAL
# of Test Articles Rejected						
% of Test Articles Rejected						
						Capture Rate

VARIANCE CALCULATION

% of Target Polymer Items Rejected (from Baseline Test) - Total % of Test Articles Rejected (from Candidate Article Tests) =

variance _____

ASSESSMENT

Variance	Capture Rate	Applicable APR Recyclability Category for "NIR Sorting Potential" (see Category Definitions in APR Design Guide for Plastics Recyclability Home Page)	Check Applicable Box
< 5%	> 51%	APR Design Guide Preferred	
> 5%	> 51%	Detrimental to Recycling	
n/a	< 51%	Renders Package Non-Recyclable per APR Definition	

Testing Facility Technician Signature _____

Comments: What features cause negative results?, What could be done to improve sorting? Etc.

These results are not to be misinterpreted or misused to judge the performance of individual machine manufacturers.



Annex 2: Sample Completed Form and Calculations



Annex 1: Report Form

NEAR INFRARED SORTING POTENTIAL OF A WHOLE PLASTIC ARTICLE Record Sheet - APR Test

BACKGROUND	
TESTING FACILITY	Acme Testing Lab
TESTING FACILITY TECHNICIAN	Wiley Coyote
DATE	November 25, 2017
CANDIDATE ARTICLE DESCRIPTION	Volume 500 ml
	Color clear
	Label Material PP
	Closure material HDPE
	Body material PET (target polymer)
	Brand/Description XX Water

MACHINERY			
NAMEPLATE THROUGHPUT FOR THE WIDTH USED -lbs/hr	2000		
WEIGHT OF MATERIAL REQUIRED FOR 50% RATED THROUGHPUT FOR 1 MINUTE: - lbs	$(2000 \div 60 \times 5) = 17$		
MATERIAL MIX			
Material	Target % by weight	Actual weight	Count
PP containers	7-12%	2.16	45
HDPE Natural containers	12-17%	2.88	57
HDPE Colored containers	16-21%	4.32	86
PET Containers	45-50%	10.80	216
PETG Containers	2-3%	0.48	9
Other Plastic Containers	10-15%	3.36	67
Total		24.0	
		141%	

$\frac{24}{17}$
 % Of material required for 1 minute run



BASELINE TEST	
Target Polymer name	<u>PET</u>
# of target polymer items ejected	<u>203 (measured)</u>
% of target polymer items ejected	$\frac{203}{216} \leftarrow \text{from material mix} = 94\%$

CANDIDATE ARTICLE TESTS						
	RUN 1	RUN 2	RUN 3	RUN 4	RUN 5	TOTAL
# of test articles ejected	<u>18</u>	<u>16</u>	<u>18</u>	<u>18</u>	<u>20</u>	<u>90</u>
% of test articles ejected	<u>90%</u>	<u>80%</u>	<u>90%</u>	<u>90%</u>	<u>100%</u>	<u>90%</u>
						Capture rate

VARIANCE CALCULATION	
% of target polymer items ejected (from baseline test) - total % of test articles ejected (from candidate article tests) =	
$94\% - 90\% =$	variance <u>4%</u>

ASSESSMENT			
Variance	Capture Rate	Applicable APR Recyclability Category for "NIR Sorting Potential" (see category definitions in APR Design Guide for Plastics Recyclability Home Page)	Check Applicable Box
< = 5%	> = 51%	APR Design Guide Preferred	☒
> 5%	> = 51%	Detrimental to Recycling	☐
n/a	< 51%	Renders Package non-Recyclable per APR Definition	☐

Testing Facility Technician Signature

Wiley Coyote

Comments: What features cause negative results?, What could be done to improve sorting? etc.

Annex 3: Part 2 Report Form – one form per test facility

NEAR INFRARED SORTING POTENTIAL OF A WHOLE PLASTIC ARTICLE

Record Sheet APR Test

Part 2B Sorter Capability

BACKGROUND (carried from primary test)	
TESTING FACILITY	_____
TESTING FACILITY TECHNICIAN	_____
DATE	_____
CANDIDATE ARTICLE DESCRIPTION	Volume _____
	Color _____
	Label Material _____
	Closure Material _____
	Body material _____ (target polymer)
	Brand/Description _____

MACHINERY (carried from primary test)	
NAME PLATE THROUGHPUT FOR THE WIDTH USED lbs/hr	_____
WEIGHT OF MATERIAL REQUIRED FOR 50% RATED THROUGHPUT FOR 1 MINUTE: lbs	_____

MATERIAL MIX (carried from primary test)			
Material	Target % by weight	Actual weight	Count
PP Containers	7-12%		
HDPE Natural Containers	12-17%		
HDPE Colored Containers	16-21%		
PET Containers	45-50%		
PETG Containers	2-3%		
Other Plastic Containers	10-15%		
Total			
			% of material required for 1 minute run

BASELINE TEST (carried from primary test)	
Target Polymer Name	_____
# of target polymer items rejected	_____
% of target polymer items rejected	_____

CANDIDATE ARTICLE TESTS WITH SORTER ADJUSTED TO CANDIDATE ARTICLE						
	RUN 1	RUN 2	RUN 3	RUN 4	RUN 5	TOTAL
# of Test Articles Rejected						
% of Test Articles Rejected						
						Capture Rate

VARIANCE CALCULATION	
% of Target Polymer Items Rejected (from Baseline Test) - Total % of Test Articles Rejected (from Candidate Article Tests) =	
variance	

ASSESSMENT			
Variance	Capture Rate	Future Applicable APR Recyclability Category for "NIR Sorting Potential" (see category definitions in APR Design Guide for Plastics Recyclability Home Page)	Check Applicable Box
< 5%	> 51%	APR Design Guide Preferred	
> 5%	> 51%	Detrimental to Recycling	
n/a	< 51%	Renders Package Non-Recyclable per APR Definition	

Testing Facility Technician Signature _____

Comments: What features cause negative results? What could be done to improve sorting? Etc.

Sorting Equipment Manufacturer Statement (if part 2 of the test was performed successfully):

Although our typical NIR Sorting machinery installed in MRF's and PET reclaimers is not currently adjusted to correctly sort the candidate article, our machinery has the capability of being adjusted to do so. Our company is aware that the candidate article may be introduced into the curbside recycling stream and will add the adjustments to new machines and software/hardware updates in order that the candidate article may be recovered by our sorters in the future.

Signature _____

Company _____



SORTING POTENTIAL TEST METHOD:

Evaluation of the Near Infrared (NIR) Sorting Potential of a Whole Plastic Article

DOCUMENT NUMBER: SORT-S-01

Revision Date: August 30, 2024

Introduction

Scope, Significance, and Use

This test is one in the series of “Sorting Potential Test Methods” developed by the Association of Plastics Recyclers (APR).

The sorting potential test methods describe laboratory-scale representations of the most commonly used collection and Material Recovery Facility (MRF) processes for handling single-stream post consumer recyclables. The test methods assume that these co-mingled recyclables are collected curbside, compacted in a typical recycling collection truck, transported to and processed through an automated MRF into bales of similar plastics, then further processed at the plastics reclaimer in their original form before being reduced in size.

These tests do not consider the plastics recycling process starting from or after size reduction at the plastics reclaimer. Nor do they represent other processes that may use different methods of collection and separation with different results. Furthermore, plastic sorting processes have some degree of variability in commercial practice. It is not the intent of this protocol to model every possible process outcome but to choose a common set of parameters widely employed and which fall squarely within those used in industry.

The sorting potential tests are intended to identify specific design features that may cause an entire package to be lost in the recycling

process. The consequences of a plastic article being mis-sorted prior to size reduction are more significant than in processes that follow size reduction, since the entire package is lost to the plastics recycling stream rather than a mere component of the package. The modeling of sorting behavior in this test enables design engineers to focus their improvement efforts and is designed to complement the wide range of tests offered by APR that form the foundation of APR’s Design Guidance for plastic package recyclability.

Typically, today’s newer single stream MRFs and PET reclaimers employ automated equipment that sort plastic packaging and other items by their NIR (near infrared) signature, either in transmission or reflection. For this equipment to operate effectively it must accurately identify the plastic article and direct it to the correct location. Otherwise, the article is either directed to the waste stream or becomes a contaminant in another recyclable stream where it is likely to not be recycled.

This specific NIR sorting potential test method provides a means of evaluating whether a plastic article can be accurately identified and sorted on pilot scale NIR sortation equipment that performs similarly to that used in production facilities. Good results in this screening test indicate that a plastic article has the potential to be sorted well in production conditions. Poor results indicate that an improvement in plastic product design is desirable to promote recovery. An optional, second part of this test method incorporates a means of determining whether the pilot equipment & software has the ability to be

adjusted to correctly identify and sort this article and if so, to capture this adjustment in production facilities.

The test involves establishing the baseline performance of a pilot NIR sorting machine by processing a known blend of material while

targeting the polymer of the test article. Then, 20 samples of the test article are added and the mix is reprocessed. Sorting efficiency of the test articles is compared to the baseline efficiency. Five passes through the NIR unit are used to develop repeat values for the test articles.


Reference Documents

- Compression Practice
[APR-SORT-P-00 Practice Compressing Plastic Articles for Laboratory Evaluation](#)
- APR Recommended Testing Facilities
<https://plasticsrecycling.org/apr-design-hub/testing-protocols-labs/apr-recommended-testing-facilities/>

Test/Method Summary and Flow Diagram

The flow diagram below outlines the test process. First, the baseline sorting efficiency for the polymer in question is established by running a mix of known items through the NIR sorter and recording the sortation results. Then, 20 of the candidate articles are added to the mix and it is processed through the NIR sorter. This is repeated five times. The results of the baseline sorting efficiency and the candidate article sorting efficiency are then compared.

Safety Statement: APR Test and Practice documents do NOT CLAIM TO ADDRESS ALL OF THE SAFETY ISSUES, IF ANY, ASSOCIATED WITH THEIR USE. These Tests and Practices may require the use of electrically powered equipment, heated equipment and molten polymers, rotating motors and drive assemblies, hydraulic powered equipment, high pressure air, and laboratory chemicals. IT IS THE RESPONSIBILITY OF THE USER TO ESTABLISH AND FOLLOW APPROPRIATE SAFETY AND HEALTH PROCEDURES WHEN UNDERTAKING THESE TESTS AND PRACTICES THAT COMPLY WITH APPLICABLE FEDERAL, STATE AND LOCAL REGULATORY REQUIREMENTS. APR and its members accept no responsibility for any harm or damages arising from the use of or reliance of these Tests and Practice documents by any party.



Equipment Required

1. Bottle compression device built per the instructions found at [APR-SORT-P-00 Practice Compressing Plastic Articles for Laboratory Evaluation](#)
2. Binary NIR bottle sorter operating in representative (reflective or transmissive) mode of typical field equipment, with applicable feed belt and discharge chutes. This test is conducted on pilot plant scale NIR sortation equipment. Please refer to APR Recommended Testing Facilities for a list of potential testing facilities: <https://plasticsrecycling.org/apr-design-hub/testing-protocols-labs/apr-recommended-testing-facilities/>

These businesses each maintain and operate pilot scale sorting equipment. There may be a service fee for pilot evaluations.

Materials Required

1. 20 identical candidate test articles provided by the test applicant. These articles should be fully decorated, i.e. with label, closures, etc. as if they were placed in a curbside bin after consumer use. Note that these articles are empty whereas some residual product may remain in the articles found in the actual recycling stream. Sorting machines are generally programmed to minimize the effects of common amounts of residual

product so this test does not consider residual product.

2. Mix of plastic articles representing the plastic material commonly processed through a container line at a MRF. This mix should be of sufficient quantity to operate the trial sorting machine at 50% nameplate throughput or greater for at least 1 minute (a general rule of thumb for nameplate capacity is 1 ton/hr per meter of machine width which equates to 34 lbs per minute or approximately 733 bottles per minute but this ratio is dependent on manufacturer). These articles are normally provided and maintained by the test lab, should be previously compressed through the actual collection system and include labels and attachments. By weight percent the mix should consist of:
 - 7-12% Polypropylene containers between 8 oz. and 2 liters
 - 12-17% HDPE natural containers between 8 oz. and 1 gallon
 - 16-21% HDPE colored containers between 8 oz. and 1 gallon
 - 45-50% PET containers between 8 oz. and 2 liters, insuring that at least 20 of the following are represented:
 - clear or light blue single serve water
 - clear 2 liter carbonated soft drink
 - green 2 liter carbonated soft drink
 - clear with shrink sleeve label less than 75% label coverage
 - 2-3% PETG containers
 - 10-15% Other plastic containers, insuring that PS, PVC and black items are represented.

Method Steps

1. Take pictures of all articles for submission including:
 - a. One candidate test article before compression
 - b. All candidate test articles after compression (one collective picture)
 - c. The mix of other articles (one collective picture)

2. Compress the candidate articles according to the APR compression practice found at: [APR-SORT-P-00 Practice Compressing Plastic Articles for Laboratory Evaluation](#)

Note: This is an extremely important step since compression helps flatten the articles, making them less likely to slide on the conveyor belt. Successful optical sorting requires articles to remain stable on the conveyor belt so the ejector can be timed with the sensor. Sorting tests performed on rounded items that are not compressed may have poor results.

3. Collect and classify the material mix (it is anticipated that the testing lab maintains this mix in its facility for use as required and the classification has already been completed):
 - a. Complete the attached form classifying the mix with the weight and count of each article type.
 - b. Insure the mix is of sufficient size to feed the sorter at 50% rated throughput or greater for at least 1 minute. It is permissible and

expected to adjust the usable width of the sorter to fall within these parameters.

4. Establish the baseline:
 - a. Set ALL sorter parameters to represent the typical machines installed in the field.
 - b. For a candidate article primarily made from PET these parameters should represent the settings at a PET reclaimer since these machines typically represent the most stringent criteria in the process.
 - c. For a candidate article primarily made from PP or HDPE these parameters should represent the settings at a MRF since they are typically the only automatic sorters in the recycling process.
 - d. Using the manufacturers operating procedure, set the sorter to positively sort the polymer which represents the candidate article. DO NOT USE THE TEST ARTICLE TO ADJUST THE SETTINGS. Note: The purpose of this test is to represent the performance of the machines in the field, not the capabilities of the latest machine version. Therefore, this test is not an appropriate brand-to-brand or machine-to-machine comparison.
 - e. Blend the material mix without the candidate articles in a container so they are randomly mixed.
 - f. Meter the mixed articles onto the accelerating belt (or vibratory feeder – depending on test facility) at a rate

at least 50% of the sorters
nameplate throughput.

- g. Record the number and percent of
the target polymer articles correctly/
positively sorted on the form below.

5. Test the candidate article.

- a. To the material mix, reintroduce the
items positively sorted from the
baseline sort.
- b. Add the candidate articles to the
material mix and blend in a
container so they are randomly
mixed.
- c. Meter the mixed articles onto the
accelerating belt (or vibratory feeder
– depending on test facility) at a rate
at least 50% of the sorters
nameplate throughput.
- d. Record the number of candidate
articles positively sorted on the form
below.
- e. Repeat 5 times.

Measurements

For each run, record the count of the “positively” ejected test articles per the report form.

Report Form

Found in Annex 1

Assessment

Variance = The difference between the sorting efficiency of the test polymer established in the baseline test, minus the sorting efficiency of the test article in aggregate of the following tests (see calculations in the report form and example).

Capture rate = The percentage of test articles correctly sorted in the aggregate of the tests. (see calculations in the report form and example).

If Variance is $\leq 5\%$: The candidate article is most likely to be sorted correctly by NIR and the APR Design Guidance category for the design feature of “optical sorting potential” is **APR Design[®] Preferred**.

If Variance is $> 5\%$ and Capture rate is $\geq 51\%$
A high percentage of the test articles will be missorted by NIR, but will most likely get sorted into the appropriate bale. The APR Design Guidance category for the design feature “optical sorting potential” is **Detrimental to Recycling**.

If Capture rate % is $< 51\%$: The candidate article will most likely be missorted by NIR and therefore the APR Design Guidance category for the design feature “optical sorting potential” is **Renders Package Non-Recyclable** per the APR definition of recyclability.

Optional, Part Two


Introduction

Scope, significance and use

It is possible that a candidate article doesn't perform well in the test described above, not due to the machine capabilities, but the programming. This may be the case when new materials are introduced into the plastics recycling stream. It is not APR's intent to stifle innovation that may be otherwise beneficial to the plastics recycling industry and as such, offers a method for these items to be integrated into it. The second part of this test evaluates the sorting machines capability of sorting these types of test articles and if applicable, to encourage industry-wide software updates to capture them. Since the predominant installed equipment base must be capable of correctly sorting these articles the test must be repeated at other test facilities to prove the concept.

Test/Method Summary and Flow Diagram

This test method involves adjusting the sorter to the candidate article and rerunning the test described above.



Method Steps

1. Snap the NIR Signature of the Candidate Article:
 - a. Using the method appropriate to the specific sorter, place one candidate article at a time under the sensor and take a snap shot of the article.
 - b. If possible, adjust the sorter to incorporate that profile into the correct polymer classification.
2. If the sorter was capable of identifying the test article, test the candidate article using the adjusted machine.
 - a. Add the candidate articles to the material mix and blend in a container so they are randomly mixed.
 - b. Meter the mixed articles onto the accelerating belt (or vibratory feeder – depending on test facility) at a rate at least 50% of the sorters nameplate throughput.
- c. Record the number of candidate articles positively sorted on the form below.
- d. Repeat 5 times.
3. Given positive results with the adjustments (variation <5% from the baseline) the applicant must then perform the test at all the test facilities listed so that the adjustments can be implemented throughout the majority of the industry. One report per equipment manufacturer should be used in this case.

Measurements

For each run, record the count of the “positively” ejected test articles per the report form below

Report Form

Found in Annex 3.

Assessment

If, at least three of the 4 facilities:

Variance is <5%: Current NIR sorting machinery has the ability to sort the candidate article correctly if adjusted but the installed machinery base has not been adjusted to do so. Through this test protocol sorting companies are aware of these adjustments and can implement them in the field. The APR is optimistic that the adjustments are implemented in the installed machinery base so that APR Design Guidance category for the design feature of “optical sorting potential” is **APR Design® Preferred** in the future.

Variance is >5% and Capture rate is >=51%: Current NIR sorting machinery has the ability to meet the basic standards of recoverability if adjusted but a high percentage will be missorted by NIR. The installed machinery base has not been adjusted to sort the candidate article. Through this test protocol sorting companies are aware of these adjustments and can implement them in the

field. The APR is optimistic that the adjustments are implemented in the installed machinery base so that APR Design Guidance category for the design feature of “optical sorting potential” is **Detrimental to Recycling** in the future.

Capture rate % is < 51%: The candidate article will most likely be missorted by NIR now and in the near future and therefore the APR Design Guidance category for the design feature “optical sorting potential” is **Renders Package Non-Recyclable** per the APR definition of recyclability.

Annexes

1. **Report form: Near Infrared Sorting Potential of a Whole Plastic Article**
2. **Sample completed report form and calculations**
3. **Part 2 report form: Near Infrared Sorting Potential of a Whole Plastic Article, Sorter Capability**

Table and Figures

None

Annex 1: Report Form

NEAR INFRARED SORTING POTENTIAL OF A WHOLE PLASTIC ARTICLE Record Sheet – APR Test

Background

Testing Facility			
Testing Facility Technician			
Date			
Candidate Article Description	Volume		
	Color		
	Label Material		
	Closure Material		
	Body Material	(target polymer)	
	Brand/Description		

Machinery

Nameplate Throughput for the Width Used (lbs/hr)	
Weight of Material Required for 50% Rated Throughput for 1 Minute	

Material Mix

Material	Target % by weight	Actual weight	Count
PP containers	7-12%		
HDPE Natural Containers	12-17%		
HDPE Colored Containers	16-21%		
PET Containers	45-50%		
PETG Containers	2-3%		
Other Plastic Containers	10-15%		
Total			
			% of material required for 1 min. run

Baseline Test

Target Polymer name _____

of target polymer items ejected _____

% of target polymer items ejected _____

Candidate Article Tests

	Run 1	Run 2	Run 3	Run 4	Run 5	Run 6
# of test articles ejected						
% of test articles ejected						
						Capture Rate

Variance Calculation

(% of target polymer items ejected [from Baseline Test]) –
 (total % of test articles ejected [from Candidate Article Tests])=

Variance _____

Assessment

Variance	Capture Rate	Applicable APR Recyclability Category for “NIR Sorting Potential” (see category descriptions in APR Design® Guide for Plastics Recyclability Homepage)	Check Applicable Box
< - 5%	> - 51%	APR Design® Preferred	
> 5%	> - 51%	Detrimental to Recycling	
n/a	< 51%	Renders Package Non-Recyclable per APR definition	

Testing Facility Technician Signature _____

Comments

What features cause negative results?, What could be done to improve sorting?, etc.

These results are not to be misinterpreted or misused to judge the performance of individual machine manufacturers.

Annex 2: Sample Completed Form and Calculations

Annex 1: Report Form

NEAR INFRARED SORTING POTENTIAL OF A WHOLE PLASTIC ARTICLE Record Sheet - APR Test

BACKGROUND			
TESTING FACILITY	Acme Testing Lab		
TESTING FACILITY TECHNICIAN	Wiley Coyote		
DATE	November 25, 2017		
CANDIDATE ARTICLE DESCRIPTION	Volume	500 ml	
	Color	clear	
	Label Material	PP	
	Closure material	HDPE	
	Body material	PET (target polymer)	
	Brand/Description	XX Water	

MACHINERY	
NAMEPLATE THROUGHPUT FOR THE WIDTH USED -lbs/hr	2000
WEIGHT OF MATERIAL REQUIRED FOR 50% RATED THROUGHPUT FOR 1 MINUTE: - lbs	$(2000 \div 60 \times 5) = 17$

MATERIAL MIX			
Material	Target % by weight	Actual weight	Count
PP containers	7-12%	2.16	45
HDPE Natural containers	12-17%	2.88	57
HDPE Colored containers	16-21%	4.32	86
PET Containers	45-50%	10.80	216
PETG Containers	2-3%	0.48	9
Other Plastic Containers	10-15%	3.36	67
Total		24.0	
		141%	

$$\frac{24}{17}$$

% Of material required for 1 minute run

BASELINE TEST	
Target Polymer name	<u>PET</u>
# of target polymer items ejected	<u>203</u> (measured)
% of target polymer items ejected	$\frac{203}{216} \leftarrow \text{from material mix} = 94\%$

CANDIDATE ARTICLE TESTS						
	RUN 1	RUN 2	RUN 3	RUN 4	RUN 5	TOTAL
# of test articles ejected	<u>18</u>	<u>16</u>	<u>18</u>	<u>18</u>	<u>20</u>	<u>90</u>
% of test articles ejected	<u>90%</u>	<u>80%</u>	<u>90%</u>	<u>90%</u>	<u>100%</u>	<u>90%</u>
						Capture rate

VARIANCE CALCULATION	
% of target polymer items ejected (from baseline test) - total % of test articles ejected (from candidate article tests) =	
<u>94%</u> - <u>90%</u>	= variance <u>4%</u>

ASSESSMENT			
Variance	Capture Rate	Applicable APR Recyclability Category for "NIR Sorting Potential" (see category definitions in APR Design Guide for Plastics Recyclability Home Page)	Check Applicable Box
< = 5%	> = 51%	APR Design Guide Preferred	☒
> 5%	> = 51%	Detrimental to Recycling	☐
n/a	< 51%	Renders Package non-Recyclable per APR Definition	☐

Testing Facility Technician Signature

Wiley Coyote

Comments: What features cause negative results?, What could be done to improve sorting? etc.

Annex 3: Part 2 Report Form *(one form per test facility)*

NEAR INFRARED SORTING POTENTIAL OF A WHOLE PLASTIC ARTICLE Record Sheet – APR Test

Background

Testing Facility			
Testing Facility Technician			
Date			
Candidate Article Description	Volume		
	Color		
	Label Material		
	Colsure Material		
	Body Material	(target polymer)	
	Brand/Description		

Machinery

Nameplate Throughput for the Width Used (lbs/hr)	
Weight of Material Required for 50% Rated Throughput for 1 Minute	

Material Mix

Material	Target % by weight	Actual weight	Count
PP containers	7-12%		
HDPE Natural Containers	12-17%		
HDPE Colored Containers	16-21%		
PET Containers	45-50%		
PETG Containers	2-3%		
Other Plastic Containers	10-15%		
Total			
			% of material required for 1 min. run

Baseline Test

Target Polymer name _____

of target polymer items ejected _____

% of target polymer items ejected _____

Candidate Article Tests

	Run 1	Run 2	Run 3	Run 4	Run 5	Run 6
# of test articles ejected						
% of test articles ejected						
						Capture Rate

Variance Calculation

(% of target polymer items ejected [from Baseline Test]) –
 (total % of test articles ejected [from Candidate Article Tests])=

Variance _____

Assessment

Variance	Capture Rate	Applicable APR Recyclability Category for “NIR Sorting Potential” (see category descriptions in APR Design® Guide for Plastics Recyclability Homepage)	Check Applicable Box
< - 5%	> - 51%	APR Design® Preferred	
> 5%	> - 51%	Detrimental to Recycling	
n/a	< 51%	Renders Package Non-Recyclable per APR definition	

Testing Facility Technician Signature _____

Comments

What features cause negative results?, What could be done to improve sorting?, etc.

Sorting Equipment Manufacturer Statement *(if part 2 of the test was performed successfully)*

Although our typical NIR sorting machinery installed in MRFs and PET reclaimers is not currently adjusted to correctly sort the candidate article, our machinery has the capability of being adjusted to do so. Our company is aware that the candidate article may be introduced into the curbside recycling stream and will add the adjustments to new machines and software/hardware updates in order that the candidate article may be recovered by our sorters in the future.

Signature _____

Company _____

Disclaimer

This document has been prepared by the Association of Plastic Recyclers as a service to the plastic industry to promote the most efficient use of the nation's plastic recycling infrastructure and to enhance the quality and quantity of recycled postconsumer plastic. The information in this document is offered without warranty of any kind, either expressed or implied, including WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, which are expressly disclaimed. APR and its members accept no responsibility for any harm or damages arising from the use of or reliance upon this information by any party. Participation in the Recognition Program is purely voluntary and does not guarantee compliance with any U.S. law or regulation or that a package or plastic article incorporating the innovation is recyclable or will be recycled.

Document Version History

<i>Version</i>	<i>Publication Date</i>	<i>Changes Made</i>
1	December 11, 2017	
2	May 15, 2018	
3	August 30, 2024	Change to Naming Convention (B) to (S) to match Single Purpose Test; Changed hyperlinks to new website