

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22094

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 3,216

Specified Net Reten: 2,894

Actual Net Reten: 1,835

Required Reten: 0.90

Date In: 2022-08-02 Time In: 21.00

Date Out: 2022-08-04 Time Out: 19.62

Total Time: 45.32

Treating Cycle Summary

Operation	Start	End	Press	Vac	Temp	Run Time
REDACTED						

Down Time		Pause Time	0.50
Cycle Running Time:			44.82
Total Cycle (Cycle Running Time + Pause Time):			45.32
Treat Notes:			
Treat Notes:			

Borings

SAP	PEN	%
1.07	1.07	100.0
1.08	1.08	100.0
1.07	1.07	100.0
1.07	1.07	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.12	1.12	100.0
1.05	1.05	100.0
1.11	1.11	100.0
1.08	1.08	100.0
0.15	0.15	100.0
1.04	1.04	100.0
1	1.00	100.0
1.09	1.09	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.06	1.06	100.0
1.06	1.06	100.0
1.03	1.03	100.0
1.03	1.03	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
0.2	0.17	

Material

Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			1	1	60	62.80
REDACTED			3	1	60	188.40
REDACTED			1	1	80	98.00
REDACTED			4	H4	95	851.20
REDACTED			1	H5	95	236.70
REDACTED			9	1	65	657.00
REDACTED			1	1	60	62.80
REDACTED			13	1	65	949.00
REDACTED			6	4	35	109.80
Totals:			39		615	3216

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22093

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 2,760

Specified Net Reten: 2,484

Actual Net Reten: 1,885

Required Reten: 0.90

Date In: 2022-08-01 Time In: 9.60

Date Out: 2022-08-02 Time Out: 20.47

Total Time: 34.87

Treating Cycle Summary

Operation Start End Press Vac Temp Run Time

REDACTED

Down Time Pause Time 0.28

Cycle Running Time: 34.60

Total Cycle (Cycle Running Time + Pause Time): 34.87

Treat Notes:

Treat Notes:

Borings

SAP	PEN	%
1.03	1.03	100.0
1.08	1.08	100.0
1.02	1.02	100.0
1.05	1.05	100.0
1.03	1.03	100.0
1.06	1.06	100.0
1	1.00	100.0
1.08	1.08	100.0
1.01	1.01	100.0
1	1.00	100.0
1.01	1.01	100.0
1.07	1.07	100.0
2	2.00	100.0
1.06	1.06	100.0
1.03	1.03	100.0
1.08	1.08	100.0
1.15	1.15	100.0
1.05	1.05	100.0
1.03	1.03	100.0
1.05	1.05	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
0.21	0.21	

Customer Order # Inspection Pcs Class Length Total cubic

Material

REDACTED

5	1	60	314.00
4	2	60	214.00
3	H1	60	230.40
8	1	60	502.40
2	H4	95	425.60
1	H5	95	236.70
1	1	100	159.10
3	H1	100	493.50
1	H2	100	184.60

Totals: 28 730 2760

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22092

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 3,019

Specified Net Reten: 2,717

Actual Net Reten: 1,839

Required Reten: 0.90

Date In: 2022-07-30 Time In: 14.75

Date Out: 2022-08-01 Time Out: 9.27

Total Time: 42.52

Treating Cycle Summary

Operation	Start	End	Press	Vac	Temp	Run Time
REDACTED						

Down Time	Pause Time	0.89
Cycle Running Time:		41.63
Total Cycle (Cycle Running Time + Pause Time):		42.52
Treat Notes:		
.		
Treat Notes:		

Borings

SAP	PEN	%
1.02	1.02	100.0
1.02	1.02	100.0
1.05	1.05	100.0
1.13	1.13	100.0
1.09	1.09	100.0
1.07	1.07	100.0
1.02	1.02	100.0
1.04	1.04	100.0
1.01	1.01	100.0
1.08	1.08	100.0
1	1.00	100.0
1.08	1.08	100.0
1.02	1.02	100.0
1.05	1.05	100.0
1.05	1.05	100.0
1.08	1.08	100.0
1.11	1.11	100.0
2	2.00	100.0
1.09	1.09	100.0
1.03	1.03	100.0
Zone 1	Zone 2	Zone 3
.25-1	2-2.5	
0.2	0.16	

Material

Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED						
			5	1	60	314.00
			1	2	60	53.50
			5	1	60	314.00
			9	1	65	657.00
			3	H4	95	638.40
			1	H2	100	184.60
			3	H5	100	765.90
			5	4	35	91.50
Totals:			32		575	3019

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22091

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 3,170

Specified Net Reten: 2,853

Actual Net Reten: 1,931

Required Reten: 0.90

Date In: 2022-07-28 Time In: 22.08

Date Out: 2022-07-30 Time Out: 14.20

Total Time: 40.12

Treating Cycle Summary

Operation	Start	End	Press	Vac	Temp	Run Time
REDACTED						

Down Time	Pause Time	0.17
Cycle Running Time:		39.95
Total Cycle (Cycle Running Time + Pause Time):		40.12
Treat Notes:		
Treat Notes:		

Borings

SAP	PEN	%
1.02	1.02	100.0
1.08	1.00	100.0
1.02	1.08	100.0
1.06	1.02	100.0
1.06	1.06	100.0
1.03	1.03	100.0
1.07	1.07	100.0
1.14	1.14	100.0
1.04	1.04	100.0
1.1	1.10	100.0
1.09	1.09	100.0
2	2.00	100.0
1.08	1.08	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.09	1.09	100.0
1.03	1.03	100.0
1	1.00	100.0
1.01	1.01	100.0
1.05	1.05	100.0
Zone 1	Zone 2	Zone 3
.25-1	2-2.5	
0.2	0.18	

Material

Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED						
			3	1	60	188.40
			14	1	60	879.20
			1	2	60	53.50
			2	1	85	220.00
			1	1	60	62.80
			4	H4	95	851.20
			3	H5	95	710.10
			9	4	35	164.70
			1	1	45	40.40
Totals:			38		595	3170

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22077

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 2,991

Specified Net Reten: 2,692

Actual Net Reten: 2,045

Required Reten: 0.90

Date In: 2022-06-29 Time In: 18.42

Date Out: 2022-07-02 Time Out: 2.53

Total Time: 56.11

Treating Cycle Summary

Operation Start End Press Vac Temp Run Time

REDACTED

Down Time Pause Time 4.02

Cycle Running Time: 52.09

Total Cycle (Cycle Running Time + Pause Time): 56.11

Treat Notes:

Treat Notes:

Borings

SAP	PEN	%
1.02	1.02	100.0
1.09	1.09	100.0
1.14	1.14	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.02	1.02	100.0
1.09	1.09	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.12	1.12	100.0
1.02	1.02	100.0
1.1	1.10	100.0
1.08	1.08	100.0
1.02	1.02	100.0
1.05	1.05	100.0
1.03	1.03	100.0
1.06	1.06	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
0.24	0.11	

Material

Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			2	3	40	51.20
REDACTED			2	3	40	51.20
REDACTED			11	2	40	324.50
REDACTED			11	2	45	382.80
REDACTED			2	2	40	59.00
REDACTED			61	1	40	2,092.30
REDACTED			1	3	45	30.30
Totals:			90		290	2991

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22078

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 2,394

Specified Net Reten: 2,155

Actual Net Reten: 1,161

Required Reten: 0.90

Date In: 2022-07-02 Time In: 3.92

Date Out: 2022-07-04 Time Out: 3.13

Total Time: 47.22

Treating Cycle Summary

Operation Start End Press Vac Temp Run Time

REDACTED

Down Time Pause Time 0.04

Cycle Running Time: 47.18

Total Cycle (Cycle Running Time + Pause Time): 47.22

Treat Notes:

Treat Notes:

Borings

SAP	PEN	%
1.03	1.03	100.0
1.1	1.10	100.0
1.09	1.09	100.0
1.03	1.03	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.01	1.01	100.0
1	1.00	100.0
1.04	1.04	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.08	1.08	100.0
1.13	1.13	100.0
1.09	1.09	100.0
1.08	1.08	100.0
1.12	1.12	100.0
1.03	1.03	100.0
1.06	1.06	100.0
2	2.00	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
0.2	0.13	

Material

Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			2	2	50	80.60
REDACTED			2	1	60	125.60
REDACTED			12	1	65	876.00
REDACTED			5	2	65	320.50
REDACTED			7	1	70	553.70
REDACTED			5	1	75	437.50
Totals:			33		385	2394

REDACTED

RECORD OF PRESSURE TREATMENT

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 2,853

Specified Net Reten: 2,568

Actual Net Reten: 2,345

Required Reten: 0.90

Date In: 2022-07-27 Time In: 4.12

Date Out: 2022-07-28 Time Out: 21.40

Total Time: 41.28

Treating Cycle Summary

Operation	Start	End	Press	Var	Temp	Run Time
REDACTED						

Down Time	Pause Time	2.35
Cycle Running Time:		38.93
Total Cycle (Cycle Running Time + Pause Time):		41.28
Treat Notes:		
Treat Notes:		

Borings

SAP	PEN	%
1.07	1.07	100.0
1.09	1.09	100.0
1.11	1.11	100.0
1.08	1.08	100.0
1.13	1.13	100.0
1.09	1.09	100.0
1.08	1.08	100.0
1.05	1.05	100.0
1.1	1.10	100.0
1.08	1.08	100.0
1.07	1.07	100.0
1.09	1.09	100.0
1.03	1.03	100.0
1.08	1.08	100.0
1.05	1.05	100.0
1.09	1.09	100.0
1.04	1.04	100.0
1.07	1.07	100.0
1.09	1.09	100.0
1.06	1.06	100.0
Zone 1	Zone 2	Zone 3
0.34	0.23	

Material

Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED						
			3	1	80	294.00
			5	1	85	550.00
			2	1	90	250.00
			2	2	60	107.00
			5	1	75	437.50
			1	H6	75	180.40
			5	1	85	550.00
			2	H4	95	425.60
			2	4	35	36.60
			1	4	40	22.20
Totals:			28		720	2853

REDACTED

RECORD OF PRESSURE TREATMENT Log #: 2-22089

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 3,363

Specified Net Reten: 3,026

Actual Net Reten: 1,996

Required Reten: 0.90

Date In: 2022-07-25 Time In: 1.28

Date Out: 2022-07-26 Time Out: 22.92

Total Time: 45.65

Treating Cycle Summary

Operation	Start	End	Press	Vac	Temp	Run Time
REDACTED						

Borings

SAP	PEN	%
1.03	1.03	100.0
1.04	1.04	100.0
1.09	1.09	100.0
1.06	1.06	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.1	1.10	100.0
1.03	1.03	100.0
1.07	1.07	100.0
1.05	1.05	100.0
1.09	1.09	100.0
1.1	1.10	100.0
1.08	1.08	100.0
1.07	1.07	100.0
1.09	1.09	100.0
1.05	1.05	100.0
Zone 1	Zone 2	Zone 3
0.23	0.17	

Down Time	Pause Time	1.92
Cycle Running Time:		43.73
Total Cycle (Cycle Running Time + Pause Time):		45.65
Treat Notes:		
Treat Notes:		

Material

Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED		3	1		80	294.00
REDACTED		2	2		80	172.40
REDACTED		12	1		60	753.60
REDACTED		4	1		80	392.00
REDACTED		11	1		60	690.80
REDACTED		1	2		75	79.70
REDACTED		5	1		80	490.00
REDACTED		5	1		80	490.00
Totals:		43			595	3363

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22088

Plant: REDACTED Process: REDACTED
Cylinder: 2 Volume: 3,217
Specified Net Reten: 2,895
Actual Net Reten: 2,145
Required Reten: 0.90

Preserv. type: DCOI

Date In: 2022-07-23 Time In: 2.25
Date Out: 2022-07-25 Time Out: 0.80
Total Time: 46.54

Treating Cycle Summary

REDACTED

Down Time	Pause Time	1.85
Cycle Running Time:		44.69
Total Cycle (Cycle Running Time + Pause Time):		46.54
Treat Notes:		
Treat Notes:		

Borings		
SAP	PEN	%
1.07	1.07	100.0
1.05	1.05	100.0
1.04	1.04	100.0
1.09	1.09	100.0
1.08	1.08	100.0
1.11	1.11	100.0
1.09	1.09	100.0
1.05	1.05	100.0
1.07	1.07	100.0
1.06	1.06	100.0
1.03	1.03	100.0
1.07	1.07	100.0
1.08	1.08	100.0
1.1	1.10	100.0
1.09	1.09	100.0
1.04	1.04	100.0
1.08	1.08	100.0
1.06	1.06	100.0
Zone 1	Zone 2	Zone 3
1.15-1	2-3-3	
0.2	0.13	

					Material	
Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			2	1	60	125.60
			15	1	65	1,095.00
			4	1	70	316.40
			2	H2	70	215.80
			5	1	75	437.50
			2	H2	75	241.60
			1	1	70	79.10
			1	1	75	87.50
			1	1	75	87.50
			3	2	75	239.10
			4	1	65	292.00
	Totals:			40		775

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22087

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 2,963

Specified Net Reten: 2,666

Actual Net Reten: 1,830

Required Reten: 0.90

Date In: 2022-07-21 Time In: 5.28

Date Out: 2022-07-23 Time Out: 1.70

Total Time: 44.43

REDACTED

Treating Cycle Summary

Operation	Start	End	Press	Vac	Temp	Run Time
-----------	-------	-----	-------	-----	------	----------

Down Time: Pause Time: 0.17

Cycle Running Time: 44.25

Total Cycle (Cycle Running Time + Pause Time): 44.43

Treat Notes:

Treat Notes:

Borings		
SAP	PEN	%
1.1	1.10	100.0
1.06	1.06	100.0
1.09	1.09	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.07	1.07	100.0
1.06	1.06	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.09	1.09	100.0
1.13	1.13	100.0
1.03	1.03	100.0
1.1	1.10	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.06	1.06	100.0
1.07	1.07	100.0
1.04	1.04	100.0
1.09	1.09	100.0
1.05	1.05	100.0
Zone 1	Zone 2	Zone 3
.25-1	2-2.5	
0.2	0.13	

REDACTED

Material					
Customer	Order #	Inspection	Pcs	Class	Length
					Total cubic
			18	1	65
					1,314.00
			1	3	65
					51.20
			9	1	70
					711.90
			5	1	70
					395.50
			5	2	70
					344.00
			2	1	65
					146.00
Totals:			40		405
					2963

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22086

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 3,284

Specified Net Reten: 2,955
Actual Net Reten: 2,063
Required Reten: 0.90

Date In: 2022-07-19 Time In: 7.93
Date Out: 2022-07-21 Time Out: 4.67
Total Time: 44.73

Treating Cycle Summary

REDACTED

Down Time	Pause Time	0.19
Cycle Running Time:		44.54
Total Cycle (Cycle Running Time + Pause Time):		44.73
Treat Notes:		
Treat Notes:		

Borings		
SAP	PEN	%
1.03	1.03	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.08	1.08	100.0
1.03	1.03	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.11	1.11	100.0
1.02	1.02	100.0
1.09	1.09	100.0
1.1	1.10	100.0
1.08	1.08	100.0
1.12	1.12	100.0
1.06	1.06	100.0
1.03	1.03	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
0.28	0.23	

						Material
Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			7	1	60	439.60
			16	1	60	1,004.80
			7	1	75	612.50
			10	2	75	797.00
			4	1	75	350.00
			1	2	75	79.70
Totals:			45		420	3284

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22085

Plant: REDACTED Process: REDACTED Preserv. type: DCOI
Cylinder: 2 Volume: 2,726
Specified Net Reten: 2,453
Actual Net Reten: 1,929
Required Reten: 0.90
Date In: 2022-07-17 Time In: 14.72
Date Out: 2022-07-19 Time Out: 7.33
Total Time: 40.62

Treating Cycle Summary

Operation Start End Press Vac Temp Run Time

REDACTED

Down Time Pause Time 0.20
Cycle Running Time: 40.41
Total Cycle (Cycle Running Time + Pause Time): 40.62
Treat Notes:
Treat Notes:

Borings		
SAP	PEN	%
1.06	1.06	100.0
1.02	1.02	100.0
1.11	1.11	100.0
1.09	1.09	100.0
1.03	1.03	100.0
1.08	1.08	100.0
1.12	1.12	100.0
1.02	1.02	100.0
1.05	1.05	100.0
1.1	1.10	100.0
1.09	1.09	100.0
1.05	1.05	100.0
1.03	1.03	100.0
1.06	1.06	100.0
Zone 1 Zone 2 Zone 3		
25.1	2.2.5	
0.24	0.15	

						Material
Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			2	1	60	125.60
			7	1	80	686.00
			3	2	80	258.60
			1	H1	80	117.90
			3	H4	80	493.80
			7	1	85	770.00
			2	5	35	31.40
			6	1	45	242.40
Totals:			31		545	2726

REDACTED

RECORD OF PRESSURE TREATMENT crg #: 2-22084

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 3,118

Specified Net Reten: 2,806

Actual Net Reten: 2,012

Required Reten: 0.90

Date In: 2022-07-15 Time In: 10.32

Date Out: 2022-07-17 Time Out: 14.22

Total Time: 51.91

Treating Cycle Summary

Operation	Start	End	Press	Vac	Temp	Run Time
REDACTED						

Down Time	Pause Time	0.08
Cycle Running Time:		51.83
Total Cycle (Cycle Running Time + Pause Time):		51.91
Treat Notes:		
.		
Treat Notes:		

Borings

SAP	PEN	%
1.1	1.10	100.0
1.09	1.09	100.0
1.07	1.07	100.0
1.04	1.04	100.0
1.08	1.08	100.0
1.11	1.11	100.0
1.04	1.04	100.0
1.08	1.08	100.0
1.03	1.03	100.0
1.09	1.09	100.0
1.12	1.12	100.0
1.07	1.07	100.0
1.06	1.06	100.0
1.1	1.10	100.0
1.03	1.03	100.0
1.05	1.05	100.0
1.09	1.09	100.0
1.08	1.08	100.0
1.05	1.05	100.0
1.04	1.04	100.0
Zone 1	Zone 2	Zone 3
0.25-1	2-2.5	
0.21	0.13	

Material

Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			14	1	60	879.20
REDACTED			22	1	65	1,606.00
REDACTED			8	1	70	632.80
Totals:			44		195	3118

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22083

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 3,038

Specified Net Reten: 2,734

Actual Net Reten: 2,085

Required Reten: 0.90

Date In: 2022-07-13 Time In: 10.50

Date Out: 2022-07-15 Time Out: 9.72

Total Time: 47.23

Treating Cycle Summary						
Operation	Start	End	Press	Vac	Temp	Run Time
REDACTED						

Down Time	Pause Time	0.28
Cycle Running Time:		46.96
Total Cycle (Cycle Running Time + Pause Time):		47.23
Treat Notes:		
.		
Treat Notes:		

Borings		
SAP	PEN	%
1.08	1.08	100.0
1.07	1.07	100.0
1.04	1.04	100.0
1.1	1.10	100.0
1.05	1.05	100.0
1.02	1.02	100.0
1.06	1.06	100.0
1.11	1.11	100.0
1.07	1.07	100.0
1.04	1.04	100.0
1.09	1.09	100.0
1.05	1.05	100.0
1.12	1.12	100.0
1.06	1.06	100.0
1.09	1.09	100.0
1.08	1.08	100.0
1.03	1.03	100.0
1.09	1.09	100.0
1.11	1.11	100.0
1.05	1.05	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
2	0.14	

						Material
Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			9	1	70	711.90
			7	1	60	439.60
			15	1	65	1,095.00
			10	1	70	791.00
Totals:			41		265	3038

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22082

Plant: REDACTED Process: REDACTED Preserv. type: DCOI
Cylinder: 2 Volume: 2,480
Specified Net Reten: 2,232
Actual Net Reten: 1,753
Required Reten: 0.90
Date In: 2022-07-11 Time In: 11.83
Date Out: 2022-07-13 Time Out: 10.12
Total Time: 46.29

Treating Cycle Summary

Operation Start End Press Vac Temp RunTime

REDACTED

Down Time Pause Time 0.06
Cycle Running Time: 46.23
Total Cycle (Cycle Running Time + Pause Time): 46.29
Treat Notes:
Treat Notes:

Borings

SAP	PEN	%
1.03	1.03	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.06	1.06	100.0
1.03	1.03	100.0
1.08	1.08	100.0
1.15	1.15	100.0
1.05	1.05	100.0
1.14	1.14	100.0
1.09	1.09	100.0
1.11	1.11	100.0
1.04	1.04	100.0
1.06	1.06	100.0
1.08	1.08	100.0
1.02	1.02	100.0
1.06	1.06	100.0
1.03	1.03	100.0
2.01	2.01	100.0
1.09	1.09	100.0
1.05	1.05	100.0
Zone 1	Zone 2	Zone 3
25.1	2.2.5	
0.21	0.12	

Customer Order # Inspection Pcs Class Length Material Total cubic

REDACTED

7	1	65	511.00
4	2	70	275.20
2	H2	70	215.80
1	1	75	87.50
1	H5	75	164.90
1	H4	80	164.60
7	1	85	770.00
1	H1	85	129.50
1	H3	85	161.70

Totals:

25 690 2480

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22081

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 2,489

Specified Net Reten: 2,240

Actual Net Reten: 1,589

Required Reten: 0.90

Date In: 2022-07-08 Time In: 7.15

Date Out: 2022-07-11 Time Out: 11.37

Total Time: 76.21

Treating Cycle Summary

Operation	Start	End	Press	Vac	Temp	Run Time
REDACTED						

Down Time	Pause Time	26.52
Cycle Running Time:		49.69
Total Cycle (Cycle Running Time + Pause Time):		76.21
Treat Notes:		
Treat Notes:		

Borings

SAP	PEN	%
1.09	1.09	100.0
1.07	1.07	100.0
1.1	1.10	100.0
2.01	2.01	100.0
1.08	1.08	100.0
1.14	1.14	100.0
1.05	1.05	100.0
1.3	1.03	100.0
1.06	1.06	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.09	1.09	100.0
1.11	1.11	100.0
1.05	1.05	100.0
1.09	1.09	100.0
1.03	1.03	100.0
1.08	1.08	100.0
1.03	1.03	100.0
1.08	1.08	100.0
1.02	1.02	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
0.24	0.18	

					Material	
Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			11	1	60	690.80
			6	1	65	438.00
			1	1	85	110.00
			10	1	90	1,250.00
Totals:			28		300	2489

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22080

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 2,615

Specified Net Reten: 2,353
Actual Net Reten: 1,626
Required Reten: 0.90

Date In: 2022-07-06 Time In: 11.82
Date Out: 2022-07-08 Time Out: 6.25
Total Time: 42.42

Treating Cycle Summary

Operation Start End Press Vac Temp Run Time

REDACTED

Down Time Pause Time 0.37
Cycle Running Time: 42.05
Total Cycle (Cycle Running Time + Pause Time): 42.42
Treat Notes:
Treat Notes:

Borings

SAP	PEN	%
2.02	2.02	100.0
1.03	1.03	100.0
1.06	1.06	100.0
1.05	1.05	100.0
1.02	1.02	100.0
1.1	1.10	100.0
1.07	1.07	100.0
1.02	1.02	100.0
1.05	1.05	100.0
1.15	1.15	100.0
1.02	1.02	100.0
1.03	1.03	100.0
1.09	1.09	100.0
1.01	1.01	100.0
1.08	1.08	100.0
1.03	1.03	100.0
1.02	1.02	100.0
1.09	1.09	100.0
1.11	1.11	100.0
1.02	1.02	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
0.23	0.13	

Customer Order # Inspection Pcs Class Length Total cubic

REDACTED

6	4	35	109.80
2	2	50	80.60
30	3	50	1,050.00
4	1	60	251.20
10	3	25	123.00
35	3	30	588.00
10	3	35	210.00
5	1	45	202.00

Totals: 102 330 2615

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22079

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 2,385

Specified Net Reten: 2,147
Actual Net Reten: 1,516
Required Reten: 0.90

Date In: 2022-07-04 Time In: 3.77
Date Out: 2022-07-06 Time Out: 11.07
Total Time: 55.30

Treating Cycle Summary						
Operation	Start	End	Press	Vac	Temp	Run Time
REDACTED						

Down Time	Pause Time	3.63
Cycle Running Time:		51.67
Total Cycle (Cycle Running Time + Pause Time):		55.30
Treat Notes:		
Treat Notes:		

Borings		
SAP	PEN	%
1.03	1.03	100.0
1.09	1.09	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.14	1.14	100.0
1.09	1.09	100.0
1.08	1.08	100.0
1.11	1.11	100.0
1.06	1.06	100.0
0.15	0.15	100.0
1.1	1.10	100.0
1.09	1.09	100.0
1.07	1.07	100.0
1.05	1.05	100.0
1.08	1.08	100.0
1.1	1.10	100.0
1.06	1.06	100.0
1.08	1.08	100.0
1.05	1.05	100.0
2	2.00	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
0.2	0.15	

						Material
Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			3	1	60	188.40
			8	1	65	584.00
			6	2	65	384.60
			7	1	90	875.00
			1	H2	90	157.80
			1	H4	90	195.60
			Totals:			26

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22075

Plant: REDACTED Process: REDACTED Preserv. type: DCOI
Cylinder: 2 Volume: 2,984
Specified Net Reten: 2,686
Actual Net Reten: 492
Required Reten: 0.90
Date In: 2022-06-27 Time In: 2.25
Date Out: 2022-06-27 Time Out: 22.47
Total Time: 20.21

+ 1690 =
2,182

Treating Cycle Summary

Operation Start End Press Vac Temp Run Time

REDACTED

Down Time Pause Time 0.13
Cycle Running Time: 20.09
Total Cycle (Cycle Running Time + Pause Time): 20.21
Treat Notes:
Treat Notes: 1. 1-40 RT from previous charge 2-22072
86-140 RT from 2-22073

Borings

SAP	PEN	%
1.08	1.08	100.0
2	2.00	100.0
1.02	1.02	100.0
1.02	1.02	100.0
0.15	0.15	100.0
1.05	1.05	100.0
1	1.00	100.0
1.01	1.01	100.0
1.02	1.02	100.0
1	1.00	100.0
1.08	1.08	100.0
1.04	1.04	100.0
1.02	1.02	100.0
1.03	1.03	100.0
1.08	1.08	100.0
1.02	1.02	100.0
1.1	1.10	100.0
1.09	1.09	100.0
1.05	1.05	100.0
1.06	1.06	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
0.2	0.10	

Customer	Order #	Inspection	Pcs	Class	Length	Material
REDACTED			86	1	40	2,949.80
			1	1	40	34.30
			87		80	2984

(ALL retreats
from previous
charges)

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22074

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 3,053

Specified Net Reten: 2,747

Actual Net Reten: 2,003

Required Reten: 0.90

Date In: 2022-06-25 Time In: 2.93

Date Out: 2022-06-27 Time Out: 1.78

Total Time: 46.84

Treating Cycle Summary						
Operation	Start	End	Press	Vac	Temp	Run Time
REDACTED						

Down Time Pause Time Cycle Running Time: 1.88

Total Cycle (Cycle Running Time + Pause Time): 44.97

Treat Notes:

Treat Notes:

Borings		
SAP	PEN	%
1	1.00	100.0
1.01	1.01	100.0
1.02	1.02	100.0
1.01	1.01	100.0
1.04	1.04	100.0
1.02	1.02	100.0
1.03	1.03	100.0
1.09	1.09	100.0
0.15	0.15	100.0
1.04	1.04	100.0
1.02	1.02	100.0
1.05	1.05	100.0
1.13	1.03	100.0
2	2.00	100.0
1.08	1.08	100.0
1	1.00	100.0
1.09	1.09	100.0
1.03	1.03	100.0
1.05	1.05	100.0
1.03	1.03	100.0
Zone 1	Zone 2	Zone 3
.25-1	2-2.5	
0.24	0.11	

Material					
Customer	Order #	Inspection	Pcs	Class	Length
REDACTED			89	1	40
Totals:			89		40

AAR

REDACTED

RECORD OF PRESSURE TREATMENT - chg # 2-22072

Plant: REDACTED Process: REDACTED Preserv. type: DCOI

Cylinder: 2 Volume: 3,018

Specified Net Reten: 2,717

Actual Net Reten: 1,981

Required Reten: 0.90

Date In: 2022-06-21 Time In: 10.53

Date Out: 2022-06-23 Time Out: 4.88

Total Time: 42.35

Treating Cycle Summary

Operation	Start	End	Press	Vac	Temp	Run Time
REDACTED						

Down Time: Pause Time: 0.90

Cycle Running Time: 41.45

Total Cycle (Cycle Running Time + Pause Time): 42.35

Treat Notes:

Treat Notes:

Borings

SAP	PEN	%
1.1	1.10	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.02	1.02	100.0
1.03	1.03	100.0
1.05	1.05	100.0
1.02	1.02	100.0
1.08	1.08	100.0
1.02	1.02	100.0
0.14	0.14	100.0
1.05	1.05	100.0
1.02	1.02	100.0
0.15	0.15	100.0
1	1.00	100.0
1.04	1.04	100.0
1.01	1.01	100.0
1.05	1.05	100.0
1	1.00	100.0
1.03	1.03	100.0
1.09	1.09	100.0
Zone 1	Zone 2	Zone 3
25-1	2-2.5	
0.2	0.18	

Customer	Order #	Inspection	Pcs	Class	Length	Material
REDACTED			88	1	40	3,018.40
Totals:			88		40	3018

RT
2.1440

REDACTED

REDACTED

RECORD OF PRESSURE TREATMENT chg #: 2-22071

Plant: REDACTED Process: REDACTED Preserv. type: DCOI
Cylinder: 2 Volume: 3,053
Specified Net Reten: 2,747
Actual Net Reten: 1,753
Required Reten: 0.90
Date In: 2022-06-19 Time In: 12.95
Date Out: 2022-06-21 Time Out: 9.97
Total Time: 45.01

Treating Cycle Summary

Operation Start End Press Vac Temp Run Time

REDACTED

Down Time: 0.09
Pause Time: 0.09
Cycle Running Time: 44.92
Total Cycle (Cycle Running Time + Pause Time): 45.01

Treat Notes:

Treat Notes:

Borings

SAP	PEN	%
1.06	1.06	100.0
1.02	1.02	100.0
1.1	1.10	100.0
1.09	1.09	100.0
1.05	1.05	100.0
1.07	1.07	100.0
0.15	0.15	100.0
1.01	1.01	100.0
1.06	1.06	100.0
1	1.00	100.0
1.04	1.04	100.0
1.03	1.03	100.0
1.05	1.05	100.0
2	2.00	100.0
1.04	1.04	100.0
0.15	0.15	100.0
1.02	1.02	100.0
1	1.00	100.0
1.03	1.03	100.0
1.06	1.06	100.0
Zone 1	Zone 2	Zone 3
.25-1	2-2.5	
0.2	0.15	

					Material	
Customer	Order #	Inspection	Pcs	Class	Length	Total cubic
REDACTED			89	1	40	3,052.70
Totals:			89		40	3053

REDACTED